

CURRAGH RESOURCES

019097

Sample Assay Sheet

Production Date:


March 1/88

Sample Origin:

Drill Core

Sample Number	Pb	Zn	Fe	Ag	Cu	HCl Sol Fe			
1 30036	2.60	4.56	3.87	41		1.44			
2 30037	1.58	3.45	3.47	25		1.28			
3 30038	0.08	4.90	7.61	2		6.98			
4 30039	2.62	5.60	3.28	43		1.83			
5 30041	2.93	6.23	6.96	44		2.59			
6 30042	7.86	18.1	24.5	145		3.08			
7 30044	0.04	3.67	6.98	2		6.18			
8 30045	1.90	5.35	3.33	31		2.33			
9 30046	0.19	1.42	8.14	4		3.02			
10 30049	3.12	7.76	33.0	77		6.40			
11 30050	3.87	7.81	11.6	66		2.13			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer:



CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

Feb 18, 88

Sample Origin:

Drill Core

	Sample Number	Pb	Zn	Fe	Ag	Cu	Fe			
1	30223	4.44	7.34	11.5	67	2.68				
2	30224	0.45	0.85	8.33	10	1.44				
3	30225	3.83	7.67	12.8	63	1.97				
4	30226	6.78	11.2	13.0	115	1.04				
5	30227	2.79	4.94	9.72	53	3.78				
6	30228	4.58	7.56	12.6	85	2.14				
7	30229	3.20	5.58	10.2	59	1.50				
8	30230	3.80	8.70	11.7	67	3.00				
9	30231	2.60	1.08	41.6	45	8.27				
10	30232	5.03	2.56	36.8	83	10.4				
11	30233	6.24	7.21	13.5	95	4.73				
12	30234	5.47	8.08	13.0	85	2.34				
13	30235	5.44	5.88	24.6	56	16.3				
14	30236	7.78	7.76	26.3	76	16.1				
15	30237	3.00	3.02	31.7	29	16.6				
16	30238	1.57	2.09	26.4	21	8.66				
17	30239	0.94	1.04	23.0	19	10.2				
18	30240	1.96	1.18	40.4	19	31.8				
19	30241	0.57	0.56	32.7	17	22.3				
20	30242	0.74	0.39	43.3	12	25.0				
21	30243	0.89	1.08	6.49	16	4.14				
22	30244	0.16	0.43	7.76	6	6.84				
23										
24										
25										
26										
27										
28										
29										
30										
31										
32										

[Signature]

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

Feb 17, 188

Sample Origin:

Drill Core

Sample Number	Pb	Zn	Fe	Ag	HCl Sol Fe
1 ✓ 30169	5.38	4.85	28.7	72	13.7
2 ✓ 30170	5.34	3.69	33.6	80	14.3
3 ✓ 30171	7.52	9.43	14.4	116	2.13
4 ✓ 30172	4.19	4.62	18.7	56	3.64
5 ✓ 30173	4.86	7.35	27.2	62	4.15
6 ✓ 30174	4.98	7.92	25.3	66	7.60
7 ✓ 30175	2.49	1.38	36.6	25	3.33
8 ✓ 30176	3.37	1.29	34.5	27	3.23
9 ✓ 30177	1.68	1.51	33.9	14	3.78
10 ✓ 30178	1.84	1.81	33.5	17	3.85
11 No Tag	0.02	0.05	3.68	0.00	3.20
12 ✓ 30179	4.46	6.92	21.1	69	2.09
13 ✓ 30180	9.40	6.56	20.0	73	3.38
14 ✓ 30181	3.66	4.96	28.7	41	2.22
15 ✓ 30182	5.23	8.93	17.3	54	3.22
16 ✓ 30183	2.24	3.72	34.5	26	4.32
17 ✓ 30184	4.30	5.25	29.7	45	2.34
18 ✓ 30185	4.62	6.15	27.1	41	2.29
19 ✓ 30186	4.86	6.84	26.1	54	2.31
20 ✓ 30187	4.65	8.35	18.0	67	2.45
21 ✓ 30188	3.13	5.91	17.2	41	7.00
22 ✓ 30189	3.53	5.99	30.2	59	4.11
23					
24					
25					
26					
27					
28					
29					
30					
31					
32					

Ken Johnston

188-2

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Feb 19, 188

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	HCl Fe
1 ✓ 30245	1.36	0.94	29.4	17	18.5
2 ✓ 30246	0.49	0.84	26.2	12	17.4
3 ✓ 30247	0.29	0.36	29.1	8	15.7
4 ✓ 30248	0.40	0.60	35.7	12	20.4
5 ✓ 30249	0.27	0.43	34.0	8	18.9
6 ✓ 30250	1.40	1.14	27.6	17	10.1
7 ✓ 30251	0.78	0.40	3.11	29	2.06
8 ✓ 30252	3.35	5.07	12.3	60	4.64
9 ✓ 30253	1.01	1.16	6.60	16	2.48
10 ✓ 30254	2.74	6.27	0.65	46	1.06
11 ✓ 30255	0.26	0.34	9.04	10	0.67
12 ✓ 30256	0.38	0.65	13.6	14	1.45
13 ✓ 30257	0.14	0.34	12.5	10	0.70
14 ✓ 30258	0.20	0.30	13.6	10	0.80
15 ✓ 30259	0.19	0.61	14.7	12	0.91
16 ✓ 30260	0.43	1.27	12.0	10	0.85
17 ✓ 30262	0.14	0.36	6.72	4	1.05
18 ✓ 30263	0.45	0.29	30.6	22	2.11
19 ✓ 30264	0.51	0.57	7.55	12	1.37
20 ✓ 30265	3.08	4.31	16.2	56	3.08
21 ✓ 30266	1.15	1.46	4.72	17	1.46
22 ✓ 30267	0.40	1.08	5.09	8	0.98
23					
24					
25					
26					
27					
28					
29					
30					
31					
32					

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

Feb 18, 188

Sample Origin:

Drill Core

	Sample Number	Pb	Zn	Fe	Ag	Hg Fe
1	30190	3.52	5.59	12.4	56	4.86
2	30191	5.94	7.84	22.1	79	2.86
3	30192	5.43	8.92	21.5	81	2.60
4	30193	8.36	8.47	21.6	110	3.57
5	30194	5.48	7.66	21.2	85	2.81
6	30195	6.38	8.19	24.8	97	6.86
7	30196	9.19	9.91	24.5	102	4.46
8	30197	6.92	8.20	20.3	71	3.25
9	30198	6.61	9.52	22.3	89	2.45
10	30199	3.76	2.63	36.8	52	7.31
11	* 30200	3.82	2.84	38.9	58	4.07
12	✓ 30201	0.48	0.35	2.21	9	0.96
13	✓ 30202	0.16	0.36	7.26	4	2.72
14	✓ 30203	0.06	1.78	12.8	2	10.6
15	✓ 30204	0.25	0.46	6.57	4	2.74
16	✓ 30205	0.62	1.52	4.61	9	2.37
17	✓ 30206	2.55	1.68	6.55	30	3.56
18	✓ 30207	3.06	5.73	5.99	46	1.85
19	✓ 30208	1.11	1.42	12.2	21	10.8
20	✓ 30209	1.60	2.98	16.4	27	12.4
21	✓ 30210	1.76	1.34	37.7	23	19.8
22	✓ 30211	1.94	1.67	9.16	28	6.98
23	✓ 30212	9.07	7.86	32.4	105	28.6
24	✓ 30213	4.17	4.99	18.5	63	7.33
25	✓ 30214	2.77	2.83	32.1	44	7.45
26	✓ 30215	5.34	6.23	15.9	81	1.98
27	✓ 30216	3.38	7.61	15.0	43	0.87
28	✓ 30217	10.9	23.2	49.5	44	0.23
29	✓ 30218	5.13	5.46	24.1	77	8.26
30	✓ 30219	6.11	5.33	32.0	75	16.9
31	✓ 30220	6.13	6.55	21.7	81	8.11
32	✓ 30221	6.12	8.48	17.2	99	20.56
33	✓ 30222	5.66	6.99	13.8	85	4.65

John Johnston

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

Feb. 23/88

Sample Origin:

Drill Core

Sample Number	Pb	Zn	Fe	Ag	HCl Sol. Fe				
1* 30200	3.81	2.76	35.1	57	8.69				
2 30278	5.39	8.31	29.6	81	1.55				
3 30279	0.01	0.27	4.45	2	3.66				
4 30280	0.98	1.67	8.34	14	4.71				
5 30281	7.78	10.2	32.5	107	30.7				
6 30282	0.70	0.90	5.39	12	41.6				
7 30283	4.91	8.97	11.3	87	5.50				
8 30284	0.84	1.14	8.44	14	7.13				
9 30285	1.97	0.84	9.03	38	7.74				
10 30286	8.78	6.94	32.2	87	31.0				
11 30287	6.44	8.00	21.5	109	13.8				
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer:

A. P. [Signature]

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Apr 16/88

Sample Origin: DRILL CORE

	g	g	g	g/TON		HCl sol Fe			
Sample Number	Pb	Zn	Fe	Ag	Cu	g			
1	30365	5.85	6.07	25.5	91	2.62			
2	30366	5.09	7.97	12.5	83	3.42			
3	30367	1.00	1.22	32.8	16	4.33			
4	30368	2.08	2.20	29.2	38	6.56			
5	30369	1.98	2.09	29.6	32	11.0			
6	30370	0.46	1.16	8.19	10	3.96			
7	30371	0.11	0.28	4.92	4	2.45			
8	30372	0.08	0.39	5.28	4	3.17			
9	30373	0.06	0.28	3.76	4	1.97			
10	30374	1.06	0.80	32.1	26	4.84			
11	30375	1.46	1.47	11.5	26	2.96			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Clara Hembler

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Apr 16/88

Sample Origin: DRILL CORE

	g ₀	g ₀	g ₀	g/TON		HCl sol Fe			
Sample Number	Pb	Zn	Fe	Ag	Cu	g ₀			
1	30335	5.65	6.72	12.4	99	1.08			
2	30336	5.21	6.91	8.54	70	1.56			
3	30337	5.26	7.95	16.9	49	4.20			
4	30338	10.7	9.13	19.3	99	3.03			
5	30339	10.4	6.23	25.8	111	4.67			
6	30340	2.78	2.96	35.4	91	4.09			
7	30341	6.40	7.53	18.0	61	5.09			
8	30342	7.31	7.53	16.8	67	6.60			
9	30343	0.73	1.14	36.3	40	3.52			
10	30344	3.15	8.67	10.0	46	7.78			
11	30345	5.15	3.61	33.8	69	4.52			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Apr 16/88

Sample Origin: DRILL CORE

	%	%	%	g/TON		HCl sol Fe			
Sample Number	Pb	Zn	Fe	Ag	Cu	%			
1	30346	1.18	0.89	11.2	10	4.86			
2	30347	1.35	1.83	11.5	14	4.76			
3	30349	0.68	1.18	13.7	6	5.61			
4	30350	0.98	1.88	31.0	14	9.49			
5	30997	6.40	7.75	11.5	99	0.51			
6	30998	4.41	8.48	18.0	64	4.62			
7	30999	0.15	0.89	10.8	0	9.93			
8	31000	2.02	2.77	23.1	19	8.82			
9	30601	2.41	3.28	24.7	25	9.69			
10	30602	0.37	0.42	29.1	4	4.11			
11	30603	2.45	2.01	30.5	27	20.2			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

April 17, 1988

Sample Origin:

Drill Core

Sample Number	Pb	Zn	Fe	Ag	Cu	HCl Sol Fe
1 30604	2.13	2.85	26.6	33		11.2
2 30605	1.21	2.25	23.9	26		10.34
3 30606	4.70	5.54	32.7	57		19.0
4 30607	4.39	3.74	34.2	53		23.2
5 30608	2.84	1.66	32.0	37		14.2
6 30609	3.06	1.76	25.0	39		21.4
7 30610	5.38	6.62	19.6	66		8.96
8 30611	0.68	1.28	28.2	20		7.39
9 30612	0.68	0.76	20.2	18		3.87
10 30613	0.23	0.72	20.2	11		6.46
11						
12 30200	3.82	2.84	38.9	58		4.07
13						
14						
15						
16						
17						
18						
19						
20						
21						
22						
23						
24						
25						
26						
27						
28						
29						
30						
31						
32						

Assayer:

Michelle Bergeron

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

April 11/88

Sample Origin:

Drill Core

	Sample Number	Pb	Zn	Fe	Ag	Cu			
1	30657				19				
2	658				12				
3	659				21				
4	660				21				
5	661				4				
6	662				33				
7	663				14				
8	664				14				
9	665				10				
10	30334				54				
11	30683				41				
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Jim

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

Feb 26/88

Sample Origin:

Drill cone

Sample Number	Pb	Zn	Fe	Ag	Cu	incl soil Fe		
1 ✓ 30268	0.24	0.54	5.95	7		0.65		
2 ✓ 30269	0.70	0.91	6.16	15		0.99		
3 * 30270 A	5.01	4.56	24.8	56		1.38		
4 * 30270	1.16	1.32	6.18	17		1.37		
5 ✓ 30271	1.04	1.56	8.50	15		2.21		
6 ✓ 30273	0.10	0.24	8.49	6		1.26		
7 ✓ 30273	0.12	0.66	11.9	6		1.47		
8 ✓ 30274	0.85	1.25	6.62	19		1.88		
9 ✓ 30275	2.21	4.72	3.37	29		1.85		
10 ✓ 30276	2.24	4.29	3.86	35		1.35		
11 ✓ 30277	1.98	5.04	4.17	27		1.38		
12								
13								
14								
15								
16								
17	L							
18								
19								
20								
21								
22								
23								
24								
25								
26								
27								
28								
29								
30								
31								
32								

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

Feb 28/88

Sample Origin:

Drill Core

	Sample Number	Pb	Zn	Fe	Ag	SHL SulfE
1	✓ 30288	1.27	1.51	7.30	26	3.35
2	✓ 30289	6.21	8.00	24.3	32	1.89
3	✓ 30291	5.60	6.01	19.7	91	9.38
4	✓ 30292	5.10	6.05	19.4	67	2.11
5	✓ 30293	2.98	2.97	30.7	40	16.9
6	✓ 30294	1.11	1.62	30.6	24	5.46
7	✓ 30295	2.71	5.40	20.7	34	5.62
8	✓ 30296	0.44	0.91	26.8	10	14.2
9	✓ 30297	0.18	0.27	10.4	6	6.80
10	✓ 30298	0.16	0.20	9.47	6	10.5
11	✓ 30299	2.77	4.88	4.51	38	0.84
12						
13						
14						
15						
16						
17						
18						
19						
20						
21						
22						
23						
24						
25						
26						
27						
28						
29						
30						
31						
32						

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: March 1, 1988

Sample Origin: Drill Core

Sample Number	Pb %	Zn %	Fe %	Ag ⁺ / _{TON}	Cu	HCl Sol Fc			
1 30323	5.04	6.63	19.7	76		1.16			
2 30324	1.76	2.45	38.7	25		9.23			
3 30325	2.00	2.63	18.3	25		3.74			
4 30326	3.42	5.67	20.5	58		1.96			
5 30327	9.78	8.88	15.4	149		2.10			
6 30328	1.94	1.22	37.1	29		11.37			
7 30329	5.27	6.45	18.6	74		8.46			
8 30330	3.97	6.70	13.0	62		2.58			
9 30331	5.22	7.03	14.5	85		2.69			
10 30332	6.29	6.02	14.0	112		1.06			
11 30333	3.07	3.37	11.8	41		3.41			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: March 1/88

Sample Origin: Drill core

Sample Number	Pb	Zn	Fe	Ag	Cu	Hd Sol Fe			
1 30300	0.80	1.43	13.5	18		0.53			
2 30301	0.45	0.63	13.2	9		0.52			
3 30302	0.43	0.50	12.7	9		0.33			
4 30303	0.36	0.22	7.84	4		0.44			
5 30304	0.80	1.45	5.76	11		1.18			
6 30305	0.96	0.99	5.40	13		0.59			
7 30306	4.60	5.12	31.1	56		23.1			
8 30307	0.29	2.22	8.71	2		7.12			
9 30308	0.57	1.45	6.48	6		3.15			
10 30309	1.50	2.87	4.54	18		2.43			
11 30300	1.81	1.93	5.97	22		3.07			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Juni

CURRAGH RESOURCES

Sample Assay Sheet


Production Date: Feb 17, 1988

Sample Origin: Drill Core

Drill Core

	Sample Number	Pb	Zn	Fe	Ag	HCl Sol Fe				
1	✓ 11485	.82	1.14	29.3	15	8.63				
2	✓ 11487	.31	.96	26.5	21	4.21				
3	✓ 11488	.87	1.73	27.4	27	5.22				
4	✓ 11489	.26	2.11	31.4	15	7.58				
5	✓ 11490	6.42	5.60	12.5	99	3.58				
6	✓ 11491	5.79	8.94	15.6	87	1.13				
7	✓ 11492	1.10	1.35	4.77	13	2.63				
8	✓ 11493	4.62	5.30	27.4	57	5.73				
9	✓ 11494	.38	1.42	10.2	9	5.26				
10	✓ 11495	.90	1.33	9.54	15	2.93				
11	✓ 11496	2.12	3.60	9.03	28	3.45				
12	✓ 11497	3.66	5.59	19.1	69	2.28				
13	✓ 11498	7.04	8.86	21.4	88	4.23				
14	✓ 11499	7.32	9.01	17.6	92	3.17				
15	* 11500	7.11	7.49	27.9	71	8.80				
16	✓ 30073	1.22	2.84	7.33	21	1.35				
17	✓ 30151	4.98	5.70	29.8	59	9.08				
18	✓ 30152	1.76	2.10	33.5	34	4.72				
19	✓ 30153	1.14	1.82	31.0	25	6.53				
20	✓ 30155	.29	.53	23.2	8	9.33				
21	✓ 30156	.62	.96	25.0	10	8.32				
22	✓ 30157	.70	.94	22.6	11	8.67				
23	✓ 30158	5.18	8.46	23.4	85	2.98				
24	✓ 30159	0.18	0.24	14.0	4	4.43				
25	✓ 30160	0.07	0.25	14.4	4	6.57				
26	✓ 30161	0.19	0.14	13.4	4	12.4				
27	✓ 30162	0.07	0.13	6.54	2	4.96				
28	✓ 30163	1.32	0.45	16.0	19	5.80				
29	✓ 30164	0.10	0.17	6.20	4	5.44				
30	✓ 30165	0.13	0.42	7.14	2	6.24				
31	✓ 30166	0.32	0.35	9.45	8	8.66				
32	✓ 30167	3.79	3.15	10.6	38	2.83				
	✓ 30168	8.34	4.98	33.0	84	5.61				

41-2021-79

Assayer: 

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Dec 9, 187

Sample Origin: Drill Core

	Sample Number	Pb	Zn	Fe	Ag	Cu HCl sol Fe			
1	✓ 11057	5.07	3.20	36.5	73	2.06			
2	✓ 11058	7.16	7.46	25.6	117	2.23			
3	✓ 11059	4.58	6.12	28.6	65	14.9			
4	- 11060	4.99	8.32	17.3	77	2.70			
5	- 11061	4.94	6.58	14.7	63	3.69			
6	✓ 11062	1.29	1.38	40.8	12	2.38			
7	✓ 11063	4.92	8.20	19.0	85	2.28			
8	- 11064	5.79	7.91	19.3	79	2.59			
9	- 11065	2.69	3.71	40.8	36	10.2			
10	- 11066	3.69	2.92	39.9	51	9.30			
11	- 11067	2.71	2.65	41.1	44	12.8			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: *[Signature]*

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Dec 9 / 87

Sample Origin: Drill Core

	Sample Number	Pb	Zn	Fe	Ag	Eu	HCl sol	Fe ₂		
1	✓ 9658	0.32	0.45	10.6	8	3.42				
2	✓ 11045	0.20	0.13	26.3	10	1.60				
3	✓ 11047	0.10	0.13	29.1	10	2.75				
4	✓ 11049	0.18	0.23	34.2	14	4.26				
5	✓ 11050	0.20	0.61	26.7	12	2.90				
6	✓ 11051	3.24	3.74	30.0	52	8.28				
7	✓ 11052	0.40	0.50	38.9	22	1.75				
8	✓ 11053	0.50	1.02	26.6	25	4.26				
9	✓ 11054	4.56	6.90	10.7	84	1.92				
10	✓ 11055	8.53	8.81	27.4	128	1.78				
11	✓ 11056	1.36	1.68	13.1	27	2.63				
12										
13										
14										
15										
16										
17										
18										
19										
20										
21										
22										
23										
24										
25										
26										
27										
28										
29										
30										
31										
32										

Assayer:

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Dec 12/87

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	Gr H ₂ SO ₄ Fe				
1 ✓ 11079	0.10	0.10	24.5	9	1.73				
2 ✓ 11080	0.15	0.17	35.0	14	2.09				
3 ✓ 11081	0.10	0.10	21.4	6	1.68				
4 - 11082	0.25	0.28	20.0	20	1.21				
5 - 11083	0.20	0.57	14.6	16	1.77				
6 - 11084	0.15	0.30	9.34	8	1.73				
7 - 11085	0.13	0.56	20.3	4	4.92				
8 - 11086	0.14	0.35	6.79	12	2.93				
9 - 11087	0.75	1.49	29.5	16	6.64				
10 - 11088	0.60	1.18	23.6	10	6.18				
11 ✓ 11091	0.04	0.18	5.41	2	3.24				
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: M. Lewis

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

dec 11/87

Sample Origin: drill core

Sample Number	Pb	Zn	Fe	Ag	HCl sol Zn Fe				
1 - 11068	2.07	2.07	36.5	34	9.74				
2 - 11069	0.70	1.29	27.8	40	9.58				
3 - 11070	2.62	2.86	37.9	44	5.20				
4 - 11071	5.60	4.88	38.3	59	6.70				
5 - 11072	4.53	6.81	10.7	65	2.72				
6 - 11073	3.34	3.67	33.9	34	6.17				
7 - 11074	0.39	0.68	36.5	8	2.58				
8 - 11075	8.00	4.28	25.2	51	3.52				
9 - 11076	4.76	2.79	28.8	45	16.1				
10 - 11077	3.87	1.54	37.2	53	13.8				
11 - 11078	0.44	0.31	29.7	20	2.24				
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Catherine

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date: Dec 18, 1987

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	Cu HCl sol Fe			
1 ✓ 11162	7.07	7.63	21.1	93	13.2			
2 ✓ 11165	6.84	7.92	18.8	77	10.9			
3 ✓ 11166	1.06	1.10	24.5	18	10.1			
4 ✓ 11176	0.67	0.85	21.9	10	7.10			
5 ✓ 11179	1.20	1.21	17.2	18	6.56			
6 ✓ 11180	0.31	0.33	6.84	4	6.45			
7 ✓ 11181	0.58	0.34	12.2	6	6.15			
8 ✓ 11182	0.10	0.25	11.9	4	5.23			
9 ✓ 11183	0.18	0.08	9.88	4	19.8	* Per the Pb & Hg		
10 ✓ 11201	0.46	0.33	21.3	198	1.22	* same result		
11 ✓ 11202	12.3	7.02	269	175	4.03			
12								
13								
14								
15								
16								
17								
18								
19								
20								
21								
22								
23								
24								
25								
26								
27								
28								
29								
30								
31								
32								

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Dec 17/87

Sample Origin: drill core

	Sample Number	Pb	Zn	Fe	Ag	HCl 50/ 20 Fe			
1	✓ 11142	0.11	0.23	32.1	10	1.60			
2	✓ 11144	0.33	0.49	37.0	20	3.28			
3	✓ 11145	0.75	0.64	37.0	26	8.31			
4	✓ 11148	7.76	3.66	11.5	46	1.53			
5	✓ 11149	0.63	0.42	24.8	14	2.48			
6	✓ 11150	0.76	0.70	36.8	24	4.57			
7	✓ 11152	1.44	1.38	35.2	28	4.41			
8	✓ 11154	3.18	6.72	9.60	42	1.93			
9	✓ 11155	5.36	7.25	14.6	113	4.69			
10	✓ 11156	0.54	3.92	16.0	10	13.4			
11	✓ 11157	2.41	3.56	34.4	40	11.9			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									


CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Dec 18, 1987

Sample Origin: Drill Core

	Sample Number	Pb	Zn	Fe	Ag	g # C / 30 l Fe			
1	✓ 11102	1.27	1.49	24.3	20	5.77			
2	✓ 11113	4.26	6.76	13.0	65	6.30			
3	✓ 11123	5.74	7.52	24.5	71	1.46			
4	✓ 11126	0.09	0.13	16.3	6	3.38			
5	✓ 11131	5.10	5.54	20.6	68	2.02			
6	✓ 11133	0.12	0.14	14.9	4	3.53			
7	✓ 11134	0.84	1.01	17.3	12	3.87			
8	✓ 11153	5.87	8.28	12.7	101	1.80			
9	✓ 11158	2.79	3.37	29.5	34	9.39			
10	✓ 11159	6.89	7.44	16.3	99	5.85			
11	✓ 11161	5.94	5.32	39.2	83	34.0			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: 

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date: Dec 29/87

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	Cu <u>As</u> <u>S</u> <u>Li</u> <u>Fe</u>				
1 ✓ 11225	5.80	5.79	24.2	77	24.5				
2 ✓ 11226	4.47	3.85	29.9	91	3.22				
3 ✓ 11227	2.48	3.10	30.1	52	3.50				
4 ✓ 11228	3.52	4.79	24.0	46	7.73				
5 ✓ 11229	5.22	4.36	30.5	67	12.1				
6 ✓ 11230	5.14	4.19	30.3	69	12.2				
7 ✓ 11231	3.94	3.16	31.8	50	6.19				
8 ✓ 11232	7.91	11.8	15.5	117	3.05				
9 ✓ 11233	1.58	2.48	9.88	24	2.73				
10 ✓ 11234	4.94	8.24	19.5	81	1.61				
11 ✓ 11235	4.77	8.90	18.0	77	2.87				
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Marge Lewis

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date:

Dec. 28/87

Sample Origin: Drill Core

	WCl	Sol Fe							
Sample Number	WCl	Sol Fe	Fe	Ag	Cu				
1 ✓ 11214	5.96								
2 ✓ 11215	6.46								
3 ✓ 11216	3.16								
4 ✓ 11217	4.00								
5 ✓ 11218	5.30								
6 ✓ 11219	2.08								
7 ✓ 11220	2.48								
8 ✓ 11221	2.65								
9 ✓ 11222	3.31								
10 ✓ 11223	4.18								
11 ✓ 11224	2.04								
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: [Signature]

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date:

Dec 28, 187.

Sample Origin:

Drill Core

	Sample Number	Pb	Zn	Fe	Ag	Cu			
1	✓ 11214	0.11	0.56	6.86	2				
2	✓ 11215	1.10	2.48	7.73	22				
3	✓ 11216	0.16	0.42	27.4	8				
4	✓ 11217	0.08	0.57	7.22	2				
5	✓ 11218	0.03	0.42	6.86	2				
6	✓ 11219	0.16	0.39	3.16	4				
7	✓ 11220	3.98	3.60	18.2	40				
8	✓ 11221	0.40	1.12	4.72	6				
9	✓ 11222	4.67	6.52	20.7	80				
10	✓ 11223	0.54	0.99	15.5	14				
11	✓ 11224	5.10	7.00	17.1	202				
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

[Handwritten Signature]

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date: Dec. 24/87

Sample Origin: Drill Core

					sol	HCl	Fe.		
Sample Number	Pb	Zn	Fe	Ag	Ag				
1 ✓ 11203	8.13	7.36	19.9	49	0.93				
2 ✓ 04	5.01	3.08	28.8	87	4.95				
3 ✓ 05	1.43	1.61	9.99	18	6.93				
4 ✓ 06	0.50	1.00	10.3	14	9.10				
5 ✓ 07	3.09	3.32	36.0	45	4.92				
6 ✓ 08	0.09	0.47	5.55	—	4.74				
7 ✓ 09	—	0.15	4.74	—	4.35				
8 ✓ 11210	0.17	0.84	8.58	46	0.70				
9 ✓ 11	3.93	6.26	25.2	48	2.81				
10 ✓ 12	4.11	11.6	17.8	67	2.48				
11 ✓ 13	1.65	3.30	12.4	20	5.46				
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Feb 14, 1988

Sample Origin: Drill Core

	Sample Number	Pb	Zn	Fe	Ag	HCl sol Fe				
1	✓ 11163	7.03	7.92	18.8	85	9.11				
2	- 11301	0.72	0.84	43.3	17	16.8				
3	- 11302	1.14	1.21	42.1	19	12.3				
4	✓ 11304	3.30	2.63	35.6	42	10.8				
5	✓ 11336	0.56	0.83	31.0	11	25.6				
6	- 11348	0.72	1.08	28.3	9	17.0				
7	- 11349	3.25	2.95	27.3	30	15.8				
8	- 11350	0.48	0.16	17.6	6	4.62				
9	- 11351	0.84	0.81	24.6	13	10.4				
10	- 11352	0.59	0.69	25.3	9	9.44				
11	- 11353	0.55	0.23	16.8	9	3.58				
12	- 11354	0.25	0.39	9.66	6	4.09				
13	- 11355	0.19	0.30	8.88	6	4.00				
14	- 11356	0.01	0.06	10.1	2	4.70				
15	✓ 11357	0.89	0.92	30.6	14	19.9				
16	- 11358	5.89	7.20	14.1	93	5.48				
17	- 11359	13.8	11.8	24.7	152	20.0				
18	- 11360	4.35	7.19	14.4	67	7.77				
19	- 11361	5.39	7.96	13.9	89	2.63				
20	- 11362	1.35	2.83	37.0	34	0.75				
21	- 11363	2.13	5.12	29.2	53	0.69				
22	- 11364	2.55	5.56	7.13	38	1.23				
23	- 11365	1.88	3.81	31.9	34	2.48				
24	- 11366	3.50	6.10	8.24	49	1.20				
25	- 11367	2.45	5.07	15.4	42	1.24				
26	- 11368	0.67	2.08	39.5	21	0.88				
27	* 11379 11369	3.58	5.89	14.1	64	4.12				
28	- 11370	4.26	7.94	10.7	66	2.98				
29	- 11371	5.81	7.18	14.6	97	3.78				
30	✓ 11372	5.57	7.73	11.8	91	4.51				
31	- 11373	7.78	7.80	15.0	114	6.78				
32	✓ 11374	6.16	8.78	19.4	85	1.18				

duplicates of samples:
 11379
 11400
 30200
 one with no tag.

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

Feb 16, 188


Sample Origin:

Drill Core

	Sample Number	Pb	Zn	Fe	Ag	HCl sol ^{Eu} Fe				
1	✓ 11452	10.0	10.7	18.1	156	4.03				
2	✓ 11453	5.72	5.78	23.5	89	11.8				
3	✓ 11454	2.83	2.67	36.8	46	29.4				
4	✓ 11455	4.87	6.86	16.0	78	21.6				
5	✓ 11456	1.20	1.75	34.6	26	8.04				
6	✓ 11457	3.14	3.33	29.4	46	7.39				
7	✓ 11458	0.67	0.91	41.2	15	12.3				
8	✓ 11459	1.64	1.82	37.8	30	10.6				
9	11460	0.13	0.34	20.4	4	8.25				
10	11461	0.52	1.04	31.1	11	10.7				
11	11462	0.17	0.57	30.6	11	7.31				
12	11463	0.23	0.53	26.2	9	7.98				
13	11464	0.24	0.59	27.2	9	9.73				
14	11465	0.32	0.42	31.3	9	6.66				
15	11466	0.18	0.19	32.4	9	8.25				
16	11467	0.29	0.62	35.8	9	11.4				
17	11468	0.65	1.67	31.5	15	13.7				
18	11469	5.62	11.6	32.0	45	24.2				
19	11470	0.62	0.63	26.7	9	13.6				
20	11471	0.38	0.80	31.3	8	12.3				
21	11472	0.49	1.28	31.5	9	11.2				
22	11473	0.43	1.02	29.3	8	12.2				
23	11474	0.40	0.66	26.1	8	9.20				
24	11475	1.21	1.15	24.1	14	12.3				
25	11476	0.42	0.28	21.2	6	6.52				
26	11477	0.51	0.52	19.9	10	5.66				
27	11478	1.36	0.73	15.2	10	8.81				
28	11479	0.93	0.73	12.8	10	6.20				
29	11480	0.13	0.27	9.94	4	3.74				
30	✓ 11481	3.67	5.26	27.7	46	22.3				
31	✓ 11482	2.65	2.73	29.9	33	11.3				
32	✓ 11483	2.90	1.60	26.3	43	11.9				
	✓ 11484	1.97	2.39	27.2	29	11.2				

11-2021-79

Assayer:



CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

Feb. 17/88

Sample Origin:

Drill Core

	Sample Number	Pb	Zn	Fe	Ag	HCl Sol	Fe			
1	✓11430	0.06	0.11	5.50	2	4.65				
2	✓11431	0.02	0.08	5.56	2	4.58				
3	✓11432	0.08	0.28	12.4	6	3.36				
4	✓11433	0.31	1.06	6.32	6	3.95				
5	✓11434	0.87	0.79	11.9	15	5.39				
6	11435	5.17	7.68	17.6	83	1.50				
7	11436	4.88	8.84	15.3	83	0.88				
8	11437	5.33	7.10	21.6	87	2.08				
9	11438	4.55	6.07	26.9	66	5.30				
10	11439	4.93	7.25	17.1	81	4.24				
11	11440	1.87	2.66	12.8	29	1.70				
12	11441	2.58	4.49	32.9	64	1.02				
13	11442	3.76	7.53	31.9	84	1.14				
14	11443	2.56	4.80	13.9	42	1.24				
15	11444	0.59	1.51	36.2	17	1.32				
16	11445	4.95	8.75	9.85	76	4.12				
17	11446	5.73	8.04	13.7	93	5.49				
18	11447	6.18	7.11	11.1	103	3.64				
19	11448	2.06	2.44	8.60	32	5.72				
20	11449	7.15	8.03	15.1	104	7.39				
21	11450	0.26	0.59	6.76	7	6.46				
22	✓11451	9.62	3.08	34.6	95	3.06				
23										
24										
25										
26										
27										
28										
29										
30										
31										
32										

[Handwritten Signature]

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Feb 15 1988

Sample Origin: Drill Core

	Sample Number	Pb	Zn	Fe	Ag	Hcl sol Fe				
1	11408	5.67	2.48	31.8	63	0.67				
2	11409	5.29	5.38	17.0	46	5.37				
3	11410	1.59	4.09	13.8	64	9.85				
4	11411	4.89	6.08	14.5	47	3.84				
5	11412	3.07	5.01	22.0	30	1.88				
6	11413	3.76	7.65	26.3	38	1.85				
7	11414	0.31	0.31	42.8	11	0.33				
8	11415	1.78	2.98	29.6	23	2.71				
9	11416	7.72	8.95	13.8	64	4.58				
10	11417	1.22	1.06	35.7	28	4.64				
11	11418	1.00	1.97	27.9	28	5.33				
12	11419	0.60	1.39	27.0	28	5.94				
13	11420	1.60	1.71	30.0	36	4.96				
14	11421	0.40	0.38	30.7	25	3.66				
15	11422	0.33	0.24	25.5	13	1.53				
16	11423	0.19	0.10	24.7	11	1.53				
17	11424	0.25	0.17	22.0	11	2.22				
18	11425	0.35	0.47	22.4	17	3.14				
19	11426	1.32	3.26	23.9	17	10.9				
20	11427	1.49	4.42	24.5	19	4.88				
21	11428	0.43	1.49	27.2	9	23.3				
22	11429	0.09	0.18	5.68	0	5.16				
23										
24										
25										
26										
27										
28										
29										
30										
31										
32										

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

Feb 15, 188

Sample Origin:

Drill Core

Sample Number	Pb	Zn	Fe	Ag	Hcl sol Fe
1 ✓ 11375	5.13	10.4	21.5	70	17.3
2 ✓ 11376	3.05	5.41	29.7	38	26.0
3 ✓ 11377	5.50	1.85	23.8	85	12.4
4 ✓ 11378	0.81	0.77	32.8	15	16.6
5 ✓* 11379	0.62	1.69	31.7	13	14.2
6 ✓ 11380	1.40	1.48	27.6	23	12.5
7 ✓ 11381	0.41	0.87	34.0	13	11.0
8 ✓ 11382	0.17	0.41	31.7	9	5.26
9 ✓ 11383	0.14	0.33	26.9	9	3.57
10 ✓ 11384	0.47	0.50	28.3	13	3.91
11 ✓ 11385	0.37	0.46	27.1	11	4.20
12 ✓ 11386	0.13	0.65	6.39	4	4.63
13 ✓ 11387	5.21	7.79	18.8	76	4.33
14 ✓ 11388	5.74	7.18	18.8	83	6.50
15 ✓ 11389	3.59	7.05	12.9	56	3.92
16 ✓ 11390	0.62	0.99	5.36	10	3.38
17 ✓ 11391	0.17	0.74	6.38	2	4.49
18 ✓ 11392	0.21	0.59	11.1	4	6.88
19 ✓ 11393	0.03	0.40	6.59	0	4.76
20 ✓ 11394	0.04	0.32	3.27	0	2.29
21 ✓ 11395	0.11	1.03	10.7	2	2.78
22 ✓ 11396	2.40	3.48	32.0	48	7.26
23 ✓ 11397	4.82	1.81	36.2	75	5.22
24 ✓ 11398	0.11	0.53	32.0	17	2.27
25 ✓ 11399	0.19	0.77	30.2	15	2.17
26 ✓* 11400	3.13	4.57	31.1	40	5.67
27 ✓ 11401	0.10	0.53	8.44	2	4.84
28 ✓ 11402	0.04	0.23	5.60	2	4.02
29 ✓ 11403	6.14	7.53	12.8	78	2.88
30 ✓ 11404	8.92	5.43	20.2	107	6.69
31 ✓ 11405	6.69	4.54	18.4	96	6.52
32 ✓ 11406	4.27	2.95	25.3	50	6.51
33 ✓ 11407	9.40	6.30	14.2	153	0.60

11-2021-79

Assayer:

Lawrence


CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date: Dec 15/87

Sample Origin: Drill Cores

Sample Number	Pb	Zn	Fe	Ag	Cu HCl sol Fe				
1 ✓ 11090	0.46	1.16	251	12	4.97				
2 ✓ 11098	1.34	0.98	12.9	19	3.37				
3 ✓ 11104	4.53	4.92	340	54	8.33				
4 ✓ 11106	0.11	0.28	17.3	8	3.65				
5 ✓ 11107	0.30	0.44	20.7	12	2.70				
6 ✓ 11108	4.30	2.77	19.1	74	5.62				
7 ✓ 11116	0.08	0.21	5.12	2	2.90				
8 ✓ 11117	1.59	2.66	14.3	21	4.72				
9 ✓ 11118	2.63	7.24	13.4	43	3.67				
10 ✓ 11120	1.17	1.65	13.4	15	5.26				
11 ✓ 11121	0.91	0.79	10.7	12	2.88				
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: 

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet


Production Date:

Nov 8, 187

Sample Origin:

Drill Cores

Sample Number	Pb	Zn	Fe	Ag	Su HCl sol Fe				
1 ✓ 11008	2.43	3.90	12.9	39	1.51				
2 ✓ 11009	5.43	7.13	29.0	93	2.60				
3 ✓ 11010	5.93	6.58	15.5	81	1.50				
4 ✓ 11011	0.93	1.26	18.9	17	6.28				
5 ✓ 11012	0.11	0.16	5.83	4	2.92				
6 ✓ 11013	0.16	0.12	18.5	12	0.54				
7 ✓ 11023	9.43	9.85	27.2	103	6.21				
8									
9									
10									
11									
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: 

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date:

Nov 21, 1987

Sample Origin:

Drill Cores

	Sample Number	Pb	Zn	Fe	Ag	Cu	Hg	Sol Fe		
1	✓ 11037	0.77	0.19	33.2	22		2.10			
2	✓ 11038	0.19	0.16	24.3	10		2.42			
3	✓ 11039	0.20	0.29	20.9	10		3.35			
4	✓ 11040	0.36	0.71	18.8	10		1.41			
5	✓ 11041	0.34	1.55	19.3	12		3.76			
6	✓ 11042	1.43	0.27	8.42	18		6.94			
7	✓ 11043	0.26	0.34	26.5	12		2.53			
8	✓ 11044	0.19	0.44	26.8	12		1.55			
9	✓ 11046	0.13	0.17	22.7	10		1.36			
10	✓ 11048	0.25	0.53	31.5	20		2.92			
11										
12										
13										
14										
15										
16										
17										
18										
19										
20										
21										
22										
23										
24										
25										
26										
27										
28										
29										
30										
31										
32										

Lou Johnston

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date:

November 9/87

Sample Origin: drill core

Sample Number	Pb*	Zn	Fe	Ag	HCl sol Fe				
1 ✓ 11001	0.14	0.14	17.6	10	1.61				
2 ✓ 11002	1.02	0.28	21.6	28	0.69				
3 ✓ 11003	0.68	0.36	19.8	22	0.93				
4 ✓ 11004	0.52	0.16	19.4	16	0.50				
5 ✓ 11005	0.37	0.40	16.4	10	1.40				
6 ✓ 11006	0.33	0.51	17.5	10	3.42				
7 ✓ 11007	0.70	1.98	19.9	12	2.65				
8									
9									
10 ✓ 11031	1.58	0.19	35.1	18	7.83				
11 ✓ 11032	0.26	0.14	29.6	4	2.05				
12 ✓ 11033	2.07	1.87	30.9	14	9.18				
13 ✓ 11034	1.88	2.13	29.9	18	2.00				
14 ✓ 11035	7.53	1.84	33.6	83	11.7				
15 ✓ 11036	0.16	0.13	28.4	6	2.23				
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date: Nov 7, 1987

Sample Origin: Drill Cores

Sample Number	Pb	Zn	Fe	Ag	HCl sol Fe	Cu			
1 ✓ 11014	8.74	7.32	25.9	110	15.3				
2 ✓ 11024	3.44	3.48	36.6	50	8.14				
3 ✓ 11025	0.67	1.19	22.0	15	12.4				
4 ✓ 11026	2.71	2.89	38.6	37	8.20				
5 ✓ 11027	6.50	7.33	17.9	75	2.81				
6 ✓ 11028	4.58	7.02	11.7	60	2.73				
7 ✓ 11029	5.98	6.60	32.4	56	3.83				
8 ✓ 11030	0.30	0.46	39.4	10	5.78				
9									
10									
11									
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Lou Johnston

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date:

Nov 7/87

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	Cu HCL	SOL FE			
1 11015	0.72	0.73	42.2	17	7.52				
2 11016	5.04	6.68	18.8	75	5.45				
3 11017	5.09	6.64	15.7	62	4.65				
4 11018	5.62	5.43	19.2	62	5.11				
5 11019	4.49	6.92	28.2	31	0.32				
6 11020	4.48	7.39	14.6	72	2.01				
7 11021	3.38	4.02	26.0	60	0.84				
8 11022	3.31	4.22	19.9	46	3.56				
9									
10									
11									
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: M. J. [Signature]

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date: NOV. 30/87

Sample Origin: DRILL CORE

Sample Number	Pb	Zn	Fe	Ag	Cu	HCl Soluble Fe
1 ✓ 11248	7.75	8.50	33.7	79		.52
2 ✓ 11249	8.47	10.0	30.9	109		.54
3 ✓ 11254	1.86	3.13	16.2	28		1.29
4 ✓ 11266	3.93	3.45	33.5	59		9.95
5 ✓ 11271	4.36	5.61	25.5	53		6.05
6 ✓ 11275	2.19	1.43	32.7	24		3.26
7 ✓ 11276	.38	1.23	19.6	14		3.47
8 ✓ 11279	5.53	4.99	10.4	49		3.02
9 ✓ 11283	.28	.14	32.8	12		3.48
10 ✓ 11287	.17	.24	25.8	16		3.10
11 ✓ 11289	.89	.07	27.1	14		1.86
12						
13						
14						
15						
16						
17						
18						
19						
20						
21						
22						
23						
24						
25						
26						
27						
28						
29						
30						
31						
32						

Assayer: Juni

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date: dec 11/87

Sample Origin: drill core

					HCl sol Fe			
Sample Number	Pb	Zn	Fe	Ag				
1 ✓ 11093	0.60	0.83	28.3	30	4.37			
2 ✓ 11094	3.48	5.43	35.7	73	0.94			
3 ✓ 11095	0.79	0.45	27.8	18	9.49			
4 ✓ 11096	1.44	1.38	27.5	26	8.32			
5 ✓ 11097	4.68	3.46	29.0	53	7.45			
6 ✓ 11099	0.68	0.63	8.58	8	3.30			
7 ✓ 11101	1.36	0.63	13.2	22	3.98			
8 ✓ 11110	7.25	10.1	25.3	111	1.94			
9 ✓ 11112	2.46	4.73	10.2	40	0.17			
10 ✓ 11114	0.05	0.67	5.40	2	4.16			
11 ✓ 11115	0.06	0.19	3.53	2	2.35			
12								
13								
14								
15								
16								
17								
18								
19								
20								
21								
22								
23								
24								
25								
26								
27								
28								
29								
30								
31								
32								

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Dec 15/87

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	# Cu SO ₄ FE				
1 ✓ 11124	0.40	0.55	21.0	10	3.16				
2 ✓ 11125	0.16	0.18	16.5	8	4.63				
3 ✓ 11127	0.16	0.20	17.5	6	3.86				
4 ✓ 11128	0.09	0.08	17.5	8	3.15				
5 ✓ 11129	0.18	0.15	19.3	10	2.03				
6 ✓ 11130	0.43	0.52	16.7	10	2.46				
7 ✓ 11132	0.07	0.43	17.8	8	2.80				
8 ✓ 11134	0.29	0.27	5.77	4	2.14				
9 ✓ 11137	0.24	0.47	7.10	4	2.78				
10 ✓ 11138	3.81	4.41	31.6	58	1.50				
11 ✓ 11140	0.07	0.13	14.3	4	2.46				
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: M. Lewis

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Feb 14, 1988

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	HCl sol Fe				
1 ✓ 11089	0.76	2.02	26.4	14	10.0				
2 ✓ 11092	0.68	0.86	26.5	31	2.48				
3 ✓ 11100	2.42	2.39	15.5	27	3.44				
4 ✓ 11103	3.87	4.57	22.2	46	7.92				
5 ✓ 11105	4.30	3.94	31.4	50	8.60				
6 ✓ 11109	6.54	9.69	33.0	99	3.70				
7 ✓ 11111	3.68	7.24	9.96	62	0.81				
8 ✓ 11122	2.86	3.85	29.9	35	2.61				
9 ✓ 11135	3.53	6.72	19.3	46	2.76				
10 ✓ 11141	0.13	0.13	9.43	4	2.22				
11 ✓ 11143	0.18	0.80	10.1	4	1.30				
12 ✓ 11147	1.61	2.69	28.4	35	3.26				
13 ✓ 11151	0.47	0.35	30.1	19	2.78				
14 ✓ 11160	0.45	1.65	10.4	10	9.20				
15 ✓ 11164	10.3	10.9	20.1	114	12.0				
16 ✓ 11168	0.93	1.12	23.7	19	16.6				
17 ✓ 11169	0.27	0.70	30.5	12	16.8				
18 ✓ 11172	0.16	0.50	23.2	8	6.48				
19 ✓ 11173	0.58	0.46	21.9	12	5.65				
20 ✓ 11174	0.56	0.36	21.7	12	7.45				
21 ✓ 11175	0.32	0.43	25.0	10	10.5				
22 ✓ 11178	0.24	0.24	18.0	10	3.03				
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Kay Johnston

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Jan 27 / 88

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	HCl _(sol) /Fe
✓ 11300	2.07	4.40	14.5	32	4.48
✓ 11303	1.94	1.61	36.7	34	7.74
✓ 11305	5.10	7.44	11.4	77	1.89
✓ 11306	5.96	8.12	16.2	93	1.13
✓ 11307	3.57	5.71	25.4	60	2.54
✓ 11308	4.33	4.90	29.8	71	5.47
✓ 11309	5.42	7.56	18.9	77	2.94
✓ 11310	1.84	3.58	6.77	22	2.82
✓ 11311	1.28	2.46	5.94	18	3.88
11312	0.03	0.17	4.60	2	3.41
✓ 11313	2.07	3.53	6.26	34	4.88
✓ 11314	1.82	2.76	4.25	28	3.36
✓ 11315	0.08	0.52	7.89	4	7.26
✓ 11316	1.49	2.91	6.69	28	4.33
✓ 11317	0.04	0.16	4.45	2	3.20
✓ 11318	0.04	0.16	3.64	2	3.29
✓ 11319	2.70	2.53	4.37	32	2.26
✓ 11320	1.62	3.17	7.01	26	2.98
✓ 11321	0.03	0.11	7.61	2	3.20
✓ 11322	4.14	7.30	16.1	67	1.08
✓ 11323	1.42	3.20	27.2	32	0.91
✓ 11324	4.77	7.91	13.4	83	2.83
23					
24					
25					
26					