

019103

DIFFERENCES IN ASSAY RESULTSCAMC vs KA

Ag (g/tonne) Difference	Ag (g/tonne) % Difference	Pb Difference	Pb % Difference	Zn Difference	Zn % Difference	Length Assayed Difference
+ 3.10	+ 5.32	- 0.06	- 1.38	+ 0.15	+ 4.40	-0.1 M
- 3.55	- 5.17	- 0.49	-11.47	+ 0.01	+ 0.12	+0.6 M
- 3.80	- 4.10	- 0.68	-14.65	- 0.66	- 8.01	0
+ 6.21	+10.94	- 0.21	- 6.36	- 0.06	- 1.16	-0.2 M
+11.76	+23.56	+ 0.38	+10.27	+ 0.68	+20.99	-1.0 M
+ 5.58	+22.52	+ 0.48	+37.50	+ 0.84	+35.90	+2.1 M
+17.11	+12.85	+ 0.35	+ 4.40	+ 0.44	+ 2.82	0
+ 9.96	+ 9.37	- 0.38	- 7.24	- 0.26	- 2.90	0
+ 1.66	+ 3.41	- 0.63	-22.34	- 0.19	- 3.58	-0.4 M
+ 1.84	+ 3.97	- 0.21	- 7.09	+ 0.04	+ 0.96	-0.3 M
+ 2.10	+22.20	- 0.01	- 2.17	+ 0.11	+18.03	+3.7 M
+35.48	+17.20	+ 1.59	+10.93	+ 0.32	+ 3.18	0
+ 9.38	+12.42	- 0.21	- 4.24	+ 0.95	+10.76	-1.8 M
-10.97	-27.30	- 0.72	-27.17	- 1.22	-22.22	+3.8 M
+ 2.07	+ 2.81	- 0.24	- 4.40	- 0.30	- 5.33	+0.3 M
+ 1.61	+ 9.33	- 0.05	- 5.38	+ 0.02	+ 1.94	+2.0 M
+ 4.30	+51.62	+ 0.17	+36.96	+ 0.58	+54.72	0
- 0.06	- 0.28	- 0.14	-14.58	- 0.05	- 2.40	+2.7 M
+ 2.28	+26.15	+ 0.05	+12.50	+ 0.16	+21.62	+3.1 M
+ 3.43	+39.07	+ 0.06	+42.86	+ 0.19	+30.65	+0.2 M
+ 6.29	+17.43	+ 0.28	+12.84	+ 0.57	+15.24	-0.3 M
+ 5.18	+27.82	+ 0.05	+ 4.76	+ 0.21	+21.00	-0.3 M
+ 3.90	+26.03	- 0.06	-13.04	+ 0.04	+10.53	+0.6 M
+ 2.60	+ 7.05	- 0.49	-17.88	- 0.30	-10.42	0
+ 2.14	+20.48	+ 0.01	+ 6.67	+ 0.04	+20.00	0
+ 6.95	+14.82	- 0.19	- 6.03	- 0.39	-10.03	0
- 3.53	-32.27	- 0.06	-11.54	- 0.03	- 2.94	-0.6 M

Ag (g/tonne) Difference	Ag (g/tonne) % Difference	Pb Difference	Pb % Difference	Zn Difference	Zn % Difference	Length Assayed Difference
+ 1.91	+11.60	- 0.11	-15.94	- 0.07	- 9.72	0
- 5.71	- 5.55	+ 0.12	+ 1.63	+ 0.19	+ 2.97	+0.1 M
+ 7.05	+10.0	+ 0.30	+ 6.52	+ 0.59	+ 9.88	-0.1 M
+ 0.75	+ 9.73	- 0.06	-31.58	- 0.03	- 8.11	-0.2 M
+ 4.54	+10.15	- 0.39	-14.94	- 0.56	-16.82	0
- 0.60	- 2.82	+ 0.07	+ 5.26	+ 0.13	+ 9.29	+0.5 M
+13.84	+23.73	+ 0.23	+ 6.39	-0.60	- 7.95	+1.0 M
+22.76	+20.23	+ 0.17	+ 2.59	- 0.10	-0.81	-0.3 M
+ 1.83	+10.91	- 0.11	-10.78	- 0.14	- 7.04	+0.3 M
+32.42	+38.69	+ 1.50	+34.17	+ 0.77	+12.69	-2.0 M
+ 5.19	+17.23	+ 0.23	+10.95	- 0.32	-24.62	-0.3 M
+ 0.45	+ 0.89	- 0.41	-15.36	+ 0.59	+ 9.08	0
+ 4.70	+ 6.89	- 0.33	- 6.06	- 0.17	- 3.02	0
+ 1.30	+ 6.34	- 0.47	-29.94	- 0.15	-10.79	0
- 6.49	+ 7.49	- 5.36	-192.45	+ 0.19	+ 3.10	0
+ 5.33	+26.96	+ 0.26	+22.61	+ 0.22	+17.46	+1.6 M
- 3.90	- 8.07	- 0.47	-15.61	- 0.34	- 6.79	-1.0 M
+20.23	+16.91	- 0.09	- 1.42	+ 0.39	+ 2.79	+0.1 M
+ 9.45	+15.23	- 0.01	- 0.32	+ 0.46	+ 9.87	+0.1 M
-10.20	-10.23	- 0.21	- 3.35	- 1.35	-11.18	+0.9 M
- 0.98	- 3.71	- 0.04	- 2.35	- 0.09	- 3.01	-1.1 M
+11.16	+15.51	+ 0.37	+ 9.00	+ 1.01	+10.52	+0.2 M
+35.16	+26.39	+ 2.50	+29.76	+ 3.21	+19.44	-0.3 M
-20.50	-29.25	- 2.00	-55.71	- 4.06	-59.18	-2.1 M
+ 7.54	+22.07	+ 0.68	+28.45	+ 0.65	+14.35	+0.8 M
- 0.03	- 0.04	- 0.38	- 7.20	- 0.01	-0.10	+0.1 M
+ 0.34	+ 2.84	- 0.02	- 4.44	+ 0.01	+ 0.79	+0.9 M
+ 0.32	+ 1.77	- 0.06	- 8.70	-0.08	- 8.00	-1.2 M
+ 6.73	+17.18	- 0.01	- 0.39	+ 0.24	+ 6.43	+1.3 M
- 9.53	-25.45	- 0.77	-33.77	- 0.87	-41.63	-1.4 M
+ 2.87	+17.72	+ 0.01	+ 1.47	+ 0.03	+ 4.11	-0.1 M
AVERAGE DIFFERENCE	<u>± 15.12%</u>		<u>± 16.65%</u>		<u>± 11.96%</u>	<u>0.9 M</u>

GRUM SAMPLE NUMBERS

SECTIONS 68W, 80W, 74W,

HOLE NO.		SAMPLE NOS.	ASSAY CERT.
^{80W} ↓ 76-A 142	CA	5301 - 5331	✓ ✓
74-A 13	CA/KA	5210 - 5213; ^{KA} 2602, 2603	✓ ✓
76-U-181	CA	5229 - 5243	✓
76-U 183	CA	5128 - 5140	
74-A 52	CA	5104 - 5123; ^{NOT RESAMPLED?} 864, 865 >KA.	✓ ✓
76-A 134	CA	5244 - 5272	✓ ✓
76-A 147	CA	5166 - 5198	✓ ✓
75-A 74	CA	5001 - 5050; 5101 - 5103	✓ ✓
75-A 106	CA	5216 - 5228	✓ ✓
76-A 143	CA	1644 - 1646	✓
76-A 145	CA	5199, 5200.; 5214, 5215	✓ ✓
74-A 45	CA	1611 - 1643	✓
76-A 153	CA	1579 - 1610	✓
74-A 17	CA/KA	5201 - 5209; ^{KA} 2653 - 2655	✓ ✓
^{68W} ↑ ^{80W} ↓ 74-A 23	CA	1647 - 1650; 5051 - 5100; 5151 - 5165	✓ ✓
75-A 79	KA	1909 - 1940	
74-A 38	KA	711 - 742	
74-A 27	KA	449 - 480; 482 - 502	
76-U 135	CA	3964 - 3979; 3997 - 4000; 4081 - 4093	
76-U 152	KA	4743 - 4753	
76-U 154	KA	4646 - 4661	
76-U 153	KA	4716 - 4742	
76-U 151	KA	4627 - 4645	
76-U 156	KA	4662 - 4676	

HOLE NO.

SAMPLE NOS.

ASSAY CERT

HOLE NO.		SAMPLE NOS.	ASSAY CERT
76-U150	KA	4198 - 4215	
76-U146	KA	4255 - 4267	
76-U140	KA	4094 - 4101	
76-U144	CA	4252 - 4254	
76-U142	KA	4202 - 4250	
74-A35	KA	648 - 679	
74-A32	KA	622 - 647	
74-A41	KA	755 - 784	
74-A24	KA	332 - 386	
76-A163	KA	715 - 749	
76-A164	CA	?	
76-A160	KA	553 - 581	
75-A76	KA	1582 - 1908	
75-A69	KA	1353 - 1371 ; 1372 - 1399	
		; 1400 ; 1601 - 1629	
^{80W} ↑ 76-U149	KA	4289 - 4300 ; 4601 - 4626	
^{74W} ↓ 76-U057	KA	2159 - 2181	
76-U44	KA	1888 - 1901	
75-A88	KA	2058 - 2084 ; 2090 - 2100	
		2085 - 2089 ; 2211 ;	?
		1832 - 1848	
76-U53	KA	2077 - 2083 ; 2085 - 2101	
76-U33	KA	1581 - 1583	
76-U30	KA	1539 - 1553	
76-U39	KA	1775 - 1819	
76-U40	KA	1820 - 1846	
76-U43	KA	1874 - 1887	
76-U52	KA	2062 - 2076	
76-U117	KA	3831 - 3840	

HOLE NO.

SAMPLE NOS.

ASSAY CERT.

76-U28	KA	1513 - 1527	
76-U29	KA	1528 - 1538	
76-U46	KA	1927 - 1947	
76-U42	KA	1854 - 1873	
76-U34	KA	1584 - 1600; 1701 - 1724; 1525 - 1527	
76-U47	KA	1948 - 1972	
76-U55		?	
75-A92	KA	1893 - 1899; 2212 - 2215	
75-A71	KA	1439 - 1459	
75-A90	KA	1849 - 1856; 1857 - 1892	
76-A141	KA	4341 - 4361	
74-A11	KA	2559 - 2572	
75-A65	KA	1280 - 1292	
76-U56	KA	2139 - 2158	
76-U45	KA	1902 - 1926	
76-U54	CA	2102 - 2106; 1207 - 1215 ; 2116 - 2138	
76-U15	KA	1278 - 1313; 1628 - 1629	
76-U51		2020 - 2025; 2046 - 2061; 2084	
76-U49	KA	2004 - 2019	
76-U41		1847 - 1853	
76-U35	KA	1728 - 1750	

GRUM ASSAY

DDH	FROM	TO	SAMPLE #	GRUM ASSAY				LENGTH M	CAMC AVERAGED VALUES				KERR ADDISON ^② AVERAGED VALUES					
				SILVER (g/TONNE)	Pb %	Zn %	Cu %		As (g/ton)	Pb %	Zn %	TOTAL LENGTH	Ag (g/ton)	Pb %	Zn %	TOTAL LENGTH		
76-A-142	159.2	161.5	5318	61	4.35	7.28	.11	2.3M										
	161.5	163.5	19	12	.42	3.98	.21	④ 2.0										
	163.5	165.0	20	22	.45	2.73	.79	1.5										
	165.0	166.1	21	69	4.17	3.81	.52	1.1	56.79	3.30	5.18	11.20 ✓	50.58	3.51	5.24	11.40 ✓		
	198.7	200.4	22	25	2.06	2.56	.26	1.7										
	242.8	243.5	23	56	3.60	3.67	.18	0.7										
	243.5	244.3	24	12	.78	.60	.19	0.8										
	244.3	245.1	25	69	5.23	4.32	.26	0.8										
	245.1	245.7	26	39	3.40	3.11	.15	③ 0.6										
	245.7	247.7	27	56	4.38	3.47	.19	2.0										
	247.7	249.2	28	49	3.98	3.68	.18	1.5										
	249.2	250.2	29	59	4.80	4.29	.21	1.0										
	250.2	252.4	30	40	2.70	2.57	.17	2.2										
	252.4	253.0	5331	82	4.76	3.83	.08	0.6M	49.91	3.70	3.24	10.2 ✓	38.15	3.32	2.56	11.2 ✓		

GRUM ASSAY

CAMC AVERAGED VALUES

KERR ADDISON^③ AVERAGED VALUES

DDH	FROM	TO	SAMPLE#	SILVER (g/TONNE)	Pb %	Zn %	Cu %	LENGTH FT	As (g/ton)	Pb %	Zn %	TOTAL LENGTH	Ag (g/ton)	Pb %	Zn %	TOTAL LENGTH		
74-A-13	134.0	144.5	5210	34	1.32	.87	.20	10.5'										
	144.5	158.5	2602	} not resampled? KA numbers				13.0										
	158.5	171.5	2603					13.0										
	404.0	409.7	5211	68	3.06	5.09	.13	5.1										
	427.0	437.0	5212	12	.78	1.65	.07	① 10.0	/	/	/	(8.14M)	/	/	/	/	/	
74-A-13	437.0	448.0	5213	14	.81	1.54	.11	11.0'	24.78	1.28	2.34	26.7ft.	19.2	.80	1.5	6.10		
76-U-181	0.0	1.5	5229	134	6.37	13.55	.16	1.5M										
	1.5	3.0	30	149	9.20	15.21	.15	1.5M										
	3.0	4.5	31	91	7.33	12.03	.25	1.5M										
	4.5	6.0	32	99	4.01	9.15	.16	① 1.5										
	6.0	7.4	33	94	5.95	12.82	.24	1.4										
	7.4	8.0	34	113	4.86	10.01	.20	0.6										
	8.0	10.0	35	167	9.80	21.30	.10	2.0										
	10.0	11.8	36	199	12.60	23.70	.06	1.8	/	/	/	11.8 M	/	/	/	/	/	/
76-U-181	49.8	51.3	37	105	4.68	9.05	.12	② 1.5	133.14	7.96'	15.60'	11.8 M	116.03	7.61	15.16	11.8		

GRUM ASSAY

CAMC AVERAGED VALUES

KERR ADDISON ④ AVERAGED VALUES

DDH	FROM	TO	SAMPLE #	SILVER (g/TONNE)	Pb %	Zn %	Cu %	LENGTH RX	As (g/ton)	Pb %	Zn %	TOTAL LENGTH	As (g/ton)	Pb %	Zn %	TOTAL LENGTH	
76-U-181	51.3	52.8	5238	106	6.47	11.90	.14	1.5M									
}	52.8	54.3	39	94	5.19	9.73	.12	1.5									
	54.3	55.8	40	106	4.99	9.07	.11	② 1.5									
	55.8	57.3	41	45	2.20	5.21	.07	1.5									
	57.3	58.8	42	118	5.78	8.07	.20	1.5									
76-U-181	58.8	60.4	43	166	7.32	9.65	.26	1.6	106.28	5.25	8.96	10.6	94.32	5.63	9.22	10.6	
<hr/>																	
74-A-52	^{157.67M} 517.3	522.3	5104	50	3.17	5.70	.04	0 5.0 FT				2.80 M					
}	^{160.97M} 522.3	526.5	105	47	2.41	4.84	.03	4.2	48.63	2.82	5.31	9.2 FT	46.97	3.45	5.50	3.20M	
	^{115.56M} 576.0	580.0	106	57	4.80	4.92	.19	4.0									
	580.0	582.3	107	69	4.88	7.85	.06	2.3									
	582.3	589.2	108	34	1.56	2.26	.25	② 6.9									
	589.2	596.0	109	44	2.51	3.99	.14	6.8									
	596.0	600.0	110	49	3.32	5.46	.09	4.0									
	600.0	604.0	111	68	4.87	5.38	.11	4.0				10.36M					
74-A-52	^{185.92} 604.0	610.0	5112	31	1.58	2.93	.33	6.0	46.31	2.96	4.16	34.0 FT	44.47	3.17	4.12	10.67	

GRUM ASSAY

CAMC AVERAGED VALUES

KERR ADDISON ⑦ AVERAGED VALUES

DDH	FROM	TO	SAMPLE #	SILVER (g/TONNE)	Pb %	Zn %	Cu %	LENGTH RX	CAMC AVERAGED VALUES				KERR ADDISON ⑦ AVERAGED VALUES					
									Ag (g/ton)	Pb %	Zn %	TOTAL LENGTH	Ag (g/ton)	Pb %	Zn %	TOTAL LENGTH		
76-A-134	171.2	174.2	5265	8	.11	.10	.52	3.0M										
}	174.2	176.2	66	25	1.55	1.40	.24	2.0										
	176.2	178.2	67	55	4.23	6.01	.12	③ 2.0										
	178.2	181.2	68	22	1.67	1.00	.13	3.0										
	181.2	183.2	69	10	.29	.60	.18	2.0										
	183.2	185.2	70	12	.36	.54	.34	2.0										
	185.2	187.2	71	10	.37	.57	.26	2.0										
76-A-134	187.2	189.7	5272	11	.36	.58	.27	2.5	17.26	.93	1.03	23.0M	15.65	.98	1.01	22.80		
76-A-147	43.7	46.1	5166	32	1.22	3.78	.03	2.4 M										
}	47.4	48.0	67	20	1.15	2.62	.06	0.6										
	48.0	49.4	68	15	.81	2.05	.05	① 1.4										
	49.4	51.0	69	12	.74	1.45	.12	1.6										
	51.0	52.7	70	21	1.40	3.39	.09	1.7	16.58	1.02	2.36	5.30	0	0	0	0		
	77.6	78.6	71	8	.50	.80	.06	1.0										
76-A-147	82.0	85.2	5172	15	.64	1.29	.15	② 3.2										

11

GRUM ASSAY

CAMC
AVERAGED VALUES

KERR ADDISON (8)
AVERAGED VALUES

DDH	FROM	TO	SAMPLE #	SILVER (g/TONNE)	Pb %	Zn %	Cu %	LENGTH	CAMC AVERAGED VALUES				KERR ADDISON (8) AVERAGED VALUES					
								Rx	As (g/ton)	Pb %	Zn %	TOTAL LENGTH	As (g/ton)	Pb %	Zn %	TOTAL LENGTH		
76-A-147	85.2	88.4	5173	3	.25	.76	.04	3.2M										
	88.4	90.0	74	9	.61	1.36	.05	② 1.6										
	90.0	92.0	75	7	.30	.58	.07	2.0										
	92.0	94.0	76	7	.55	1.41	.03	2.0	8.33 ✓	.46 ✓	1.06 ✓	12.0 ✓	4.03 ✓	.29 ✓	.48 ✓	12.0 ✓		
	94.0	97.0	77	7	.58	1.49	.03	3.0										
	97.0	99.0	78	25	.61	1.07	.15	2.0										
	99.0	101.0	79	17	.49	2.38	.10	① 2.0										
	101.0	103.0	80	52	2.99	5.07	.10	2.0										
	103.0	105.0	81	15	.49	1.29	.10	2.0										
	105.0	106.8	82	20	.75	1.38	.11	1.8	21.48 ✓	.96 ✓	2.08 ✓	12.8 M ✓	21.54 ✓	1.10 ✓	2.13 ✓	10.10 ✓		
	146.9	148.4	83	9	.50	.92	.06	1.5										
	148.4	150.0	84	6	.32	.50	.08	1.6										
	150.0	152.0	85	8	.27	.61	.09	③ 2.0										
	152.0	154.5	86	15	.71	1.29	.07	2.5										
	154.5	156.1	87	2	.10	.21	.07	1.6										
	156.1	157.6	88	9	.33	.67	.20	1.5	8.72 ✓	.40 ✓	.74 ✓	10.70 M ✓	6.44 ✓	.35 ✓	.58 ✓	7.6 ✓		
76-A-147	160.7	163.4	5189	6	.04	.29	.20	④ 2.7										

complete interval not sampled

GRUM ASSAY

LENGTH

CAMC AVERAGED VALUES

KERR ADDISON ⑩ AVERAGED VALUES

DDH	FROM	TO	SAMPLE#	SILVER (g/TONNE)	Pb %	Zn %	Cu %	LENGTH	As (g/ton)	Pb %	Zn %	TOTAL LENGTH	Ag (g/ton)	Pb %	Zn %	TOTAL LENGTH	
75-A-74	338.0	343.0	5007	21	.66	.34	.40	5.0 FT									
	343.0	348.0	08	8	.11	.13	.38	5.0									
	348.0	353.0	09	11	.09	.18	.57 ②	5.0									
	353.0	358.0	10	11	.10	.22	.40	5.0									
	358.0	363.0	11	11	.14	.40	.52	5.0									
	363.0	368.0	12	10	.10	.40	.25	5.0				15.85M					
	368.0	375.0	13	7	.12	.51	.13	7.0	14.98	.46	.38	52.0 FT	11.08	.52	.34	15.24M	
	515.3	520.7	14	15	.75	.61	.20	5.4									
	526.0	530.0	15	30	2.15	2.37	.26	③ 4.0				2.59M					
	530.0	534.5	16	43	3.27	3.34	.22	4.5	36.88	2.74	2.88	8.5	34.28	3.23	3.18	2.6M	
	534.5	539.0	17	7	.23	.24	.18	4.5									
	539.0	543.0	18	14	.14	.15	.19	4.0									
	543.0	547.0	19	8	.17	.12	.17	④ 4.0									
	547.0	551.0	20	11	.06	.05	.16	4.0									
	551.0	555.0	21	13	.14	.26	.24	4.0									
	555.0	559.0	22	14	.18	.36	.24	4.0									
75-A-74	559.0	562.0	5023	11	.16	.26	.16	3.0									

160.32

114.29M

162.91

162.91

GRUM ASSAY

LENGTH

CAMC AVERAGED VALUES

KERR ADDISON ⑫ AVERAGED VALUES

DDH	FROM	TO	SAMPLE #	SILVER (g/TONNE)	Pb %	Zn %	Cu %	LENGTH	CAMC AVERAGED VALUES				KERR ADDISON ⑫ AVERAGED VALUES					
									As (g/ton)	Pb %	Zn %	TOTAL LENGTH	Ag (g/ton)	Pb %	Zn %	TOTAL LENGTH		
75-A 74	658.0	663.0	5041	9	.07	.24	.27	5.0 FT										
	663.0	668.0	42	12	.40	.18	.18	5.0										
	668.0	673.0	43	11	.21	.19	.21	5.0										
	673.0	678.0	44	40	2.69	2.98	.20	⑤ 5.0										
	678.0	683.0	45	11	.28	.15	.18	5.0										
	683.0	688.0	46	10	.27	.23	.24	5.0										
	688.0	692.0	47	12	.50	.74	.15	4.0										
	692.0	695.4	48	100	6.63	7.73	.16	3.4										
	695.4	700.0	49	5	.18	.18	.02	4.6				26.67M						
	700.0	704.0	5050	23	1.62	1.12	.20	4.0	16.46	.69	.92	87.5 FT	14.55	.80	.79	27.67		
	732.5	737.6	5101	22	1.57	1.36	.28	5.1										
	953.0	958.0	5102	5	.11	.07	.02	⑥ 5.0				2.9 M	not sampled.					
	958.0	962.5	5103	4	.04	.02	.01	4.5	4.53	.08	.05	9.5 FT	0.7	0	0	0		

GRUM ASSAY

DDH	FROM	TO	SAMPLE #	SILVER (g/TONNE)	Pb %	Zn %	Cu %	LENGTH
75-A 106	46.9	49.2	5216	153	10.79	8.03	.06	① 2.3 M
	49.2	50.5	17	14	1.36	3.52	.03	1.3
	90.3	91.4	18	139	11.60	8.03	.09	1.1
	151.3	154.2	19	97	5.48	9.05	.05	2.9
	154.2	154.8	20	87	5.32	6.77	.11	② 0.6
	154.8	157.0	21	96	6.82	9.21	.06	2.2
	157.0	159.8	22	37	1.93	2.38	.10	2.8
	159.8	162.0	23	54	3.82	5.53	.06	2.2
	162.0	163.9	24	24	1.26	1.88	.03	1.9
	168.7	172.0	25	8	.16	.49	.19	3.3
	172.0	175.0	26	7	.13	.27	.23	③ 3.0
	175.0	178.0	27	10	.26	.36	.24	3.0
75-A 106	178.0	181.3	5228	6	.22	.35	.18	3.3

CAMC AVERAGED VALUES				KERR ADDISON (B) AVERAGED VALUES			
As (g/ton)	Pb %	Zn %	TOTAL LENGTH	Ag (g/ton)	Pb %	Zn %	TOTAL LENGTH
102.81	7.38	6.40	3.6	108.52	7.26	6.21	3.5
70.48	4.60	5.97	13.7	63.43	4.30	5.38	13.8
7.71	.19	.37	12.6	6.96	.25	.40	12.80

GRUM ASSAY

DDH	FROM	TO	SAMPLE #	SILVER (g/TONNE)	Pb %	Zn %	Cu %	LENGTH
76-A 145	41.8	43.3	5199	13	.81	.94	.09	1.5 M
}	48.0	50.3	5200	148	11.40	12.80	.12	2.3
	78.3	80.0	5214	26	1.39	2.85	.14	① 1.7
76-A 145	80.0	83.1	5215	55	3.28	3.59	.29	3.1
210M								
74-A 17	689.0	700.0	5201	28	1.86	1.51	.50	11.0 FT
	711.0	727.0	5202	27	1.80	1.78	.28	① 14.0
	745.2	753.0	5203	27	1.58	1.35	.21	7.8
	761.0	771.0	2653					10.0
	771.0	778.0	2654					7.0
	778.0	784.0	2655					6.0
	787.0	798.5	5204	17	1.14	.94	.09	12.5
	798.5	808.0	5205	21	1.26	2.07	.16	① 9.5
	808.0	818.5	5206	16	.99	1.17	.15	10.5
	818.5	828.5	5207	32	1.96	1.75	.24	10.0
	828.5	833.0	5208	22	1.42	1.05	.25	5.0

CAMC AVERAGED VALUES

As (g/ton)	Pb %	Zn %	TOTAL LENGTH
/	/	/	/
44.73	2.61	3.33	4.8
27.34	1.77	1.59	32.80 FT
/	/	/	14.48M
21.26	1.33	1.40	47.50 FT

KERR ADDISON ⑭ AVERAGED VALUES

Ag (g/ton)	Pb %	Zn %	TOTAL LENGTH
/	/	/	/
40.19	3.00	3.89	4.8
21.86	1.26	1.27	14.02


GRUM ASSAY

LENGTH

CAMC AVERAGED VALUES

KERR ADDISON ⁽¹⁵⁾ AVERAGED VALUES

DDH	FROM	TO	SAMPLE#	SILVER (g/TONNE)	Pb %	Zn %	Cu %	LENGTH	As (g/ton)	Pb %	Zn %	TOTAL LENGTH	As (g/ton)	Pb %	Zn %	TOTAL LENGTH	
74-A-45	146.0	167.0	1611	67	4.63	7.23	.12	21.0 FT									
	167.0	170.0	1612					NO RECOVERY 3.0									
	170.0	174.0	1613	37	2.64	5.83	.04	4.0									
	174.0	183.5	14	37	1.96	5.15	.03	9.5									
	183.5	190.0	15	60	3.37	5.05	.04	6.5									
	190.0	200.0	16	72	4.51	12.90	.06	10.0									
	200.0	203.0	17	105	7.52	5.05	.04	3.0	58.32	3.60	7.55	33.0 FT	44.48	3.37	8.15	9.14	
	210.5	218.0	18	99	6.17	9.05	.08	7.5				10.06M					
	242.1	251.0	19	11	0.45	1.21	.10	8.9									
	251.0	255.0	20	119	6.90	15.9	.13	4.0									
	255.0	260.0	21	124	7.94	15.50	.14	5.0									
	260.0	266.0	22	162	9.08	16.20	.24	6.0									
	266.0	275.0	23	157	9.49	16.80	.18	9.0									
	275.0	277.0	24	165	7.73	16.20	.13	2.0									
	277.0	284.0	25	17	1.42	2.41	.11	7.0									
	284.0	288.5	26	64	3.05	5.73	.12	4.5	112.48	6.57	12.39	37.50	89.72	6.40	12.49	11.73	
74-A-45	545.0	550.5	1627	4	0.19	0.42	.06	5.5				11.43M					



GRUM ASSAY

CAMC AVERAGED VALUES

KERR ADDISON (16) AVERAGED VALUES

DDH	FROM	TO	SAMPLE #	SILVER (g/TONNE)	Pb %	Zn %	Cu %	LENGTH FT	CAMC AVERAGED VALUES				KERR ADDISON (16) AVERAGED VALUES						
									As (g/ton)	Pb %	Zn %	TOTAL LENGTH	Ag (g/ton)	Pb %	Zn %	TOTAL LENGTH			
74-A-45	550.5	556.0	1628	42	2.99	5.09	.14	③ 5.5 FT											
}	556.0	562.0	29	6	0.22	0.35	.10	6.0	/	/	/	/	/	/	/	/	/	/	
	562.0	567.0	30	16	.73	2.29	.13	5.0	16.77	1.02	1.99	22 FT	14.94	1.13	2.13	6.4			
74-A-45	633.0	636.0	31	78	2.66	3.87	.02	3.0				6.71M							
}	636.0	640.0	32	125	6.79	8.53	.09	④ 4.0											
	640.0	645.0	33	40	2.62	3.34	.06	5.0	/	/	/	/	/	/	/	/	/	/	
	645.0	649.7	34	99	5.32	8.27	.18	4.7	83.79	4.39	6.07	16.70	51.37	2.89	5.30	7.01			
	652.9	660.0	35	35	2.52	2.20	.24	7.1				5.09M							
	660.0	665.0	36	20	1.81	0.37	.24	5.0											
	665.0	670.0	37	84	6.81	3.46	.23	5.0											
	670.0	680.0	38	18	1.07	0.22	.30	⑤ 10.0											
	680.0	685.0	39	11	0.38	0.18	.25	5.0											
	685.0	690.0	40	20	1.20	1.10	.21	5.0											
	690.0	692.0	41	33	2.17	1.08	.32	2.0											
74-A-45	697.0	699.0	1643	22	1.40	2.51	.23	2.0	30.12	2.10	1.30	46.10'	24.93	1.87	1.62	14.30			
												14.05M							

GRUM ASSAY

DDH	FROM	TO	SAMPLE #	SILVER (g/TONNE)	Pb %	Zn %	Cu %	LENGTH	CAMC AVERAGED VALUES				KERR ADDISON (18) AVERAGED VALUES					
								ft	As (g/ton)	Pb %	Zn %	TOTAL LENGTH	Ag (g/ton)	Pb %	Zn %	TOTAL LENGTH		
76-A-153	190.3	191.8	1596	12	.77	1.07	.22	1.5 M										
	191.8	192.5	97	19	1.16	1.82	.35	0.7										
	192.5	194.0	98	39	2.00	0.07	.30	1.5										
	194.0	197.0	99	8	0.58	0.71	.23	3.0										
	197.0	199.9	1600	20	1.23	1.89	.33	2.9										
	199.9	200.6	1601	23	1.74	2.70	.27	0.7										
	200.6	201.8	1602	47	2.89	2.70	.21	1.2										
	201.8	203.0	1603	16	.77	2.59	.08	1.2										
	203.0	206.0	04	19	.96	1.15	.35	3.0										
	206.0	207.5	05	9	.53	0.58	.27	1.5										
	207.5	209.0	06	30	1.87	1.22	.11	1.5										
	209.0	209.6	07	39	2.89	3.50	.09	0.6										
	209.6	210.9	08	20	0.78	0.98	.41	1.3										
	210.9	212.4	09	23	1.58	1.07	.18	1.5										
76-A-153	212.4	214.0	1610	9	0.46	0.44	.22	1.6	19.77	1.15	1.26	25.2M	14.44	.89	1.04	23.60		

GRUM ASSAY

DDH	FROM	TO	SAMPLE#	SILVER (g/TONNE)	Pb %	Zn %	Cu %	Rx
76-U-183	0.0	1.6	5128	84	5.23	11.40	.20	1.6
	1.6	3.0	29	43	2.57	1.83	.11	1.4
	3.0	4.5	5130	34	1.75	3.18	.15	① 1.5
	4.5	6.0	5130	34	1.75	3.18	.15	1.5
	6.0	7.5	31	41	2.86	3.48	.10	1.5
	7.5	9.7	32	52	3.90	6.69	.08	1.2
	9.7	11.2	33	93	6.09	12.00	.22	1.5
	11.2	12.7	34	142	8.00	15.10	.18	1.5
	12.7	14.2	35	130	7.32	13.10	.06	1.5
	14.2	15.7	36	78	3.90	7.63	.23	② 1.5
	15.7	17.2	37	75	4.95	9.50	.20	1.5
	17.2	18.3	38	91	4.57	13.20	.20	1.1
	18.3	20.3	39	177	7.13	20.60	.03	2.0
	20.3	21.9	5140	143	8.08	18.20	.05	1.6

CAMC AVERAGED VALUES

As (g/ton)	Pb %	Zn %	TOTAL LENGTH
48.33	3.01	5.01	8.70 M
119.66	6.36	14.0	12.2 M

KERR ADDISON ①⑨ AVERAGED VALUES

Ag (g/ton)	Pb %	Zn %	TOTAL LENGTH
52.23	3.48	5.35	9.7
99.43	6.45	13.61	12.10

GRUM ASSAY

CAMC AVERAGED VALUES

KERR ADDISON⁽²²⁾ AVERAGED VALUES

DDH	FROM	TO	SAMPLE #	SILVER (g/TONNE)	Pb %	Zn %	Cu %	RX	CAMC AVERAGED VALUES				KERR ADDISON ⁽²²⁾ AVERAGED VALUES					
									As (g/ton)	Pb %	Zn %	TOTAL LENGTH	Ag (g/ton)	Pb %	Zn %	TOTAL LENGTH		
74-A-23	347.0	355.0	5064	51	2.64	7.45	.01	③ 8.0										
		108.66M 355.0	65	43	2.83	11.71	.05	1.5	71.94	4.11	9.6	20.01	60.78	3.74	8.59	5.94		
		110.94M 364.0	66	47	2.72	4.96	.07	5.9				6.1M						
	377.0	382.0	5067	153	8.06	17.50	.09	5.0										
	382.0	387.0	68	178	10.60	18.60	.07	5.0										
	387.0	391.1	69	169	8.04	17.60	.11	④ 4.1										
	391.1	393.0	70	100	7.52	17.70	.03	1.9										
	393.0	398.0	71	129	9.09	19.91	.11	5.0										
	398.0	122.83M 403.0	72	158	13.20	22.30	.03	5.0	133.24	8.40	16.51	31.90	98.08	5.9	13.37	10.06		
	403.0	122.83M 409.0	73	137	7.27	12.51	.10	6.0				9.72M						
	409.0	415.0	74	100	5.34	10.71	.14	⑤ 6.0										
	415.0	420.0	75	12	.24	1.30	.15	5.0										
	420.0	129.53M 425.0	76	12	.44	1.03	.12	5.0	70.09	3.59	6.86	22.00	90.59	5.59	10.92	8.83		
	425.0	129.53M 430.0	77	14	.21	1.21	.14	5.0				6.71M						
	430.0	435.0	78	38	2.95	5.47	.10	⑥ 5.0										
74-A-23	435.0	134.26M 440.5	79	49	3.86	6.69	.06	5.5	34.16	2.39	4.53	15.5	26.62	1.71	3.88	3.97		
												4.72						

74-A-23

DDH	FROM	TO	SAMPLE #	SILVER (g/ton)	Pb %	Zn %	Cu %	Rx
74-A-23	440.5 ^{134.26}	445.5	5080	134	7.69	18.5	.03	5.5
	445.5	451.1	81	119	7.47	15.31	.13	④ 5.6
	451.1	457.1	82	48	4.16	5.44	.11	6.0
	457.1	463.1 ^{141.15 M}	83	28	2.16	2.46	.09	6.0
	463.1 ^{141.15 M}	469.1	84	10	.34	.67	.13	6.0
	469.1	474.4	85	10	.41	.81	.14	5.3
	474.4	477.3	86	28	1.78	3.58	.09	2.9
	477.3	483.0	87	15	.71	1.92	.14	5.7
	483.0	489.0	88	14	.47	.94	.11	② 6.0
	489.0	495.0	89	8	.23	.70	.17	6.0
	495.0	501.0	90	8	.20	1.18	.14	6.0
	501.0	507.0	91	8	.11	1.79	.29	6.0
	507.0	513.0 ^{156.35 M}	92	15	.51	1.01	.18	6.0
74-A-23	513.0 ^{156.35 M}	520.6	93	13	.42	.35	.40	③ 7.6

CAMC
AVERAGED VALUES

As (g/ton)	Pb %	Zn %	TOTAL LENGTH
80.49	5.28	10.17	23.10
			7.04 M
11.98	.45	1.27	49.9
			15.21 M

KERR ADDISON ②③
AVERAGED VALUES

Ag (g/ton)	Pb %	Zn %	TOTAL LENGTH
80.52	5.66	10.18	7.01
11.64	.47	1.26	14.32

GRUM ASSAY

CAMC AVERAGED VALUES

KERR ADDISON (24) AVERAGED VALUES

ID	FROM	TO	SAMPLE #	GRUM ASSAY					CAMC AVERAGED VALUES				KERR ADDISON (24) AVERAGED VALUES				
				SILVER (g/ton)	Pb %	Zn %	Cu %	Rx	As (g/ton)	Pb %	Zn %	TOTAL LENGTH	Ag (g/ton)	Pb %	Zn %	TOTAL LENGTH	
74-A 23	520.6	526.0	5094	14	.18	.37	.53	5.4									
	526.0	531.0	95	30	1.23	2.78	.35	5.0									
	531.0	536.0	96	38	1.72	1.51	.40	5.0									
	536.0	542.5	97	26	1.24	1.23	.34	6.5									
	542.5	549.1	98	21	.61	.37	.29	6.6									
	549.1	554.0	99	8	.10	.88	.44	(3) 4.9									
	554.0	558.0	5100	8	.06	.60	.30	4.0									
	558.0	563.0	151	3	.03	.50	.15	5.0									
	563.0	569.0	152	7	.16	.42	.19	6.0									
	569.0	576.0	153	31	1.39	2.09	.32	5.0									
	576.0	578.0	154	18	1.20	1.53	.09	4.0	18.11	.69	1.00	65.0	17.79	.72	1.08	21.05	
	235.60M	773.0	5155	64	4.59	7.11	.07	(4) 6.0				19.81M					
	779.0	785.3	156	3	.11	.22	.04	6.3									
	785.3	790.3	157	55	3.24	4.08	.27	5.0	39.18	2.57	3.73	17.30	32.45	2.58	3.49	3.96	
	790.3	795.3	158	33	1.74	1.50	.40	5.0				5.27M					
	795.3	800.3	159	38	2.76	1.75	.42	(5) 5.0									
74-A 23	800.3	804.6	5160	42	2.36	3.18	.21	4.3	37.45	2.28	2.09	14.30	46.98	3.05	2.96	5.76	
												4.36					

GRUM ASSAY

DD	FROM	TO	SAMPLE #	SILVER (g/TONNE)	Pb %	Zn %	Cu %	Rx
74-A-23	262.88 ^M 862.5	866.3	5161	17	.88	1.17	.17	3.8
	866.3	870.0	162	19	.60	.35	.27	3.7
	267.02 ^M 870.0	876.7	163	14	.60	.69	.22	6.1
	903.2	909.5	164	32	1.95	1.78	.22	6.3
	913.6	920.0	165	20	.85	1.05	.16	6.4

CAMC AVERAGED VALUES

As (g/ton)	Pb %	Zn %	TOTAL LENGTH
16.20	.68	.73	13.6
			4.15

KERR ADDISON⁽²⁵⁾ AVERAGED VALUES

Ag (g/ton)	Pb %	Zn %	TOTAL LENGTH
13.33	.67	.70	4.26