

1980 Drilling

CODING FORM

DATE

PAGE NO

OF


GRAM ASSAY DATA ADDITIONS & CORRECTIONS

Line No.

DDHID	FROM	TO	AI	%Pb	%Zn	Ag	%Cu	Au	%Hg	S.G.	NI
A-200	63.7	64.9	1.2	0.81	1.38	20.00	0.15	0.07		2.92	
	64.9	66.1	1.2	1.76	2.45	24.00	0.10	0.55		2.91	
	66.1	67.7	1.6	11.10	15.23	131.00	0.14	0.69		4.44	
	67.7	68.8	1.1	0.99	1.12	17.00	0.14	0.75		3.08	
	68.8	70.0	1.2	1.10	1.28	22.00	0.18	-0.14		3.16	
	70.0	71.2	1.2	10.90	19.68	141.00	0.13	1.23		4.24	
	71.2	72.5	1.3	9.10	15.49	129.00	0.22	1.58		4.52	
	72.5	73.9	1.4	1.55	2.52	32.00	0.10	0.82		3.21	
	73.9	78.7	4.8	-0.5	-0.5	-0.5	-0.5	-0.5		-0.5	
	78.7	79.8	1.1	0.92	1.41	15.00	0.10	1.10		2.88	
	79.8	80.8	1.0	1.45	1.81	20.00	0.08	0.55		2.94	
	80.8	157.5	76.7	-0.5	-0.5	-0.5	-0.5	-0.5		-0.5	
	157.5	159.0	1.5	0.10	0.39	4.00	0.09	0.07		2.85	
	159.0	160.5	1.5	0.01	0.28	2.00	0.16	0.34		2.81	
	160.5	162.0	1.5	0.03	0.05	2.00	0.06	0.14		2.81	
	162.0	163.5	1.5	0.06	0.21	2.00	0.07	0.14		2.86	
	163.5	165.4	1.9	0.60	1.40	10.00	0.10	0.62		2.88	
	165.4	167.2	1.8	-0.5	-0.5	-0.5	-0.5	-0.5		-0.5	
	167.2	168.9	1.7	0.12	0.65	4.0	0.13	0.27		2.88	
	168.9	175.0	6.1	-0.5	-0.5	-0.5	-0.5	-0.5		-0.5	
	175.0	175.9	0.9	9.50	6.67	122.00	0.13	1.10		4.03	
	175.9	177.5	1.6	1.60	2.36	23.00	0.02	0.34		2.89	
	177.5	179.0	1.5	0.59	1.30	12.00	0.02	0.41		2.88	
	179.0	180.7	1.7	2.12	3.91	33.00	0.22	0.62		2.95	

GRUM ASSAY DATA ADDITIONS & CORRECTIONS

Line No.	DDHID	FROM	TO	AI	%Pb	%Zn	Ag	%Cu	Au	%Hg	S.G.	MIL
1	A-201	120.9	122.0	1.1	4.15	6.50	72.00	0.07	0.69		3.71	
2		122.0	130.9	8.9	-0.5	-0.5	-0.5	-0.5	-0.5		-0.5	
3		130.9	131.9	1.0	1.75	1.83	38.00	0.10	0.41		3.49	
4		131.9	132.9	1.0	0.59	0.43	20.00	0.25	0.62		3.63	
5		132.9	134.4	1.5	0.04	0.04	4.00	0.06	0.14		2.80	
6		134.4	135.9	1.5	0.04	0.03	4.00	0.09	0.34		2.92	
7		135.9	137.4	1.5	0.01	0.02	2.00	0.04	0.21		2.89	
8		137.4	138.9	1.5	0.04	0.02	2.00	0.02	0.07		2.86	
9		138.9	140.4	1.5	0.05	0.02	5.00	0.06	0.21		2.88	
10		140.4	141.9	1.5	0.16	0.20	5.00	0.07	0.55		2.82	
11		141.9	143.0	1.1	0.94	0.68	20.00	0.19	0.14		3.57	
12		143.0	144.1	1.1	0.84	0.45	19.00	0.17	0.27		3.28	
13		144.1	146.3	2.2	-0.5	-0.5	-0.5	-0.5	-0.5		-0.5	
14		146.3	147.8	1.5	0.01	0.03	3.00	0.05	0.07		2.86	
15		147.8	149.3	1.5	0.07	0.05	3.00	0.07	0.14		2.86	
16		149.3	150.8	1.5	0.05	0.06	3.00	0.04	0.00		2.92	
17		150.8	152.3	1.5	0.05	0.04	2.00	0.04	0.00		2.92	
18		152.3	153.7	1.4	0.23	0.20	4.00	0.04	0.00		2.96	
19		153.7	172.4	18.7	-0.5	-0.5	-0.5	-0.5	-0.5		-0.5	
20		172.4	173.7	1.3	1.71	1.36	31.00	0.37	1.37		4.12	
21		173.7	174.6	0.9	0.02	0.04	2.00	0.03	0.07		2.87	
22		174.6	186.0	11.4	-0.5	-0.5	-0.5	-0.5	-0.5		-0.5	
23		186.0	187.1	1.1	5.03	4.87	80.00	0.19	0.82		4.10	
24		187.1	188.2	1.1	2.54	2.77	36.00	0.12	0.41		3.44	



FROM

CODING FORM

DATE

PAGE NO

OF

GRUM ASSAY DATA ADDITIONS & CORRECTIONS

Line No.	DDHID	FROM	TO	AI	%Pb	%Zn	Ag	%Cu	Au	%Hg	S.G	NI
1	A-202	40.6	41.5	0.9	1.81	2.55	29.0	0.27	0.82	.	3.44	
2		41.5	42.6	1.1	8.85	14.10	116.0	0.22	1.44	.	4.09	
3		42.6	43.7	1.1	8.84	15.30	161.0	0.32	2.40	.	4.80	
4		43.7	44.6	0.9	2.41	4.40	45.0	0.08	0.62	.	3.21	
5		44.6	45.4	0.8	0.16	0.48	2.0	0.02	0.07	.	2.89	
6		45.4	105.7	60.3	-0.5	-0.5	-0.5	-0.5	-0.5	.	-0.5	
7		105.7	107.2	1.5	0.46	0.08	3.0	0.01	0.14	.	2.91	
8		107.2	141.5	34.3	-0.5	-0.5	-0.5	-0.5	-0.5	.	-0.5	
9		141.5	143.0	1.5	0.19	0.45	3.0	0.06	0.07	.	2.83	
10		143.0	144.5	1.5	0.03	0.12	4.0	0.10	0.14	.	2.94	
11		144.5	146.0	1.5	0.02	0.10	4.0	0.15	0.07	.	2.91	
12		146.0	147.5	1.5	0.09	0.22	5.0	0.10	0.00	.	2.90	
13		147.5	149.2	1.7	0.03	0.09	2.0	0.05	0.00	.	3.56	
14		149.2	150.4	1.2	-0.5	-0.5	0.5	-0.5	-0.5	.	-0.5	
15		150.4	151.3	1.4	0.15	0.35	4.0	0.12	0.21	.	2.93	
16		151.3	153.1	1.3	0.98	3.30	22.0	0.04	0.27	.	2.92	
17		153.1	153.6	0.5	5.00	4.90	76.0	0.27	1.58	.	4.33	
18		153.6	155.1	1.5	1.90	3.60	31.0	0.05	0.41	.	3.08	
19		155.1	156.6	1.5	1.09	2.70	19.0	0.01	0.14	.	2.95	
20		156.6	158.0	1.4	0.80	2.09	17.0	0.01	0.21	.	2.93	
21		158.0	162.2	4.2	-0.5	-0.5	0.5	-0.5	-0.5	.	-0.5	
22		162.2	163.2	1.0	0.04	0.09	3.0	0.00	0.14	.	2.87	
23		163.2	164.3	1.1	0.33	0.40	3.0	0.01	0.21	.	2.88	
24		164.3	166.3	2.0	-0.5	-0.5	-0.5	-0.5	-0.5	.	-0.5	

GRUM ASSAY DATA ADDITIONS & CORRECTIONS

Line No.	DDH/D	FROM TO		AI	%Pb	%Zn	Ag	%Cu	Au	%Hg	S.G.	MIL
		1	2									
1	A-202	166.3	168.0	1.7	0.11	0.14	3.0	0.02	0.21	.	2.82	
2		168.0	168.8	0.8	4.55	3.69	59.0	0.21	1.30	.	4.57	
3		168.8	170.4	1.6	9.70	9.50	119.0	0.11	1.30	.	4.71	
4		170.4	172.0	1.6	6.00	7.50	105.0	0.17	1.23	.	4.30	
		172.0	173.6	1.6	5.30	7.00	80.0	0.09	0.96	.	4.01	
		173.6	174.7	1.1	0.72	0.61	13.0	0.03	1.37	.	4.00	
		174.7	175.8	1.1	1.11	0.51	17.0	0.37	1.30	.	4.63	
		175.8	176.8	1.0	0.90	0.12	15.0	0.41	1.23	.	4.42	
		176.8	178.3	1.5	3.80	1.18	33.0	0.12	1.17	.	4.07	
		178.3	179.8	1.5	8.66	7.05	104.0	0.18	1.71	.	4.35	
		179.8	181.4	1.6	4.43	6.99	75.0	0.14	0.69	.	4.15	
		181.4	182.9	1.5	1.61	1.47	28.0	0.44	1.30	.	3.53	
		182.9	184.4	1.5	1.90	2.03	33.0	0.37	2.33	.	3.74	
		184.4	185.9	1.5	1.07	1.41	23.0	0.78	0.69	.	3.59	
		185.9	187.4	1.5	1.51	2.82	23.0	0.22	0.48	.	3.70	
		187.4	188.4	1.0	0.82	0.43	12.0	0.23	0.55	.	3.45	
		188.4	189.9	1.5	0.86	1.28	15.0	0.42	0.75	.	3.50	
		189.9	191.4	1.5	0.60	1.02	12.0	0.40	0.41	.	3.32	
		191.4	192.8	1.4	1.16	2.14	20.0	0.31	0.41	.	3.21	
		192.8	194.4	1.6	0.40	1.10	11.0	0.09	0.48	.	4.03	
		194.4	196.0	1.6	0.39	0.79	16.0	0.38	0.62	.	4.16	
		196.0	196.9	0.9	0.05	0.07	2.0	0.13	0.27	.	2.95	
		196.9	198.2	1.3	1.27	1.14	19.0	0.08	0.62	.	3.09	
		198.2	199.7	1.5	0.08	0.10	3.0	0.01	0.41	.	2.90	

FROM

CODING FORM


DATE

PAGE NO

OF

GRUM ASSAY DATA ADDITIONS & CORRECTIONS

Line No.	DDHID	FROM	TO	AI	%Pb	%Zn	Ag	%Cu	Au	%Hg	S.G	ML
1	A-203	54.2	55.3	1.1	0.16	0.62	5.00	0.00	0.07		2.91	
2		55.3	68.6	13.3	-0.5	-0.5	-0.5	-0.5	-0.5		-0.5	
3		68.6	69.3	0.7	9.20	8.90	118.00	0.17	1.85		4.46	
4		69.3	69.7	0.4	-0.5	-0.5	-0.5	-0.5	-0.5		-0.5	
5		69.7	71.2	1.5	11.80	18.60	156.00	0.14	0.75		4.35	
6		71.2	72.7	1.5	12.50	23.00	155.00	0.21	0.89		4.56	
7		72.7	74.2	1.5	8.30	16.50	111.00	0.16	0.75		4.56	
8		74.2	75.7	1.5	4.10	6.60	83.00	0.26	1.37		4.27	
9		75.7	76.2	0.5	-0.5	-0.5	-0.5	-0.5	-0.5		-0.5	
10		76.2	77.4	1.2	6.55	8.36	76.00	0.06	0.69		3.76	
11		77.4	78.7	1.3	10.90	14.40	135.00	0.12	1.03		4.57	
12		78.7	84.4	5.7	-0.5	-0.5	-0.5	-0.5	-0.5		-0.5	
13		84.4	86.0	1.6	0.21	0.31	5.00	0.02	0.21		2.87	
14		86.0	89.2	3.2	0.79	1.68	14.00	0.02	0.34		2.92	
15		89.2	90.8	1.6	0.51	0.62	15.00	0.04	0.21		2.93	
16		90.8	104.2	13.4	-0.5	-0.5	-0.5	-0.5	-0.5		-0.5	
17		104.2	105.9	1.7	4.62	6.37	86.00	0.16	0.27		3.43	
18		105.9	106.8	0.9	2.67	3.68	40.00	-0.05	0.21		3.06	
19		106.8	108.3	1.5	8.63	8.61	144.00	0.24	1.58		4.67	
20		108.3	109.8	1.5	5.80	8.30	119.00	0.34	1.51		4.75	
21		109.8	111.4	1.6	3.50	5.70	63.00	0.22	2.13		4.50	
22		111.4	112.4	1.0	2.50	2.80	52.00	0.36	1.99		4.62	
23		112.4	113.9	1.5	0.34	0.54	10.00	0.03	0.14		2.84	
24		113.9	115.4	1.5	0.45	0.53	12.00	0.11	0.34		2.89	



FROM

CODING FORM

DATE

PAGE NO. OF

GRUM ASSAY DATA ADDITIONS & CORRECTIONS

Line No.

DESID	FROM	TO	AI	%Pb	%Zn	Ag	%Cu	Au	%Hg	S.G
A-203	115.4	116.9	1.5	0.25	0.23	7.00	0.12	0.21		2.83
	116.9	118.4	1.5	0.11	0.10	7.00	0.06	0.21		2.83
	118.4	119.9	1.5	0.04	0.13	7.00	0.22	0.21		2.85
	119.9	121.4	1.5	0.02	0.03	4.00	0.03	0.07		2.83
	121.4	122.9	1.5	0.02	0.08	2.00	0.12	0.21		2.90
	122.9	124.4	1.5	0.09	0.21	6.00	0.08	0.21		2.81
	124.4	125.4	1.0	0.40	0.50	13.00	0.23	0.27		3.32
	125.4	126.4	1.0	0.02	0.02	4.00	0.11	0.14		2.90
	126.4	127.2	0.8	0.40	0.27	17.00	0.14	0.21		3.68
	127.2	128.3	1.1	1.18	1.09	25.00	0.20	0.41		3.45
	128.3	129.4	1.1	0.99	0.62	17.00	0.11	0.62		2.98
	129.4	130.9	1.5	2.80	2.70	32.00	0.18	0.48		3.35
	130.9	132.3	1.4	1.71	1.62	26.00	0.17	0.27		3.59
	132.3	133.5	1.2	0.14	0.06	5.00	0.08	0.07		2.92
	133.5	134.7	1.2	0.11	0.23	5.00	0.20	1.30		2.98
	134.7	136.0	1.3	0.30	0.65	7.00	0.11	0.27		3.06
	136.0	137.3	1.3	0.17	0.23	3.00	0.02	0.27		2.93
	137.3	184.9	47.6	-0.5	-0.5	-0.5	-0.5	-0.5		-0.5
	184.9	186.3	1.4	0.07	0.14	2.00	0.02	0.07		2.94
	186.3	187.7	1.4	0.23	0.16	3.00	0.03	0.21		2.87
	187.7	189.1	1.4	0.23	0.18	3.00	0.02	0.14		2.82
	189.1	190.8	1.7	1.93	2.02	27.00	0.19	0.14		3.68
	190.8	192.2	1.4	0.10	0.26	2.00	0.01	0.14		2.86
	192.2	193.2	1.0	0.01	0.04	1.00	0.01	0.14		2.83

GRUM ASSAY DATA ADDITIONS & CORRECTIONS

Line No.	DDHID	FROM	TO	AI	%Pb	%Zn	Ag	%Cu	Au	%Hg	S.G.	M.I.
1	A-204	100.5	102.0	1.5	0.69	0.68	13.00	0.06	0.27	.	2.94	
2		102.0	103.5	1.5	0.42	0.61	5.00	0.04	0.14	.	2.85	
3		103.5	105.0	1.5	1.06	0.32	10.00	0.04	0.55	.	2.85	
4		105.0	106.6	1.6	0.55	0.26	6.00	0.03	0.75	.	2.83	
		106.6	108.2	1.6	1.12	0.51	13.00	0.03	0.27	.	2.88	
		108.2	109.7	1.5	0.03	0.05	2.00	0.04	0.21	.	2.85	
		109.7	111.3	1.6	0.04	0.13	1.00	0.03	0.14	.	2.82	
		111.3	112.1	0.8	0.04	0.17	4.00	0.07	0.34	.	3.01	
		112.1	113.6	1.5	0.06	0.13	15.00	0.04	0.21	.	2.88	
		113.6	115.1	1.5	0.17	0.10	4.00	0.02	0.14	.	2.83	
		115.1	116.7	1.6	0.43	0.09	6.00	0.02	0.41	.	2.91	
		116.7	118.3	1.6	0.27	0.15	4.00	0.01	0.07	.	2.84	
		118.3	135.6	17.3	-0.5	-0.5	-0.5	0.5	-0.5	.	-0.5	
14		135.6	136.9	1.3	0.13	0.37	5.00	0.17	0.75	.	2.98	
15		136.9	138.2	1.3	0.12	0.56	5.00	0.15	0.34	.	3.08	
16		138.2	139.5	1.3	0.18	0.35	6.00	0.10	0.34	.	2.93	
17		139.5	140.9	1.4	0.02	0.32	2.00	0.07	0.14	.	2.87	
18		140.9	142.3	1.4	0.02	0.14	4.00	0.13	0.48	.	3.02	
19		142.3	142.9	0.6	-0.5	-0.5	-0.5	0.5	-0.5	.	-0.5	
20		142.9	144.4	1.5	0.14	0.26	4.00	0.04	0.14	.	2.90	
21		144.4	145.9	1.5	0.10	0.30	5.00	0.09	0.21	.	2.92	
22		145.9	147.3	1.4	0.50	1.07	14.00	0.11	0.41	.	2.96	
23		147.3	148.7	1.4	1.55	3.00	35.00	0.02	0.41	.	2.91	
24		148.7	150.1	1.4	0.69	1.53	14.00	0.01	0.34	.	2.93	

GRUM ASSAY DATA ADDITIONS & CORRECTIONS

Line No.	DDHID	FROM	TO	AI	%Pb	%Zn	Ag	%Cu	Au	%Hg	S.G.	ML
1	A-205	65.2	66.2	1.0	3.90	1.10	66.00	0.15	0.96	.	3.95	
2		66.2	67.5	1.3	1.85	2.40	29.00	0.04	0.62	.	2.90	
3		67.5	68.9	1.4	0.98	1.22	14.00	0.03	0.34	.	2.88	
4		68.9	91.0	22.1	0.5	0.5	0.5	0.5	0.5	.	-0.5	
5		91.0	92.0	1.0	0.54	1.38	7.00	0.01	0.62	.	2.97	
6		92.0	93.1	1.1								
7		93.1	94.4	1.3	5.90	10.10	97.00	0.11	0.96	.	4.01	
8		94.4	95.3	0.9	1.20	3.00	41.00	0.27	1.10	.	4.89	
9		95.3	96.6	1.3	5.50	7.40	102.00	0.19	0.89	.	4.86	
10		96.6	97.9	1.3	7.20	13.60	138.00	0.16	1.17	.	4.39	
11		97.9	99.6	1.7	6.20	10.80	95.00	0.22	0.69	.	4.89	
12		99.6	101.2	1.6	7.10	14.60	103.00	0.22	2.26	.	4.71	
13		101.2	102.7	1.5	3.50	5.20	52.00	0.07	0.82	.	3.46	
14		102.7	104.2	1.5	0.39	0.99	15.00	0.16	0.48	.	3.14	
15		104.2	105.7	1.5	0.08	0.16	7.00	0.10	0.21	.	3.03	
16		105.7	107.2	1.5	0.07	0.51	7.00	0.11	0.21	.	3.05	
17		107.2	108.7	1.5	0.08	0.83	7.00	0.11	0.14	.	3.02	
18		108.7	110.2	1.5	0.39	2.21	31.00	0.16	0.21	.	3.06	
19		110.2	111.7	1.5	0.27	0.41	9.00	0.06	0.34	.	2.89	
20		111.7	113.2	1.5	0.20	0.98	7.00	0.06	0.41	.	2.86	
21		113.2	114.7	1.5	0.19	1.35	13.00	0.16	0.55	.	3.37	
22		114.7	116.2	1.5	0.26	0.89	14.00	0.18	0.41	.	3.21	
23		116.2	117.7	1.5	0.16	0.36	6.00	0.06	0.27	.	2.93	
24		117.7	122.5	4.8	-0.5	0.5	0.5	-0.5	-0.5	.	-0.5	

FROM

CODING FORM

DATE

PAGE NO


OF

GRUM ASSAY DATA ADDITIONS & CORRECTIONS

Line No.	DDHID	FROM	TO	RI	%Pb	%Zn	Ag	%Cu	Au	%Hg	S.G.	Mill
1	A-205	122.5	124.0	1.5	0.08	0.30	6.00	0.05	0.21	.	2.86	
2		124.0	125.5	1.5	0.05	0.73	11.00	0.08	0.21	.	2.97	
3		125.5	127.0	1.5	0.23	1.14	17.00	0.13	0.82	.	3.13	
4		127.0	128.5	1.5	1.56	2.21	35.00	0.17	0.00	.	3.41	
5		128.5	130.0	1.5	1.58	1.75	39.00	0.13	0.55	.	3.16	
6		130.0	131.5	1.5	2.31	1.62	42.00	0.06	0.75	.	3.11	
7		131.5	133.0	1.5	1.65	1.44	31.00	0.12	0.89	.	3.21	
8		133.0	134.5	1.5	0.33	1.06	29.00	0.13	0.89	.	3.06	
9		134.5	135.9	1.4	0.36	0.93	15.00	0.16	0.48	.	3.31	
10		135.9	137.1	1.2	0.13	1.85	8.00	0.17	0.69	.	3.63	
11		137.1	138.8	1.7	0.10	0.47	7.00	0.14	0.69	.	3.40	
12		138.8	140.5	1.7	0.32	1.08	14.00	0.21	0.76	.	3.32	
13		140.5	142.2	1.7	0.09	1.71	9.00	0.24	0.34	.	2.95	
14		142.2	143.9	1.7	0.13	1.76	14.00	0.24	0.48	.	3.04	
15		143.9	145.7	1.8	0.11	1.79	11.00	0.21	0.41	.	2.97	
16		145.7	147.4	1.7	0.84	1.92	21.00	0.12	0.62	.	3.43	
17		147.4	149.0	1.6	0.11	1.92	12.00	0.64	0.48	.	3.33	
18		149.0	150.6	1.6	0.04	1.30	6.00	0.24	0.34	.	2.94	
19		150.6	152.2	1.6	0.10	1.14	6.00	0.13	0.27	.	2.87	
20		152.2	153.8	1.6	0.05	1.18	6.00	0.10	0.21	.	2.84	
21		153.8	155.3	1.5	0.04	1.19	6.00	0.13	0.21	.	2.88	
22		155.3	156.5	1.2	0.05	0.81	0.06	0.15	0.41	.	3.12	
23		156.5	158.0	1.5	0.08	1.30	2.00	0.15	0.21	.	2.99	
24		158.0	159.5	1.5	0.08	0.82	0.00	0.05	0.14	.	2.87	

GRUM ASSAY DATA ADDITIONS & CORRECTIONS

Line No.	DDHID	FROM	TO	AI	%Pb	%Zn	Ag	%Cu	Au	%Hg	S.G	ML
	A-206	104.5	108.8	4.3	5.80	11.00	104.00	0.22	0.82	.	4.01	
		108.8	126.8	18.0	-0.5	-0.5	-0.5	-0.5	-0.5	.	-0.5	
		126.8	129.8	3.0	0.14	0.17	5.00	0.06	0.82	.	2.67	
		129.8	132.6	2.8	0.23	0.42	7.00	0.05	0.41	.	2.76	
		132.6	133.1	0.5	0.18	0.70	5.00	0.13	0.14	.	3.22	
		133.1	201.9	67.8	-0.5	-0.5	-0.5	-0.5	-0.5	.	-0.5	
		201.9	203.6	1.7	0.18	0.20	5.00	0.16	0.41	.	2.90	
		203.6	224.5	20.9	-0.5	-0.5	-0.5	-0.5	-0.5	.	-0.5	
		224.5	227.1	2.6	2.70	2.90	39.00	0.14	0.48	.	3.55	
		227.1	228.6	1.5	4.00	3.50	41.00	0.14	1.30	.	3.89	
		228.6	229.7	1.1	2.01	0.99	30.00	0.24	1.44	.	3.91	
		229.7	231.1	1.4	2.90	1.13	44.00	0.11	1.51	.	3.91	
		231.1	232.5	1.4	0.98	0.62	24.00	0.21	2.19	.	3.98	
		232.5	236.3	3.8	-0.5	-0.5	-0.5	-0.5	-0.5	.	-0.5	
		236.3	237.8	1.5	0.12	0.25	5.00	0.14	0.27	.	3.05	
		237.8	239.3	1.5	0.07	0.12	5.00	0.43	0.14	.	3.06	
		239.3	240.8	1.5	0.03	0.03	3.00	0.18	0.14	.	3.09	
		240.8	242.3	1.5	0.04	0.03	2.00	0.11	0.07	.	2.99	
		242.3	243.9	1.6	0.02	0.03	1.00	0.02	0.07	.	2.88	
		243.9	245.5	1.6	0.01	0.04	2.00	0.04	0.07	.	2.93	
		245.5	247.1	1.6	0.01	0.06	1.00	0.08	0.34	.	2.93	
		247.1	248.4	1.3	-0.5	-0.5	-0.5	-0.5	-0.5	.	-0.5	
		248.4	249.6	1.2	0.01	0.07	1.00	0.04	0.07	.	2.90	
		249.6	254.6	5.0	-0.5	-0.5	-0.5	-0.5	-0.5	.	-0.5	



FROM

CODING FORM

DATE

PAGE NO. OF

GRUM ASSAY DATA ADDITIONS & CORRECTIONS

Line No.	DD#ID	FROM	TO	A.I.	%Pb	%Zn	Ag	%Cu	Au	%Hg	S.G.
1	A-208	76.7	77.6	0.9	3.40	3.00	60.00	0.39	0.27	.	3.82
2		77.6	78.4	0.8	0.14	0.03	4.00	0.09	0.14	.	2.84
3		78.4	80.0	1.6	1.08	0.74	22.00	0.23	0.34	.	3.57
4		80.0	81.6	1.6	2.40	1.72	39.00	0.20	0.55	.	3.87
5		81.6	82.7	1.1	0.83	0.43	13.00	0.06	0.21	.	3.09
6		82.7	83.5	0.8	6.70	8.30	109.00	0.18	0.82	.	4.09
7		83.5	84.2	0.7	5.80	8.70	99.00	0.22	6.58	.	4.64
8		84.2	85.6	1.4	5.90	12.30	115.00	0.05	0.75	.	4.95
9		85.6	87.0	1.4	4.70	7.57	77.00	0.10	0.41	.	4.47
10		87.0	88.4	1.4	5.70	8.23	80.00	0.05	1.44	.	4.50
11		88.4	125.5	37.1	-0.5	-0.5	-0.5	-0.5	-0.5	.	-0.5
12		125.5	126.4	0.9	3.40	4.50	55.00	0.24	1.99	.	4.00
13		126.4	140.3	13.9	-0.5	-0.5	-0.5	-0.5	-0.5	.	-0.5
14		140.3	141.8	1.5	1.08	2.53	20.00	0.07	0.34	.	3.00
15		141.8	143.3	1.5	0.51	0.81	10.00	0.08	0.34	.	2.92
16		143.3	144.8	1.5	0.68	1.23	12.00	0.07	0.41	.	2.83
17		144.8	146.3	1.5	0.95	1.95	16.00	0.07	0.41	.	2.87
18		146.3	147.7	1.4	0.70	1.20	11.00	0.07	0.41	.	2.84
19		147.7	149.1	1.4	0.63	1.25	11.00	0.05	0.27	.	2.82
20		149.1	150.5	1.4	0.65	1.07	11.00	0.07	0.21	.	2.85
21		150.5	153.3	2.8	1.16	1.91	16.00	0.07	0.34	.	2.86
22		153.3	154.7	1.4	0.31	0.57	6.00	0.05	0.27	.	2.77
23		154.7	156.1	1.4	1.02	2.30	14.00	0.07	0.48	.	2.86
24		156.1	172.4	16.3	-0.5	-0.5	-0.5	-0.5	-0.5	.	-0.5

FROM

CODING FORM

DATE

PAGE NO.

OF

GRUM ASSAY DATA ADDITIONS & CORRECTIONS

Line No.	DDHID	FROM	TO	AZ	%Pb	%Zn	Ag	%Cu	Au	%Hg	S.G	ML
1	A-209	65.0	65.8	0.8	4.10	4.00	74.00	0.18	1.44		4.84	
2		65.8	67.4	1.6	5.30	8.40	101.00	0.34	1.78		4.76	
3		67.4	68.7	1.3	4.40	4.90	89.00	0.48	2.13		4.23	
4		68.7	69.9	1.2	6.80	8.10	97.00	0.15	1.17		4.80	
5		69.9	71.3	1.4	6.00	10.80	94.00	0.13	1.03		4.50	
6		71.3	96.9	25.6	-0.5	-0.5	-0.5	-0.5	-0.5		-0.5	
7		96.9	98.9	2.0	0.28	0.50	5.00	0.07	0.00		2.81	
8		98.9	100.3	1.4	0.24	0.30	4.00	0.06	0.07		2.74	
9		100.3	101.4	1.1	0.28	0.64	5.00	0.10	0.00		2.93	
10		101.4	110.9	9.5	-0.5	-0.5	-0.5	-0.5	-0.5		-0.5	
11		110.9	112.1	1.2	1.20	1.33	19.00	0.12	0.34		3.31	
12		112.1	113.6	1.5	1.78	2.90	25.00	0.14	0.27		3.49	
13		113.6	117.1	3.5	-0.5	-0.5	-0.5	-0.5	-0.5		-0.5	
14		117.1	119.1	2.0	1.46	2.80	27.00	0.28	1.37		4.35	
15		119.1	120.7	1.6	2.60	4.10	48.00	0.35	1.51		4.37	
16		
17		
18		
19		
20		
21		
22		
23		
24		

GRUM ASSAY DATA ADDITIONS & CORRECTIONS

Line No.	DDHID	FROM	TO	AI	%Pb	%Zn	Ag	%Cu	Au	%Hg	S.G	Mill
1	A-211	53.3	55.3	2.0	8.10	20.10	138.00	0.04	1.30	.	3.79	
2		55.3	57.3	2.0	8.00	18.40	144.00	0.07	0.69	.	3.62	
3		57.3	58.6	1.3	6.30	15.60	112.00	0.05	0.62	.	3.70	
4		58.6	59.7	1.1	2.70	7.50	62.00	0.28	0.65	.	4.55	
5		59.7	60.8	1.1	1.35	2.80	30.00	0.12	0.82	.	4.82	
6		60.8	62.4	1.6	7.60	17.70	144.00	0.06	0.41	.	3.83	
7		62.4	63.6	1.2	5.00	11.40	92.00	0.07	0.69	.	3.56	
8		63.6	65.1	1.5	3.20	6.10	58.00	0.05	0.69	.	3.46	
9		65.1	66.3	1.2	4.70	10.40	82.00	0.02	0.62	.	3.62	
10		66.3	67.6	1.3	6.40	16.40	120.00	0.05	1.10	.	3.95	
11		67.6	68.9	1.3	7.40	16.40	132.00	0.10	1.23	.	4.20	
12		68.9	70.6	1.7	8.20	17.10	134.00	0.16	1.92	.	4.30	
13		70.6	72.0	1.4	6.30	8.60	104.00	0.21	2.40	.	3.78	
14		72.0	73.8	1.8	0.20	0.45	12.00	0.26	1.03	.	3.64	
15		73.8	75.1	1.3	0.08	0.51	10.00	0.15	0.69	.	3.21	
16		75.1	76.3	1.2	0.08	0.54	12.00	0.18	0.75	.	3.31	
17		76.3	78.3	2.0	0.08	0.73	14.00	0.24	0.89	.	3.32	
18		78.3	80.3	2.0	0.06	0.35	14.00	0.28	0.89	.	3.54	
19		80.3	81.5	1.2	0.14	1.00	17.00	0.22	0.75	.	3.55	
20		81.5	83.2	1.7	0.06	0.33	9.00	0.31	0.69	.	3.51	
21		83.2	84.4	1.2	2.20	1.73	162.00	0.26	1.17	.	3.66	
22		84.4	85.7	1.3	3.20	3.20	45.00	0.15	1.17	.	3.42	
23		85.7	87.7	2.0	6.90	9.50	82.00	0.16	1.37	.	3.62	
24		87.7	89.7	2.0	3.40	4.50	55.00	0.08	1.58	.	3.37	

GRUM ASSAY DATA ADDITIONS & CORRECTIONS

Line No.	DDHID	FROM	TO	AI	%Pb	%Zn	Ag	%Cu	Au	%Hg	S.G.	111																																																																				
Card Col.	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41	42	43	44	45	46	47	48	49	50	51	52	53	54	55	56	57	58	59	60	61	62	63	64	65	66	67	68	69	70	71	72	73	74	75	76	77	78	79	80
1	A-211	89.7	91.2	1.5	1.29	1.35	18.00	0.12	0.96	.	3.49																																																																					
2		91.2	92.8	1.6	1.05	1.34	24.00	0.13	0.69	.	3.19																																																																					
3		92.8	94.5	1.7	0.75	0.92	14.00	0.36	0.82	.	3.53																																																																					
4		94.5	96.3	1.8	0.43	0.40	10.00	0.26	0.69	.	3.56																																																																					
5		96.3	98.3	2.0	0.27	0.61	8.00	0.15	0.55	.	3.28																																																																					
6		98.3	100.3	2.0	0.40	0.67	12.00	0.15	0.69	.	3.36																																																																					
7		100.3	102.3	2.0	0.95	1.32	22.00	0.18	0.69	.	3.38																																																																					
8		102.3	104.3	2.0	0.07	0.28	8.00	0.16	0.41	.	3.21																																																																					
9		104.3	106.3	2.0	0.07	0.32	6.00	0.23	0.48	.	3.29																																																																					
10		106.3	108.3	2.0	0.07	0.17	6.00	0.15	0.41	.	3.21																																																																					
11		108.3	110.3	2.0	0.10	0.24	14.00	0.53	0.55	.	3.48																																																																					
12		110.3	112.3	2.0	0.07	0.37	10.00	0.27	0.27	.	2.96																																																																					
13		112.3	113.0	0.7	0.07	0.60	8.00	0.34	0.34	.	3.02																																																																					
14		113.0	114.0	1.0	0.06	0.28	8.00	0.21	0.27	.	3.19																																																																					
15		114.0	116.0	2.0	0.06	0.33	4.00	0.09	0.21	.	2.89																																																																					
16		116.0	118.0	2.0	0.07	0.64	8.00	0.15	0.27	.	2.97																																																																					
17		118.0	120.0	2.0	0.06	0.37	6.00	0.13	0.34	.	2.92																																																																					
18		120.0	122.0	2.0	0.01	0.64	3.00	0.04	0.21	.	2.85																																																																					
19		122.0	124.0	2.0	0.02	0.59	4.00	0.15	0.34	.	3.04																																																																					
20		124.0	125.7	1.7	1.48	1.11	22.00	0.17	1.10	.	3.22																																																																					
21		125.7	128.0	2.3	2.50	1.16	40.00	0.40	1.44	.	4.68																																																																					
22		128.0	129.7	1.7	3.90	1.73	66.00	0.33	1.71	.	4.67																																																																					
23		129.7	131.0	1.3	1.41	1.42	30.00	0.42	1.58	.	4.69																																																																					
24		131.0	132.3	1.3	1.77	1.58	33.00	0.36	1.65	.	4.85																																																																					

GRUM ASSAY DATA ADDITIONS & CORRECTIONS

Line No.	DD#ID	FROM	TO	AI	%Pb	%Zn	Ag	%Cu	Au	%Hg	S.G.	ML
1	A-212	67.1	68.4	1.3	4.40	8.34	62.00	0.09	0.62	.	4.68	
2		68.4	69.7	1.3	6.20	11.85	.	0.07	1.17	.	4.36	
3		69.7	71.0	1.3	4.70	8.90	86.00	0.11	1.37	.	4.70	
4		71.0	72.3	1.3	8.00	14.20	127.00	0.17	1.58	.	3.78	
		72.3	74.1	1.8	5.40	12.30	134.00	0.20	1.58	.	3.78	
		74.1	74.9	0.8	3.50	7.70	64.00	0.05	0.82	.	4.61	
		74.9	76.2	1.3	3.90	19.20	179.00	0.07	1.44	.	3.78	
		76.2	77.5	1.3	7.70	18.40	141.00	0.08	1.37	.	4.09	
		77.5	79.1	1.6	4.60	8.70	99.00	0.07	0.89	.	4.63	
		79.1	80.8	1.7	4.50	8.10	98.00	0.09	0.89	.	4.68	
		80.8	82.8	2.0	2.30	5.70	44.00	0.03	0.55	.	3.64	
		82.8	83.7	0.9	6.80	7.30	114.00	0.07	0.88	.	4.51	
		83.7	85.6	1.9	4.20	9.20	101.00	0.06	0.75	.	3.52	
		85.6	86.3	0.7	2.30	5.80	42.00	0.04	0.48	.	4.53	
		86.3	88.7	2.4	6.20	11.10	127.00	0.17	1.30	.	4.37	
		88.7	90.1	1.4	5.80	11.10	101.00	0.04	1.23	.	4.22	
		90.1	91.6	1.5	8.80	13.80	142.00	0.06	0.75	.	3.78	
		91.6	92.8	1.2	0.11	1.09	14.00	0.18	0.75	.	3.42	
		92.8	94.0	1.2	1.44	4.30	32.00	0.22	0.75	.	3.49	
		94.0	96.1	2.1	5.40	11.20	89.00	0.23	1.58	.	4.56	
		96.1	97.4	1.3	5.10	8.80	86.00	0.12	1.23	.	3.90	
		97.4	99.4	2.0	1.18	1.80	25.00	0.17	0.69	.	3.29	
		99.4	101.4	2.0	0.17	1.22	13.00	0.13	0.34	.	3.23	
		101.4	103.4	2.0	0.09	0.50	7.00	0.12	0.27	.	2.91	

FROM

CODING FORM

DATE

PAGE NO

OF

GRUM ASSAY DATA ADDITIONS & CORRECTIONS

Line No.	DDHID	FROM	TO	A.I.	%Pb	%Zn	Ag	%Cu	Au	%Hg	S.G.	MI
1	A-212	103.4	106.1	2.7	0.36	0.59	13.00	0.11	0.27	.	2.69	
2		106.1	108.1	2.0	0.39	1.22	13.00	0.16	0.34	.	3.11	
3		108.1	110.1	2.0	0.32	0.81	12.00	0.11	0.48	.	3.02	
4		110.1	112.2	2.0	0.24	0.75	9.00	0.14	0.34	.	3.16	
5		112.2	114.2	2.0	0.22	0.80	11.00	0.22	0.69	.	3.60	
6		114.2	116.2	2.0	0.35	0.91	11.00	0.23	0.69	.	3.63	
7		116.2	117.9	1.7	0.39	0.62	14.00	0.22	0.62	.	3.67	
8		117.9	120.0	2.1	0.09	0.54	13.00	0.26	0.62	.	3.34	
9		120.0	122.0	2.0	0.05	0.46	7.00	0.20	0.34	.	3.02	
10		122.0	124.0	2.0	0.11	0.75	11.00	0.30	0.34	.	3.73	
11		124.0	127.1	3.1	0.11	0.58	12.00	0.41	0.21	.	3.10	
12		127.1	129.1	2.0	0.33	1.22	10.00	0.22	0.41	.	3.30	
13		129.1	131.1	2.0	0.04	0.78	12.00	0.65	0.48	.	3.21	
14		131.1	132.1	1.0	0.04	1.38	12.00	0.83	0.41	.	3.28	
15		132.1	134.1	2.0	0.05	1.51	12.00	0.76	0.34	.	3.19	
16		134.1	136.1	2.0	0.17	1.10	10.00	0.43	0.34	.	3.42	
17		136.1	138.1	2.0	0.03	1.10	9.00	0.53	0.27	.	3.05	
18		138.1	139.5	1.4	0.08	3.93	7.00	0.12	0.14	.	3.00	
19		139.5	140.9	1.4	0.06	0.57	8.00	0.24	0.34	.	3.19	
20		140.9	142.1	1.2	0.05	1.06	10.00	0.29	0.48	.	3.43	
21		142.1	143.2	1.1	2.00	2.90	40.00	0.32	1.17	.	3.79	
22		143.2	145.2	2.0	1.36	3.80	29.00	0.42	1.23	.	4.56	
23		145.2	147.2	2.0	0.90	4.70	20.00	0.28	1.17	.	4.67	
24		147.2	149.2	2.0	0.77	2.60	18.00	0.40	1.23	.	4.75	

FROM

CODING FORM

DATE

PAGE NO

OF

GRUM ASSAY DATA ADDITIONS & CORRECTIONS

Line No.	DDHID	FROM	TO	A.I.	%Pb	%Zn	Ag	%Cu	Au	%Hg	S.G.	M.I.
1	A-213	37.2	38.6	1.4	2.80	1.76	67.00	0.33	0.96	.	4.32	
2		38.6	44.8	6.2	-0.5	-0.5	-0.5	-0.5	-0.5	.	-0.5	
3		44.8	47.7	2.9	1.16	0.93	18.00	0.16	0.41	.	3.44	
4		47.7	49.0	1.3	5.80	5.00	84.00	0.17	1.78	.	4.59	
5		49.0	49.3	0.3	-0.5	-0.5	-0.5	-0.5	-0.5	.	-0.5	
6		49.3	51.4	2.1	7.10	7.40	108.00	0.09	1.23	.	4.25	
7		51.4	52.6	1.2	-0.5	-0.5	-0.5	-0.5	-0.5	.	-0.5	
8		52.6	53.3	0.7	1.80	2.90	27.00	0.19	1.17	.	3.76	
9		53.3	54.9	1.6	0.97	1.76	20.00	0.12	0.82	.	3.29	
10		54.9	56.1	1.2	6.20	7.80	114.00	0.16	1.71	.	4.27	
11		56.1	57.3	1.2	4.08	5.18	57.00	0.14	1.30	.	4.27	
12		57.3	58.2	0.9	0.43	0.47	13.00	0.13	1.37	.	3.35	
13		58.2	59.2	1.0	2.43	4.70	23.00	0.12	1.58	.	3.73	
14		59.2	61.6	2.4	3.59	4.80	54.00	0.27	1.30	.	4.56	
15		61.6	63.1	1.5	1.00	1.33	13.00	0.14	0.34	.	3.39	
16		63.1	64.3	1.2	0.47	0.80	9.00	0.04	0.07	.	2.94	
17		64.3	115.8	51.5	-0.5	-0.5	-0.5	-0.5	-0.5	.	-0.5	
18		115.8	117.1	.	3.89	5.08	73.00	0.10	0.41	.	3.58	
19		117.1	242.0	124.9	-0.5	-0.5	-0.5	-0.5	-0.5	.	-0.5	
20		242.0	246.9	.	2.50	2.40	36.00	0.20	0.82	.	3.64	
21		246.9	260.2	13.3	-0.5	-0.5	-0.5	-0.5	-0.5	.	-0.5	
22		260.2	262.2	.	2.72	2.01	40.00	0.22	1.44	.	4.14	
23		262.2	272.0	9.8	-0.5	-0.5	-0.5	-0.5	-0.5	.	-0.5	
24		272.0	273.6	.	0.39	0.45	10.00	0.14	0.34	.	2.96	

