

019187

CYPRUS ANVIL MINING CORPORATION

Page 1 of 3

DY 79-X-11

GEOCHEMICAL LOG

Kamloops Research and Assay Lab

From	To*	Int.	Samp. No.	Ag/AA GMS/MT	Ag/FA GMS/MT	Pb %	Zn %	Pb+Zn %	S.G.	Cu %	BaO %	Au GMS/MT	Po %	Py %	Hg %	Rec.	Unit
742.1	742.6	0.5	1135	109.0		6.30	8.30	14.60		0.27						0.5	4G4
742.6	743.3	0.7	1136	16.0		1.01	0.67	1.68		0.39						0.7	4C9
745.6	747.7	2.1	1137	15.0		1.41	0.95	2.36		0.24						2.1	4K9
747.7	749.7	2.0	1138	34.0	36.0	6.50	0.93	7.43	4.46	0.26	0.86	1.82	4.60	31.47	.002	2.0	4K8
749.7	750.9	1.2	1139	100.0	103.0	7.78	6.44	14.22	4.33	0.10	9.02	1.03	4.94	17.57	.005	1.2	4G4
750.9	751.5	0.6	1140	52.0	50.0	3.73	2.97	6.70	4.50	0.16	0.27	1.78	9.67	30.02	.002	0.6	4K8
751.5	753.0	1.5	1141	95.0	92.0	7.07	5.80	12.87	4.63	0.08	14.99	1.03	7.50	16.67	.004	1.0	4G4
753.0	754.0	1.0	1142	74.0	73.0	6.86	3.12	9.98	4.60	0.29	0.99	1.82	6.75	29.62	.003	1.0	4K8
754.0	755.4	1.4	1143	97.0	89.0	6.12	6.66	12.78	4.57	0.11	23.87	0.82	5.48	14.20	.005	1.4	4G4
755.4	757.5	2.1	1144	25.0		1.37	0.99	2.36		0.32						1.8	4K8
757.5	759.3	1.8	1145	14.0		0.34	0.29	0.63		0.35						1.8	4K9
759.3	761.1	1.8	1146	18.0		1.15	0.83	1.98		0.42						1.8	4K9
761.1	762.1	1.0	1147	315.0	131.0	12.35	6.50	18.85	4.56	0.06	0.87	0.58	19.75	11.01	.004	1.0	4J4
762.1	762.7	0.6	1148	31.0	35.0	2.60	4.47	7.07	2.84	0.04	0.45	0.51	2.66	7.06	.003	0.6	4G4
762.7	763.5	0.8	1149	79.0	80.0	7.00	5.84	12.84	4.12	0.10	5.97	0.55	16.78	11.52	.003	0.8	4D8
763.5	765.5	2.0	1150	84.0	86.0	5.40	5.80	11.20	4.33	0.06	21.66	0.48	5.82	12.96	.005	2.0	4G4
765.5	767.1	1.6	1251	81.0	74.0	5.61	9.18	14.79	4.38	0.04	22.18	0.45	10.00	8.73	.006	1.6	4A4
767.1	769.6	2.5	1252	29.0	27.0	1.91	3.60	5.51	2.66	0.03	0.62	0.48	2.00	5.36	.004	2.5	4A4
769.6	770.1	0.5	1253	98.0	90.0	5.17	6.94	12.11	4.37	0.15	2.83	1.06	0.86	31.11	.007	0.5	4E1
779.2	779.8	0.6	1254	36.0		1.78	2.76	4.54		0.36						0.6	4E9
779.8	781.5	1.7	1255	155.0	143.0	11.86	7.87	19.73	4.50	0.12	6.33	1.41	3.27	21.52	.005	1.7	4G4
781.5	783.0	1.5	1256	105.0	99.0	7.24	5.00	12.24	4.50	0.13	2.64	1.27	3.56	29.11	.004	1.5	4G4
783.0	784.7	1.7	1257	145.0	145.0	8.05	9.44	17.49	4.50	0.20	17.25	1.92	0.84	17.09	.007	1.7	4G4
784.7	785.7	1.0	1258	53.0	47.0	2.56	0.81	3.37	4.61	0.26	0.28	1.27	2.30	36.08	.002	1.0	4K4
785.7	787.2	1.5	1259	99.0	92.0	7.36	8.45	15.81	4.66	0.12	4.66	1.03	2.38	26.84	.006	1.5	4K4
787.2	789.2	2.0	1260	74.0	67.0	3.32	2.63	5.95	4.10	0.22	0.78	0.79	3.62	33.68	.003	1.0	4K4
789.2	790.7	1.5	1261	100.0	92.0	7.26	8.79	16.05	4.61	0.17	20.98	0.51	1.46	15.10	.007	1.5	4G4
790.7	792.3	1.6	1262	77.0	-	4.80	3.36	8.16	4.45	0.17	0.64	0.48	4.18	32.66	.003	1.6	4E8
792.3	793.6	1.3	1263	33.0	39.0	1.20	1.11	2.31	4.24	0.48	0.96	0.58	3.96	30.95	.002	1.3	4E8
793.6	795.0	1.4	1264	95.0	89.0	6.02	6.27	12.29	4.39	0.08	21.53	0.93	8.83	10.69	.004	1.4	4G4