

MEMO TO: Dave Wright
 FROM: Lee Pigage
 DATE: February 25, 1987
 SUBJECT: 1986 Diamond Drill Core Assays (Round 2)

The enclosed spreadsheets contain the assay results for 8 drill holes: 86F-17, 86F-19 - 86F-25.

The most serious problem is the 10 samples missing from 86F-17. Sample assay sheets from your lab for all other analyses in this drill hole are dated Dec. 12/86 and Dec. 19/86. I would guess that the samples went "missing" or were mislaid sometime before they were delivered to your lab. A "trace" should be placed on these samples.

Sample 2E14 - 86F21 90.5-95 is from drill hole 86F-21. The sample number should be 10610.

Our sampler sheets show two samples with number 10618 and no sample 10616:

DRILLHOLE	FROM	TO	ROCK TYPE	SAMPLE NUMBER
86F-21	280.7	289.0	1D419	10618
86F-22	262.0	267.0	2D0	10618

This sampling error apparently did not extend to your lab because you have separate analyses for 10616 and 10618. Unfortunately the analyses are very similar, making it difficult to differentiate the samples. I am arbitrarily making the following assignment:

DRILLHOLE	FROM	TO	ROCK TYPE	SAMPLE NUMBER
86F-21	280.7	289.0	1D419	10618
86F-22	262.0	267.0	2D0	10616

I will be checking the core boxes when I arrive in Faro to verify this guesstimate.

You reported one sample with no label (E 35581), and I have one vacant space in my 86F-23 spreadsheet. I have therefore assumed that your sample corresponds to sample 4983. Analyses for samples 4983 and 4984 do not match the field drill logs; these samples would match much better if they were reversed in the drill hole. I have arbitrarily reversed the order of these two samples in the drill hole. The samples should be re-analyzed to confirm that it was a sampling/core splitting problem.

I have also underlined several assays which seem suspect based on our field drill logs. Please re-run these analyses to confirm the values.

I shall be coming to Faro next week to enter most of these analyses into the DDHDB.

Cheers,

Lee

cc: Gregg Jilson
Faro Geology

DDH	FROM feet	TO feet	SAMPLE	INT feet	REC feet	REC %	UNIT	SG	PB %	ZN %	AG g/t	PD %	PY %	PB+ZN %	FE-TOTAL %	Pb/(Pb+Zn)
86F-17	7.0	11.5	35470	4.5	5.9	100	26AC	3.6	4.20	12.52	42	3.14	15.94	16.72	19.08	0.25
86F-17	11.5	17.0	35471	5.5		0	2A4						0.00	0.00		ERR
86F-17	17.0	21.8	35472	4.8		0	2A4	3.6	3.15	6.07	68	0.95	18.70	9.22	19.65	0.34
86F-17	21.8	26.0	35473	4.2		0	2C3	4.1	0.35	1.25	12	1.04	36.53	1.60	37.57	0.22
86F-17	26.0	31.0	35474	5.0		0	2C3	4.1	0.13	0.72	6	2.92	36.21	0.85	39.13	0.15
86F-17	31.0	36.0	35475	5.0		0	2C3	4.0	0.39	1.37	8	4.34	30.13	1.76	34.47	0.22
86F-17	36.0	42.0	35476	6.0		0	2C3						0.00	0.00		ERR
86F-17	42.0	48.0	35477	6.0		0	2C3						0.00	0.00		ERR
86F-17	48.0	53.2	35478	5.2		0	2C3	4.2	1.96	4.38	16	1.40	30.80	6.34	32.20	0.31
86F-17	53.2	59.0	35479	5.8		0	2D09	3.3	1.08	1.30	36	3.53	12.94	2.38	16.47	0.45
86F-17	59.0	64.0	35480	5.0		0	2D09	3.5	0.06	0.48	8	0.78	25.28	0.54	26.06	0.11
86F-17	64.0	70.0	35481	6.0		0	2C0						0.00	0.00		ERR
86F-17	70.0	76.0	35482	6.0		0	2C0	3.5	1.50	4.24	16	2.13	18.60	5.74	20.73	0.26
86F-17	76.0	81.0	35483	5.0		0	2E10						0.00	0.00		ERR
86F-17	81.0	86.0	35484	5.0		0	2E10	3.9	0.25	0.99	8	2.00	28.57	1.24	30.57	0.20
86F-17	86.0	93.0	35485	7.0		0	2E10	4.0	0.63	2.04	8	0.98	33.74	2.67	34.72	0.24
86F-17	93.0	99.0	35486	6.0		0	2E10						0.00	0.00		ERR
86F-17	99.0	105.0	35487	6.0		0	2CE	3.5	2.09	3.72	26	1.55	21.06	5.81	22.61	0.36
86F-17	105.0	111.5	35488	6.5		0	2CE	4.0	0.10	0.78	16	1.06	29.01	0.88	30.07	0.11
86F-17	111.5	116.0	35489	4.5		0	2C3	4.0	0.05	0.73	14	1.33	30.42	0.78	31.75	0.06
86F-17	116.0	122.0	35490	6.0		0	2C3	4.0	0.07	1.21	16	0.61	30.83	1.28	31.44	0.05
86F-17	122.0	127.5	35491	5.5		0	2C3						0.00	0.00		ERR
86F-17	127.5	132.5	35492	5.0		0	2C3						0.00	0.00		ERR
86F-17	132.5	137.5	35493	5.0		0	2C3	3.9	0.87	2.48	12	1.52	27.86	3.35	29.38	0.26
86F-17	137.5	143.0	35494	5.5		0	2C3	3.9	0.32	2.33	8	1.37	27.27	2.65	28.64	0.12
86F-17	143.0	146.8	35495	3.8		0	2C3	4.1	0.03	0.41	4	1.04	32.98	0.44	34.02	0.07
86F-17	146.8	152.0	35496	5.2		0	2C3	4.0	0.05	1.43	4	1.24	29.98	1.48	31.22	0.03
86F-17	152.0	156.5	35497	4.5		0	2C3	3.9	0.28	2.07	6	0.51	27.70	2.35	28.21	0.12
86F-17	156.5	160.0	35498	3.5		0	2E14	3.9	0.08	2.65	4	0.65	25.79	2.73	26.44	0.03
86F-17	160.0	164.0	35499	4.0		0	2E14	4.0	2.25	4.22	10	1.44	23.48	6.47	24.92	0.35
86F-17	164.0	168.7	35500	4.7		0	2D354	3.9	5.68	6.68	26	3.00	15.09	12.36	18.09	0.46
86F-17	168.7	173.0	35141	4.3		0	2D354	3.8	3.39	9.43	20	1.64	23.08	12.82	24.72	0.26
86F-17	173.0	178.0	35142	5.0		0	2D354	3.5	2.95	6.77	28	3.01	17.51	9.72	20.52	0.30
86F-17	178.0	183.0	35143	5.0		0	2AD	3.2	1.54	2.76	22	3.88	10.67	4.30	14.55	0.36
86F-17	183.0	188.0	35144	5.0		0	2D05	3.1	1.12	2.60	16	2.79	4.20	3.72	6.99	0.30
86F-17	188.0	193.0	35145	5.0		0	2D05	2.9	0.36	0.98	10	3.10	8.15	1.34	11.25	0.27
86F-17	193.0	198.0	35146	5.0		0	2D05	3.0	0.63	1.81	12	2.88	9.06	2.44	11.94	0.26
86F-17	198.0	203.0	35147	5.0		0	2D05	3.2	0.29	0.95	6	6.13	14.27	1.24	20.40	0.23
86F-17	203.0	211.5	35148	8.5		0	2D05	3.3	0.69	2.68	14	4.57	15.39	3.37	19.96	0.20
86F-17	211.5	218.5	35149	7.0		0	2D05	3.3	0.36	0.35	18	4.84	16.15	0.71	20.99	0.51
86F-17	218.5	223.0	35150	4.5		0	2D05	3.5	3.23	5.10	40	4.39	15.83	8.33	20.22	0.39
86F-17	223.0	226.0	35087	3.0		0	2D05	3.1	3.24	2.37	44	6.50	10.00	5.61	16.50	0.58
86F-17	226.0	230.6	35088	4.6		0	2B4	2.9	2.04	6.72	30	2.80	1.85	8.76	4.65	0.23
86F-17	230.6	235.5	35089	4.9		0	2B4						0.00	0.00		ERR
86F-17	235.5	240.3	35090	4.8		0	2B4	3.0	4.46	4.12	50	3.10	3.55	8.58	6.65	0.52
86F-17	240.3	244.7	35091	4.4		0	2B4						0.00	0.00		ERR
86F-17	244.7	249.0	35092	4.3		0	2B4						0.00	0.00		ERR
86F-17	249.0	252.5	35093	3.5		0	2A4	3.0	4.20	9.31	58	2.69	2.29	13.51	4.98	0.31
86F-17	252.5	255.5	35094	3.0		0	2B45	3.0	1.10	3.35	32	2.84	3.49	4.45	6.33	0.25
86F-17	255.5	266.0	35095	10.5		0	1D419	3.0	1.99	4.48	94	3.13	2.77	6.47	5.90	0.31
86F-17	266.0	270.7	35096	4.7		0	2B45	3.0	3.81	6.12	76	2.81	2.64	9.93	5.45	0.38
86F-17	270.7	275.3	35097	4.6		0	2B45	3.0	3.29	5.15	32	3.91	3.61	8.44	7.52	0.39
86F-17	275.3	280.2	35098	4.9		0	2B45	3.0	4.67	6.78	60	2.34	1.71	11.45	4.05	0.41

DDH	FROM feet	TO feet	SAMPLE	INT feet	REC feet	REC %	UNIT	SG	PB %	ZN %	AG g/t	PD %	PY %	PB+ZN %	FE-TOTAL %	Pb/(Pb+Zn)
86F-17	280.2	285.1	35099	4.9		0	2B45	3.1	4.28	10.51	52	2.39	1.52	14.79	3.91	0.29
86F-17	285.1	290.0	35100	4.9		0	2B45	3.0	4.87	4.99	50	3.80	2.54	9.86	6.34	0.49
86F-17	290.0	295.1	4964	5.1		0	2B45	3.2	2.95	6.76	42	3.44	1.62	9.71	5.06	0.30
86F-17	295.1	300.0	4965	4.9		0	2B45	3.0	2.09	7.27	38	2.78	1.02	9.36	3.80	0.22
86F-17	300.0	305.0	4966	5.0		0	2D0	3.0	0.86	2.52	19	3.07	4.11	3.38	7.18	0.25

FILE = 86F-17.WR1

DDH	FROM feet	TO feet	SAMPLE	INT feet	REC feet	REC %	UNIT	S6	PB %	ZN %	AG g/t	PO %	PY %	PB+ZN %	FE-TOTAL %	PB/(PB+ZN)
86F-19	100.9	105.0	35441	4.1	4.6	100	2D45	3.5	0.62	4.35	10	2.95	17.15	4.97	20.10	0.12
86F-19	105.0	111.7	35442	6.7	7.5	100	2C35	3.8	0.18	1.08	6	1.29	28.81	1.26	30.10	0.14
86F-19	111.7	117.0	35443	5.3		0	2E180	4.2	0.12	0.75	6	6.08	30.52	0.87	36.60	0.14
86F-19	117.0	122.6	35444	5.6	5.6	100	2E180	4.0	0.05	0.99	4	4.68	30.12	1.04	34.80	0.05
86F-19	122.6	127.0	35445	4.4	4.4	100	2C38	3.9	0.04	1.76	4	7.43	22.37	1.80	29.80	0.02
86F-19	127.0	132.3	35446	5.3		0	2C38	3.9	0.35	2.16	4	7.89	25.61	2.51	33.50	0.14
86F-19	132.3	137.0	35447	4.7	5.0	100	2C38	4.0	0.70	1.71	6	6.70	25.00	2.41	31.70	0.29
86F-19	137.0	141.0	35448	4.0	4.9	100	2C38	3.9	1.00	1.99	14	8.56	26.24	2.99	34.80	0.33
86F-19	141.0	145.2	35449	4.2	4.2	100	2C38	3.6	2.77	1.21	56	4.98	19.72	3.98	24.70	0.70
86F-19	145.2	151.1	35450	5.9	6.0	100	2E814	4.1	0.47	2.15	10	6.92	29.88	2.62	36.80	0.18
86F-19	151.1	154.4	35451	3.3	4.1	100	2E41	4.2	5.63	10.00	16	2.76	27.44	15.63	30.20	0.36
86F-19	154.4	158.3	35452	3.9	4.4	100	2E41	4.2	4.26	9.46	12	2.42	26.68	13.72	29.10	0.31
86F-19	158.3	164.0	35453	5.7	6.2	100	2D35	3.6	2.82	8.13	18	2.59	18.01	10.95	20.60	0.26
86F-19	164.0	170.5	35454	6.5	7.0	100	2D35	3.5	2.62	9.46	22	3.82	17.18	12.08	21.00	0.22
86F-19	170.5	175.7	35455	5.2	5.1	98	2E4	4.8	3.33	8.29	22	3.96	34.94	11.62	38.90	0.29
86F-19	175.7	178.6	35456	2.9	3.1	100	2A34	3.9	4.03	11.90	38	2.88	20.12	15.93	23.00	0.25
86F-19	178.6	183.5	35457	4.9	4.9	100	2A4	2.9	1.41	1.73	20	2.35	2.91	3.14	5.26	0.45
86F-19	183.5	188.9	35458	5.4	4.7	87	2A4	3.0	1.05	2.19	16	4.63	8.17	3.24	12.80	0.32
86F-19	188.9	192.0	35459	3.1	4.7	100	2A4	2.9	0.55	2.26	12	1.87	18.63	2.81	20.50	0.20
86F-19	192.0	199.3	35460	7.3	7.6	100	2D5	3.1	0.97	3.66	16	2.97	8.13	4.63	11.10	0.21
86F-19	199.3	204.0	35461	4.7	4.9	100	2D0	2.8	<u>0.16</u>	<u>0.17</u>	14	2.03	3.51	0.33	5.54	0.48
86F-19	204.0	209.0	35462	5.0	4.9	98	2D0	3.0	<u>0.07</u>	<u>0.12</u>	6	3.83	4.48	0.19	8.31	0.37
86F-19	209.0	214.0	35463	5.0	7.7	100	2D0	3.0	<u>0.25</u>	<u>0.71</u>	10	3.61	4.24	0.96	7.85	0.26
86F-19	214.0	224.0	35464	10.0	11.1	100	1D419	2.8	0.60	0.39	14	2.19	1.56	0.99	3.75	0.61
86F-19	224.0	233.5	35465	9.5	10.2	100	1D419	2.8	0.22	0.31	6	2.35	2.05	0.53	4.40	0.42
86F-19	233.5	243.0	35466	9.5	10.2	100	1D419	2.9	0.24	0.22	12	2.45	1.92	0.46	4.37	0.52
86F-19	243.0	251.0	35467	8.0	8.5	100	1D29	2.8	0.10	0.19	2	2.48	1.45	0.29	3.93	0.34
86F-19	251.0	259.0	35468	8.0	7.7	96	1D419	2.8	0.38	0.73	8	2.72	1.98	1.11	4.70	0.34
86F-19	259.0	267.0	35469	8.0	9.0	100	1D419	2.8	0.36	0.83	8	3.64	2.52	1.19	6.16	0.30

FILE = 86F-19.WR1

DDH	FROM feet	TO feet	SAMPLE	INT feet	REC feet	REC %	UNIT	SG	PB %	ZN %	AG g/t	PO %	PY %	PB+ZN %	FE-TOTAL %	PB/(PB+ZN)
B6F-20	11.0	21.8	10653	10.8	9.9	92	2E4@	4.1	4.14	6.46	48	2.64	27.36	10.60	30.00	0.39
B6F-20	21.8	27.0	10654	5.2	4.1	79	2E1	4.6	1.28	1.43	16	1.14	38.96	2.71	40.10	0.47
B6F-20	27.0	30.5	10655	3.5	2.3	66	2E1	4.4	0.19	0.31	8	1.59	35.91	0.50	37.50	0.38
B6F-20	30.5	36.5	10656	6.0	5.4	90	2A34	3.6	0.29	0.83	6	0.32	24.08	1.12	24.40	0.26
B6F-20	36.5	41.5	10657	5.0	4.3	86	2A34	3.5	1.07	4.92	16	1.27	19.33	5.99	20.60	0.18
B6F-20	41.5	44.6	10658	3.1	2.7	87	2C3	4.0	0.87	1.90	14	1.35	31.35	2.77	32.70	0.31
B6F-20	44.6	49.0	10659	4.4	4.2	95	2C3	4.2	1.07	2.08	6	7.18	29.82	3.15	37.00	0.34
B6F-20	49.0	54.5	10660	5.5	5.2	95	2E4	4.4	1.80	4.19	8	7.99	30.21	5.99	38.20	0.30
B6F-20	54.5	59.5	10661	5.0	4.6	92	2E4	4.2	1.96	3.99	8	6.98	28.72	5.95	35.70	0.33
B6F-20	59.5	64.0	10662	4.5		0	2E4	4.4	2.57	4.14	12	8.25	29.45	6.71	37.70	0.38
B6F-20	64.0	68.5	10663	4.5	4.5	100	2E4	4.5	1.22	2.11	6	8.93	30.67	3.33	39.60	0.37
B6F-20	68.5	72.7	10664	4.2	4.1	98	2E4	4.1	<u>0.07</u>	<u>1.64</u>	4	6.46	31.14	1.71	37.60	0.04
B6F-20	72.7	78.0	10665	5.3	5.1	96	2E4	4.2	<u>0.03</u>	<u>0.67</u>	2	2.87	34.53	0.70	37.40	0.04
B6F-20	78.0	83.0	10666	5.0	4.9	98	2E4	4.2	<u>0.04</u>	<u>1.93</u>	4	4.22	32.28	1.97	36.50	0.02
B6F-20	83.0	87.5	10667	4.5	4.3	96	2E4	4.2	<u>0.24</u>	<u>0.63</u>	6	1.27	34.73	0.87	36.00	0.28
B6F-20	87.5	93.0	10668	5.5	5.4	98	2A34	3.7	2.21	5.23	8	1.82	24.98	7.44	26.80	0.30
B6F-20	93.0	97.2	10669	4.2	4.1	98	2A34	3.8	0.36	2.15	4	2.61	28.29	2.51	30.90	0.14
B6F-20	97.2	101.8	10670	4.6	4.3	93	2A34	3.3	2.96	5.78	36	2.39	11.91	8.74	14.30	0.34
B6F-20	101.8	106.8	10671	5.0	4.8	96	2A34	3.7	1.23	3.22	14	1.46	33.84	4.45	35.30	0.28
B6F-20	106.8	113.0	10672	6.2	5.1	82	2E41	4.0	<u>0.43</u>	<u>3.37</u>	6	5.16	29.54	3.80	34.70	0.11
B6F-20	113.0	117.0	10673	4.0		0	2E1	3.8	0.14	1.72	4	5.05	28.65	1.86	33.70	0.08
B6F-20	117.0	121.2	10674	4.2	2.5	60	2E81	3.8	0.06	1.01	6	5.27	26.43	1.07	31.70	0.06
B6F-20	121.2	126.5	10675	5.3	5.1	96	2E81	3.8	0.09	1.63	2	4.49	28.31	1.72	32.80	0.05
B6F-20	126.5	131.8	10676	5.3	5.2	98	2E81	4.0	0.06	1.74	4	6.60	30.10	1.80	36.70	0.03
B6F-20	131.8	136.8	10677	5.0	4.9	98	2C3	3.6	0.10	0.83	4	5.75	23.05	0.93	28.80	0.11
B6F-20	136.8	141.0	10678	4.2		0	2C3	3.9	0.11	1.65	4	7.18	26.72	1.76	33.90	0.06
B6F-20	141.0	145.5	10679	4.5	4.4	98	2C3	4.1	0.20	2.38	10	7.33	28.67	2.58	36.00	0.08
B6F-20	145.5	150.5	10680	5.0	4.7	94	2C3	3.9	1.86	2.89	38	5.72	26.08	4.75	31.80	0.39
B6F-20	150.5	155.0	10681	4.5	3.2	71	2E1	<u>3.4</u>	0.30	1.27	6	4.01	35.69	1.57	39.70	0.19
B6F-20	155.0	158.6	10682	3.6	3.5	97	2E1	<u>4.3</u>	0.05	1.18	2	3.50	36.70	1.23	40.20	0.04
B6F-20	158.6	162.0	10683	3.4	3.2	94	2E4	4.2	<u>0.35</u>	<u>1.24</u>	2	3.72	35.08	1.59	38.80	0.22
B6F-20	162.0	167.5	10684	5.5	5.3	96	2E4	4.5	<u>3.54</u>	<u>5.94</u>	8	3.82	34.18	9.48	38.00	0.37
B6F-20	167.5	173.0	10685	5.5		0	2A4	4.5	2.86	6.41	8	3.53	34.37	9.27	37.90	0.31
B6F-20	173.0	179.0	10686	6.0	3.8	63	2A4	3.7	3.59	8.93	18	2.27	20.13	12.52	22.40	0.29
B6F-20	179.0	184.1	10687	5.1	4.2	82	2A4	3.6	6.27	12.50	44	3.26	13.04	18.77	16.30	0.33
B6F-20	184.1	190.0	10688	5.9	4.9	83	2A4	4.0	4.58	11.20	24	1.90	26.10	15.78	28.00	0.29
B6F-20	190.0	194.7	10689	4.7	3.5	74	2C0	3.0	0.71	1.60	40	2.56	8.54	2.31	11.10	0.31
B6F-20	194.7	200.8	10690	6.1	4.7	77	2C0	3.1	0.50	1.71	8	3.79	9.91	2.21	13.70	0.23
B6F-20	200.8	206.7	10691	5.9	5.1	86	2C0	3.1	0.90	2.78	16	2.92	11.78	3.68	14.70	0.24
B6F-20	206.7	211.0	10692	4.3	4.2	98	2C0	2.8	0.96	1.83	14	2.39	2.21	2.79	4.60	0.34
B6F-20	211.0	216.0	10693	5.0	3.3	66	2C0	2.9	0.13	0.18	4	3.37	5.33	0.31	8.70	0.42

FILE = B6F-20.WR1

DDH	FROM feet	TO feet	SAMPLE	INT feet	REC feet	REC %	UNIT	SG	PB %	ZN %	AG g/t	PD %	PY %	PB+ZN %	FE-TOTAL %	PB/(PB+ZN)
B6F-21	10.0	16.0	34751	6.0		0	2C38	3.9	0.48	1.38	10	1.52	30.88	1.86	32.40	0.26
B6F-21	16.0	21.0	34752	5.0		0	2C38	4.1	0.75	1.02	8	4.71	30.49	1.77	35.20	0.42
B6F-21	21.0	26.0	34753	5.0	4.7	94	2C38	4.1	0.25	1.58	10	6.66	28.94	1.83	35.60	0.14
B6F-21	26.0	31.0	34754	5.0	4.8	96	2C38	4.2	0.37	1.19	4	4.84	30.96	1.56	35.80	0.24
B6F-21	31.0	36.0	34755	5.0		0	2C38	4.3	0.06	0.56	4	4.13	35.57	0.62	39.70	0.10
B6F-21	36.0	41.0	34756	5.0	4.7	94	2C38	4.4	0.49	0.37	6	2.56	37.44	0.86	40.00	0.57
B6F-21	41.0	43.0	34757	2.0		0	2C38	3.7	0.87	1.03	4	0.81	28.99	1.90	29.80	0.46
B6F-21	43.0	47.0	10613	4.0	3.8	95	2D34	3.2	<u>0.58</u>	<u>0.98</u>	8	2.42	15.48	1.56	17.90	0.37
B6F-21	47.0	52.3	34758	5.3		0	2A4	3.7	0.70	1.22	12	2.76	22.44	1.92	25.20	0.36
B6F-21	52.3	62.2	10614	9.9		0	1D4	3.0	0.83	0.13	38	3.32	2.53	0.96	5.85	0.86
B6F-21	62.2	67.0	34759	4.8		0	2C3	3.7	1.11	2.09	14	2.84	23.76	3.20	26.60	0.35
B6F-21	67.0	71.5	34760	4.5		0	2C3	3.9	0.79	1.34	8	1.13	25.97	2.13	27.10	0.37
B6F-21	71.5	75.5	34761	4.0	3.8	95	2C3	4.0	0.15	0.40	4	0.80	30.40	0.55	31.20	0.27
B6F-21	75.5	80.5	34762	5.0		0	2C3	3.9	0.04	1.42	2	1.89	30.91	1.46	32.80	0.03
B6F-21	80.5	85.5	34763	5.0	4.9	98	2E81	4.5	0.14	1.15	2	6.36	30.74	1.29	37.10	0.11
B6F-21	85.5	90.5	34764	5.0	4.8	96	2E81	3.8	0.63	0.74	4	7.47	28.93	1.37	36.40	0.46
B6F-21	90.5	95.0	10610	4.5	3.9	87	2E14	3.9	0.76	2.07	4	1.54	28.26	2.83	29.80	0.27
B6F-21	95.0	99.5	34765	4.5	4.3	96	2E14	3.7	0.70	1.08	6	1.02	30.68	1.78	31.70	0.39
B6F-21	99.5	104.0	34766	4.5	4.2	93	2E14	4.6	1.03	0.55	14	0.44	35.16	1.58	35.60	0.65
B6F-21	104.0	108.5	34767	4.5	4.4	98	2E14	3.9	3.09	0.31	34	0.47	29.73	3.40	30.20	0.91
B6F-21	108.5	114.0	10612	5.5	4.9	89	BXA	3.7	3.95	7.10	22	2.39	20.01	11.05	22.40	0.36
B6F-21	114.0	121.7	34768	7.7	7.2	94	2A3	3.9	0.96	1.36	12	1.01	24.49	2.32	25.50	0.41
B6F-21	121.7	126.7	34769	5.0	4.7	94	2C38	4.1	0.50	1.42	2	3.36	32.34	1.92	35.70	0.26
B6F-21	126.7	131.7	34770	5.0		0	2C38	3.9	0.34	1.36	2	7.33	24.47	1.70	31.80	0.20
B6F-21	131.7	136.3	34771	4.6	4.5	98	2C38	4.1	0.12	0.37	4	5.20	31.30	0.49	36.50	0.24
B6F-21	136.3	140.5	34772	4.2	3.9	93	2C38	4.0	0.15	1.33	2	1.48	31.82	1.48	33.30	0.10
B6F-21	140.5	145.5	34773	5.0	4.6	92	2C38	4.0	0.10	1.81	2	2.00	30.20	1.91	32.20	0.05
B6F-21	145.5	151.2	34774	5.7		0	2C38	4.2	0.22	1.38	2	3.03	27.27	1.60	30.30	0.14
B6F-21	151.2	155.2	10615	4.0	3.6	90	2E148	4.1	0.67	1.97	6	4.65	28.25	2.64	32.90	0.25
B6F-21	155.2	161.0	34775	5.8	5.3	91	2D3	4.2	0.59	1.80	4	2.17	27.83	2.39	30.00	0.25
B6F-21	161.0	166.0	34776	5.0	4.8	96	2D3	3.6	0.13	2.21	4	1.66	24.34	2.34	26.00	0.06
B6F-21	166.0	174.0	34777	8.0	7.1	89	2D3	4.0	2.50	6.00	8	2.95	24.75	8.50	27.70	0.29
B6F-21	174.0	177.0	34778	3.0		0	2D5	4.2	6.79	6.16	74	2.08	34.02	12.95	36.10	0.52
B6F-21	177.0	182.0	34779	5.0	4.4	88	2D5	3.8	1.07	3.20	30	1.95	18.55	4.27	20.50	0.25
B6F-21	182.0	186.0	34780	4.0		0	2D5	3.4	2.48	5.88	24	3.16	12.84	8.36	16.00	0.30
B6F-21	186.0	190.0	34781	4.0		0	2D5	3.3	1.57	2.10	36	1.76	5.44	3.67	7.20	0.43
B6F-21	190.0	194.5	34782	4.5	4.2	93	2D5	2.9	1.67	3.07	22	2.51	3.99	4.74	6.50	0.35
B6F-21	194.5	200.0	34783	5.5	4.0	73	2D5	2.9	1.19	3.02	20	3.33	6.87	4.21	10.20	0.28
B6F-21	200.0	205.0	34784	5.0	4.8	96	2D5	3.1	1.32	2.05	18	3.64	8.76	3.37	12.40	0.39
B6F-21	205.0	210.0	34785	5.0	4.9	98	2D5	3.2	1.04	1.72	16	3.41	9.99	2.76	13.40	0.38
B6F-21	210.0	215.0	34786	5.0		0	2D5	3.1	2.16	1.55	42	2.48	3.42	3.71	5.90	0.58
B6F-21	215.0	219.0	34787	4.0	3.5	88	2A4	3.3	5.00	7.42	44	3.93	15.37	12.42	19.30	0.40
B6F-21	219.0	231.3	10611	12.3	10.2	83	2D54	2.9	1.92	5.05	32	4.19	10.91	6.97	15.10	0.28
B6F-21	231.3	237.0	34788	5.7	5.4	95	2D5	2.8	1.05	3.65	26	2.57	2.54	4.70	5.11	0.22
B6F-21	237.0	242.0	34789	5.0	4.4	88	2D5	2.8	0.85	3.46	20	1.76	1.15	4.31	2.91	0.20
B6F-21	242.0	247.0	34790	5.0		0	2D5	2.8	0.71	2.82	16	1.12	2.18	3.53	3.30	0.20
B6F-21	247.0	252.0	34791	5.0	4.9	98	2D5	2.9	2.00	3.96	36	2.29	3.28	5.96	5.57	0.34
B6F-21	252.0	257.0	34792	5.0	4.7	94	2D5	2.9	1.32	3.55	24	1.93	4.41	4.87	6.34	0.27
B6F-21	257.0	264.0	34793	7.0	6.3	90	2D5	2.9	1.52	4.43	26	2.66	3.17	5.95	5.83	0.26
B6F-21	264.0	269.0	34794	5.0	4.1	82	2D5	2.9	0.84	3.13	22	1.66	2.81	3.97	4.47	0.21
B6F-21	269.0	272.0	34795	3.0	2.8	93	2D5	2.9	1.63	3.47	24	2.94	3.71	5.10	6.65	0.32
B6F-21	272.0	277.5	34796	5.5	4.6	84	2D5	2.9	0.27	0.28	10	2.80	3.50	0.55	6.30	0.49
B6F-21	277.5	280.7	34797	3.2	2.9	91	1D419	2.9	0.62	1.20	26	3.33	3.57	1.82	6.90	0.34

DDH	FROM feet	TO feet	SAMPLE	INT feet	REC feet	REC %	UNIT	SG	PB %	ZN %	AG g/t	PO %	PY %	PB+ZN %	FE-TOTAL %	PB/(PB+ZN)
86F-21	280.7	289.0	10618	8.3	7.5	90	1D419	2.7	0.53	1.65	8	2.02	2.06	2.18	4.08	0.24
86F-21	289.0	296.5	34798	7.5	7.1	95	1D419	2.9	2.11	0.97	22	2.66	3.38	3.08	6.04	0.69
86F-21	296.5	299.0	34799	2.5	2.3	92	1D419	3.0	3.45	1.85	40	4.24	7.26	5.30	11.5	0.65

FILE = 86F-21.WR1

DDH	FROM feet	TO feet	SAMPLE	INT feet	REC feet	REC %	UNIT	SG	PB %	ZN %	AG g/t	PD %	PY %	PB+ZN %	FE-TOTAL %	PB/(PB+ZN)
86F-22	104.3	108.2	10629	3.9	3.7	95	1H0	3.0	1.98	3.28	44	2.84	3.03	5.26	5.87	0.38
86F-22	108.2	110.4	10630	2.2	2.1	95	267	4.3	4.27	6.49	84	20.10	10.20	10.76	30.30	0.40
86F-22	110.4	115.0	10631	4.6	3.9	85	1H0	3.2	2.82	2.26	44	7.22	10.88	5.08	18.10	0.56
86F-22	115.0	117.5	10632	2.5	2.4	96	267	4.0	3.73	6.00	68	12.50	16.30	9.73	28.80	0.38
86F-22	117.5	123.0	10633	5.5	5.3	96	1H0	4.4	2.46	3.80	46	8.06	12.44	6.26	20.50	0.39
86F-22	123.0	131.2	10634	8.2	7.9	96	1H0	3.0	1.37	0.95	18	5.50	3.69	2.32	9.19	0.59
86F-22	131.2	135.0	10635	3.8	3.7	97	267	4.3	5.74	7.63	64	4.43	17.67	13.37	22.10	0.43
86F-22	135.0	141.5	10636	6.5	6.1	94	2E4	4.5	3.44	2.90	48	6.55	29.35	6.34	35.90	0.54
86F-22	141.5	146.8	10637	5.3	5.0	94	2E4	4.5	1.33	1.15	14	5.23	28.77	2.48	34.00	0.54
86F-22	146.8	152.2	10638	5.4	5.2	96	2E4	4.6	1.13	0.40	24	10.10	32.10	1.53	42.20	0.74
86F-22	152.2	156.5	10639	4.3	4.2	98	2E4#	4.5	5.11	5.51	22	12.20	26.00	10.62	38.20	0.48
86F-22	156.5	160.8	10640	4.3	4.1	95	2E4#	4.4	4.12	4.12	26	13.00	24.80	8.24	37.80	0.50
86F-22	160.8	165.2	10641	4.4	4.3	98	2E4#	4.3	0.45	0.20	6	9.74	31.96	0.65	41.70	0.69
86F-22	165.2	170.1	10642	4.9	4.7	96	2E80	4.7	2.23	2.69	30	3.90	37.20	4.92	41.10	0.45
86F-22	170.1	174.5	10643	4.4	4.2	95	2E80	4.7	2.06	1.62	50	7.37	34.43	3.68	41.80	0.56
86F-22	174.5	179.0	10644	4.5	4.5	100	2E80	4.4	1.89	0.79	36	10.90	30.10	2.68	41.00	0.71
86F-22	179.0	183.3	10645	4.3	4.1	95	2E80	4.4	2.83	2.10	48	12.70	27.30	4.93	40.00	0.57
86F-22	183.3	188.7	10646	5.4	5.0	93	2E80	4.4	2.38	3.17	34	14.20	28.20	5.55	42.40	0.43
86F-22	188.7	192.0	10647	3.3	2.9	88	2E4	4.8	3.18	4.56	28	2.27	35.93	7.74	38.20	0.41
86F-22	192.0	196.0	10648	4.0	3.6	90	2E4	4.1	0.85	2.39	18	4.26	29.54	3.24	33.80	0.26
86F-22	196.0	199.5	10649	3.5	2.9	83	2E4	4.6	4.18	5.47	32	3.98	32.92	9.65	36.90	0.43
86F-22	199.5	203.7	10650	4.2	3.6	86	2E4	4.7	2.57	5.33	24	2.13	35.87	7.90	38.00	0.33
86F-22	203.7	206.0	10652	2.3	1.8	78	2E4	4.7	5.21	5.96	32	0.79	36.91	11.17	37.70	0.47
86F-22	206.0	209.6	10617	3.6	3.4	94	2D45	3.7	3.77	4.11	34	3.31	20.49	7.88	23.80	0.48
86F-22	209.6	214.4	10601	4.8	4.5	94	2D59	2.9	1.03	4.21	24	2.72	2.59	5.24	5.31	0.20
86F-22	214.4	218.7	10602	4.3		0	2D59	3.1	0.33	2.41	10	6.92	9.88	2.74	16.80	0.12
86F-22	218.7	223.7	10603	5.0	4.8	96	2D59	3.1	1.07	2.07	22	6.66	8.04	3.14	14.70	0.34
86F-22	223.7	228.5	10604	4.8	4.8	100	2D59	2.9	0.84	1.63	16	1.84	2.38	2.47	4.22	0.34
86F-22	228.5	232.6	10626	4.1	3.8	93	2D0	2.9	<u>0.34</u>	<u>0.78</u>	11	2.52	2.90	1.12	5.42	0.30
86F-22	232.6	236.5	10627	3.9	3.1	79	1CD4	2.9	0.03	0.10	0	3.03	1.11	0.13	4.14	0.23
86F-22	236.5	240.3	10605	3.8	3.3	87	1CD4	2.9	0.03	0.03	4	3.81	0.33	0.06	4.14	0.50
86F-22	240.3	244.7	10606	4.4	4.2	95	1CD4	2.9	0.02	0.12	2	5.24	2.16	0.14	7.40	0.14
86F-22	244.7	248.8	10607	4.1	3.8	93	1CD4	2.8	0.06	0.05	4	3.00	1.14	0.11	4.14	0.55
86F-22	248.8	254.5	10628	5.7	5.6	98	2D0	2.9	<u>0.68</u>	<u>1.16</u>	10	2.29	2.61	1.84	4.90	0.37
86F-22	254.5	258.0	10608	3.5	3.2	91	2A4	2.9	0.68	2.91	16	4.03	4.68	3.59	8.71	0.19
86F-22	258.0	262.0	10609	4.0	3.8	95	2A4	2.9	0.75	2.23	16	3.40	1.93	2.98	5.33	0.25
86F-22	262.0	267.0	10616	5.0	4.8	96	2D0	2.8	1.03	1.92	8	2.18	1.99	2.95	4.17	0.35
86F-22	267.0	272.0	10619	5.0	4.7	94	2D0	2.8	1.11	1.24	12	2.44	3.80	2.35	6.24	0.47
86F-22	272.0	278.5	10620	6.5	5.9	91	2A74	2.9	0.41	1.30	8	3.93	3.15	1.71	7.08	0.24
86F-22	278.5	284.0	10621	5.5	5.4	98	2A74	2.8	0.80	1.48	16	4.43	0.72	2.28	5.15	0.35
86F-22	284.0	290.7	10622	6.7	6.4	96	2A74	2.9	0.52	1.55	12	3.97	1.83	2.07	5.80	0.25
86F-22	290.7	297.0	10623	6.3	5.9	94	2A74	2.8	0.66	2.31	18	3.62	2.05	2.97	5.67	0.22
86F-22	297.0	302.0	10624	5.0	4.8	96	2D4	3.9	33.60	2.43	276	2.85	1.53	36.03	4.38	0.93
86F-22	302.0	306.0	10625	4.0	3.7	93	2L14	2.8	0.89	1.59	17	2.07	1.70	2.48	3.77	0.36

DDH	FROM feet	TO feet	SAMPLE	INT feet	REC feet	REC %	UNIT	SG	PB %	ZN %	AG g/t	PD %	PY %	PB+ZN %	FE-TOTAL %	PB/(PB+ZN)
86F-23	106.0	111.0	4967	5.0	4.9	98	2E4	4.1	3.58	6.30	57	2.54	25.06	9.88	27.60	0.36
86F-23	111.0	116.0	4968	5.0		0	2E4	4.7	9.96	8.75	167	4.29	22.11	18.71	26.40	0.53
86F-23	116.0	122.5	4969	6.5	4.4	68	2E4	3.7	2.66	10.90	19	3.70	14.20	13.56	17.90	0.20
86F-23	122.5	127.0	4970	4.5	4.3	96	2E4	3.9	5.02	10.10	55	4.86	24.84	15.12	29.70	0.33
86F-23	127.0	132.0	4971	5.0	4.9	98	2A3	3.8	0.93	1.09	11	2.17	24.83	2.02	27.00	0.46
86F-23	132.0	136.5	4972	4.5		0	2E0	4.6	0.25	0.36	8	2.37	40.13	0.61	42.50	0.41
86F-23	136.5	140.0	4973	3.5		0	2E0	4.7	0.64	0.86	8	1.53	40.17	1.50	41.70	0.43
86F-23	140.0	144.5	4974	4.5	4.1	91	2A34	3.9	1.32	4.99	9	1.30	23.20	6.31	24.50	0.21
86F-23	144.5	148.7	4975	4.2	4.0	95	2A34	3.8	2.10	6.11	19	1.73	21.47	8.21	23.20	0.26
86F-23	148.7	152.7	4976	4.0		0	2A34	3.8	0.48	1.80	11	0.90	30.10	2.28	31.00	0.21
86F-23	152.7	156.7	4977	4.0	3.9	98	2A34	3.9	0.50	1.30	9	1.50	29.40	1.80	30.90	0.28
86F-23	156.7	161.5	4978	4.8	4.5	94	2E81	4.2	0.57	2.11	6	6.59	30.01	2.68	36.60	0.21
86F-23	161.5	166.5	4979	5.0	4.3	86	2E81	4.2	1.31	2.36	8	8.32	30.78	3.67	39.10	0.36
86F-23	166.5	170.8	4980	4.3	3.0	70	2E81	4.2	0.71	1.89	8	7.20	28.20	2.60	35.40	0.27
86F-23	170.8	177.0	4981	6.2	5.8	94	2E1	4.1	0.08	0.61	9	0.89	35.01	0.69	35.90	0.12
86F-23	177.0	183.0	4982	6.0	4.2	70	2E1	3.8	0.59	0.72	9	1.10	28.00	1.31	29.10	0.45
86F-23	183.0	189.0	4984	6.0		0	2D34	3.4	3.34	8.62	20	2.81	14.19	11.96	17.00	0.28
86F-23	189.0	193.2	4983	4.2	3.8	90	2C35	3.4	0.90	2.57	10	5.75	18.65	3.47	24.40	0.26
86F-23	193.2	198.0	4985	4.8	4.5	94	2C35	3.6	0.38	0.79	20	9.27	21.43	1.17	30.70	0.32
86F-23	198.0	204.0	4986	6.0	5.7	95	2D45	3.8	3.38	5.94	20	5.52	7.98	9.32	13.50	0.36

FILE = 86F-23.WR1

DDH	FROM feet	TO feet	SAMPLE	INT feet	REC feet	REC %	UNIT	SG	PB %	ZN %	AG g/t	PD %	PY %	PB+ZN %	FE-TOTAL %	PB/(PB+ZN)
B6F-24	130.6	135.0	10738	4.4	4.2	95	2D4	3.5	2.81	5.81	56	7.44	15.86	8.62	23.30	0.33
B6F-24	135.0	142.3	10739	7.3	5.8	79	2CD	2.9	0.46	1.05	16	3.61	6.15	1.51	9.76	0.30
B6F-24	142.3	146.0	10740	3.7	3.5	95	2B4	4.5	4.81	6.58	72	1.84	20.56	11.39	22.40	0.42
B6F-24	146.0	150.0	10741	4.0	3.7	93	2F64	4.7	6.24	5.45	76	2.82	27.48	11.69	30.30	0.53
B6F-24	150.0	160.6	10742	10.6	4.5	42	2F64	4.6	9.23	8.61	128	4.29	18.81	17.84	23.10	0.52
B6F-24	150.6	166.5	10743	15.9	5.5	35	2E4	4.7	2.48	1.80	32	1.55	40.45	4.28	42.00	0.58
B6F-24	166.5	171.5	10744	5.0	4.7	94	2E64	4.7	4.69	6.56	64	0.86	33.14	11.25	34.00	0.42
B6F-24	171.5	175.5	10745	4.0		0	2E4	4.7	3.53	4.97	44	2.23	35.67	8.50	37.90	0.42
B6F-24	175.5	180.0	10746	4.5	3.6	80	2E48	4.8	3.16	3.84	32	4.56	30.14	7.00	34.70	0.45
B6F-24	180.0	184.0	10747	4.0	1.5	38	2E48	4.8	3.80	4.17	38	2.26	37.74	7.97	40.00	0.48
B6F-24	184.0	192.5	10748	8.5	3.3	39	2E0	4.6	2.90	3.67	34	1.91	39.09	6.57	41.00	0.44
B6F-24	192.5	199.5	10749	7.0	6.3	90	2E0	4.5	1.26	0.77	20	0.48	39.62	2.03	40.10	0.62
B6F-24	199.5	205.0	10750	5.5	4.7	85	2E0	4.6	1.06	0.90	14	0.37	41.23	1.96	41.60	0.54
B6F-24	205.0	211.0	4987	6.0	4.6	77	2E0	4.6	2.27	3.49	26	1.89	35.91	5.76	37.80	0.39
B6F-24	211.0	217.0	4988	6.0	5.6	93	2E01	4.7	3.35	2.76	36	1.13	39.17	6.11	40.30	0.55
B6F-24	217.0	221.5	4989	4.5	4.3	96	2E01	4.6	1.28	0.45	16	0.34	38.46	1.73	38.80	0.74
B6F-24	221.5	226.3	4990	4.8	4.1	85	2E01	4.7	2.97	3.93	34	1.10	36.60	6.90	37.70	0.43
B6F-24	226.3	232.0	4991	5.7	5.6	98	2D3	4.4	3.07	5.72	48	4.75	29.75	8.79	34.50	0.35
B6F-24	232.0	238.0	4992	6.0	5.9	98	2D3	4.4	2.07	2.29	16	5.61	34.59	4.36	40.20	0.47
B6F-24	238.0	243.5	4993	5.5	5.1	93	2D3	3.9	1.20	1.10	20	1.78	30.32	2.30	32.10	0.52
B6F-24	243.5	247.0	4994	3.5	3.5	100	2E80	4.2	0.47	0.85	6	10.30	31.60	1.32	41.90	0.36
B6F-24	247.0	250.5	4995	3.5	3.3	94	2E14	4.5	<u>0.04</u>	1.59	4	3.67	36.93	1.63	40.60	0.02
B6F-24	250.5	255.5	4996	5.0	4.1	82	2E14	3.7	<u>2.91</u>	0.51	80	5.86	20.94	3.42	26.80	0.85
B6F-24	255.5	259.5	4997	4.0	3.8	95	2E14	<u>3.4</u>	<u>0.04</u>	1.11	4	2.58	36.42	1.15	39.00	0.03
B6F-24	259.5	264.3	4998	4.8	4.5	94	2E14	4.2	0.55	1.38	6	3.94	33.46	1.93	37.40	0.28
B6F-24	264.3	271.0	4999	6.7	6.6	99	2E4	4.5	5.81	8.21	16	6.32	27.68	14.02	34.00	0.41
B6F-24	271.0	275.0	5000	4.0		0	2E1	4.2	0.31	1.59	6	4.12	31.98	1.90	36.10	0.16
B6F-24	275.0	279.0	43051	4.0		0	2E1	4.1	0.79	0.71	10	4.28	31.92	1.50	36.20	0.53
B6F-24	279.0	283.0	43052	4.0	3.1	78	2E1	4.0	0.75	1.18	6	3.28	31.52	1.93	34.80	0.39
B6F-24	283.0	287.0	43053	4.0	3.0	75	2E1	4.1	0.69	2.55	4	5.22	31.18	3.24	36.40	0.21
B6F-24	287.0	291.0	43054	4.0	3.3	83	2E08	4.3	4.35	8.09	12	4.91	28.09	12.44	33.00	0.35
B6F-24	291.0	295.0	43055	4.0	3.8	95	2E08	4.2	2.88	6.31	10	4.76	29.14	9.19	33.90	0.31
B6F-24	295.0	299.0	43056	4.0	3.7	93	2E08	4.5	4.02	8.37	10	6.16	24.94	12.39	31.10	0.32
B6F-24	299.0	302.0	43057	3.0	2.2	73	2E08	4.2	1.45	4.23	6	6.25	29.75	5.68	36.00	0.26
B6F-24	302.0	306.5	43058	4.5	3.8	84	2E08	4.5	1.09	2.20	6	5.92	34.68	3.29	40.60	0.33
B6F-24	306.5	311.0	43059	4.5	4.2	93	2E08	4.2	1.14	1.93	8	6.63	30.47	3.07	37.10	0.37
B6F-24	311.0	315.0	43060	4.0	2.8	70	2E08	4.4	0.65	1.71	8	7.31	32.19	2.36	39.50	0.28
B6F-24	315.0	319.5	43061	4.5	3.9	87	2E08	4.4	0.87	1.80	8	6.86	33.24	2.67	40.10	0.33
B6F-24	319.5	324.0	43062	4.5	4.2	93	2E08	4.2	0.22	1.14	6	7.53	29.37	1.36	36.90	0.16
B6F-24	324.0	327.0	43063	3.0	0.9	30	BXA	2.9	0.14	0.47	8	6.10	6.30	0.61	12.40	0.23
B6F-24	327.0	331.5	43064	4.5		0	2E4	4.8	4.49	8.39	20	1.50	35.40	12.88	36.90	0.35
B6F-24	331.5	335.5	43065	4.0		0	2ED	4.4	5.02	9.28	26	2.59	29.31	14.30	31.90	0.35
B6F-24	335.5	339.5	43066	4.0	3.9	98	2A34	4.5	5.21	10.30	26	1.94	29.56	15.51	31.50	0.34
B6F-24	339.5	344.0	43067	4.5	4.1	91	2A34	3.7	3.86	9.52	24	2.30	19.30	13.38	21.60	0.29
B6F-24	344.0	348.8	43068	4.8	4.4	92	2A34	3.5	1.40	5.76	20	2.45	18.95	7.16	21.40	0.20
B6F-24	348.8	351.5	43069	2.7		0	2A34	3.5	4.87	10.10	26	3.28	11.72	14.97	15.00	0.33
B6F-24	351.5	355.0	43070	3.5	3.2	91	2A34	4.1	3.91	9.45	20	2.61	24.39	13.36	27.00	0.29
B6F-24	355.0	359.3	43071	4.3	4.0	93	2A34	3.5	2.23	6.50	14	1.81	17.99	8.73	19.80	0.26
B6F-24	359.3	363.5	43072	4.2	3.9	93	2A34	3.4	4.32	12.80	24	2.23	11.57	17.12	13.80	0.25
B6F-24	363.5	367.0	43073	3.5	3.5	100	2J732	3.9	8.27	20.70	34	10.00	8.60	28.97	18.60	0.29
B6F-24	367.0	373.0	43074	6.0	5.1	85	2D5	3.1	1.54	5.29	16	5.12	8.28	6.83	13.40	0.23

DDH	FROM feet	TO feet	SAMPLE	INT feet	REC feet	REC %	UNIT	SG	PB %	ZN %	AG g/t	PD %	PY %	PB+ZN %	FE-TOTAL %	PB/(PB+ZN)
86F-25	167.5	170.0	10694	2.5	2.4	96	2D0	3.1	2.02	3.39	36	5.83	9.27	5.41	15.10	0.37
86F-25	170.0	175.5	10695	5.5	3.3	60	1D4	2.8	0.47	0.27	10	2.95	2.53	0.74	5.48	0.64
86F-25	175.5	181.0	10696	5.5	3.1	56	2LE34	3.7	4.31	3.97	74	11.10	15.30	8.28	26.40	0.52
86F-25	181.0	185.0	10697	4.0	1.7	43	2LE34	4.3	5.30	4.95	84	14.80	21.50	10.25	36.30	0.52
86F-25	185.0	189.7	10698	4.7	2.4	51	2LE34	3.5	2.97	2.38	44	8.38	17.42	5.35	25.80	0.56
86F-25	189.7	195.7	10699	6.0	5.9	98	2G4	4.1	5.00	5.01	72	2.61	21.29	10.01	23.90	0.50
86F-25	195.7	200.0	10700	4.3	4.1	95	2E4L	3.6	0.87	1.01	30	5.31	23.39	1.88	28.70	0.46
86F-25	200.0	207.8	10701	7.8	7.4	95	1H4	2.9	0.72	0.31	38	7.99	4.11	1.03	12.10	0.70
86F-25	207.8	212.5	10702	4.7	4.4	94	2E4	4.1	2.44	1.23	32	1.55	36.45	3.67	38.00	0.66
86F-25	212.5	217.6	10703	5.1	5.0	98	2E4	4.6	1.69	2.40	22	1.73	38.97	4.09	40.70	0.41
86F-25	217.6	221.6	10704	4.0	5.7	100	2E4	4.7	2.57	3.91	22	0.60	41.50	6.48	42.10	0.40
86F-25	221.6	226.0	10705	4.4	3.9	89	2E4	4.3	4.78	3.40	28	1.78	77.82	8.18	<u>79.60</u>	0.58
86F-25	226.0	232.5	10706	6.5	5.7	88	2E4	4.6	3.17	3.17	32	4.26	36.04	6.34	<u>40.30</u>	0.50
86F-25	232.5	239.8	10707	7.3	6.8	93	2C3	4.0	2.18	0.17	34	0.36	33.14	2.35	33.50	0.93
86F-25	239.8	244.6	10708	4.8	4.7	98	2E0	4.6	1.54	0.86	24	2.46	40.04	2.40	42.50	0.64
86F-25	244.6	250.7	10709	6.1	5.9	97	2E0	4.8	1.47	0.75	20	1.55	39.85	2.22	41.40	0.66
86F-25	250.7	258.0	10710	7.3	6.9	95	2E84	4.6	2.93	2.30	44	4.47	36.03	5.23	40.50	0.56
86F-25	258.0	264.0	10711	6.0	5.8	97	2E84	4.5	3.15	3.95	36	5.80	32.70	7.10	38.50	0.44
86F-25	264.0	268.8	10712	4.8	4.4	92	2E84	4.4	1.14	2.78	14	7.97	31.53	3.92	39.50	0.29
86F-25	268.8	273.0	10713	4.2	3.5	83	2E4	4.4	<u>0.92</u>	<u>1.12</u>	8	1.51	38.39	2.04	39.90	0.45
86F-25	273.0	278.0	10714	5.0	4.8	96	2E4	4.8	5.35	8.18	44	1.27	36.03	13.53	37.30	0.40
86F-25	278.0	282.0	10715	4.0	4.7	100	2E4	4.5	<u>0.13</u>	<u>0.14</u>	6	0.40	39.80	0.27	40.20	0.48
86F-25	282.0	286.7	10716	4.7	2.1	45	2E4	4.5	<u>2.06</u>	<u>1.88</u>	16	1.95	37.55	3.94	39.50	0.52
86F-25	286.7	290.0	10717	3.3	2.3	70	2E84	4.5	1.63	1.95	14	6.27	34.93	3.58	41.20	0.46
86F-25	290.0	295.0	10718	5.0	4.2	84	2E84	4.0	1.46	2.12	12	2.30	31.90	3.58	34.20	0.41
86F-25	295.0	299.0	10719	4.0	3.9	98	2E84	4.5	2.35	5.33	16	6.73	32.37	7.68	39.10	0.31
86F-25	299.0	303.0	10720	4.0	3.8	95	2E84	4.6	<u>0.52</u>	<u>0.82</u>	6	<u>0.60</u>	43.60	1.34	44.20	0.39
86F-25	303.0	306.5	10721	3.5	2.2	63	2E84	4.6	1.45	2.24	12	8.06	33.44	3.69	41.50	0.39
86F-25	306.5	310.0	10722	3.5	3.2	91	2E4	4.6	2.10	3.00	24	5.42	35.68	5.10	41.10	0.41
86F-25	310.0	315.0	10723	5.0	3.9	78	2E4	4.7	3.00	6.15	20	4.10	33.10	9.15	37.20	0.33
86F-25	315.0	319.0	10724	4.0	3.4	85	2E4	4.5	2.70	5.38	20	1.78	36.32	8.08	38.10	0.33
86F-25	319.0	324.0	10725	5.0	3.6	72	2E4	4.8	3.46	5.21	20	0.88	37.62	8.67	38.50	0.40
86F-25	324.0	330.0	10726	6.0	3.7	62	2E4	4.7	2.00	3.48	14	1.06	40.64	5.48	41.70	0.36
86F-25	330.0	335.0	10727	5.0	4.1	82	2E4	4.6	4.90	9.35	22	1.98	33.32	14.25	35.30	0.34
86F-25	335.0	339.0	10728	4.0	3.7	93	2E4	4.6	3.45	6.85	16	2.14	32.66	10.30	34.80	0.33
86F-25	339.0	343.5	10729	4.5	4.2	93	2E4	4.4	4.16	8.59	20	2.13	32.97	12.75	35.10	0.33
86F-25	343.5	348.0	10730	4.5	2.3	51	2D5	3.3	1.27	1.87	18	6.81	13.39	3.14	20.20	0.40
86F-25	348.0	355.0	10731	7.0	6.8	97	2D5	3.0	1.25	2.73	24	2.58	4.21	3.98	6.79	0.31
86F-25	355.0	361.3	10732	6.3	5.8	92	2D5	3.0	2.11	2.06	32	2.41	2.52	4.17	4.93	0.51
86F-25	361.3	364.0	10733	2.7	2.6	96	2C05	3.3	0.25	0.43	8	10.60	13.70	0.68	24.30	0.37
86F-25	364.0	367.0	10734	3.0	2.9	97	2D75	3.6	1.63	4.34	24	13.50	15.40	5.97	28.90	0.27
86F-25	367.0	374.0	10735	7.0	6.8	97	2D5	3.1	0.40	2.09	10	3.63	11.97	2.49	15.60	0.16
86F-25	374.0	378.5	10736	4.5	4.5	100	2C0	2.8	0.68	1.44	16	1.83	4.52	2.12	6.35	0.32
86F-25	378.5	383.0	10737	4.5	4.4	98	2C0	2.9	0.81	2.12	16	3.16	3.96	2.93	7.12	0.28