

019306

Gum Mineralized Zones

Pg. 1.

			Pb	Zn	Ag
A-1	853.0 - 863.7	10.7'	Mineralized.		
A-4	481.5 - 491.5	10.0'	Mineralized.		
	515.0 - 527.0	12.0'	Mineralized.		
	537.5 - 562.3	24.8'	Mineralized.		
	656.0 - 682.5	26.5'	5.51	8.60	3.31
A-5	420.0 - 426.0	6.0'	10.60	9.62	3.84
	508.0 - 591.8	83.8	3.92	8.54	1.99
A-6			No INTERSECTIONS		
A-8	238.0 - 267.0	29.0'	Mineralized		
	306.8 - 322.0	15.2	2.47	5.65	1.04
	583.5 - 592.5	9.0	3.23	6.11	1.48
A-9	373.8 - 410.0	36.2	Mineralized		
	410.0 - 416.0	6.0	5.55	7.92	0.80
	434.0 - 479.0	45.0'	4.32	7.15	2.25
A-10	518.0 - 623.0	105.0'	4.39	6.75	1.95
	623.0 - 730.0	107.0'	weak mineralization.		
	730.0 - 756.0	26.0'	5.14	8.03	2.63
	756.0 767.0 - 775.4	8.4'	3.00	6.72	1.82
	775.4 - 785.0 802.0	26.6'	Mineralized		
	802.0 - 815.0	13.0'	4.50 - 6.27		2.24

			Pb	Zn	Ag.
A. 11	379.0 - 387.0	8.0'	6.00	6.84	2.70
	387.0 - 453.5	66.5'	Mineralized		
	493.5 - 506.5	13.0'	4.55	3.87	0.87
	584.0 - 599.0	15.0'	7.37	11.45	3.92
	693.0 - 704.0	11.0'	Mineralized		
	728.0 - 736.5	8.5'	Mineralized		
	736.5 - 745.0	8.5'	3.38	5.28	1.92
A. 12	745.0 - 755.0	10.0'	Mineralized		
	755.0 - 763.0	8.0'	2.33	7.80	1.26
	811.0 - 853.5	42.5	Mineralized		
	895.0 - 1044.5	149.5	Mineralized		
	1044.5 - 1054.5	10.0	4.73	6.96	2.80
A. 13	133.5 - 145.5	12.0	Mineralized		
	145.5 - 202.0	56.5'	5.38	4.80	2.22
	202.0 - 219.0	17.0'	Mineralized		
	398.0 - 410.5	12.5	Mineralized		
	428.0 - 448.0	20.0	Mineralized.		
A. 14	632.0 - 636.0	4.0	Mineralized		
	873.0 - 896.0	23.0'	Mineralized		
	896.0 - 905.0	9.0'	6.53	6.96	2.67
	905.0 - 942.0	37.0'	Mineralized.		

			Pb	Zn	As.
A-15	424.4 - 433.9	8.5'		Mineralized	
	453.0 - 502.0	49.0'	4.25	4.00	2.11
	520.0 - 570.0	50.0'		Mineralized	
	570.0 - 580.0	10.0'	3.60	5.58	1.42
	580.0 - 623.0	43.0'		Mineralized.	
A-16	761.0 - 861.0	100.0'		Mineralized	
	861.0 - 888.0	27.0'	2.33	3.85	1.14
	888.0 - 903.0	15.0'		Mineralized	
A-17	689.0 - 728.0	39.0'		Mineralized	
	745.0 - 778.0	33.0'		Mineralized	
	778.0 - 784.0	6.0'	6.38	7.92	2.56
	784.0 - 797.0	13.0'		Mineralized	
	797.0 - 802.0	5.0'	3.15	5.04	1.32
	802.0 - 846.5	44.5'		Mineralized.	
A-18	1021.0 - 1043.0	22.0'	5.62	9.73	3.16
	1043.0 - 1057.0			Mineralized	
	1057.0 - 1066.0	9.0'	5.01	8.62	2.79
	1071.0 - 1113.0	42.0'	2.64	4.85	1.69
	1113.0 - 1120.0			Mineralized.	

		Pb	Zn	Ag
A 19	335.8 - 345.6	9.8	Miscalc'd	
	345.6 - 355.0	9.4	6.68	5.64 3.18
	442.0 - 467.3	25.3	Miscalc'd	
	467.3 - 471.3	4.0	7.35	9.36 4.08
	471.3 - 493.0	21.7	Miscalc'd	
	493.0 - 500.5	7.5	4.95	6.96 1.76
	500.5 - 510.0	9.5	Miscalc'd	
	521.4 - 531.3	9.9'	Miscalc'd	
	531.3 - 583.3	52.0'	3.56	6.23 1.76
	601.6 - 603.3	1.7'	2.18	5.10 1.48
	637.0 - 673.5	36.5	5.09	8.12 2.39
	673.5 - 711.1	37.6	Miscalc'd	
	711.1 - 718.5	7.4'	2.85	4.02 0.98
	718.5 - 753.0	34.5	Miscalc'd	

A-20	603.0 - 632.0		Miscalc'd	
	632.0 - 637.0	5.0'	2.85	5.52 1.04
	637.0 - 667.0		Miscalc'd	
	667.0 - 676.0	9.0'	4.08	6.07 1.82
	689.0 - 693.0	4.0	4.35	6.72 2.12
	693.0 - 703.0	10.0	Miscalc'd	
	703.0 - 733.0	30.0	3.36	6.87 1.99
	733.0 - 759.0	26.0'	Miscalc'd.	
	778.0 - 783.0	5.0'	Miscalc'd	
	783.0 - 789.0	6.0'	3.15	5.28 2.46
	812.0 - 826.0	14.0'	4.20	4.86 1.99
	843.0 - 848.0	5.0'	Miscalc'd.	

		Pb	Zn	Ag
A-21	328.4 - 331.6	3.2	Mixed	
	331.6 - 378.0	46.4'	4.72	7.75 2.02
	378.0 - 404.2	26.2	Mixed	
	434.0 - 439.0	5.0'	Mixed	
	548.0 - 565.5	17.5'	Mixed	
	590.0 - 594.5	4.5'	Mixed	
	594.5 - 657.0	62.5'	4.38	7.56 1.90
	657.0 - 667.3	10.3'	Mixed	
	689.4 - 814.8	125.4	Mixed	

A-22	506.0 - 507.6	1.6	Mixed	
	571.5 - 593.8	22.3	Mixed	
	593.8 - 606.2	12.4'	5.42	6.05 2.44
	606.2 - 619.1	12.9	Mixed	
	754.2 - 798.5	44.3'	3.42	5.97 1.75
	798.5 - 810.4	11.9'	Mixed	
	810.4 - 820.2	9.8'	3.83	6.96 1.52
	820.2 - 828.6	8.4'	Mixed	
	828.6 - 844.6	16.0'	4.35	7.87 1.89
	887.6 - 900.4	12.8'	Mixed	
	900.4 - 914.8	14.4'	5.31	10.36 2.82
	914.8 - 918.0	3.2'	Mixed	
	1125.1 - 1170.2	45.1'	4.27	7.23 2.16
	1170.2 - 1191.8	21.6'	Mixed	

Pb Zn Ag
 2.87 5.28 1.48

 90.4'


			Pb	Zn	Ag.
A-23	256.0 - 462.0	206.0	3.82	7.64	1.80
	462.0 - 578.0	116.0'	Mineralized		
	772.5 - 779.5	7.0'	4.80	6.48	1.76
	785.5 - 810.0	24.5'	Mineralized		
	862.0 - 876.0	14.0'	Mineralized		
	904.5 - 909.0	4.5'	Mineralized		
	913.5 - 920.0	7.0'	Mineralized.		

A-24	458.7 - 493.6	34.9	4.60	3.98	1.93
	581.5 - 585.3	3.8	Mineralized		
	585.3 585.3 - 669.7	84.4	3.99	6.46	1.73
	669.7 - 711.0	41.3	Mineralized		
	711.0 - 716.6	5.6	3.30	6.12	1.24
	716.6 - 748.0	31.4	Mineralized		
	748.0 - 758.0	10.0	2.90	5.60	2.08
	758.0 - 767.0	9.0	Mineralized		
	819.0 - 826.0	7.1	Mineralized.		
	826.1 - 831.6	5.5	4.65	8.88	2.82
	831.6 - 844.2	12.6	Mineralized.		
	1078.8 - 1127.4	48.6	6.11	10.60	2.82
	1127.4 - 1132.4	5.0	Mineralized.		

A-25 No INTERSECTIONS.

			Pb	Zn	Ag
A. 26	153.0 - 330.0	177.0'	4.45	8.64	2.18
	330.0 - 344.5	14.5'	Mineralized		
	344.5 - 348.5	4.0	7.05	8.04	2.85
	348.5 - 482.7	134.2	Mineralized (421.5 - 482.7 narrow)		
	595.5 - 601.4	5.9'	Mineralized		
	684.6 - 694.7	10.1'	3.39	4.65	1.78
A. 27	525.8 - 528.0	2.2	Mineralized		
	528.0 - 557.0	29.0 29.0	2.66	4.99	1.54
	557.0 - 646.0	89.0	Mineralized		
	646.0 - 658.3	12.8'	2.69	5.38	1.32
	658.3 - 681.0 706.0	47.7	Mineralized		
	706.0 - 739.0	33.0	4.74	5.39	2.10
	739.0 - 769.0	30.0	Mineralized		
	847.0 - 943.0		=		
	1068.5 - 1124.5		=		
	847.0 - 920.0	73.0'	Mineralized		
	920.0 - 925.0	5.0'	3.00	4.38	1.15
	925.0 - 943.3	18.3'	Mineralized		
	1068.5 - 1089.5	21.0'	Mineralized		
	1089.5 - 1109.5	20.0'	4.09	7.98	1.94
	1109.5 - 1124.5	15.0'	Mineralized		

EST GRADES GRUM.

A-27  1068.5 - 1090.0 Mixed
1090.0 - 1124.5 8% Cobind.

A-28 281.0 - 303.0 22.0' 10% Cobind.
383.0 - 387.0 4.0' Mixed.
702.0 - 705.0 3.0' Mixed.
705.0 - 727.0 22.0' 7% Cobind.
727.0 - 749.0 22.0' Mixed.
829.0 - 834.0 5.0' Mixed
849.0 - 854.0 5.0' Mixed.
(383-737 Massive Sulphide).

A-29 1209.0 - ~~1320~~ 1333.0 ^{124.0'} Mixed.
1333.0 - 1345.0 12.0' 9% Cobind.

A-30 474.0 - 529.0 55.0' 9% Cobind.
545.0 - 552.0 7.0' Mixed.
552.0 - 561.0 9.0' 11% Cobind.
561.0 - 582.0 21.0' Mixed.
582.0 - 599.0 17.0' 8% Cobind.
599.0 - 645.0 46.0' Mixed (near ore)
645.0 - 664.0 19.0' Mixed.
702.0 - 741.0 39.0' 14% Cobind

A-31 378.5-380.5 2.0' 12% Combined.
 404.5-408.0 3.5' Mineralized.
 438.3-446.3 8.0' Mineralized (near ore).
 553.2-571.0 17.8' 8% Combined.

A-32 513.0-521.5 8.5' 9% Combined.
 931.5-940.2 8.7' 8% Combined.
 940.2-980.5 40.3' Mineralized.
 980.5-993.0 12.5 9% Combined.
 993.0-1016.5 23.5 Mineralized
 1016.5-1076.5 60.0' 6% Combined.

A-33 — NO REPORT

A-34 — NO REPORT

A-35 ~~521.0-536.5~~ 15.5' ~~7-8% Combined.~~
 536.5-
 521.0-561.9 40.9' 7-8% Combined.