

REFRACTORY ORES METALLURGICAL COMPARISON

RECEIVED
SEP 12 1969
KERR ADDISON
MINES LTD.

019845

14

CONFIDENTIAL

	COMPANY	TEST	DATE	FLOAT	LEAD - %			ZINC - %			Pb + Zn%	Pb + Zn%
					Head	Con	Recovery	Head	Con.	Recovery	Assay	Recovery
ANVIL	Galigher	Lab.	Feb. 1967	<u>Differential</u>	3.4	70.1	89.0	5.9	54.0	86.0	124	175
B.M. & S. #12	B.M. & S.	<u>Mill</u>	1968		3.4	32.2	66.7	8.6	50.7	76.6	83	143
VANGORDA	Noranda	Lab.	1954		3.2	46.1	77.6	5.2	53.0	49.5	99	127
	Mitsui	Lab.	1969		4.0	49.8	77.0	4.9	49.4	60.4	99	137
	Galigher	Lab.	1968		3.9	56.5	72.5	5.1	50.8	51.5	107	124
		Lab	1969		4.1	48.2	73.8	4.8	55.4	42.7	104	116
SWIM LAKE	Galigher	Lab.	1968		4.1	47.1	61.4	5.1	54.0	39.9	101	101
	Mitsui	Lab.	1969		3.6	52.2	71.7	4.4	52.7	75.3	105	147
VANGORDA	Mitsui	Lab.	1956	<u>Bulk</u>	3.8	20.4	78.2	5.2	35.6	92.3	56	170
	Noranda	Lab.	1965		3.7	24.2	81.5	5.3	36.4	85.0	61	166
B.M. & S. #6	B.M. & S.	<u>Mill</u>	Feb. 1969		2.5	13.8	69.7	5.7	36.5	79.8	50	149