

**CURRAGH INC. GEOLOGY DEPARTMENT FARO DIVISION  
ESTIMATE OF MINING RESERVES - FARO AY TARGET ZONE**

SECTION	AREA (SQ FT)	PROJECTED S (FT)	PROJECTED N (FT)	TOTAL	VOLUME (BCY)	T/BCY	TONNES	HOLE ID	LENGTH	%Pb	%Zn	PB+ZN	%Pb	%Zn	PB+ZN
115+000	9604.31	35	70.25	105.25	37,439	2,889	108,161	92RD-01 92RD-02 92RD-03 74006 75007 77018	74 92 70 70 36 123	1.31 2.39 2.42 2.38 0.91 2.12	2.82 5.27 5.37 5.79 2.16 5.58	4.13 7.66 7.79 8.17 3.07 7.70	2.04	4.81	6.85
114+000	8270.23	70.25	70.25	140.5	43,036	2,889	124,331	92RD-04 92RD-05 92RD-06 92RD-07	115 11 137 35	3.64 1.8 3.08 2.13	7.73 3.16 7.17 4.96	11.37 4.96 10.25 7.09	3.14	6.98	10.12
113+000	6336.64	70.25	70.25	140.5	32,974	2,889	95,262	92RD-08 92RD-09	11 53	4.05 1.23	9.17 3.75	13.22 4.98	1.71	4.68	6.40
112+000	6652.9	70.25	70.25	140.5	34,620	2,889	100,016	66004	29	2.82	5.28	8.10	2.82	5.28	8.10
111+000	2350.24	70.25	70.25	140.5	12,230	2,889	35,332	92RD-13 92RD-14 92RD-15	90 72 100	3.41 1.9 2.43	7.51 3.76 4.14	10.92 5.66 6.57	2.62	5.19	7.81
110+000	2035.92	70.25	70.25	140.5	10,594	2,889	30,607	92RD-16 92RD-17	21 67	2.43 2.25	3.86 3.95	6.29 6.20	2.29	3.93	6.22
TOTAL UNDILUTED							493,709						2.47	5.40	7.87
TOTAL DILUTED							488,772						2.24	4.91	7.15

RESERVES ARE CLASSIFIED AS **PROBABLE** *PROVEN*  
 MINING RECOVERY ..... 90%  
 DILUTION..... 10%  
 G486 F:IFAROTARGIAY\_MRES.WK3  
 C.V.R.; M. WASEL OCT 28/92

*Faro  
Reserves  
AY Zone / Profit*

020002

**Curragh Inc.**

**AY Zone – DDH Assay Composites**

DDH assay								Composite			
Hole ID	From	To	Int Sample	SG	%Pb+Zn	%Pb	%Zn	Length	%Pb+Zn	%Pb	%Zn
74006	0.0	27.0	27.0	0	2.7	-1	-1				
	27.0	32.0	5.0	72154	3.68	10.65	3.56				
	32.0	37.0	5.0	72155	4.43	11.88	4.14				
	37.0	42.0	5.0	72156	4.58	12.71	6.98				
	42.0	47.0	5.0	72157	4.48	10.39	5.56				
	47.0	52.0	5.0	72158	4.70	5.44	2.55				
	52.0	57.0	5.0	72159	4.68	11.43	5.83				
	57.0	62.0	5.0	72160	4.64	14.98	7.81				
	62.0	67.0	5.0	72161	3.45	6.30	3.20				
	67.0	72.0	5.0	72162	2.76	0.22	-1.00				
	72.0	77.0	5.0	72163	2.72	-1.00	-1.00				
	77.0	82.0	5.0	72164	2.86	0.54	0.27				
	82.0	87.0	5.0	72165	3.55	7.60	2.27				
	87.0	92.0	5.0	72166	3.14	5.49	0.90				
	92.0	97.0	5.0	72167	2.80	1.14	0.53				
	97.0	102.0	5.0	72168	3.75	3.06	1.80				
	102.0	107.0	5.0	72169	4.20	12.15	3.37				
	107.0	112.0	5.0	72170	3.32	7.64	3.44				
	112.0	117.0	5.0	72171	4.06	8.50	2.71				
	117.0	122.0	5.0	72172	4.64	7.17	3.04				
	122.0	127.0	5.0	72173	4.66	8.08	3.67				
	127.0	132.0	5.0	72174	4.13	6.62	2.91				
	132.0	137.0	5.0	72175	4.67	1.34	0.62				
	137.0	142.0	5.0	72176	4.60	3.53	1.74				
	142.0	147.0	5.0	72177	4.76	12.17	5.31				
	147.0	152.0	5.0	72178	4.36	5.75	1.88				
	152.0	157.0	5.0	72179	4.15	4.33	1.30				
	157.0	162.0	5.0	72180	3.95	1.47	-1.00				
	162.0	167.0	5.0	72181	4.25	1.22	-1.00				
	167.0	172.0	5.0	72182	4.19	0.98	-1.00				
	172.0	177.0	5.0	72183	4.51	1.37	0.26				
	177.0	182.0	5.0	72184	4.34	0.67	0.17				
	182.0	187.0	5.0	72185	4.60	1.62	0.22				
	187.0	192.0	5.0	72186	4.27	9.56	3.15				
	192.0	197.0	5.0	72187	4.09	18.76	5.38				
	197.0	202.0	5.0	72188	4.07	22.83	7.53				
	202.0	207.0	5.0	72189	4.02	13.06	3.89				
	207.0	212.0	5.0	72190	3.83	14.41	3.70				
	212.0	217.0	5.0	72191	4.34	18.45	5.76				
	217.0	222.0	5.0	72192	4.47	14.80	4.92				
	222.0	227.0	5.0	72193	4.07	9.56	2.49				
	227.0	232.0	5.0	72194	4.11	8.54	1.66				
	232.0	237.0	5.0	72195	3.71	10.62	2.93				
	237.0	242.0	5.0	72196	3.27	9.16	1.50				
	242.0	247.0	5.0	72197	3.03	6.08	1.37				
	247.0	252.0	5.0	72198	3.19	5.18	1.34				
	252.0	257.0	5.0	72199	3.18	5.96	0.95				
	257.0	262.0	5.0	72200	3.12	1.28	0.23				
	262.0	267.0	5.0	72201	4.00	5.17	0.21				
	267.0	272.0	5.0	72202	4.91	4.00	1.01				
	272.0	277.0	5.0	72203	4.18	15.32	4.40				

**Curragh Inc.**

**AY Zone – DDH Assay Composites**

DDH assay									Composite			
Hole ID	From	To	Int	Sample	SG	%Pb+Zn	%Pb	%Zn	Length	%Pb+Zn	%Pb	%Zn
	277.0	282.0	5.0	72204	4.18	26.33	8.13	18.20				
	282.0	287.0	5.0	72205	4.66	24.03	7.73	16.30				
	287.0	292.0	5.0	72206	4.83	20.91	8.08	12.83				
	292.0	297.0	5.0	72207	4.50	23.96	8.96	15.00				
	297.0	302.0	5.0	72208	3.65	26.07	7.47	18.60				
	302.0	307.0	5.0	72209	4.42	13.61	5.06	8.55				
	307.0	312.0	5.0	72210	3.95	24.07	7.17	16.90				
	312.0	317.0	5.0	72211	4.07	21.93	6.33	15.60				
	317.0	322.0	5.0	72212	4.88	12.81	5.36	7.45				
	322.0	327.0	5.0	72213	4.76	8.69	3.03	5.66				
	327.0	332.0	5.0	72214	4.13	9.52	2.52	7.00				
	332.0	337.0	5.0	72215	3.21	2.70	0.82	1.88				
74006	337.0	342.0	5.0	72216	3.54	7.06	2.28	4.78	ay zone			
	342.0	347.0	5.0	72217	3.95	3.66	0.95	2.71				
	347.0	352.0	5.0	72218	4.73	6.35	2.40	3.95				
	352.0	357.0	5.0	72219	4.51	6.50	1.72	4.78				
	357.0	362.0	5.0	72220	4.34	4.87	1.15	3.72				
	362.0	367.0	5.0	72221	3.86	3.67	0.65	3.02				
	367.0	372.0	5.0	72222	3.83	6.73	2.35	4.38				
	372.0	377.0	5.0	72223	3.33	5.95	1.73	4.22				
	377.0	382.0	5.0	72224	4.03	16.28	4.53	11.75				
	382.0	387.0	5.0	72225	4.20	13.90	3.90	10.00				
	387.0	392.0	5.0	72226	3.53	12.13	2.31	9.82				
	392.0	397.0	5.0	72227	3.09	5.18	1.20	3.98				
	397.0	402.0	5.0	72228	3.52	12.12	3.33	8.79				
	402.0	407.0	5.0	72229	3.31	9.98	4.82	5.16	70	8.17	2.38	5.79
75007	0.0	49.0	49.0	0	2.70	-1.00	-1.00	-1.00				
	49.0	50.0	1.0	72842	3.56	0.25	0.20	0.05				
	50.0	55.0	5.0	72843	3.36	1.14	0.18	0.96				
	55.0	60.0	5.0	72844	3.58	2.96	0.76	2.20				
	60.0	65.0	5.0	72845	3.66	8.26	4.55	3.71				
	65.0	70.0	5.0	72846	4.03	6.85	2.23	4.62				
	70.0	75.0	5.0	72847	3.64	5.94	1.94	4.00				
	75.0	80.0	5.0	72848	3.73	4.12	1.12	3.00				
	80.0	85.0	5.0	72849	3.49	5.90	1.76	4.14				
	85.0	90.0	5.0	72850	3.51	6.16	1.78	4.38				
	90.0	95.0	5.0	72851	3.50	6.35	1.50	4.85				
	95.0	100.0	5.0	72852	3.41	1.74	0.25	1.49				
	100.0	105.0	5.0	72853	3.46	7.96	3.76	4.20				
	105.0	110.0	5.0	72854	3.22	5.85	1.12	4.73				
	110.0	115.0	5.0	72855	3.27	6.03	1.50	4.53				
	115.0	120.0	5.0	72856	3.44	1.71	0.23	1.48				
	120.0	125.0	5.0	72857	3.43	6.46	1.30	5.16				
	125.0	130.0	5.0	72858	3.36	8.46	1.88	6.58				
	130.0	135.0	5.0	72859	3.44	0.79	0.26	0.53				
	135.0	140.0	5.0	72860	3.37	5.93	1.88	4.05				
	140.0	145.0	5.0	72861	3.44	2.17	1.01	1.16				
	145.0	150.0	5.0	72862	3.53	1.63	0.72	0.91				
	150.0	155.0	5.0	72863	3.27	6.31	3.09	3.22				
	155.0	160.0	5.0	72864	3.39	1.51	0.33	1.18				
	160.0	165.0	5.0	72865	3.25	4.28	1.50	2.78				

**Curragh Inc.**

**AY Zone – DDH Assay Composites**

DDH assay									Composite			
Hole ID	From	To	Int Sample	SG	%Pb+Zn	%Pb	%Zn	Length	%Pb+Zn	%Pb	%Zn	
	165.0	170.0	5.0	72866	3.22	5.17	0.67	4.50				
	170.0	175.0	5.0	72867	3.31	2.35	0.42	1.93				
	175.0	180.0	5.0	72868	3.29	4.95	1.74	3.21				
	180.0	185.0	5.0	72869	3.12	6.35	1.87	4.48				
	185.0	190.0	5.0	72870	2.87	3.45	1.35	2.10				
	190.0	195.0	5.0	72871	4.02	18.62	6.02	12.60				
	195.0	200.0	5.0	72872	4.72	18.25	6.05	12.20				
	200.0	205.0	5.0	72873	4.76	8.29	1.91	6.38				
	205.0	210.0	5.0	72874	4.79	7.45	1.20	6.25				
	210.0	215.0	5.0	72875	4.85	10.84	3.53	7.31				
	215.0	220.0	5.0	72876	4.67	24.65	7.45	17.20				
	220.0	225.0	5.0	72877	3.22	5.94	0.67	5.27				
75007	225.0	230.0	5.0	72878	3.14	2.50	0.50	2.00	ay zone			
	230.0	235.0	5.0	72879	2.89	0.79	0.35	0.44				
	235.0	240.0	5.0	72880	2.84	1.58	0.76	0.82				
	240.0	245.0	5.0	72881	2.79	0.42	0.35	0.07				
	245.0	250.0	5.0	72882	2.99	2.72	0.45	2.27				
	250.0	255.0	5.0	72883	3.05	4.82	1.12	3.70				
	255.0	261.0	6.0	72884	3.18	7.70	2.52	5.18	36	3.07	0.91	2.16
77018	0.0	26.0	26.0	0	2.70	-1.00	-1.00	-1.00				
	26.0	31.0	5.0	74365	4.65	5.22	1.52	3.70				
	31.0	36.0	5.0	74366	4.18	1.93	0.14	1.79				
	36.0	40.0	4.0	74367	3.77	1.17	0.12	1.05				
	40.0	43.0	3.0	74368	3.95	1.64	0.61	1.03				
	43.0	47.0	4.0	74369	4.12	2.01	0.13	1.88				
	47.0	50.0	3.0	74370	3.59	8.63	1.50	7.13				
	50.0	53.5	3.5	74371	4.00	15.19	4.68	10.51				
	53.5	56.0	2.5	74372	3.76	5.37	1.27	4.10				
	56.0	59.0	3.0	74373	4.38	3.53	0.17	3.36				
	59.0	62.0	3.0	74374	4.25	2.44	0.29	2.15				
	62.0	66.0	4.0	74375	4.19	3.23	0.63	2.60				
	66.0	69.0	3.0	74376	4.17	4.54	0.86	3.68				
	69.0	70.5	1.5	74377	3.71	16.14	3.77	12.37				
	70.5	71.5	1.0	74378	3.14	4.55	1.25	3.30				
	71.5	76.5	5.0	74379	3.48	27.73	7.73	20.00				
	76.5	81.5	5.0	74380	3.88	1.04	0.54	0.50				
	81.5	86.5	5.0	74381	3.59	0.51	0.20	0.31				
	86.5	91.0	4.5	74382	3.71	15.11	5.22	9.89				
	91.0	96.0	5.0	74383	3.33	8.80	1.37	7.43				
	96.0	101.0	5.0	74384	3.41	14.09	3.98	10.11				
	101.0	106.0	5.0	74385	3.66	13.65	4.29	9.36				
	106.0	113.0	7.0	74386	3.43	9.01	1.76	7.25				
	113.0	118.0	5.0	74387	3.25	6.67	1.94	4.73				
	118.0	123.0	5.0	74388	3.20	1.53	0.50	1.03				
	123.0	128.0	5.0	74389	3.56	5.04	0.90	4.14				
	128.0	132.0	4.0	74390	4.73	8.83	2.08	6.75				
	132.0	137.0	5.0	74391	4.41	24.26	7.66	16.60				
	137.0	141.0	4.0	74392	4.24	32.17	9.37	22.80				
	141.0	145.0	4.0	74393	3.25	2.78	0.83	1.95				

**Curragh Inc.**

**AY Zone – DDH Assay Composites**

DDH assay									Composite			
Hole ID	From	To	Int	Sample	SG	%Pb+Zn	%Pb	%Zn	Length	%Pb+Zn	%Pb	%Zn
77018	145.0	149.0	4.0	74394	3.40	1.05	0.23	0.82	ay zone			
	149.0	153.0	4.0	74395	3.55	3.86	0.65	3.21				
	153.0	157.0	4.0	74396	3.36	9.65	2.76	6.89				
	157.0	161.0	4.0	74397	3.37	18.39	3.69	14.70				
	161.0	165.0	4.0	74398	3.25	11.43	2.43	9.00				
	165.0	169.0	4.0	74399	3.43	10.49	2.22	8.27				
	169.0	174.0	5.0	74400	4.54	4.98	1.38	3.60				
	174.0	179.0	5.0	74401	4.73	3.86	1.38	2.48				
	179.0	184.0	5.0	74402	3.11	13.46	2.85	10.61				
	184.0	187.0	3.0	74403	4.69	2.04	0.54	1.50				
	187.0	192.0	5.0	74404	3.37	13.28	3.37	9.91				
	192.0	195.0	3.0	74405	4.29	6.29	2.18	4.11				
	195.0	200.0	5.0	74406	4.49	5.22	1.72	3.50				
	200.0	205.0	5.0	74407	4.08	7.35	2.14	5.21				
	205.0	210.0	5.0	74408	4.27	10.01	3.26	6.75				
	210.0	214.0	4.0	74409	3.73	11.72	2.49	9.23				
	214.0	219.0	5.0	74410	3.47	11.44	2.67	8.77				
	219.0	224.0	5.0	74411	3.26	7.75	2.90	4.85				
	224.0	229.0	5.0	74412	3.22	2.72	0.32	2.40				
	229.0	234.0	5.0	74413	3.19	6.00	0.62	5.38				
	234.0	239.0	5.0	74414	3.32	13.53	3.02	10.51				
	239.0	243.0	4.0	74415	3.44	13.16	3.71	9.45				
	243.0	247.0	4.0	74416	3.51	15.61	4.13	11.48				
	247.0	252.0	5.0	74417	4.87	3.72	1.34	2.38				
	252.0	257.0	5.0	74418	3.28	4.64	0.88	3.76				
	257.0	262.0	5.0	74419	3.34	2.98	0.34	2.64				
	262.0	267.0	5.0	74420	3.39	6.44	3.11	3.33				
	267.0	272.0	5.0	74421	3.33	7.93	2.16	5.77				
	272.0	277.0	5.0	74422	3.48	7.61	0.92	6.69				
	277.0	282.0	5.0	74423	3.53	6.05	1.24	4.81				
	282.0	287.0	5.0	74424	3.68	4.26	1.28	2.98				
	287.0	292.0	5.0	74425	4.28	8.51	4.77	3.74				
	292.0	297.0	5.0	74426	3.47	5.23	1.90	3.33	123	7.70	2.12	5.58
66004	0.0	243.0	243.0	0	2.70	-1.00	-1.00	-1.00				
	243.0	248.0	5.0	70262	2.70	0.02	0.01	0.01				
	248.0	253.0	5.0	70263	2.70	2.41	0.01	2.40				
	253.0	258.0	5.0	70264	2.70	6.70	2.10	4.60				
	258.0	306.0	48.0	0	2.70	-1.00	-1.00	-1.00				
	306.0	311.0	5.0	70267	2.70	10.20	3.20	7.00				
	311.0	316.0	5.0	70268	2.70	7.10	2.60	4.50				
	316.0	321.0	5.0	70269	2.70	2.60	0.60	2.00				
	321.0	326.0	5.0	70270	2.70	6.60	2.30	4.30				
	326.0	331.0	5.0	70271	4.29	3.80	1.50	2.30				
	331.0	336.0	5.0	70272	2.70	7.20	2.10	5.10				
	336.0	341.0	5.0	70273	2.70	3.10	0.50	2.60				
	341.0	346.0	5.0	70274	2.70	5.70	0.70	5.00				
	346.0	351.0	5.0	70275	2.70	8.20	2.90	5.30				
	351.0	356.0	5.0	70276	2.70	6.20	2.70	3.50				
	356.0	361.0	5.0	70277	2.70	11.90	4.60	7.30				
	361.0	366.0	5.0	70278	2.70	13.30	5.20	8.10				
	366.0	371.0	5.0	70279	2.70	4.40	1.90	2.50				

**Curragh Inc.**

**AY Zone – DDH Assay Composites**

DDH assay								Composite			
Hole ID	From	To	Int Sample	SG	%Pb+Zn	%Pb	%Zn	Length	%Pb+Zn	%Pb	%Zn
	371.0	376.0	5.0 70280	2.70	2.30	0.20	2.10				
	376.0	381.0	5.0 70281	2.70	2.11	0.01	2.10				
	381.0	386.0	5.0 70282	2.70	2.31	0.01	2.30				
	386.0	391.0	5.0 70283	2.70	2.41	0.01	2.40				
	391.0	396.0	5.0 70284	2.70	2.30	1.60	0.70				
	396.0	401.0	5.0 70285	2.70	5.80	2.50	3.30				
	401.0	406.0	5.0 70286	2.70	3.40	1.40	2.00				
	406.0	411.0	5.0 70287	2.70	5.90	1.40	4.50				
	411.0	416.0	5.0 70288	2.70	6.50	2.40	4.10				
	416.0	421.0	5.0 70289	2.70	4.41	0.01	4.40				
	421.0	426.0	5.0 70290	2.70	2.70	0.20	2.50				
	426.0	431.0	5.0 70291	2.70	2.60	0.40	2.20				
	431.0	436.0	5.0 70292	2.70	6.50	2.40	4.10				
	436.0	441.0	5.0 70293	2.70	19.60	6.50	13.10				
	441.0	446.0	5.0 70294	2.70	30.10	11.30	18.80				
	446.0	451.0	5.0 70295	2.70	30.20	10.00	20.20				
	451.0	456.0	5.0 70296	2.70	16.90	6.10	10.80				
	456.0	461.0	5.0 70297	2.70	15.30	5.20	10.10				
	461.0	466.0	5.0 70298	2.70	5.40	1.80	3.60				
	466.0	471.0	5.0 70299	2.70	10.50	3.70	6.80				
	471.0	476.0	5.0 70300	2.70	11.90	4.00	7.90				
	476.0	481.0	5.0 70301	2.70	11.90	4.70	7.20				
	481.0	486.0	5.0 70302	2.70	8.20	3.40	4.80				
	486.0	491.0	5.0 70303	2.70	10.20	3.70	6.50				
	491.0	496.0	5.0 70304	2.70	12.60	4.40	8.20				
	496.0	501.0	5.0 70305	2.70	10.40	3.80	6.60				
	501.0	506.0	5.0 70306	2.70	8.30	3.30	5.00				
	506.0	511.0	5.0 70307	2.70	7.50	2.90	4.60				
	511.0	516.0	5.0 70308	2.70	8.30	2.20	6.10				
66004	516.0	521.0	5.0 70309	2.70	7.50	2.10	5.40	ay zone			
	521.0	526.0	5.0 70310	2.70	8.70	3.50	5.20				
	526.0	531.0	5.0 70311	2.70	11.50	3.90	7.60				
	531.0	536.0	5.0 70312	2.70	14.80	5.30	9.50				
	536.0	539.0	3.0 70313	2.70	6.10	2.60	3.50				
	539.0	545.0	6.0 70314	2.70	0.71	0.01	0.70	29	8.11	2.82	5.28
	545.0	700.0	155.0 0	2.70	-1.00	-1.00	-1.00				

**CURRAGH INC. FARO OPERATIONS**  
**1992 ROTARY DRILLHOLE LOGS - AY ZONE**

HOLE ID	LENGTH	DIP	AZIMUTH	MINE GRID			MODEL GRID			FROM	TO	RFT	ROCK UNIT	SAMPLE #	GPA	GSI	FR-200	GPI
				EAST	NORTH	ELEVATION	EAST	NORTH										
SQRD-01	53	0	25	14377.113	9795.465	3642.530	22243.35	39981.81										
SQRD-01									11	23	12	2F	71510	1.98	3.93	5.82	30.3	
SQRD-01									23	35	12	2EF	71511	1.76	3.86	6.82	29.8	
SQRD-01									35	42	7	2EF	71512	1.33	3.10	4.43	23.7	
SQRD-01									42	52	10	1D4				0.00		
SQRD-01									52	59	7	2EF	71513	0.70	1.99	2.39	20.1	
SQRD-01									59	64	5	2A47	71514	1.47	3.10	4.57	20.0	
SQRD-01									64	74	10	2A47	71515	1.52	3.79	5.41	30.0	
SQRD-01									74	83	9	2L						
Thrd size Int.									0	74	74			1.31	2.82	4.13	26.9	
SQRD-02	107	-2	61	14393.341	9792.332	3643.819	22262.61	39967.92										
SQRD-02									0	11	11	2F	72516	3.00	6.73	6.73	43.6	
SQRD-02									11	23	12	2F	72517	2.50	6.29	7.79	42.1	
SQRD-02									23	35	12	2F	72518	2.82	5.29	7.91	40.8	
SQRD-02									35	47	12	2DF	72519	2.10	4.00	6.10	27.0	
SQRD-02									47	59	12	2D	71520	2.00	4.52	6.32	31.3	
SQRD-02									59	71	12	2D4	71521	3.10	5.64	11.74	25.0	
SQRD-02									71	83	12	2A4	71522	2.30	5.39	7.99	23.4	
SQRD-02									83	92	9	2E4	71523	1.26	2.91	4.16	19.6	
SQRD-02									92	107	15	2L						
Thrd size Int.									0	92	92			2.38	6.27	7.65	30.7	
SQRD-03	53	-44	40	14399.559	9790.424	3642.242	22255.95	39982.17										
SQRD-03									0	11	11	2E4	71524	2.23	4.02	6.25	41.1	
SQRD-03									11	23	12	2F4	71525	3.40	6.74	12.14	23.6	
SQRD-03									23	35	12	2F4	71526	2.17	5.57	7.74	21.0	
SQRD-03									35	40	5	2A+-4	71527	1.50	3.95	5.43	18.4	
SQRD-03									40	47	7	2L/2D4	71528	2.20	3.67	5.87	17.9	
SQRD-03									47	59	12	2D4	71529	2.69	5.24	7.93	17.9	
SQRD-03									59	70	11	2A3+-4	71531	2.05	4.71	6.78	17.0	
SQRD-03									70	73	3	1D0						
SQRD-03									73	83	10	2L						
Thrd size Int.									0	70	70			2.42	6.37	7.79	22.7	
SQRD-04	119	0	33	14262.635	9788.999	3622.234	22150.55	39964.84										
SQRD-04									0	11	11	2F44	71532	6.75	16.40	23.16	21.7	
SQRD-04									11	23	12	2F4	71533	4.95	12.00	16.95	27.7	
SQRD-04									23	35	12	2E44	71534	4.30	9.42	13.72	36.5	
SQRD-04									35	47	12	2E4	71535	3.18	6.92	8.90	37.0	
SQRD-04									47	59	12	2E4	71536	3.04	4.95	7.90	40.8	
SQRD-04									59	71	12	2E4	71537	3.15	5.82	9.37	43.3	
SQRD-04									71	83	12	2E4	71538	1.75	3.89	5.44	31.1	
SQRD-04									83	95	12	2E4	71539	4.10	9.32	13.42	30.7	
SQRD-04									95	107	12	2D45	71540	3.20	6.65	9.95	26.9	
SQRD-04									107	115	5	2A+-4/100	71541	1.65	2.57	4.22	17.4	
SQRD-04									115	119	4	2L						
Thrd size Int.									0	115	115			3.84	7.73	11.37	31.9	
SQRD-05	23	-47	45	14256.501	9781.457	3617.708	22146.18	39966.99										
SQRD-05									0	11	11	2A0	71542	1.80	3.16	4.96	7.8	
SQRD-05									11	23	12	2L						
Thrd size Int.									0	11	11			1.80	3.16	4.96	7.5	
SQRD-06	143	-1	55	14146.341	9612.559	3620.950	22092.28	39056.99										
SQRD-06									0	11	11	2E4+-5	71543	2.48	7.33	9.81	29.6	
SQRD-06									11	23	12	2D+-5	71544	3.45	10.40	13.85	27.2	
SQRD-06									23	35	12	2D+-5	71545	2.35	5.53	7.98	27.4	
SQRD-06									35	47	12	2E4+-5	71546	2.80	6.46	9.25	36.9	
SQRD-06									47	59	12	2E4+-5	71547	3.13	8.24	11.37	30.7	
SQRD-06									59	71	12	2E48	71548	2.53	5.57	9.10	32.5	
SQRD-06									71	83	12	2E48	71549	4.80	10.80	15.10	32.8	
SQRD-06									83	95	12	2E48	233451	3.40	6.42	9.52	40.6	
SQRD-06									95	107	12	2E48	233452	3.10	5.49	8.59	40.7	
SQRD-06									107	119	12	2EF	233453	3.50	7.82	11.12	40.4	
SQRD-06									119	131	12	2E48	233454	3.15	6.31	9.46	34.0	
SQRD-06									131	137	6	2A4	233455	1.69	3.15	4.83	28.0	
SQRD-06									137	143	8	1D0						
Thrd size Int.									0	137	137			3.08	7.17	10.24	33.5	
SQRD-07	47	-36	54	14140.882	9613.315	3617.918	22088.93	39061.27										
SQRD-07									0	11	11	2E4	233456	2.90	6.57	9.47	36.8	
SQRD-07									11	23	12	2A+-4	233457	3.15	7.48	10.63	26.1	
SQRD-07									23	30	7	2A0	233458	0.80	1.12	1.72	13.4	
SQRD-07									30	35	5	2A0	233459	0.35	0.53	0.88	9.3	
SQRD-07									35	47	12	2L						
Thrd size Int.									0	35	35			2.13	4.96	7.09	24.8	
SQRD-08	11			14057.695	9569.402	3616.130	22076.84	39152.69										
SQRD-08									0	11	11	2A4	233460	4.05	9.17	13.22	14.5	
SQRD-08									11	23	12	2A+-4	233461	0.35	0.53	1.18	20.2	
SQRD-08									23	25	2	2A+-4	233462	0.80	2.65	3.45	19.4	
SQRD-08									25	36	11	2A+-4	233463	3.00	6.51	12.81	14.3	
SQRD-08									36	47	11	2A0	233464	2.36	7.09	9.44	10.0	
SQRD-08									47	53	5	10Q/2D	233465					
SQRD-08									53	59	5	1D0						
Thrd size Int.									0	53	53			1.22	3.75	4.98	13.3	
SQRD-13	119	0	65	13931.951	10157.469	3738.282	22194.55	39452.35										
SQRD-13									0	11	11	2E+-4	10401	3.95	6.48	10.34	36.1	
SQRD-13									11	23	12	2E+-4	10402	4.23	6.95	11.19	37.7	
SQRD-13																		