

CURRAGH RESOURCES CORPORATION

020139

Sample Assay Sheet

Production Date:

Nov 7, 1987

Sample Origin:

Drill Cores

					HCl sol Fe ₂			
Sample Number	Pb	Zn	Fe	Ag	Cu			
1 11014	8.74	7.32	25.9	110	15.3			
2 11014	3.44	3.48	36.6	50	8.14			
3 11025	0.67	1.19	22.0	15	12.4			
4 11026	2.71	2.89	38.6	37	8.20			
5 11027	6.50	7.33	17.9	75	2.81			
6 11028	4.58	7.02	11.7	60	2.73			
7 11029	5.98	6.60	32.4	56	3.83			
8 11030	0.30	0.46	39.4	10	5.78			
9								
10								
11								
12								
13								
14								
15								
16								
17								
18								
19								
20								
21								
22								
23								
24								
25								
26								
27								
28								
29								
30								
31								
32								

Law Johnston

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date: Nov 7/87

Sample Origin: Drill Core

					HC	SO ₄ FE			
Sample Number	Pb	Zn	Fe	Ag	CR				
1 11015	0.72	0.73	42.2	17	7.52				
2 11016	5.04	6.68	18.8	75	5.45				
3 11017	5.09	6.64	15.7	62	4.65				
4 11018	5.62	5.43	19.2	62	5.11				
5 11019	4.49	6.42	38.2	31	0.32				
6 11020	4.98	7.39	14.6	72	2.01				
7 11021	3.38	4.02	26.0	60	0.84				
8 11022	3.31	8.22	19.9	46	3.56				
9									
10									
11									
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date:


Nov 8, 1987

Sample Origin:

Drill Cores

Sample Number	Pb	Zn	Fe	Ag	Cu HCl sol Fe			
1 11008	2.43	3.90	12.9	39	1.51			
2 11009	5.43	7.13	29.0	93	2.60			
3 11010	5.93	6.58	15.5	81	1.50			
4 11011	0.93	1.26	18.9	17	6.28			
5 11012	0.11	0.16	5.83	4	2.92			
6 11013	0.16	0.12	18.5	12	0.54			
7 11023	9.43	9.85	27.2	103	6.21			
8								
9								
10								
11								
12								
13								
14								
15								
16								
17								
18								
19								
20								
21								
22								
23								
24								
25								
26								
27								
28								
29								
30								
31								
32								

Assayer:



CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date: November 9/87

Sample Origin: drill core

Sample Number	Pb	Zn	Fe	Ag	HCl sol Fe				
1 11001	0.14	0.14	17.6	10	1.61				
2 11002	1.02	0.28	21.6	28	0.69				
3 11003	0.68	0.36	19.8	22	0.93				
4 11004	0.52	0.16	19.4	16	0.50				
5 11005	0.37	0.40	16.4	10	1.40				
6 11006	0.33	0.51	17.5	10	3.42				
7 11007	0.70	1.98	19.9	12	2.65				
8									
9									
10 11031	1.58	0.19	35.1	18	7.83				
11 11032	0.26	0.14	29.6	4	2.05				
12 11033	2.07	1.87	30.9	14	9.18				
13 11034	1.88	2.13	29.9	18	2.00				
14 11035	7.53	1.84	33.6	83	11.7				
15 11036	0.16	0.13	28.4	6	2.23				
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date: Nov 21, 1987

Sample Origin: Drill Cores

Sample Number	Pb	Zn	Fe	Ag	Cu	Hg	Sol Fe		
1 11037	0.77	0.19	33.2	22	2.10				
2 11038	0.19	0.16	24.3	10	2.42				
3 11039	0.20	0.29	20.9	10	3.35				
4 11040	0.36	0.71	18.8	10	1.41				
5 11041	0.34	1.55	19.3	12	3.76				
6 11042	1.43	0.27	8.42	18	6.94				
7 11043	0.26	0.34	26.5	12	2.53				
8 11044	0.19	0.44	26.8	12	1.55				
9 11046	0.13	0.17	22.7	10	1.36				
10 11048	0.25	0.53	31.5	20	2.92				
11									
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									


CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date: NOV. 30/87

Sample Origin: DRILL CORE

	Sample Number	Pb	Zn	Fe	Ag	Cu	HCl soluble Fe			
1	11248	7.75	8.50	33.7	79		1.52			
2	11249	8.47	10.0	30.9	109		1.54			
3	11254	1.86	3.13	16.2	28		1.29			
4	11266	3.93	3.45	33.5	59		9.95			
5	11271	4.36	5.61	25.5	53		6.05			
6	11275	2.19	1.43	32.7	24		3.26			
7	11276	.38	1.23	19.6	14		3.47			
8	11279	5.53	4.99	10.4	49		3.02			
9	11283	.28	.14	32.8	12		3.48			
10	11287	.17	.24	25.8	16		3.10			
11	11289	.89	.07	27.1	14		1.86			
12										
13										
14										
15										
16										
17										
18										
19										
20										
21										
22										
23										
24										
25										
26										
27										
28										
29										
30										
31										
32										

Assayer: 

CURRAGH RESOURCES

Sample Assay Sheet


Production Date:

Dec 9 / 87.

Sample Origin:

Drill Core

Sample Number	Pb	Zn	Fe	Ag	Sn HCl sol Fe			
1	9658	0.32	0.45	10.6	8	3.42		
2	11045	0.20	0.13	26.3	10	1.60		
3	11047	0.10	0.13	29.1	10	2.75		
4	11049	0.18	0.23	34.2	14	4.26		
5	11050	0.20	0.61	26.7	12	2.90		
6	11051	3.24	3.74	30.0	52	8.28		
7	11052	0.40	0.50	38.9	22	1.75		
8	11053	0.50	1.02	26.6	25	4.26		
9	11054	4.56	6.90	10.7	84	1.92		
10	11055	8.53	8.81	27.4	128	1.78		
11	11056	1.36	1.68	13.1	27	2.63		
12								
13								
14								
15								
16								
17								
18								
19								
20								
21								
22								
23								
24								
25								
26								
27								
28								
29								
30								
31								
32								




CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Dec 9, 187

Sample Origin: Drill Core

	Sample Number	Pb	Zn	Fe	Ag	Cu HCl sol Fe			
1	11057	5.07	3.20	36.5	73	2.06			
2	11058	7.16	7.46	25.6	117	2.23			
3	11059	4.58	6.12	28.6	65	14.9			
4	11060	4.99	8.32	17.3	77	2.70			
5	11061	4.94	6.58	14.7	63	3.69			
6	11062	1.29	1.38	40.8	12	2.38			
7	11063	4.92	8.20	19.0	85	2.28			
8	11064	5.79	7.91	19.3	79	2.59			
9	11065	2.69	3.71	40.8	36	10.2			
10	11066	3.69	2.92	39.9	51	9.30			
11	11067	2.71	2.65	41.1	44	12.8			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: 

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

dec 11/87

Sample Origin:

Drill core

					HCl sol	Fe			
Sample Number	Pb	Zn	Fe	Ag	20				
1 11068	2.07	2.07	36.5	34	9.74				
2 11069	0.70	1.29	27.8	40	9.58				
3 11070	2.62	2.86	37.9	44	5.20				
4 11071	5.60	4.88	38.3	59	6.70				
5 11072	4.53	6.81	10.7	65	2.72				
6 11073	3.34	3.67	33.9	34	6.17				
7 11074	0.39	0.68	36.5	8	2.58				
8 11075	8.00	4.28	25.2	51	3.52				
9 11076	4.76	2.79	28.8	45	16.1				
10 11077	3.87	1.54	37.2	53	13.8				
11 11078	0.44	0.31	29.7	20	2.24				
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Catherine

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date: dec 11/87

Sample Origin: drill core

					HCl sol Fe				
	Sample Number	Pb	Zn	Fe	Ag				
1	11093	0.60	0.83	28.3	30	4.37			
2	11094	3.48	5.43	35.7	73	0.94			
3	11095	0.79	0.45	27.8	18	9.49			
4	11096	1.44	1.38	27.5	26	8.32			
5	11097	4.68	3.46	29.0	53	7.45			
6	11099	0.68	0.63	8.58	8	3.30			
7	11101	1.36	0.63	13.2	22	3.98			
8	11110	7.25	10.1	25.3	111	1.94			
9	11112	2.46	4.73	10.2	40	0.17			
10	11114	0.05	0.67	5.40	2	4.16			
11	11115	0.06	0.19	3.53	2	2.35			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Catherine

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Dec 12/87

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	Gr H ₂ SO ₄ Fe				
1	11079	0.10	0.10	24.5	9	1.73			
2	11080	0.15	0.17	35.0	14	2.09			
3	11081	0.10	0.10	21.4	6	1.68			
4	11082	0.25	0.28	20.0	20	1.21			
5	11083	0.20	0.57	14.6	16	1.77			
6	11084	0.15	0.30	9.94	9	1.73			
7	11085	0.13	0.56	30.3	4	4.92			
8	11086	0.14	0.35	6.79	12	2.93			
9	11087	0.75	1.49	29.5	16	6.64			
10	11088	0.60	1.18	23.6	10	6.18			
11	11091	0.04	0.18	5.41	2	3.54			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet


Production Date:

Dec 15/87

Sample Origin:

Drill Cores

	Sample Number	Pb	Zn	Fe	Ag	Cu HCl sol/Fe			
1	11090	0.46	1.16	25.1	12	4.97			
2	11098	1.34	0.98	12.9	19	3.37			
3	11104	4.53	4.92	34.0	54	8.33			
4	11106	0.11	0.28	17.3	8	3.65			
5	11107	0.30	0.44	20.7	12	2.70			
6	11108	4.30	2.77	19.1	74	5.62			
7	11116	0.08	0.21	5.12	2	2.90			
8	11117	1.59	2.66	14.3	21	4.72			
9	11118	2.63	7.24	13.4	43	3.67			
10	11120	1.17	1.65	13.4	15	5.26			
11	11121	0.91	0.79	10.7	12	2.88			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: 

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Dec 15/87

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	H₂O SO ₄ FE				
1 11124	0.40	0.55	21.0	10	3.16				
2 11125	0.16	0.18	16.5	8	4.63				
3 11127	0.16	0.20	17.5	6	3.86				
4 11128	0.09	0.08	12.5	8	3.15				
5 11129	0.18	0.15	19.3	10	2.03				
6 11130	0.43	0.52	16.7	10	2.86				
7 11132	0.07	0.43	17.8	8	2.80				
8 11134	0.29	0.27	5.77	4	2.14				
9 11137	0.24	0.47	7.10	4	2.78				
10 11138	3.81	4.41	31.6	58	1.50				
11 11140	0.07	0.12	14.2	4	2.46				
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Dec 17/87

Sample Origin: drill core

Sample Number	Pb	Zn	Fe	Ag	HCl sol or Fe			
1 11142	0.11	0.23	32.1	10	1.60			
2 11144	0.33	0.49	37.0	20	3.28			
3 11145	0.75	0.64	37.0	26	8.31			
4 11148	7.76	3.66	11.5	46	1.53			
5 11149	0.63	0.42	24.8	14	2.48			
6 11150	0.76	0.70	36.8	24	4.57			
7 11152	1.44	1.38	35.2	28	4.41			
8 11154	3.18	6.72	9.60	42	1.73			
9 11155	5.36	7.25	14.6	113	4.69			
10 11156	0.54	3.72	16.0	10	13.4			
11 11157	2.41	3.56	34.4	40	11.9			
12								
13								
14								
15								
16								
17								
18								
19								
20								
21								
22								
23								
24								
25								
26								
27								
28								
29								
30								
31								
32								

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date:

Dec 28, 187.

Sample Origin:

Drill Core

	Sample Number	Pb	Zn	Fe	Ag	Cu				
1	11214	0.11	0.56	6.86	2					
2	11215	1.10	2.48	7.73	22					
3	11216	0.16	0.42	2.74	8					
4	11217	0.08	0.57	7.22	2					
5	11218	0.03	0.42	6.86	2					
6	11219	0.16	0.39	3.16	4					
7	11220	3.98	3.60	18.2	40					
8	11221	0.40	1.12	4.72	6					
9	11222	4.67	6.52	20.7	80					
10	11223	0.54	0.99	15.5	14					
11	11224	5.10	7.00	17.1	202					
12										
13										
14										
15										
16										
17										
18										
19										
20										
21										
22										
23										
24										
25										
26										
27										
28										
29										
30										
31										
32										

Assayer:

[Handwritten Signature]

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date: Dec. 28/87

Sample Origin: Drill Core

	HCl	Sol Fe							
Sample Number	Fe	Fe	Fe	Ag	Cu				
1	11214	5.96							
2	11215	6.46							
3	11216	3.16							
4	11217	4.00							
5	11218	5.30							
6	11219	2.08							
7	11220	2.48							
8	11221	2.65							
9	11222	3.31							
10	11223	4.18							
11	11224	2.04							
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: [Signature]

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date: Dec 29/87

Sample Origin: Drill Core

	Sample Number	Pb	Zn	Fe	Ag	Cr H ₂ SO ₄ / Fe				
1	11225	5.80	5.79	24.2	77	2.45				
2	11226	4.47	3.85	29.9	91	3.22				
3	11227	2.48	3.10	30.1	52	3.50				
4	11228	3.52	4.79	34.0	46	7.73				
5	11229	5.22	4.36	30.5	67	12.1				
6	11230	5.14	4.19	30.3	69	12.2				
7	11231	3.94	3.16	31.8	50	6.19				
8	11232	7.91	11.8	15.5	117	3.05				
9	11233	1.58	2.48	9.88	24	2.73				
10	11234	4.94	8.54	19.5	81	1.61				
11	11235	4.77	8.90	18.0	77	2.87				
12										
13										
14										
15										
16										
17										
18										
19										
20										
21										
22										
23										
24										
25										
26										
27										
28										
29										
30										
31										
32										

Assayer: Marge Lewis

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date: Dec. 29/87

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	HCl Sol Fe			
1 11236	6.51	9.68	13.1	99	2.71			
2 11237	12.6	10.4	28.5	140	13.2			
3 11238	15.1	10.2	30.1	142	14.7			
4 11239	8.02	10.1	13.8	91	2.97			
5 11240	2.10	3.73	24.8	40	4.12			
6 11241	1.28	1.19	27.2	30	6.10			
7 11242	1.20	.98	39.7	26	3.86			
8 11243	.11	.28	42.1	14	1.46			
9 11244	.32	.51	34.0	18	4.54			
10 11245	.44	.58	35.2	16	7.31			
11 11246	5.18	6.72	7.69	97	0.72			
12 11247	6.45	10.0	32.6	75	0.48			
13 11250	6.24	7.26	15.9	101	0.57			
14 11251	8.91	10.9	31.2	138	0.51			
15 11252	10.5	11.9	30.4	85	0.68			
16 11253	8.04	9.94	31.2	117	1.02			
17 11255	1.45	2.26	13.4	22	1.32			
18 11256	5.28	6.81	34.9	75	0.79			
19 11257	5.56	8.14	33.8	73	1.31			
20 11258	4.90	6.77	34.3	71	6.13			
21								
22								
23								
24								
25								
26								
27								
28								
29								
30								
31								
32								

11-2021-79

18 19 20

16-1

Assayer: Pb, Zn, Tot Fe

Silver & HCl Sol Fe - Kathy

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date: Dec 24/87

Sample Origin: Drill Core

					Sol	HCl	Fe.		
Sample Number	Pb	Zn	Fe	Ag	Ag				
1	11203	8.12	7.36	19.9	49	0.93			
2	04	5.01	3.08	28.8	87	4.95			
3	05	1.43	1.61	9.99	18	6.93			
4	06	0.50	1.00	10.3	14	9.10			
5	07	3.09	3.32	36.0	45	4.92			
6	08	0.09	0.47	5.55	/	4.74			
7	09	/	0.15	4.74	/	4.35			
8	11210	0.17	0.84	8.58	46	0.70			
9	11	3.93	6.26	25.2	48	2.81			
10	12	4.11	11.6	17.8	67	2.48			
11	13	1.65	3.30	12.4	20	5.46			
12									
13		1							
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date: Dec 18, 1987

Sample Origin: Drill Core

	Sample Number	Pb	Zn	Fe	Ag	Cu HCl sol Fe			
1	11162	7.07	7.63	21.1	93	13.2			
2	11165	6.84	7.92	18.8	77	10.9			
3	11166	1.06	1.10	24.5	18	10.1			
4	11176	0.67	0.85	21.9	10	7.10			
5	11179	1.20	1.21	17.2	18	6.56			
6	11180	0.31	0.33	6.84	4	6.45			
7	11181	0.58	0.34	12.2	6	6.15			
8	11182	0.10	0.25	11.9	4	5.23			
9	11183	0.18	0.08	9.88	4	19.8			
10	11201	0.46	0.33	21.3	198	1.22			
11	11202	12.3	7.02	26.9	175	4.03			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

* Per the Pb & Hg
* same result

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:


Dec 18, 187

Sample Origin:

Drill Core

	Sample Number	Pb	Zn	Fe	Ag	Ga #C/30/Fe			
1	11102	1.27	1.49	24.3	20	5.77			
2	11113	4.26	6.76	13.0	65	6.30			
3	11123	5.74	7.52	24.5	71	1.46			
4	11126	0.09	0.13	16.3	6	3.38			
5	11131	5.10	5.54	20.6	68	2.02			
6	11133	0.12	0.14	14.9	4	3.53			
7	11134	0.84	1.01	17.3	12	3.87			
8	11153	5.87	8.28	12.7	101	1.80			
9	11158	2.79	3.37	29.5	34	9.39			
10	11159	6.89	7.44	16.3	99	5.85			
11	11161	5.94	5.32	39.2	83	34.0			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer:



CURRAGH RESOURCES CORPORATION

Sample Assay Sheet

Production Date: Jan 5/88

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	Hg ^{Cu} SOL FE				
1	11171	1.38	3.04	28.2	16	12.4			
2	11259	3.37	5.06	13.8	42	4.79			
3	11260	1.92	4.08	9.53	28	6.17			
4	11261	0.65	1.45	5.50	12	3.59			
5	11262	3.54	5.22	26.6	61	3.86			
6	11263	4.66	8.93	10.5	79	1.89			
7	11264	1.32	1.27	10.0	20	8.13			
8	11265	7.46	8.74	20.3	89	9.19			
9	11267	5.87	8.81	16.3	89	3.69			
10	11268	5.12	6.63	14.5	77	5.09			
11	11269	1.42	0.51	3.13	16	0.33			
12	11270	4.08	5.06	18.5	38	0.56			
13	11272	7.64	10.2	12.3	75	1.16			
14	11273	3.25	2.88	37.6	45	7.26			
15	11277	0.55	0.27	19.8	10	0.68			
16	11278	6.91	5.73	10.2	69	2.59			
17	11280	1.53	0.39	29.1	20	1.92			
18	11281	3.41	2.11	31.4	42	3.06			
19	11282	3.92	4.58	19.6	47	8.19			
20	11284	0.25	0.26	21.3	18	1.66			
21	11285	0.13	0.15	28.4	14	3.39			
22	11286	0.16	0.13	23.8	14	2.67			
23	11288	0.17	0.24	25.5	12	3.41			
24	11290	0.73	0.48	32.3	16	3.62			
25	11291	0.19	0.31	19.0	10	3.43			
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:


Jan 26, 188

Sample Origin:

Drill Core

Sample Number	Pb	Zn	Fe	Ag	HCl sol Fe				
1 11297	0.44	0.44	34.6	30	3.52				
2 11298	0.78	0.59	27.7	34	4.99				
3 11299	1.12	1.41	29.7	37	5.61				
4 11139	0.28	0.43	11.4	6	2.68				
5 11146	2.35	2.22	38.4	50	10.8				
6 11167	1.02	0.71	28.4	14	12.7				
7 11170	0.43	0.83	31.1	10	14.2				
8 11177	3.23	5.02	23.4	34	13.7				
9 11292	0.28	0.40	19.7	12	2.04				
10 11293	0.28	0.38	22.9	14	1.73				
11 11294	0.17	0.32	23.2	12	1.62				
12 11295	0.18	0.25	24.2	14	2.45				
13 11296	0.17	0.17	28.4	26	1.87				
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer:



CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Jan 27, 1988

Sample Origin: Drill Core

	Sample Number	Pb	Zn	Fe	Ag	HCl sol Fe				
1	11325	0.03	0.20	6.15	4	5.56				
2	11326	7.70	7.36	18.4	105	9.51				
3	11327	3.96	4.01	16.8	53	12.4				
4	11328	3.71	2.69	33.7	55	25.9				
5	11329	1.01	0.84	37.6	24	9.64				
6	11330	0.33	0.51	36.9	14	6.50				
7	11331	2.36	2.00	27.1	32	11.6				
8	11332	1.50	1.68	29.1	22	13.6				
9	11333	2.31	1.53	34.0	28	19.6				
10	11334	1.73	1.00	31.1	28	21.0				
11	11335	1.51	0.99	31.4	22	28.0				
12	11337	0.50	0.53	27.4	22	18.9				
13	11338	0.26	0.45	22.2	8	12.0				
14	11339	0.74	0.62	29.0	14	15.7				
15	11340	1.96	1.97	30.2	26	18.1				
16	11341	1.35	3.03	34.3	20	15.0				
17	11342	0.24	0.42	30.9	10	11.6				
18	11343	0.55	0.96	30.4	10	8.33				
19	11344	0.40	0.45	25.4	10	7.53				
20	11345	4.03	0.78	23.0	38	7.59				
21	11346	3.87	0.85	18.7	36	6.31				
22	11347	1.16	1.60	32.5	12	17.5				
23										
24										
25										
26										
27										
28										
29										
30										
31										
32										

V

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

Jan 27 / 88

Sample Origin:

Drill Core

Sample Number	Pb	Zn	Fe	Ag	HCl ₂ /Fe	
1	11300	2.07	4.40	14.5	32	4.48
2	11303	1.94	1.61	36.7	34	7.74
3	11305	5.10	7.44	11.4	77	1.89
4	11306	5.96	8.12	16.2	93	1.13
5	11307	3.57	5.71	25.4	60	2.54
6	11308	4.33	4.90	29.8	71	5.47
7	11309	5.42	7.56	18.9	77	2.94
8	11310	1.84	3.58	6.77	22	2.82
9	11311	1.28	2.46	5.94	18	3.88
10	11312	0.03	0.17	4.60	2	3.41
11	11313	2.07	3.53	6.26	34	4.88
12	11314	1.82	2.76	4.25	28	3.36
13	11315	0.08	0.52	7.89	4	7.26
14	11316	1.49	2.91	6.69	28	4.33
15	11317	0.04	0.16	4.45	2	3.20
16	11318	0.04	0.16	3.64	2	3.29
17	11319	2.70	2.53	4.37	32	2.26
18	11320	1.62	3.17	7.01	26	2.98
19	11321	0.03	0.11	7.61	2	3.20
20	11322	4.14	7.30	16.1	67	1.08
21	11323	1.42	3.20	27.2	32	0.91
22	11324	4.77	7.91	13.4	83	2.83
23						
24						
25						
26						
27						
28						
29						
30						
31						
32						

Assayer:

Lawford



CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

Feb 14, 1988

Sample Origin:

Drill Core

	Sample Number	Pb	Zn	Fe	Ag	HCl sol Fe				
1	11163	7.03	7.92	18.8	85	9.11				
2	11301	0.72	0.84	43.3	17	16.8				
3	11302	1.74	1.21	42.1	19	12.3				
4	11304	3.30	2.63	35.6	42	10.8				
5	11336	0.56	0.83	31.0	11	25.6				
6	11348	0.72	1.08	28.3	9	17.0				
7	11349	3.25	2.95	27.3	30	15.8				
8	11350	0.48	0.16	17.6	6	4.62				
9	11351	0.84	0.81	24.6	13	10.4				
10	11352	0.59	0.69	25.3	9	9.44				
11	11353	0.55	0.23	16.8	9	3.58				
12	11354	0.25	0.39	9.66	6	4.09				
13	11355	0.19	0.30	8.88	6	4.00				
14	11356	0.01	0.06	10.1	2	4.70				
15	11357	0.89	0.92	30.6	14	19.9				
16	11358	5.89	7.20	14.1	93	5.48				
17	11359	13.8	11.8	24.7	152	20.0				
18	11360	4.35	7.19	14.4	67	7.77				
19	11361	5.39	7.96	13.9	89	2.63				
20	11362	1.35	2.83	37.0	34	0.75				
21	11363	2.13	5.12	29.2	53	0.69				
22	11364	2.55	5.56	7.13	38	1.23				
23	11365	1.88	3.81	31.9	34	2.48				
24	11366	3.50	6.10	8.24	49	1.20				
25	11367	2.45	5.07	15.4	42	1.24				
26	11368	0.67	2.08	39.5	21	0.88				
27	11379	3.58	5.89	14.1	64	4.12				
28	11370	4.26	7.94	10.7	66	2.98				
29	11371	5.81	7.18	14.6	97	3.78				
30	11372	5.57	7.73	11.8	91	4.51				
31	11373	7.78	7.80	15.0	114	6.78				
32	11374	6.16	8.78	19.4	85	1.18				

Assayer:



CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

Feb 14 / 88

Sample Origin:

Drill Core

Sample Number	Pb	Zn	Fe	Ag	HCl sol Fe				
1 11089	0.76	2.02	26.4	14	10.0				
2 11092	0.68	0.86	26.5	31	2.48				
3 11100	2.42	2.39	15.5	27	3.44				
4 11103	3.87	4.57	22.2	46	7.92				
5 11105	4.30	3.94	31.4	50	8.60				
6 11109	6.54	9.69	33.0	99	3.70				
7 11111	3.68	7.24	9.96	62	0.81				
8 11122	2.86	3.85	29.9	35	2.61				
9 11135	3.53	6.72	19.3	46	2.76				
10 11141	0.13	0.13	9.43	4	2.22				
11 11143	0.18	0.80	10.1	4	1.30				
12 11147	1.61	2.69	28.4	35	3.26				
13 11151	0.47	0.35	30.1	19	2.78				
14 11160	0.45	1.65	10.4	10	9.20				
15 11164	10.3	10.9	20.1	114	12.0				
16 11168	0.93	1.12	23.7	19	16.6				
17 11169	0.27	0.70	30.5	12	16.8				
18 11172	0.16	0.50	23.2	8	6.48				
19 11173	0.58	0.46	21.9	12	5.65				
20 11174	0.56	0.36	21.7	12	7.45				
21 11175	0.32	0.43	25.0	10	10.5				
22 11178	0.24	0.24	18.0	10	3.03				
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Kau Johnston

①
✓

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

Feb 15, 88

Sample Origin:

Drill Core

Sample Number	Pb	Zn	Fe	Ag	HCl Sol. Fe
1 11375	5.13	10.4	21.5	70	17.3
2 11376	3.05	5.41	29.7	38	26.0
3 11377	5.50	1.85	23.8	85	12.4
4 11378	0.81	0.77	32.8	15	16.6
5 11379	0.62	1.69	31.7	13	14.2
6 11380	1.40	1.48	27.6	23	12.5
7 11381	0.41	0.87	34.0	13	11.0
8 11382	0.17	0.41	31.7	9	5.26
9 11383	0.14	0.33	26.9	9	3.57
10 11384	0.47	0.50	28.3	13	3.91
11 11385	0.37	0.46	27.1	11	4.20
12 11386	0.13	0.65	6.39	4	4.63
13 11387	5.21	7.79	18.8	76	4.33
14 11388	5.74	7.18	18.8	83	6.50
15 11389	3.59	7.05	12.9	56	3.92
16 11390	0.62	0.99	5.36	10	3.38
17 11391	0.17	0.74	6.38	2	4.49
18 11392	0.21	0.59	11.1	4	6.88
19 11393	0.03	0.40	6.59	0	4.76
20 11394	0.04	0.32	3.27	0	2.29
21 11395	0.11	1.03	10.7	2	2.78
22 11396	2.40	3.48	32.0	48	7.26
23 11397	4.82	1.81	36.2	75	5.22
24 11398	0.11	0.53	32.0	17	2.27
25 11399	0.19	0.77	30.2	15	2.17
26 11400	3.13	4.57	31.1	40	5.67
27 11401	0.10	0.53	8.44	2	4.84
28 11402	0.04	0.23	5.60	2	4.02
29 11403	6.14	7.53	12.8	78	2.88
30 11404	8.92	5.43	20.2	107	6.69
31 11405	6.69	4.54	18.4	96	6.52
32 11406	4.27	2.95	25.3	50	6.51
33 11407	9.40	6.30	14.2	153	0.60

11-2021-79

Assayer:



CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Feb 15 188

Sample Origin: Drill Core

	Sample Number	Pb	Zn	Fe	Ag	HCl Sol Fe				
1	11408	5.67	24.8	31.8	63	0.67				
2	11409	5.29	5.38	17.0	46	5.37				
3	11410	1.59	4.09	13.8	64	9.85				
4	11411	4.89	6.88	14.5	47	3.84				
5	11412	3.07	5.01	22.0	30	1.88				
6	11413	3.76	7.65	26.3	38	1.85				
7	11414	0.31	0.31	42.8	11	0.33				
8	11415	1.78	2.98	29.6	23	2.71				
9	11416	7.72	8.95	13.8	64	4.58				
10	11417	1.22	1.06	35.7	28	4.64				
11	11418	1.00	1.97	27.9	28	5.33				
12	11419	0.60	1.39	27.0	28	5.94				
13	11420	1.60	1.71	30.0	36	4.96				
14	11421	0.40	0.38	30.7	25	3.66				
15	11422	0.33	0.24	25.5	13	1.53				
16	11423	0.19	0.10	24.7	11	1.53				
17	11424	0.25	0.17	22.0	11	2.22				
18	11425	0.35	0.47	22.4	17	3.14				
19	11426	1.32	3.26	23.9	17	10.9				
20	11427	1.49	4.42	24.5	19	4.88				
21	11428	0.43	1.49	27.2	9	23.3				
22	11429	0.09	0.18	5.68	0	5.16				
23										
24										
25										
26										
27										
28										
29										
30										
31										
32										

Assayer:

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Feb 16, 188

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	HCl sol Fe
1 11452	10.0	10.7	18.1	156	4.03
2 11453	5.72	5.78	23.5	89	11.8
3 11454	2.83	2.67	36.8	46	29.4
4 11455	4.87	6.86	16.0	78	21.6
5 11456	1.20	1.75	34.6	26	8.04
6 11457	3.14	3.33	29.4	46	7.39
7 11458	0.67	0.91	41.2	15	12.3
8 11459	1.64	1.82	37.8	30	10.6
9 11460	0.13	0.34	20.4	4	8.25
10 11461	0.52	1.04	31.1	11	10.7
11 11462	0.17	0.57	30.6	11	7.31
12 11463	0.23	0.53	26.2	9	7.98
13 11464	0.24	0.59	27.2	9	9.73
14 11465	0.32	0.42	31.3	9	6.66
15 11466	0.18	0.19	32.4	9	8.25
16 11467	0.29	0.62	35.8	9	11.4
17 11468	0.65	1.67	31.5	15	13.7
18 11469	5.62	11.6	32.0	45	24.2
19 11470	0.62	0.63	26.7	9	13.6
20 11471	0.38	0.80	31.3	8	12.3
21 11472	0.49	1.28	31.5	9	11.2
22 11473	0.43	1.02	29.3	8	12.2
23 11474	0.40	0.66	26.1	8	9.20
24 11475	1.21	1.15	24.1	14	12.3
25 11476	0.42	0.28	21.2	6	6.52
26 11477	0.51	0.52	19.9	10	5.66
27 11478	1.36	0.73	15.2	10	8.81
28 11479	0.93	0.73	12.8	10	6.20
29 11480	0.13	0.27	9.94	4	3.74
30 11481	3.07	5.26	27.7	46	22.3
31 11482	2.65	2.73	29.9	33	11.3
32 11483	2.90	1.60	26.3	43	11.9
11484	1.97	2.39	27.2	29	11.2

CURRAGH RESOURCES

Sample Assay Sheet


Production Date:

Feb 17, 188

Sample Origin:

Drill Core

	Sample Number	Pb	Zn	Fe	Ag	HCl Sol Fe				
1	30169	5.38	4.85	28.7	72	13.7				
2	30170	5.34	3.69	33.6	80	14.3				
3	30171	7.52	9.43	14.4	116	2.13				
4	30172	4.19	4.62	18.7	56	3.64				
5	30173	4.86	7.35	27.2	62	4.15				
6	30174	4.98	7.92	25.3	66	7.60				
7	30175	2.49	1.38	36.6	25	3.33				
8	30176	3.37	1.29	34.5	27	3.23				
9	30177	1.68	1.51	33.9	14	3.78				
10	30178	1.84	1.81	33.5	17	3.85				
11	No Tag	0.02	0.05	3.68	0.00	3.20				
12	30179	4.46	6.92	21.1	69	2.09				
13	30180	9.40	6.56	20.0	73	3.38				
14	30181	3.66	4.96	28.7	41	2.22				
15	30182	5.23	8.93	17.3	54	3.22				
16	30183	2.24	3.72	34.5	26	4.32				
17	30184	4.30	5.25	29.7	45	2.34				
18	30185	4.62	6.15	27.1	41	2.29				
19	30186	4.86	6.84	26.1	54	2.31				
20	30187	4.65	8.35	18.0	67	2.45				
21	30188	3.12	5.91	17.2	41	7.00				
22	30189	3.53	5.99	30.2	59	4.11				
23										
24										
25										
26										
27										
28										
29										
30										
31										
32										



CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

Feb. 17/88

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	HCl Sol	Fe
1 11430	0.06	0.11	5.50	2	4.65	
2 11431	0.02	0.08	5.56	2	4.58	
3 11432	0.08	0.28	12.4	6	3.36	
4 11433	0.31	1.06	6.32	6	3.95	
5 11434	0.87	0.79	11.9	15	5.39	
6 11435	5.17	7.68	17.6	83	1.50	
7 11436	4.88	8.84	15.3	83	0.88	
8 11437	5.33	7.10	21.6	87	2.08	
9 11438	4.55	6.07	26.9	66	5.30	
10 11439	4.93	7.25	17.1	81	4.24	
11 11440	1.87	2.66	12.8	29	1.70	
12 11441	2.58	4.49	32.9	64	1.02	
13 11442	3.76	7.53	31.9	84	1.14	
14 11443	2.56	4.80	13.9	42	1.24	
15 11444	0.59	1.51	36.2	17	1.32	
16 11445	4.95	8.75	9.85	76	4.12	
17 11446	5.73	8.04	13.7	93	5.49	
18 11447	6.18	7.11	11.1	103	3.64	
19 11448	2.06	2.44	8.60	32	5.72	
20 11449	7.15	8.03	15.1	104	7.39	
21 11450	0.26	0.59	6.76	7	6.46	
22 11451	9.62	3.08	34.6	95	3.06	
23						
24						
25						
26						
27						
28						
29						
30						
31						
32						

[Handwritten Signature]

CURRAGH RESOURCES

Sample Assay Sheet


Production Date:

Feb 17 / 88

Sample Origin:

Drill Core

Sample Number	Pb	Zn	Fe	Ag	HCl Sol Fe
1 11485	.82	1.14	29.3	15	8.63
2 11487	.31	.96	26.5	21	4.21
3 11488	.87	1.73	27.4	27	5.22
4 11489	.26	2.11	31.4	15	7.58
5 11490	6.42	5.60	12.5	99	3.58
6 11491	5.79	8.94	15.6	87	1.13
7 11492	1.10	1.35	4.77	13	2.63
8 11493	4.62	5.30	27.4	57	5.73
9 11494	.38	1.42	10.2	9	5.26
10 11495	.90	1.33	9.54	15	2.93
11 11496	2.12	3.60	9.03	28	3.45
12 11497	3.66	5.59	19.1	69	2.28
13 11498	7.04	8.86	21.4	88	4.23
14 11499	7.32	9.01	17.6	92	3.17
15 11400	7.11	7.49	27.9	71	8.80
16 30073	1.22	2.84	7.33	21	1.35
17 30151	4.98	5.70	29.8	59	9.08
18 30152	1.76	2.10	33.5	34	4.72
19 30153	1.14	1.82	31.0	25	6.53
20 30155	.29	.53	23.2	8	9.33
21 30156	.62	.96	25.0	10	8.32
22 30157	.70	.94	22.6	11	8.67
23 30158	5.18	8.46	23.4	85	2.98
24 30159	0.18	0.24	14.0	4	4.43
25 30160	0.07	0.25	14.4	4	6.57
26 30161	0.19	0.14	13.4	4	12.4
27 30162	0.07	0.13	6.54	2	4.96
28 30163	1.32	0.45	16.0	19	5.80
29 30164	0.10	0.17	6.20	4	5.44
30 30165	0.13	0.42	7.14	2	6.24
31 30166	0.32	0.35	9.45	8	8.66
32 30167	3.79	3.15	10.6	38	2.83
30168	8.34	4.98	33.0	84	5.61



CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Feb 18, 1988

Sample Origin: Drill Core

	Sample Number	Pb	Zn	Fe	Ag	HKTS Fe
1	30190	3.52	5.59	12.4	56	4.86
2	30191	5.94	7.84	22.1	79	2.86
3	30192	5.43	8.92	21.5	81	2.60
4	30193	8.36	8.47	21.6	110	3.57
5	30194	5.48	7.66	21.2	85	2.81
6	30195	6.38	8.19	24.8	97	6.86
7	30196	9.19	9.91	24.5	102	4.46
8	30197	6.92	8.20	20.3	71	3.25
9	30198	6.61	9.52	22.3	89	2.45
10	30199	3.76	2.63	36.8	52	7.31
11	30200	3.82	2.84	38.9	58	4.07
12	30201	0.48	0.35	2.21	9	0.96
13	30202	0.16	0.36	7.26	4	2.72
14	30203	0.06	1.78	12.8	2	10.6
15	30204	0.25	0.46	6.57	4	2.74
16	30205	0.62	1.52	4.61	9	2.37
17	30206	2.55	1.68	6.55	30	3.56
18	30207	3.06	5.73	5.99	46	1.85
19	30208	1.11	1.42	12.2	21	10.8
20	30209	1.60	2.98	16.4	27	12.4
21	30210	1.76	1.34	37.7	23	19.8
22	30211	1.94	1.67	9.16	28	6.98
23	30212	9.07	7.86	32.4	105	28.6
24	30213	4.17	4.99	18.5	63	7.33
25	30214	2.77	2.83	32.1	44	7.45
26	30215	5.34	6.23	15.9	81	1.98
27	30216	3.38	7.61	15.0	43	0.87
28	30217	10.9	23.2	49.5	44	0.23
29	30218	5.13	5.46	24.1	77	8.26
30	30219	6.17	5.33	32.0	75	16.9
31	30220	6.13	6.55	21.7	81	8.11
32	30221	6.12	8.48	17.2	99	20.56
33	30222	5.66	6.99	13.8	85	4.65

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

Feb 18, 1988

Sample Origin:

Drill Core

Sample Number	Pb	Zn	Fe	Ag	HCl Sol Fe	
1	30223	4.44	7.34	11.5	67	2.68
2	30224	0.45	0.85	8.33	10	1.44
3	30225	3.83	7.67	12.8	63	1.97
4	30226	6.78	11.2	13.0	115	1.04
5	30227	2.79	4.94	9.72	53	3.78
6	30228	4.58	7.56	12.6	85	2.14
7	30229	3.20	5.58	10.2	59	1.50
8	30230	3.80	8.70	11.7	67	3.00
9	30231	2.60	1.08	41.6	45	8.27
10	30232	5.03	2.56	36.8	83	10.4
11	30233	6.24	7.21	13.5	95	4.73
12	30234	5.47	8.08	13.0	85	2.34
13	30235	5.44	5.88	24.6	56	16.3
14	30236	7.78	7.76	26.3	76	16.1
15	30237	3.00	3.02	31.7	29	16.6
16	30238	1.57	2.09	26.4	21	8.66
17	30239	0.94	1.04	23.0	19	10.2
18	30240	1.96	1.18	40.4	19	31.8
19	30241	0.57	0.56	32.7	17	22.3
20	30242	0.74	0.39	43.3	12	25.0
21	30243	0.89	1.08	6.49	16	4.14
22	30244	0.16	0.43	7.76	6	6.84
23						
24						
25						
26						
27						
28						
29						
30						
31						
32						

Assayer:

[Signature]

21

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

Feb 19, 188

Sample Origin:

Drill Core

	Sample Number	Pb	Zn	Fe	Ag	HCl Sol Fe				
1	30245	1.36	0.94	29.4	17	18.5				
2	30246	0.49	0.84	26.2	12	17.4				
3	30247	0.29	0.36	29.1	8	15.7				
4	30248	0.40	0.60	35.7	12	20.4				
5	30249	0.27	0.43	34.0	8	18.9				
6	30250	1.40	1.14	27.6	17	10.1				
7	30251	0.78	0.40	3.11	29	2.06				
8	30252	3.35	5.07	12.3	60	4.64				
9	30253	1.01	1.16	6.60	16	2.48				
10	30254	2.74	6.27	0.65	46	1.06				
11	30255	0.26	0.34	9.04	10	0.67				
12	30256	0.38	0.65	13.6	14	1.45				
13	30257	0.14	0.34	12.5	10	0.70				
14	30258	0.20	0.30	13.0	10	0.80				
15	30259	0.19	0.61	14.7	12	0.91				
16	30260	0.43	1.27	12.0	10	0.85				
17	30262	0.14	0.36	6.72	4	1.05				
18	30263	0.45	0.29	30.6	22	2.11				
19	30264	0.51	0.57	7.55	12	1.37				
20	30265	3.08	4.31	16.2	56	3.08				
21	30266	1.15	1.46	4.72	17	1.46				
22	30267	0.40	1.08	5.09	8	0.98				
23										
24										
25										
26										
27										
28										
29										
30										
31										
32										

Lau Johnson

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

Feb. 23/88

Sample Origin:

Mill Core

Sample Number	Pb	Zn	Fe	Ag	HCl Sol. Fe				
1 30200	3.81	2.76	35.1	57	8.69				
2 30278	5.39	8.31	29.6	81	1.55				
3 30279	0.01	0.27	4.45	2	3.66				
4 30280	0.98	1.67	8.34	14	4.71				
5 30281	7.78	10.2	32.5	107	30.7				
6 30282	0.70	0.90	5.39	12	41.6				
7 30283	4.91	8.97	11.3	87	5.50				
8 30284	0.84	1.14	8.44	14	7.13				
9 30285	1.97	0.84	9.03	38	7.74				
10 30286	8.78	6.94	32.2	87	31.0				
11 30287	6.44	8.00	21.5	109	13.8				
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer:

[Handwritten Signature]



CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Feb 26/88

Sample Origin: Drill core

	Sample Number	Pb	Zn	Fe	Ag	Cu	total sol Fe		
1	30268	0.24	0.54	5.95	7		0.65		
2	30269	0.70	0.91	6.16	15		0.99		
3	30270 A	5.01	4.56	24.8	56		1.38		
4	30270	1.16	1.32	6.18	17		1.37		
5	30271	1.04	1.56	8.50	15		2.21		
6	30273	0.10	0.24	8.49	6		1.26		
7	30273	0.12	0.66	11.9	6		1.47		
8	30274	0.85	1.25	6.62	19		1.88		
9	30275	2.21	4.72	3.37	29		1.85		
10	30276	2.24	4.29	3.86	35		1.35		
11	30277	1.98	5.04	4.17	27		1.38		
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Jam

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Feb 28/88

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	GR SILTE				
1 30288	1.27	1.51	2.30	26	3.35				
2 30289	6.21	8.00	24.3	32	1.89				
3 30291	5.60	6.01	19.7	91	9.38				
4 30292	5.10	6.05	19.4	67	2.11				
5 30293	2.98	2.97	30.7	40	16.9				
6 30294	1.11	1.62	30.6	24	5.46				
7 30295	2.71	5.40	20.7	34	5.62				
8 30296	0.44	0.91	26.8	10	14.2				
9 30297	0.18	0.27	10.4	6	6.80				
10 30298	0.16	0.20	9.47	6	10.5				
11 30299	2.77	4.88	4.51	38	0.84				
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: March 1, 1988

Sample Origin: Drill Core

Sample Number	Pb _{ppm}	Zn _{ppm}	Fe _{ppm}	Ag _{ppm}	Cu	HCl Sol Fe
1 30323	5.04	6.63	19.7	76		1.16
2 30324	1.76	2.45	38.7	25		9.23
3 30325	2.00	2.63	18.3	25		3.74
4 30326	3.42	5.67	20.5	58		1.96
5 30327	9.78	8.88	15.4	149		2.10
6 30328	1.94	1.22	37.1	29		11.37
7 30329	5.27	6.45	18.6	74		8.46
8 30330	3.97	6.70	13.0	62		2.58
9 30331	5.22	7.03	14.5	85		2.69
10 30332	6.29	6.02	14.0	112		1.06
11 30333	3.07	3.37	11.8	41		3.41
12						
13						
14						
15						
16						
17						
18						
19						
20						
21						
22						
23						
24						
25						
26						
27						
28						
29						
30						
31						
32						

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

March 1/88

Sample Origin:

Drill cone

Sample Number	Pb	Zn	Fe	Ag	Cu	H ₂ O Sol Fe			
1 30311	2.27	4.42	5.18	27		1.58			
2 30312	4.78	10.2	12.0	56		3.21			
3 30313	3.70	5.29	12.5	45		7.86			
4 30314	0.90	1.04	7.08	12		4.42			
5 30315	1.43	1.30	14.5	21		9.78			
6 30316	4.39	4.94	25.4	48		9.57			
7 30317	3.29	3.79	23.4	41		2.67			
8 30319	7.82	8.28	12.4	91		1.59			
9 30320	4.02	6.89	12.3	44		0.99			
10 30321	3.14	5.92	24.2	31		0.56			
11 30322	4.14	7.40	20.6	43		0.80			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Jem



CURRAGH RESOURCES

Sample Assay Sheet

Production Date: March 1/88

Sample Origin: Drill core

Sample Number	Pb	Zn	Fe	Ag	Cu	Hd Sol Fe			
1 30300	0.80	1.43	13.5	18		0.53			
2 30301	0.45	0.63	13.2	9		0.52			
3 30302	0.43	0.50	12.7	9		0.33			
4 30303	0.36	0.22	7.84	4		0.44			
5 30304	0.80	1.45	5.76	11		1.18			
6 30305	0.96	0.99	5.40	13		0.59			
7 30306	4.60	5.12	31.1	56		23.1			
8 30307	0.29	2.22	8.71	2		7.12			
9 30308	0.57	1.45	6.48	6		3.15			
10 30309	1.50	2.87	4.54	18		2.43			
11 30300	1.81	1.93	5.97	22		3.07			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: J. J. J.

✓ CURRAGH RESOURCES

Sample Assay Sheet

Production Date: March 1/88

Sample Origin: Drill Core

	Sample Number	Pb	Zn	Fe	Ag	Cu	H ₂ O Sol Fe			
1	30036	2.60	4.56	3.87	41		1.44			
2	30037	1.58	3.45	3.47	25		1.28			
3	30038	0.08	4.90	7.61	2		6.98			
4	30039	2.62	5.60	3.28	43		1.83			
5	30041	2.93	6.23	6.96	44		2.59			
6	30042	7.86	18.1	24.5	145		3.08			
7	30044	0.04	3.67	6.98	2		6.18			
8	30045	1.90	5.35	3.33	31		2.33			
9	30046	0.19	1.42	8.14	4		3.02			
10	30049	3.12	7.76	33.0	77		6.40			
11	30050	3.87	7.81	11.6	66		2.13			
12										
13										
14										
15										
16										
17										
18										
19										
20										
21										
22										
23										
24										
25										
26										
27										
28										
29										
30										
31										
32										

Assayer: Jani

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: MAR 5/88

Sample Origin: ~~DRILL~~ DRILL CORE

	%	%	%	g/TON					
Sample Number	Pb	Zn	Fe	Ag	Cu				
1	30005	0.09	0.17	6.35	0				
2	30018	1.55	4.52	9.45	22				
3	30020	2.74	6.35	8.95	40				
4	30024	3.29	3.35	6.12	49				
5	30035	2.98	5.52	6.96	49				
6	30058	2.48	5.11	8.95	40				
7	30061	1.92	3.81	11.0	35				
8	30065	1.93	4.70	10.2	31				
9	30066	2.38	4.98	9.30	35				
10	30562	3.48	6.30	5.48	49				
11	30819	6.85	7.79	6.64	107				
12	30826	3.05	4.46	5.56	44				
13	30907	0.96	1.61	7.73	18				
14	30919	1.88	5.97	5.17	27				
15	30920	2.94	5.60	7.15	44				
16	30922	2.35	4.74	7.06	35				
17	30928	2.87	5.14	7.24	40				
18	30930	4.98	9.37	10.1	80				
19	30931	2.78	4.58	8.28	40				
20	30932	2.42	5.43	6.70	35				
21	30938	2.22	4.14	5.03	36				
22	30939	1.84	4.26	7.10	27				
23	30942	0.86	1.12	5.24	13				
24	30944	2.13	4.87	1.36	31				
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Mary Lewis

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: ~~March~~ April 1, 1988

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	Cu	HCl			
						Sol. Fe			
1	30614	3.04	1.66	3.52	30	0.59			
2	30615	2.20	4.67	3.64	32	0.86			
3	30616	1.37	2.99	4.34	22	1.47			
4	30617	1.21	2.77	2.91	20	1.16			
5	30618	2.30	5.63	2.56	42	1.13			
6	30619	2.61	4.99	3.07	46	0.80			
7	30620	1.87	3.19	3.83	34	0.83			
8	30621	2.54	4.30	7.24	40	0.54			
9	30622	0.15	0.89	4.31	4	2.51			
10	30623	1.40	3.73	0.13	24	4.17			
11	30624A [±]	5.22	5.69	3.21	73	5.91			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

April 1, 1988

Sample Origin:

Drill Core

Sample Number	Pb	Zn	Fe	Ag	Cu	HCl Sol Fe			
1 30625	1.07	2.42	28.8	28		1.08			
2 30625	2.60	5.36	10.0	42		5.57			
3 30626	0.07	0.44	5.44	2		3.92			
4 30627	0.04	0.19	4.30	2		2.43			
5 30628	0.05	0.15	4.46	2		3.70			
6 30629	0.62	0.92	10.3	10		6.08			
7 30630	0.17	0.55	8.02	4		5.55			
8 30631	0.35	0.86	9.62	6		4.65			
9 30632	4.38	2.95	34.9	67		9.69			
10 30633	5.62	3.90	24.5	77		7.11			
11 30634	5.50	7.11	22.2	69		9.88			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Michelle Bergeron

✓

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: April 1, 1988

Sample Origin: Drill Core

	Sample Number	Pb	Zn	Fe	Ag	Cu	HCl			
1	30635	0.73	1.07	62.9	13		501 Fe 0.90			
2	30636	2.19	1.86	42.5	131		15.3			
3	30637	3.19	4.26	20.0	48		5.13			
4	30638	4.20	5.98	23.5	62		4.27			
5	30639	5.58	7.20	11.8	81		1.71			
6	30640	1.05	2.07	36.5	15		4.39			
7	30641	1.34	0.81	29.5	15		1.78			
8	30642	3.41	5.69	20.0	54		1.50			
9	30643	5.34	6.45	35.3	69		2.04			
10	30644	3.53	7.09	23.1	46		1.87			
11	30645	4.30	7.63	20.8	71		1.88			
12										
13										
14										
15										
16										
17										
18										
19										
20										
21										
22										
23										
24										
25										
26										
27										
28										
29										
30										
31										
32										

✓

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: _____

Sample Origin: DRILL CORE

	%	%	%	g/TON		HCl sol. Fe			
Sample Number	Pb	Zn	Fe	Ag	Cu				
1	30646	3.23	6.33	21.0	55	1.98			
2	30647	4.87	6.81	18.8	65	1.86			
3	30648	0.94	0.60	20.4	22	1.27			
4	30649	1.41	0.44	17.2	24	1.54			
5	30650	0.55	0.22	21.9	12	1.29			
6	30651	1.18	0.76	22.1	14	1.21			
7	30652	1.46	1.00	20.1	20	1.55			
8	30653	0.41	0.60	32.1	12	2.91			
9	30654	0.17	0.28	29.2	12	2.30			
10	30655	0.39	0.50	26.2	14	1.81			
11	30656	0.20	0.12	26.9	8	6.03			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Chris Hamelara

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: April 3, 1988

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	Cu	HCl SA Fe
1 30657	0.41	0.21	23.1	0.09		3.60
2 30658	1.38	1.94	26.7	0.06		7.02
3 30659	0.26	0.53	24.3	0.10		2.59
4 30660	0.27	1.19	21.1	0.10		2.47
5 30661	0.45	0.93	23.0	0.02		2.84
6 30662	0.93	0.34	4.73	0.16		4.12
7 30663	2.92	2.96	20.0	0.07		4.62
8 30664	0.93	0.57	25.1	0.07		5.76
9 30665	0.39	0.75	21.4	0.05		5.86
10 30834	4.13	4.90	18.3	0.26		13.3
11 30683	3.53	1.52	44.5	0.20		24.4
12						
13						
14						
15						
16						
17						
18						
19						
20						
21						
22						
23						
24						
25						
26						
27						
28						
29						
30						
31						
32						

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: April 4, 1988

Sample Origin: Drill core

Sample Number	Pb	Zn	Fe	Ag	Cu	\$/Cl			
1 30695	0.41	0.89	25.2	8	✓	12.3			
2 30696	0.72	0.61	25.6	10		8.72			
3 30697	0.75	0.70	25.9	12		8.09			
4 30698	2.17	1.37	18.1	24		6.45			
5 30699	1.50	2.22	17.0	20		14.4			
6 30700	0.30	0.61	11.0	6		9.20			
7 30951	5.00	7.24	7.71	73		1.62			
8 30952	0.61	0.27	39.4	16		1.71			
9 30953	4.89	8.90	14.5	56		2.93			
10 30954	11.5	11.0	13.3	107		2.70			
11 30955	5.16	6.42	34.2	52		7.93			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: April 4/88

Sample Origin: DRILL CORE

	%	%	%	g/ton		HCl sol. Fe			
Sample Number	Pb	Zn	Fe	Ag	Cu				
1	30956	1.87	2.99	38.9	18		4.85		
2	30957	0.45	0.33	31.6	14		0.99		
3	30958	0.99	1.92	27.4	14		1.94		
4	30959	5.50	6.65	89.7	69		2.71		
5	30960	2.88	1.45	31.4	32		6.80		
6	30961	2.50	2.32	31.1	26		9.83		
7	30962	0.34	0.24	37.2	16		4.92		
8	30963	0.11	0.10	38.1	12		4.53		
9	30964	0.82	0.22	33.2	16		6.39		
10	30965	0.63	0.09	31.0	14		1.66		
11	30966	3.73	1.14	30.8	36		4.93		
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Clare Handlane

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: April 4, 1988

Sample Origin: Drill Core

						HCl			
Sample Number	Pb	Zn	Fe	Ag	Cu	Sol Fl			
1 30684	7.16	6.79	16.2	93		8.64			
2 30685	5.81	7.79	10.7	95		4.09			
3 30686	3.88	8.16	8.52	77		1.19			
4 30687	3.19	5.35	9.74	47		5.11			
5 30688	4.92	7.04	17.6	73		3.84			
6 30689	1.95	3.06	24.7	29		8.39			
7 30690	1.36	1.62	23.3	22		6.54			
8 30691	0.77	0.89	5.59	12		4.11			
9 30692	2.44	1.62	34.1	28		27.1			
10 30693	1.13	0.69	33.4	16		26.0			
11 30694	0.38	0.51	29.4	12		23.0			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: _____

Sample Origin: DRILL CORE

	g/g	g/g	g/g	g/TON		HLR Sol. Fe			
Sample Number	Pb	Zn	Fe	Ag	Cu				
1	30967	4.40	5.69	21.2	50	3.19			
2	30968	4.41	3.13	36.0	54	17.5			
3	30969	0.51	0.33	29.8	19	3.38			
4	30970	0.31	0.38	27.2	14	2.38			
5	30971	1.51	1.27	28.1	35	3.31			
6	30972	0.20	0.45	25.9	17	9.92			
7	30973	0.56	1.02	22.2	17	2.14			
8	30974	0.29	0.39	21.9	19	4.74			
9	30975	0.41	0.38	33.2	23	2.44			
10	30976	0.26	0.38	30.3	21	3.17			
11	30977	0.36	0.44	19.8	17	4.08			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Clare Hamilton

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: April 5, 1988

Sample Origin: Drill Core

						HCl			
	Sample Number	Pb	Zn	Fe	Ag	Cu	sol Fe		
1	30978	0.45	1.19	18.3	14		4.02		
2	30979	0.41	1.21	13.6	10		5.05		
3	30980	0.06	0.34	4.19	2		3.57		
4	30981	0.38	0.77	39.0	20		13.2		
5	30982	1.80	5.02	36.1	32		12.2		
6	30983	3.15	4.94	39.5	44		8.77		
7	30984	7.82	6.44	34.2	115		7.59		
8	30985	9.64	5.80	34.6	107		7.77		
9	30986	3.71	4.39	37.7	51		9.09		
10	30987	5.17	4.81	35.6	69		5.61		
11	30988	5.93	6.44	16.4	83		3.82		
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: April 5, 1988

Sample Origin: Drill Core

						HCl			
Sample Number	Pb	Zn	Fe	Ag	Cu	Sol Fe			
1 30379	0.59	0.43	35.1	14		3.77			
2 30380	0.67	1.43	12.2	14		8.78			
3 30381	0.92	1.41	42.2	16		10.9			
4 30382	3.62	5.50	29.4	32		9.60			
5 30383	0.46	0.63	40.6	22		6.45			
6 30384	1.24	0.87	34.4	22		5.08			
7 30385	0.71	0.73	25.2	18		8.63			
8 30386	2.58	1.63	18.1	32		8.07			
9 30387	0.68	0.90	27.3	14		8.77			
10 30388	0.25	0.47	28.6	14		4.32			
11 30389	1.46	0.50	22.0	18		3.41			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Alano Hamela

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: April 5, 1988

Sample Origin: _____

	%	%	%	g/ton		HCl			
Sample Number	Pb	Zn	Fe	Ag	Cu	sol Fe			
1 30989	3.09	4.42	27.2	52		8.82			
2 30990	3.66	4.82	30.2	55		2.28			
3 30991	2.35	3.25	26.2	41		1.92			
4 30992	4.33	6.82	29.8	47		11.7			
5 30993	6.34	11.9	27.8	64		6.3			
6 30994	0.16	0.29	46.5	19		13.4			
7 30995	0.18	0.85	35.3	14		5.84			
8 30996	0.10	0.28	40.3	19		3.11			
9 30376	6.60	8.10	14.4	80		1.80			
10 30377	1.78	0.59	36.5	23		7.12			
11 30378	1.18	0.98	40.8	17		7.73			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: April 5, 1988

Sample Origin: DRILL CORE

	%	%	%	g/TON		HCl sol Fe			
Sample Number	Pb	Zn	Fe	Ag	Cu				
1	30390	1.73	0.42	21.6	22		4.50		
2	30391	1.55	2.21	21.9	66		4.63		
3	30666	6.02	4.38	22.3	95		5.13		
4	30667	0.83	0.50	5.60	10		2.94		
5	30668	0.12	0.82	30.0	6		13.9		
6	30669	0.89	2.16	21.2	18		9.12		
7	30670	2.09	4.11	32.9	30		14.8		
8	30671	2.59	4.08	28.5	26		7.04		
9	30672	1.07	2.61	25.8	14		6.55		
10	30673	4.68	6.70	25.2	40		5.08		
11	30674	1.08	2.43	29.5	26		3.52		
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Chris Hansen

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: April 6, 1988

Sample Origin: Drill Core

	%	%	%	g/ton		HCl			
Sample Number	Pb	Zn	Fe	Ag	Cu	sol Fe			
1	30675	0.39	1.91	26.4	14	5.26			
2	30676	1.66	6.30	25.6	26	7.51			
3	30677	9.12	11.3	24.6	117	13.0			
4	30678	6.12	4.54	28.3	65	13.1			
5	30679	0.27	0.85	21.4	14	5.29			
6	30680	0.33	0.77	13.3	8	4.74			
7	30681	0.14	0.24	10.2	6	4.03			
8	30682	0.70	1.43	34.2	20	8.51			
9	30351	6.16	7.81	20.0	101	3.30			
10	30352	1.99	2.62	41.6	40	7.96			
11	30353	6.17	8.46	16.0	91	22.9			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: April 6, 1988

Sample Origin: Vengorda Core

Sample Number	% Pb	% Zn	% Fe	g/Ton Ag	Cu	HCl sol Fe			
1	30354	2.15	1.49	10.8	32	7.24			
2	30355	0.61	0.32	34.0	24	9.48			
3	30356	1.47	1.26	35.4	32	9.40			
4	30357	3.36	5.80	10.3	53	2.16			
5	30358	2.64	4.69	9.45	40	2.56			
6	30359	1.85	2.12	11.0	27	2.99			
7	30360	1.22	2.23	9.20	18	3.73			
8	30361	4.91	0.63	40.0	71	0.67			
9	30362	2.81	0.47	40.0	59	0.58			
10	30363	0.66	0.49	6.25	8	0.89			
11	30364	0.84	1.16	6.87	10	4.54			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

3084 3rd sheet

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: April 17, 1988

Sample Origin: Drill Core

	Sample Number	Pb	Zn	Fe	Ag	Cu	HCl Sol			
							Fe			
1	30604	2.13	2.85	26.6	33		11.2			
2	30605	1.21	2.25	23.8	26		6.34			
3	30606	4.76	5.54	32.7	57		19.0			
4	30607	4.39	3.74	34.2	53		23.2			
5	30608	2.84	1.66	32.0	37		14.2			
6	30609	3.06	1.76	25.0	39		21.4			
7	30610	5.38	6.62	19.6	66		8.96			
8	30611	0.68	1.28	28.2	20		7.39			
9	30612	0.68	0.76	20.2	18		3.87			
10	30613	0.25	0.72	20.2	11		6.46			
11										
12	30200	3.82	2.84	38.9	58		4.07			
13										
14										
15										
16										
17										
18										
19										
20										
21										
22										
23										
24										
25										
26										
27										
28										
29										
30										
31										
32										

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: April 18, 1988

Sample Origin: Drill Core

						HCl Sol			
	Sample Number	Pb	Zn	Fe	Ag	Cu	Fe		
1	30029	1.50	2.22	4.41	24		1.75		
2	30035	2.65	5.47	7.20	49		1.54		
3	30040	1.92	3.20	3.83	32		1.67		
4	30042	3.81	6.94	17.6	65		5.61		
5	30043	4.31	9.27	5.57	75		2.58		
6	30047	2.05	5.68	5.37	30		2.64		
7	30052	1.32	2.82	8.81	24		3.00		
8	30054	1.75	4.31	7.29	20		4.13		
9	30056	0.06	0.14	7.52	0		7.05		
10	30058	2.21	5.18	8.93	36		3.01		
11	30061	1.72	3.54	11.1	32		3.74		
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: MAY 7/88

Sample Origin: DRILL CORE

	%	%	%	S/ton		HCl sol. Fe %			
Sample Number	Pb	Zn	Fe	Ag	Cu				
1	30001	1.34	4.81	4.42	23	1.73			
2	30002	1.07	2.98	2.70	19	1.48			
3	30010	0.12	0.23	6.32	0	5.71			
4	30012	0.05	1.39	8.48	0	6.86			
5	30022	1.29	5.00	5.35	26	4.01			
6	30026	2.02	4.04	6.48	34	3.46			
7	30030	2.64	5.04	6.53	46	2.29			
8	30032	1.09	6.05	8.32	21	5.61			
9	30036	2.64	5.10	5.00	42	1.66			
10	30037	1.60	3.73	4.41	28	1.37			
11	30038	0.08	0.51	8.10	4	7.04			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Oliver Hamolana

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: May 9, 1988

Sample Origin: Drill Core

	Sample Number	Pb	Zn	Fe	Ag	Cu	HCl sol			
							Fe			
1	30079	1.40	1.37	7.79	23		0.58			
2	30102	2.73	7.14	8.31	60		4.38			
3	30105	1.56	2.59	9.40	31		3.90			
4	30115	0.21	0.34	9.12	4		7.60			
5	30116	1.11	2.17	17.9	25		8.93			
6	30120	0.50	1.00	6.43	8		3.33			
7	30471	0.67	0.34	3.38	12		2.28			
8	30472	2.97	0.88	20.9	66		20.7			
9	30473	1.26	0.64	5.50	23		1.29			
10	30475	0.14	0.68	4.01	4		2.33			
11	30476	0.05	2.21	7.44	2		5.29			
12										
13										
14										
15										
16										
17										
18										
19										
20										
21										
22										
23										
24										
25										
26										
27										
28										
29										
30										
31										
32										

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: May 10, 1988

Sample Origin: Drill Core

						HCl sol			
Sample Number	Pb	Zn	Fe	Ag	Cu	Fe			
1	30477	0.15	0.84	5.24	2	3.20			
2	30478	7.45	16.2	18.4	124	7.44			
3	30482	0.66	1.75	17.5	11	9.12			
4	30485	7.19	9.44	8.59	95	1.90			
5	30488	5.31	8.57	18.0	80	2.10			
6	30542	0.64	0.79	12.7	9	7.99			
7	30543	0.87	1.81	25.8	16	11.4			
8	30550	3.78	8.65	7.65	73	3.42			
9	30551	4.59	5.98	8.49	64	3.41			
10	30575	2.70	5.31	12.6	46	1.53			
11	30576	2.92	5.30	7.04	42	3.54			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

MAY 11/88

Sample Origin: DRILL CORE

	%	%	%	g/tow		ML or 1 Fe			
Sample Number	Pb	Zn	Fe	Ag	Cu	%			
1	30810	0.50	3.00	9.91	8	6.79			
2	30811	0.65	4.30	10.9	10	9.33			
3	30812	2.69	5.93	8.90	45	5.18			
4	30814	8.77	17.1	28.0	180	1.35			
5	30815	0.48	4.45	10.7	8	8.96			
6	30816	6.15	9.69	21.8	109	3.36			
7	30817	3.44	5.63	18.7	67	2.65			
8	30818	3.22	5.09	7.41	53	2.57			
9	30819	6.78	7.69	6.65	111	2.84			
10	30820	2.31	3.10	3.88	34	1.25			
11	30821	2.45	4.55	7.45	32	5.42			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: May 11, 1988

Sample Origin: Drill Core

	%	%	%	g/TON		HCl sol Fe %			
Sample Number	Pb	Zn	Fe	Ag	Cu				
1 30595	0.80	2.26	4.27	16		1.65			
2 30800	1.42	3.73	6.88	30		0.74			
3 30801	1.53	3.47	5.73	34		0.62			
4 30802	2.38	6.88	5.31	46		0.99			
5 30803	2.84	5.42	11.8	48		1.19			
6 30804	4.48	7.20	6.48	30		2.28			
7 30805	1.75	4.03	8.04	65		3.72			
8 30806	1.68	4.80	6.27	28		1.28			
9 30807	1.34	4.81	8.24	24		2.92			
10 30808	0.57	1.10	18.9	26		0.60			
11 30809	0.36	5.55	14.0	8		11.2			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Core Handover

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: May 12, 1988

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	Cu	HCl sol Fe			
1 30822	3.50	5.93	6.18	56		1.54			
2 30823	3.39	6.23	4.26	46		1.63			
3 30824	3.44	6.60	5.95	52		3.01			
4 30825	1.04	2.32	9.01	27		0.59			
5 30826	2.80	4.10	5.79	44		0.76			
6 30827	2.37	3.40	6.39	37		0.81			
7 30828	2.50	4.07	7.57	39		1.07			
8 30829	2.62	4.24	5.16	37		1.48			
9 30830	0.45	0.89	6.26	9		2.76			
10 30833	4.79	8.27	17.4	83		1.07			
11 30834	1.01	1.56	5.95	15		2.58			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: May 13, 1988

Sample Origin: Drill Core

						HCl			
	Sample Number	Pb	Zn	Fe	Ag	Cu	sol Fe		
1	30835	4.06	8.29	13.5	66		3.43		
2	30836	11.8	16.7	16.2	188		3.05		
3	30837	1.08	2.05	5.23	21		2.40		
4	30838	1.09	2.91	8.45	25		3.34		
5	30839	1.88	3.72	11.8	38		2.22		
6	30840	2.93	7.94	13.8	64		1.97		
7	30841	1.89	4.65	9.06	38		4.01		
8	30851	0.69	0.71	19.3	17		6.67		
9	30852	4.90	4.64	29.7	70		5.73		
10	30853	0.47	0.92	19.5	15		1.48		
11	30854	2.49	3.76	15.0	40		2.90		
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

2

Sample Assay Sheet

Production Date:

MAY 17/88

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	Cu	HCl sol Fe
1 30487	5.29	11.4	11.1	82		2.34
2 30519	10.2	20.9	23.3	176		2.35
3 30524	3.47	11.2	12.2	62		2.46
4 30528	0.41	0.71	8.15	9		4.83
5 30529	0.28	1.19	7.61	9		3.86
6 30532	0.37	0.94	5.92	8		2.60
7 30538	0.15	0.22	6.88	8		6.24
8 30546	0.11	1.93	11.9	8		9.76
9 30548	0.19	6.76	17.9	11		14.4
10 30574	3.02	6.62	9.83	57		2.12
11 30580	1.85	3.23	12.2	40		0.87
12						
13 30586	3.72	8.49	5.70	60		1.18
14 30597	1.16	2.42	5.73	21		2.65
15 30863	4.46	9.91	12.9	70		1.95
16 30876	2.68	6.42	40.5	31		1.38
17 30877	4.43	11.9	33.3	74		1.73
18 30878	6.98	17.2	30.3	99		4.44
19 30879	11.2	22.9	18.7	201		2.75
20 30880	4.18	9.88	35.3	75		3.56
21 30881	3.98	2.77	23.3	48		1.12
22 30883	0.15	0.62	22.5	12		1.28
23 30884	3.82	7.10	10.8	58		1.62
24						
25						
26						
27						
28						
29						
30						
31						
32						

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

MAY 17/88

Sample Origin:

DRILL CORE

	%	%	%	g/ton		HCl sol. Fe			
Sample Number	Pb	Zn	Fe	Ag	Cu	%			
1	30855	5.90	7.50	29.1	85	4.08			
2	30856	5.26	6.78	27.2	79	3.81			
3	30857	3.00	5.31	11.4	51	5.20			
4	30858	0.05	0.19	481	0	3.54			
5	30859	0.64	1.11	928	10	5.26			
6	30860	3.18	6.93	2.47	44	0.95			
7	30867	6.11	15.4	22.6	111	4.01			
8	30870	1.80	8.44	20.5	32	6.99			
9	30871	6.75	18.0	24.6	129	6.86			
10	30874	9.86	27.1	21.4	137	1.60			
11	30875	1.01	17.9	27.3	178	0.99			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Claus Henstler

4

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: _____

Sample Origin: Drill Core

					sol Fe				
Sample Number	Pb	Zn	Fe	Ag	CU				
1	30041	3.05	6.68	7.72	46	3.06			
2	30103	1.81	3.61	8.49	35	4.20			
3	30109	0.32	1.09	8.61	9	7.86			
4	30110	3.69	7.06	12.2	69	6.21			
5	30111	2.17	4.22	8.29	37	3.79			
6	30117	0.42	1.00	8.10	13	2.83			
7	30121	9.24	16.3	24.0	153	2.98			
8	30126	0.92	2.13	3.28	17	2.35			
9	30127	1.79	2.58	2.86	26	1.30			
10	30128	4.52	2.10	8.10	69	3.05			
11	30130	1.52	3.86	12.1	28	3.16			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Margaret Yu

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: MAY 18/88

Sample Origin: DRILL CORE

	%	%	%	g/ton		HCl sol Fe			
Sample Number	Pb	Zn	Fe	Ag	Cu	%			
1 30940	1.53	4.41	10.5	31		3.37			
2 30943	0.04	0.29	5.12	0		2.87			
3 30946	5.05	9.10	19.1	96		1.37			
4 30013	1.52	2.80	5.65	28		2.63			
5 30014	2.58	6.00	7.11	26		3.55			
6 30025	0.11	4.38	10.7	6		9.85			
7 30027	1.91	3.76	6.76	33		1.60			
8 30031	2.28	5.03	7.07	39		3.01			
9 30034	5.90	11.8	8.90	100		5.09			
10 30068	0.04	0.13	5.70	0		5.75			
11 30071	0.59	2.18	8.03	17		0.32			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Claus Kemelinen

L

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: May 18, 1988

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	Cu	HCl Sol Fe			
1 30886	4.56	9.56	30.3	79		2.96			
2 30887	1.55	5.97	21.7	21.2		8.96			
3 30888	5.08	10.4	24.9	98		1.18			
4 30889	3.99	8.81	32.7	75		2.48			
5 30890	0.37	0.82	11.3	6		1.02			
6 30891	5.51	10.4	24.8	97		3.32			
7 30892	6.25	13.2	32.0	93		4.27			
8 30893	3.42	6.22	21.3	54		3.42			
9 30894	6.72	12.7	18.6	116		4.23			
10 30895	9.92	2.29	19.4	162		2.12			
11 30897	0.24	5.18	10.3	7		0.42			
12 30898	0.65	0.94	7.75	12		0.49			
13 30899	0.27	2.14	8.24	6		3.92			
14 30900	1.09	2.91	15.4	17		8.38			
15 30901	0.09	0.24	6.73	4		6.40			
16 30914	2.05	4.57	10.4	31		6.44			
17 30915	2.55	4.80	8.02	37		0.68			
18 30916	2.30	3.85	8.03	35		0.63			
19 30918	3.72	5.25	8.67	48		0.72			
20 30923	2.95	4.16	10.5	46		0.70			
21 30929	3.20	6.01	10.1	46		0.90			
22 30933	2.49	4.07	8.27	37		0.79			
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Michelle Bergeron

L

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: 25 May 88

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	Cu	HCl sol			
						Fe			
1 30131	3.72	6.39	11.4	59		1.57			
2 30132	5.57	9.69	12.8	87		1.39			
3 30133	1.18	1.83	10.4	25		3.28			
4 30135	1.82	4.61	12.9	42		0.93			
5 30138	7.52	14.7	13.4	112		2.24			
6 30139	3.58	6.53	11.6	57		3.77			
7 30141	3.82	6.92	12.5	70		3.70			
8 30143	0.95	3.09	3.63	23		0.62			
9 30145	0.15	0.50	6.50	8		5.94			
10 30147	0.58	2.20	9.52	11		7.80			
11 30150	2.74	4.94	9.44	42		1.94			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Margaret Yu

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: May 25, 1988

Sample Origin: Drill Core

	%	%	%	g/TON		HCl sol			
Sample Number	Pb	Zn	Fe	Ag	Cu	Fe			
1	30008	0.60	1.43	6.80	13		6.02		
2	30033	2.27	5.07	5.21	40		1.60		
3	30059	1.80	2.91	7.88	32		3.70		
4	30067	0.84	1.23	10.7	15		7.33		
5	30069	0.83	2.85	3.38	15		2.78		
6	30072	1.92	3.44	8.13	30		0.66		
7	30078	1.42	1.71	10.1	25		0.43		
8	30082	0.11	0.20	5.19	4		3.88		
9	30083	2.31	3.43	10.8	38		2.96		
10	30588	1.65	3.19	8.09	25		1.34		
11	30593	0.34	2.08	29.7	9		14.3		
12	30420	6.96	13.6	20.5	118		1.64		
13	30422	0.07	0.41	5.38	4		4.02		
14	30428	8.54	14.0	24.6	148		1.67		
15	30430	3.50	8.50	8.60	59		0.53		
16	30434	4.84	7.88	16.9	91		8.79		
17	30436	5.04	7.15	29.8	96		0.88		
18	30479	2.84	3.73	15.6	49		1.02		
19	30481	2.06	5.64	4.74	40		1.87		
20	30573	2.30	5.66	9.04	42		1.74		
21	30584	1.32	3.99	3.66	25		1.12		
22	30585	1.91	4.78	6.50	32		1.16		
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

May 31, 188

Sample Origin:

Drill Core

Sample Number	Pb	Zn	Fe	Ag	HCP _{sol} Fe				
1 30747	0.75	8.75	12.3	11	10.7				
2 30748	7.54	15.1	22.6	141	4.37				
3 30749	0.69	1.06	14.0	20	4.64				
4 30882	0.45	0.82	28.6	15	1.35				
5 30474	1.11	1.89	8.16	24	2.00				
6 30486	3.91	7.71	12.3	56	7.45				
7 30104	1.62	3.14	10.1	24	4.06				
8 30125	2.27	5.70	4.53	35	1.06				
9 30799	2.70	3.89	3.62	39	0.75				
10 30831	1.64	1.16	12.2	28	2.52				
11 30832	12.4	20.5	11.0	212	2.07				
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer:

Lauren Johnson

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: June 1, 1988

Sample Origin: Drill Core

	%	%	%	g/Ton		HCl sol			
Sample Number	Pb	Zn	Fe	Ag	Cu	Fe			
1	30750	1.78	4.11	4.82	35	2.20			
2	30751	1.91	3.96	6.45	35	2.70			
3	30752	2.55	5.24	6.06	49	2.63			
4	30753	1.71	3.84	4.23	25	3.09			
5	30754	1.46	3.90	3.34	29	1.57			
6	30755	1.12	4.87	7.83	21	6.22			
7	30756	0.21	4.22	9.43	8	8.90			
8	30757	2.12	4.08	4.37	41	2.15			
9	30758	1.28	3.37	3.36	27	1.38			
10	30759	0.46	2.40	12.2	10	8.63			
11	30760	0.76	3.50	10.7	16	4.70			
12	30761	0.75	2.59	7.61	12	5.74			
13	30762	1.31	2.89	3.10	23	0.58			
14	30763	1.29	3.12	7.60	25	0.57			
15	30764	2.30	5.59	4.77	37	1.02			
16	30765	1.18	2.70	3.88	23	0.95			
17	30766	1.66	3.33	6.95	25	1.86			
18	30767	0.45	2.76	9.34	12	7.70			
19	30768	1.25	0.32	13.8	23	7.38			
20	30770	0.21	0.32	5.78	6	3.64			
21	30771	0.16	0.42	3.52	4	1.95			
22	30772	0.19	0.48	4.34	6	2.48			
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: June 6, 1988

Sample Origin: Drill Core

Sample Number	% Pb	% Zn	% Fe	g/Ton Ag	Cu	% HCl Sol Fe			
1	30773	0.40	0.91	6.06	7		2.82		
2	30774	0.48	1.21	7.12	11		2.15		
3	30775	1.75	1.75	12.1	41		2.10		
4	30776	0.25	2.50	13.6	4		10.9		
5	30777	11.1	9.07	23.4	178		2.90		
6	30778	5.28	6.79	9.98	89		1.71		
7	30779	3.29	6.96	8.96	58		2.80		
8	30780	2.93	6.03	5.71	56		0.99		
9	30781	2.31	6.12	5.92	48		1.05		
10	30782	1.92	5.66	5.18	37		2.13		
11	30783	1.90	4.20	4.08	32		2.14		
12	30784	3.03	5.60	13.9	50		3.00		
13	30785	1.05	1.52	18.1	19		6.58		
14	30786	1.63	2.87	13.5	31		4.67		
15	30787	7.38	10.3	18.2	124		1.67		
16	30788	1.39	2.93	9.04	23		4.71		
17	30789	2.64	5.69	9.15	48		2.27		
18	30790	2.58	5.84	17.8	52		1.18		
19	30791	1.62	3.68	12.0	37		1.35		
20	30792	4.71	10.3	20.0	104		2.33		
21	30793	3.45	7.97	15.1	68		1.33		
22	30794	3.83	7.16	17.2	70		1.27		
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: June 6, 1988

Sample Origin: Drill Core

	%	%	%	g/Ton		HCl sol			
Sample Number	Pb	Zn	Fe	Ag	Cu	Fe			
1 30124	2.42	5.55	4.04	37		0.95			
2 30426	5.73	11.9	13.3	95		3.44			
3 30431	11.0	17.8	25.2	153		7.46			
4 30435	3.75	6.21	20.3	72		0.40			
5 30520	5.11	8.32	14.0	101		2.93			
6 30521	8.67	15.7	18.2	155		4.85			
7 30527	0.27	0.39	6.11	4		4.91			
8 30531	4.27	6.66	13.6	80		5.34			
9 30534	6.80	9.97	8.83	105		3.09			
10 30592	1.38	3.40	6.83	21		1.88			
11 30865	13.1	2.42	14.6	16		6.10			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Alamo Kavalama

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: June 1, 1988

Sample Origin: Drill Core

	%	%	%	g/Ton		HCl sol			
Sample Number	Pb	Zn	Fe	Ag	Cu	Fe			
1	30423	0.09	0.26	2.98	6	1.54			
2	30433	3.99	8.05	16.8	97	0.47			
3	30522	0.46	1.49	8.27	10	6.89			
4	30523	0.26	0.18	6.29	4	5.95			
5	30525	0.72	1.64	6.46	10	4.05			
6	30526	0.20	0.55	5.45	6	3.37			
7	30536	9.88	15.0	8.70	170	4.48			
8	30540	1.75	3.52	5.14	31	2.63			
9	30590	1.64	4.07	5.24	31	1.17			
10	30594	0.09	0.24	4.93	4	4.02			
11	30598	0.46	5.33	11.1	8	3.84			
12									
13	30530	4.63	11.3	28.5	85	2.38			
14	30535	11.6	17.1	15.2	186	3.44			
15	30539	9.61	17.1	10.7	161	5.95			
16	30541	1.93	4.07	4.29	28	1.66			
17	30579	1.52	3.55	2.35	28	0.84			
18	30581	1.08	2.63	3.34	21	0.85			
19	30583	1.32	2.73	2.94	25	0.68			
20	30589	1.63	2.15	4.76	23	0.93			
21	30591	1.16	3.78	7.39	21	1.01			
22	30596	0.08	0.16	5.23	2	4.45			
23	30599	0.47	0.75	6.59	9	1.75			
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: June 8, 1988

Sample Origin: Drill Core

	Sample Number	Pb	Zn	Fe	Ag	Cu	HCl sol			
							Fe			
1	30062	1.84	3.16	6.88	29		4.79			
2	30070	0.96	1.49	6.87	13		3.89			
3	30123	2.28	4.33	8.55	27		3.14			
4	30425	0.42	0.75	6.56	7		2.23			
5	30446	4.90	5.05	33.5	66		1.57			
6	30549	3.30	6.58	6.75	63		3.84			
7	30795	4.26	7.29	13.2	66		1.11			
8	30797	2.62	5.25	18.1	47		7.96			
9	30896	1.10	2.54	10.6	18		1.43			
10	30941	1.71	3.33	6.78	24		3.07			
11	30996	0.12	0.32	39.3	22		3.31			
12	30129	0.37	0.88	3.56	7		2.02			
13	30136	5.20	11.3	8.95	89		1.44			
14	30137	7.60	16.9	11.4	127		2.19			
15	30429	5.91	10.1	30.3	91		2.35			
16	30432	5.49	9.46	15.4	109		0.74			
17	30582	0.76	3.07	3.43	18		0.72			
18	30587	3.00	7.29	4.27	47		3.06			
19	30864	2.71	4.93	12.0	36		0.82			
20	30902	0.87	1.65	7.56	16		2.03			
21	30903	1.03	1.63	5.93	18		3.16			
22	30904	0.67	1.17	6.24	15		1.44			
23										
24										
25										
26										
27										
28										
29										
30										
31										
32										

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: JUNE 8/88

Sample Origin: DRILL CORE

	g	g	g	g/TON		Hcl sol Fe			
Sample Number	Pb	Zn	Fe	Ag	Cu				
1 30076	1.77	3.04	10.7	35		0.90			
2 30134	2.11	4.41	10.8	43		1.24			
3 30140	0.74	5.56	10.7	13		8.71			
4 30421	0.14	0.43	3.39	4		1.90			
5 30437	4.78	6.75	32.1	113		0.64			
6 30438	2.47	1.69	34.4	61		1.42			
7 30439	0.06	0.12	4.38	4		2.04			
8 30441	5.53	8.96	22.0	82		0.65			
9 30484	4.64	6.67	13.8	72		0.97			
10 30861	3.40	4.87	2.94	48		0.75			
11 30862	2.93	2.04	4.53	43		0.45			
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Oliver Hameloni

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: June 11, 1988

Sample Origin: Drill Core

	%	%	%	g/ton		HCl sol			
Sample Number	Pb	Zn	Fe	Ag	Cu	Fe			
1	30905	2.18	2.62	4.57	32		0.71		
2	30906	0.96	2.51	7.29	15		1.16		
3	30907	0.87	1.46	7.79	15		2.58		
4	30908	1.20	2.57	10.8	21		1.35		
5	30909	2.02	5.05	7.12	38		0.70		
6	30910	1.11	2.14	6.94	21		0.44		
7	30911	2.80	3.57	8.32	40		0.68		
8	30912	1.45	5.40	8.59	23		0.83		
9	30913	1.13	3.23	5.37	17		0.57		
10	30917	2.22	3.54	6.89	32		0.53		
11	30919	1.72	6.01	5.27	25		0.80		
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

Assayer: Michelle Bergeron

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: June 12, 1988

Sample Origin: Drill Core

						HCl sol			
Sample Number	Pb	Zn	Fe	Ag	Cu	Fe			
1 30928	2.70	5.16	7.29	40		0.74			
2 30930	4.95	9.04	10.1	84		3.62			
3 30931	2.67	4.75	8.29	44		0.75			
4 30932	2.29	5.42	6.58	36		0.77			
5 30934	2.42	4.86	8.23	40		0.70			
6 30936	0.67	1.19	9.15	13		0.32			
7 30937	2.51	2.21	8.20	49		0.48			
8 30945	3.36	6.93	15.4	61		2.63			
9									
10									
11									
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: June 12, 1988

Sample Origin: Drill Core

						HCl sol			
	Sample Number	Pb	Zn	Fe	Ag	Cu	Fe		
1	30920	2.63	5.69	7.31	44		0.78		
2	30921	2.15	4.99	8.98	38		0.65		
3	30922	2.12	4.89	7.12	34		0.70		
4	30924	2.09	4.44	10.6	42		0.62		
5	30925	1.57	3.12	9.55	32		0.53		
6	30926	1.34	2.96	11.9	28		0.53		
7	30927	2.45	4.12	8.94	42		0.57		
8	30928	2.05	4.01	5.05	32		0.66		
9	30939	1.68	4.02	7.15	28		0.75		
10	30942	0.79	1.08	5.44	11		2.66		
11	30944	1.96	4.76	1.76	34		0.97		
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: Jan 26, 188

Sample Origin: Drill Core

	Sample Number	Pb	Zn	Fe	Ag	Hg/Sb/Fe			
1	11297	0.44	0.44	34.6	30	3.52			
2	11298	0.78	0.59	27.7	34	4.99			
3	11299	1.12	1.41	29.7	37	5.61			
4	11397	0.28	0.43	11.4	6	2.68			
5	11146	2.35	2.22	38.4	50	10.8			
6	11167	1.02	0.71	28.4	14	12.7			
7	11170	0.43	0.83	31.1	10	14.2			
8	11177	3.23	5.02	23.4	34	13.7			
9	11292	0.28	0.40	19.7	12	2.04			
10	11293	0.28	0.38	22.9	14	1.73			
11	11294	0.17	0.32	23.2	12	1.62			
12	11295	0.18	0.25	24.2	14	2.45			
13	11296	0.17	0.17	28.4	26	1.87			
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

GURRAGH RESOURCES

Sample Assay Sheet

Production Date: Feb 14 1988

Sample Origin: Drill Core

Sample Number	Pb	Zn	Fe	Ag	HCl sol	Fe
1 11089	0.76	202	26.4	14	10.0	
2 11092	0.68	0.86	26.5	31	2.48	
3 (11100)	2.42	2.39	15.5	27	3.44	
4 (11103)	3.87	4.57	22.2	46	7.92	
5 (11105)	4.30	3.94	31.4	50	8.60	
6 (11109)	6.54	9.69	33.0	99	3.70	
7 (11111)	3.68	7.24	9.96	62	0.81	
8 (11122)	2.86	3.85	29.9	35	2.61	
9 (11135)	3.53	6.72	19.3	46	2.76	
10 (11141)	0.13	0.13	9.43	4	2.22	
11 11143	0.18	0.80	10.1	4	1.30	
12 11147	1.61	2.69	28.4	35	3.26	
13 11151	0.47	0.35	30.1	19	2.78	
14 11160	0.45	1.65	10.4	10	9.20	
15 11164	10.3	10.9	20.1	114	12.0	
16 11168	0.93	1.12	23.7	19	16.6	
17 11169	0.27	0.70	30.5	12	16.8	
18 11172	0.16	0.50	23.2	8	6.48	
19 11173	0.58	0.46	21.9	12	5.65	
20 11174	0.56	0.36	21.7	12	7.45	
21 11175	0.32	0.43	25.0	10	10.5	
22 11178	0.24	0.24	18.0	10	3.03	
23						
24						
25						
26						
27						
28						
29						
30						
31						
32						