

020142

CURRAGH RESOURCES

Sample Assay Sheet

Production Date:

December 10/88

Sample Origin: Drill Core 16953-16963

886-05
886-03

Sample Number	Pb	Zn	Fe	Ag	As	HLSOI Fe	P _y	Pb+Zn
1 16953	2.88	3.41	37.6	46		1.13	36.47	6.29
2 16954	2.55	4.23	10.3	35		4.03	6.27	6.78
3 16955	2.01	2.94	16.8	33		1.96	14.84	4.95
4 16956	2.83	2.74	33.9	35		15.0	18.9	5.57
5 16957	2.32	2.63	19.2	33		6.72	12.48	4.95
6 16958	6.94	4.52	28.9	94		0.85	28.05	11.46
7 16959	2.96	1.78	38.4	40		1.37	37.03	4.74
8 16960	8.87	14.7	20.9	121		1.41	19.49	23.77
9 16961	5.25	9.83	24.3	83		2.76	21.54	14.68
10 16962	0.56	1.10	10.5	14		3.27	7.23	1.66
11 16963	2.68	4.82	21.2	48		0.83	20.37	7.5
12								
13								
14								
15								
16								
17								
18								
19								
20								
21								
22								
23								
24								
25								
26								
27								
28								
29								
30								
31								
32								

Grun 1986 Assays.

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: December 10/88

Sample Origin: Drill Core 16964-16974

886-03
886-01

Sample Number	Pb	Zn	Fe	Ag	Gr	HCL SOL			
						Fe Po	P _y	Pb+Zn	
1 16964	3.33	3.79	35.7	58		0.74	34.96	7.18	7.12
2 16965	0.69	3.21	30.0	22		6.23	23.77	3.9	
3 16966	0.31	1.61	19.2	7		3.65	15.55	1.92	
4 16967	5.98	10.6	25.4	98		1.79	23.61	16.58	
5 16968	7.30	13.0	29.8	115		2.37	27.43	26.3	
6 16969	6.42	13.1	31.3	98		5.90	25.4	19.52	
7 16970	2.41	3.15	35.1	34		18.0	17.1	5.56	
8 16971	4.55	9.28	4.65	72		2.81	1.84	13.83	
9 16972	1.37	4.29	10.4	24		6.34	4.06	5.66	
10 16973	0.20	3.01	17.4	5		13.2	4.2	3.21	
11 16974	0.87	2.32	36.0	5		0.90	35.1	3.19	
12									
13									
14									
15									
16									
17									
18									
19									
20									
21									
22									
23									
24									
25									
26									
27									
28									
29									
30									
31									
32									

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: _____

Sample Origin: Drill core 16975-16985

886-01

Sample Number	Pb	Zn	Fe	Ag	Cu	Pg	Py	Pb+Zn
1 16975	1.11	2.88	8.70	17		1.16	7.54	3.99
2 6	3.98	7.67	27.3	91		.77	26.53	11.65
3 7	9.62	16.7	25.5	154		1.17	24.33	26.32
4 8	11.3	16.8	19.6	177		3.56	16.04	28.1
5 9	11.4	17.5	20.8	165		4.27	16.53	28.9
6 16980	4.62	8.00	10.5	74		1.61	8.89	12.62
7 1	2.93	7.41	7.29	61		2.22	5.07	10.34
8 2	1.84	4.10	5.33	32		.75	4.58	5.94
9 3	2.37	4.46	4.25	36		2.01	2.24	6.83
10 4	1.58	1.82	5.67	19		2.39	3.28	3.4
11 16985	1.07	1.17	5.40	15		2.31	3.09	2.24
12								
13								
14			Fe	UCC	sol.			
15 16975			1.16					
16 6			0.77					
17 7			1.17					
18 8			3.56					
19 9			4.27					
20 16980			1.61					
21 1			2.22					
22 2			0.75					
23 3			2.01					
24 4			2.39					
25 16985			2.31					
26								
27								
28								
29								
30								
31								
32								

CURRAGH RESOURCES

Sample Assay Sheet

Production Date: December 11/88

Sample Origin: Drill Core 16986-16995

88 G-01

Sample Number	Pb	Zn	Fe	Ag	Cu	Hcl Sol		
						Fe %	Py	Pb+Zn
1 16986	0.51	1.46	8.80	9		4.49	4.31	2.15
2 16987	0.92	1.78	17.2	19		3.81	14.19	2.7
3 16988	7.85	12.5	21.8	132		2.05	19.75	26.35
4 16989	8.55	13.5	22.3	155		1.87	20.43	22.05
5 16990	2.43	6.26	18.8	51		1.89	16.91	8.69
6 16991	2.72	4.49	17.8	51		2.09	15.71	7.21
7 16992	2.40	5.14	8.58	45		1.25	5.33	7.54
8 16993	3.48	8.65	19.9	72		3.21	16.69	12.13
9 16994	2.78	8.01	10.9	55		3.53	7.37	10.79
10 16995	2.91	8.79	14.6	58		6.58	0.2	11.7
11								
12								
13								
14								
15								
16								
17								
18								
19								
20								
21								
22								
23								
24								
25								
26								
27								
28								
29								
30								
31								
32								