

813 Samples

Hole Number: 87V-01

Number of intervals: 31

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY	MISSING SAMP
87V-01	21.9	23.5	1.5	0.2	12.0	11153	464		14.15	5.87	8.28	101.00		1.80	10.90	12.70	72.0	77.0	0.6		
87V-01	23.5	25.8	2.3	1.5	66.7	11154	464		9.90	3.18	6.72	42.00		1.93	7.67	9.60	77.0	84.5	5.0		
87V-01	25.8	26.6	0.9	0.9	100.0	11155	464		12.61	5.36	7.25	113.00		4.69	9.91	14.60	84.5	87.3	3.0		
87V-01	26.6	27.0	0.4	0.6	100.0	11156	3C#3		4.46	0.54	3.92	10.00		13.40	2.60	16.00	87.3	88.5	2.1		
87V-01	27.0	28.3	1.4	1.5	100.0	11157	4K#4		5.97	2.41	3.56	40.00		11.90	22.50	34.40	88.5	93.0	5.0		
87V-01	28.3	29.4	1.1	1.2	100.0	11158	4K#4		6.16	2.79	3.37	34.00		9.39	20.11	29.50	93.0	96.6	4.0		
87V-01	29.4	30.5	1.1	1.3	100.0	11159	4648		14.33	6.89	7.44	99.00		5.85	10.45	16.30	96.6	100.1	4.4		
87V-01	30.5	31.0	0.5	0.6	100.0	11160	3C#4		2.10	0.45	1.65	10.00		9.20	1.20	10.40	100.1	101.8	2.0		
87V-01	31.0	31.9	0.9	0.7	79.3	11161	4J42		11.26	5.94	5.32	83.00		34.00	5.20	39.20	101.8	104.7	2.3		
87V-01	31.9	33.2	1.2	1.6	100.0	11162	4648		14.70	7.07	7.63	93.00		13.20	7.90	21.10	104.7	108.8	5.1		
87V-01	33.2	34.7	1.5	1.7	100.0	11163	4648		14.95	7.03	7.92	85.00		9.11	9.69	18.80	108.8	113.8	5.7		
87V-01	34.7	35.9	1.2	1.2	100.0	11164	4D48		21.20	10.30	10.90	114.00		12.00	8.10	20.10	113.8	117.7	4.0		
87V-01	35.9	37.0	1.1	1.2	100.0	11165	4D48		14.76	6.84	7.92	77.00		10.90	7.90	18.80	117.7	121.4	3.8		
87V-01	37.0	38.6	1.6	1.5	88.9	11166	4C37		2.16	1.06	1.10	18.00		10.10	14.40	24.50	121.4	126.8	4.8		
87V-01	38.6	39.9	1.3	1.6	100.0	11167	4C37		1.73	1.02	0.71	14.00		12.70	15.70	28.40	126.8	131.0	5.4		
87V-01	39.9	41.5	1.6	1.7	100.0	11168	4C37		2.05	0.93	1.12	19.00		16.60	7.10	23.70	131.0	136.1	5.6		
87V-01	41.5	43.3	1.8	1.8	100.0	11169	4C37		0.97	0.27	0.70	12.00		16.80	13.70	30.50	136.1	142.0	6.0		
87V-01	43.3	44.5	1.2	1.6	100.0	11170	4C37		1.26	0.43	0.83	10.00		14.20	16.90	31.10	142.0	146.0	5.4		
87V-01	44.5	46.3	1.8	1.6	86.7	11171	4C37		4.42	1.38	3.04	16.00		12.40	15.80	28.20	146.0	152.0	5.2		
87V-01	46.3	47.6	1.2	1.5	100.0	11172	4C38		0.66	0.16	0.50	8.00		6.48	16.72	23.20	152.0	156.1	5.0		
87V-01	47.6	49.0	1.4	1.5	100.0	11173	4C38		1.04	0.58	0.46	12.00		5.65	16.25	21.90	156.1	160.6	4.8		
87V-01	49.0	50.3	1.3	1.4	100.0	11174	4C38		0.92	0.56	0.36	12.00		7.45	14.25	21.70	160.6	165.0	4.5		
87V-01	50.3	51.7	1.4	1.5	100.0	11175	4C38		0.75	0.32	0.43	10.00		10.50	14.50	25.00	165.0	169.5	5.0		
87V-01	51.7	52.9	1.2	1.4	100.0	11176	4C38		1.52	0.67	0.85	10.00		7.10	14.80	21.90	169.5	173.5	4.5		
87V-01	52.9	53.6	0.8	1.0	100.0	11177	4D34		8.25	3.23	5.02	34.00		13.70	9.70	23.40	173.5	176.0	3.4		
87V-01	53.6	54.7	1.0	1.0	100.0	11178	4C3		0.48	0.24	0.24	10.00		3.03	14.97	18.00	176.0	179.3	3.3		
87V-01	54.7	56.2	1.6	2.0	100.0	11179	4C38		2.41	1.20	1.21	18.00		6.56	10.64	17.20	179.3	184.5	6.4		
87V-01	56.2	57.8	1.6	1.6	100.0	11180	4L24		0.64	0.31	0.33	4.00		6.45	0.39	6.84	184.5	189.7	5.2		
87V-01	57.8	59.5	1.7	1.9	100.0	11181	4L25		0.92	0.58	0.34	6.00		6.15	6.05	12.20	189.7	195.3	6.3		
87V-01	59.5	61.3	1.8	1.9	100.0	11182	4L25		0.35	0.10	0.25	4.00		5.23	6.67	11.90	195.3	201.2	6.2		
87V-01	61.3	63.2	1.9	1.9	100.0	11183	4L25		0.26	0.18	0.08	4.00		9.88	9.92	19.80	201.2	207.3	6.3		

Hole Number: 87V-02

Number of intervals: 32

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TD (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-02	22.9	25.0	2.1	0.9	44.3	11403	464		13.67	6.14	7.53	78.00		2.88	9.92	12.80	75.0	82.0	3.1	
87V-02	25.0	26.5	1.5	1.4	92.0	11404	464		14.35	8.92	5.43	107.00		6.69	13.51	20.20	82.0	87.0	4.6	
87V-02	26.5	28.0	1.5	1.9	100.0	11405	4E6		11.23	6.69	4.54	96.00		6.52	11.88	18.40	87.0	92.0	6.1	
87V-02	28.0	30.2	2.1	2.0	92.9	11406	4E6		7.22	4.27	2.95	50.00		6.51	18.79	25.30	92.0	99.0	6.5	
87V-02	30.2	31.1	0.9	0.6	70.0	11407	464		15.70	9.40	6.30	153.00		0.60	13.60	14.20	99.0	102.0	2.1	
87V-02	31.1	32.1	1.0	0.7	75.0	11408	4E4		8.15	5.67	2.48	63.00		0.67	31.13	31.80	102.0	105.2	2.4	
87V-02	32.1	32.6	0.6	0.6	100.0	11409	464		10.67	5.29	5.38	46.00		5.37	11.63	17.00	105.2	107.1	2.1	
87V-02	32.6	33.0	0.3	0.3	100.0	11410	3C#4		5.68	1.59	4.09	64.00		9.85	3.95	13.80	107.1	108.2	1.1	
87V-02	33.0	33.8	0.9	1.0	100.0	11411	464		10.97	4.89	6.08	47.00		3.84	10.66	14.50	108.2	111.0	3.2	
87V-02	33.8	34.7	0.9	1.5	100.0	11412	464		8.08	3.07	5.01	30.00		1.88	20.12	22.00	111.0	114.0	4.8	
87V-02	34.7	36.0	1.2	1.3	100.0	11413	464		11.41	3.76	7.65	38.00		1.85	24.45	26.30	114.0	118.0	4.2	
87V-02	36.0	36.6	0.6	1.0	100.0	11414	4E0		0.62	0.31	0.31	11.00		0.33	42.47	42.80	118.0	120.0	3.2	
87V-02	36.6	37.4	0.9	1.0	100.0	11415	4E06		4.76	1.78	2.98	23.00		2.71	26.89	29.60	120.0	122.8	3.2	
87V-02	37.4	38.5	1.1	0.8	77.1	11416	464		16.67	7.72	8.95	64.00		4.58	9.22	13.80	122.8	126.3	2.7	
87V-02	38.5	40.1	1.6	2.0	100.0	11417	4E1		2.28	1.22	1.06	28.00		4.64	31.06	35.70	126.3	131.5	6.7	
87V-02	40.1	41.5	1.4	1.6	100.0	11418	4C3		2.97	1.00	1.97	28.00		5.33	22.57	27.90	131.5	136.0	5.1	
87V-02	41.5	42.3	0.8	1.1	100.0	11419	4C3		1.99	0.60	1.39	28.00		5.94	21.06	27.00	136.0	138.7	3.5	
87V-02	42.3	43.3	1.0	1.1	100.0	11420	4C3		3.31	1.60	1.71	36.00		4.96	25.04	30.00	138.7	142.0	3.6	
87V-02	43.3	44.0	0.8	0.8	100.0	11421	4C3		0.78	0.40	0.38	25.00		3.66	27.04	30.70	142.0	144.5	2.7	
87V-02	44.0	45.4	1.4	1.6	100.0	11422	4E1		0.57	0.33	0.24	13.00		1.53	23.97	25.50	144.5	149.0	5.1	
87V-02	45.4	47.0	1.6	1.7	100.0	11423	4E1		0.29	0.19	0.10	11.00		1.53	23.17	24.70	149.0	154.2	5.7	
87V-02	47.0	48.7	1.7	2.0	100.0	11424	4E1		0.42	0.25	0.17	11.00		2.22	19.78	22.00	154.2	159.8	6.4	
87V-02	48.7	50.4	1.7	1.8	100.0	11425	4E1		0.82	0.35	0.47	17.00		3.14	19.26	22.40	159.8	165.5	5.9	
87V-02	50.4	51.8	1.3	1.5	100.0	11426	4D3		4.58	1.32	3.26	17.00		10.90	13.00	23.90	165.5	169.9	4.9	
87V-02	51.8	53.2	1.4	1.4	100.0	11427	4D3		5.91	1.49	4.42	19.00		4.88	19.62	24.50	169.9	174.5	4.6	
87V-02	53.2	53.9	0.7	0.9	100.0	11428	4L24		1.92	0.43	1.49	9.00		23.30	3.90	27.20	174.5	176.9	2.8	
87V-02	53.9	55.5	1.6	1.6	100.0	11429	3608		0.27	0.09	0.18	0.00		5.16	0.52	5.68	176.9	182.0	5.1	
87V-02	55.5	57.0	1.5	1.6	100.0	11430	3608		0.17	0.06	0.11	2.00		4.65	0.85	5.50	182.0	187.0	5.4	
87V-02	57.0	59.0	2.0	2.1	100.0	11431	3608		0.10	0.02	0.08	2.00		4.58	0.98	5.56	187.0	193.6	7.0	
87V-02	59.0	59.9	0.9	1.0	100.0	11432	4C0		0.36	0.08	0.28	6.00		3.36	9.04	12.40	193.6	196.5	3.2	
87V-02	59.9	62.0	2.1	2.1	100.0	11433	4L4		1.37	0.31	1.06	6.00		3.95	2.37	6.32	196.5	203.4	7.0	
87V-02	62.0	62.5	0.5	0.6	100.0	11434	4L124		1.66	0.87	0.79	15.00		5.39	6.51	11.90	203.4	205.0	2.0	

Hole Number: 87V-03

Number of intervals: 29

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TD (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-03	26.2	27.9	1.6	1.7	100.0	11357	4E0#		1.81	0.89	0.92	14.00		19.90	10.70	30.60	86.0	91.4	5.6	
87V-03	27.9	28.9	1.0	1.0	100.0	11358	4G4#		13.09	5.89	7.20	93.00		5.48	8.62	14.10	91.4	94.7	3.4	
87V-03	28.9	30.0	1.2	1.4	100.0	11359	4G4#		25.60	13.80	11.80	152.00		20.00	4.70	24.70	94.7	98.5	4.5	
87V-03	30.0	31.0	1.0	1.3	100.0	11360	4G4B		11.54	4.35	7.19	67.00		7.77	6.63	14.40	98.5	101.7	4.2	
87V-03	31.0	32.1	1.1	1.2	100.0	11361	4G4B		13.35	5.39	7.96	89.00		2.63	11.27	13.90	101.7	105.3	4.0	
87V-03	32.1	33.4	1.3	1.3	100.0	11362	4E4		4.18	1.35	2.83	34.00		0.75	36.25	37.00	105.3	109.5	4.3	
87V-03	33.4	34.2	0.9	0.9	100.0	11363	4E4		7.25	2.13	5.12	53.00		0.69	28.51	29.20	109.5	112.3	3.1	
87V-03	34.2	35.9	1.7	2.0	100.0	11364	4A4#		8.11	2.55	5.56	38.00		1.23	5.90	7.13	112.3	117.8	6.5	
87V-03	35.9	36.6	0.7	0.7	100.0	11365	4E41		5.69	1.88	3.81	34.00		2.48	29.42	31.90	117.8	120.2	2.4	
87V-03	36.6	37.7	1.1	1.3	100.0	11366	4A4#		9.60	3.50	6.10	49.00		1.20	7.04	8.24	120.2	123.7	4.3	
87V-03	37.7	39.1	1.4	1.4	100.0	11367	4A4#		7.52	2.45	5.07	42.00		1.24	14.16	15.40	123.7	128.2	4.5	
87V-03	39.1	40.5	1.5	1.3	87.5	11368	4E0		2.75	0.67	2.08	21.00		0.88	38.62	39.50	128.2	133.0	4.2	
87V-03	40.5	41.4	0.9	1.1	100.0	11369	4G4B		9.47	3.58	5.89	64.00		4.12	9.98	14.10	133.0	135.9	3.6	
87V-03	41.4	42.4	1.0	1.1	100.0	11370	4G4B		12.20	4.26	7.94	66.00		2.98	7.72	10.70	135.9	139.2	3.7	
87V-03	42.4	43.4	1.0	1.1	100.0	11371	4G4B		12.99	5.81	7.18	97.00		3.78	10.82	14.60	139.2	142.5	3.7	
87V-03	43.4	44.5	1.1	1.2	100.0	11372	4G4B		13.30	5.57	7.73	91.00		4.51	7.29	11.80	142.5	146.0	4.1	
87V-03	44.5	45.6	1.1	1.2	100.0	11373	4G4B		15.58	7.78	7.80	114.00		6.78	8.22	15.00	146.0	149.6	3.9	
87V-03	45.6	46.8	1.2	1.3	100.0	11374	4G4B		14.94	6.16	8.78	85.00		1.18	18.22	19.40	149.6	153.6	4.2	
87V-03	46.8	47.8	1.0	1.0	100.0	11375	4D47#		15.53	5.13	10.40	70.00		17.30	4.20	21.50	153.6	156.8	3.3	
87V-03	47.8	49.0	1.2	1.3	100.0	11376	4D47#		8.46	3.05	5.41	38.00		26.00	3.70	29.70	156.8	160.9	4.3	
87V-03	49.0	50.1	1.1	1.0	94.4	11377	4D#		7.35	5.50	1.85	85.00		12.40	11.40	23.80	160.9	164.5	3.4	
87V-03	50.1	51.4	1.3	1.6	100.0	11378	4C3B		1.58	0.81	0.77	15.00		16.60	16.20	32.80	164.5	168.7	5.1	
87V-03	51.4	53.1	1.7	1.7	100.0	11380	4C3B		2.88	1.40	1.48	23.00		12.50	15.10	27.60	168.7	174.2	5.7	
87V-03	53.1	55.0	1.9	1.9	100.0	11379	4C3B		2.31	0.62	1.69	13.00		14.20	17.50	31.70	174.2	180.5	6.3	
87V-03	55.0	56.5	1.5	1.6	100.0	11381	4C3		1.28	0.41	0.87	13.00		11.00	23.00	34.00	180.5	185.5	5.1	
87V-03	56.5	58.0	1.4	1.3	91.5	11382	4C3		0.58	0.17	0.41	9.00		5.26	26.44	31.70	185.5	190.2	4.3	
87V-03	58.0	59.6	1.6	1.6	96.3	11383	4C3		0.47	0.14	0.33	9.00		3.57	23.33	26.90	190.2	195.6	5.2	
87V-03	59.6	61.0	1.4	1.6	100.0	11384	4C3		0.97	0.47	0.50	13.00		3.91	24.39	28.30	195.6	200.1	5.4	
87V-03	61.0	62.8	1.8	1.8	100.0	11385	4C3		0.83	0.37	0.46	11.00		4.20	22.90	27.10	200.1	206.0	5.9	

Hole Number: 87V-04

Number of intervals: 40

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-04	32.5	34.5	2.1	1.7	80.9	11014	4EGH		16.06	8.74	7.32	110.00		15.30	10.60	25.90	106.5	113.3	5.5	
87V-04	34.5	36.0	1.5	1.5	100.0	11015	4E08		1.45	0.72	0.73	17.00		7.52	34.68	42.20	113.3	118.1	5.0	
87V-04	36.0	37.2	1.2	1.1	92.3	11016	4E48		11.72	5.04	6.68	75.00		5.45	13.35	18.80	118.1	122.0	3.6	*
87V-04	37.2	38.2	1.0	1.3	100.0	11017	4E48		11.78	5.09	6.69	62.00		4.65	11.05	15.70	122.0	125.4	4.2	*
87V-04	38.2	39.5	1.3	1.3	100.0	11018	4G48		11.05	5.62	5.43	62.00		5.11	14.09	19.20	125.4	129.6	4.2	
87V-04	39.5	40.2	0.7	0.8	100.0	11019	4E4		11.41	4.49	6.92	31.00		0.32	37.88	38.20	129.6	132.0	2.6	
87V-04	40.2	41.8	1.6	1.7	100.0	11020	4G4		12.37	4.98	7.39	72.00		2.01	12.59	14.60	132.0	137.2	5.6	
87V-04	41.8	43.3	1.5	1.6	100.0	11021	4E48		11.40	3.38	8.02	60.00		0.84	25.16	26.00	137.2	142.2	5.3	
87V-04	43.3	44.7	1.4	1.1	77.8	11022	4E48		11.53	3.31	8.22	46.00		3.56	16.34	19.90	142.2	146.7	3.5	
87V-04	44.7	45.9	1.2	1.2	100.0	11023	4E4*		19.28	9.43	9.85	103.00		6.21	20.99	27.20	146.7	150.5	4.1	
87V-04	45.9	47.4	1.6	1.6	100.0	11024	4E4		6.92	3.44	3.48	50.00		8.14	28.46	36.60	150.5	155.6	5.3	
87V-04	47.4	48.8	1.4	1.5	100.0	11025	3C*		1.86	0.67	1.19	15.00		12.40	9.60	22.00	155.6	160.1	5.0	
87V-04	48.8	49.9	1.1	1.1	100.0	11026	4E48		5.60	2.71	2.89	37.00		8.20	30.40	38.60	160.1	163.7	3.6	
87V-04	49.9	52.1	2.2	0.6	27.4	11027	4G48		13.83	6.50	7.33	75.00		2.81	15.09	17.90	163.7	171.0	2.0	
87V-04	52.1	53.6	1.5	1.7	100.0	11028	4G48		11.60	4.58	7.02	60.00		2.73	8.97	11.70	171.0	176.0	5.7	
87V-04	53.6	54.0	0.4	0.5	100.0	11029	4E4		12.58	5.98	6.60	56.00		3.83	28.57	32.40	176.0	177.3	1.6	
87V-04	54.0	55.2	1.1	1.2	100.0	11030	4E1		0.76	0.30	0.46	10.00		5.78	33.62	39.40	177.3	181.0	3.9	
87V-04	55.2	56.3	1.1	1.3	100.0	11031	4E1		1.77	1.58	0.19	18.00		7.83	27.27	35.10	181.0	184.7	4.3	
87V-04	56.3	57.8	1.5	1.5	100.0	11032	4C38		0.40	0.26	0.14	4.00		2.05	27.55	29.60	184.7	189.5	5.0	
87V-04	57.8	58.5	0.8	0.9	100.0	11033	4E08		3.94	2.07	1.87	14.00		9.18	21.72	30.90	189.5	192.0	3.0	
87V-04	58.5	59.9	1.4	1.6	100.0	11034	4E0#8		4.01	1.88	2.13	18.00		2.00	27.90	29.90	192.0	196.5	5.2	
87V-04	59.9	61.4	1.6	0.8	49.0	11035	4E4#8		9.37	7.53	1.84	83.00		11.70	21.90	33.60	196.5	201.6	2.5	
87V-04	61.4	62.8	1.3	1.3	95.5	11036	4C3		0.29	0.16	0.13	6.00		2.23	26.17	28.40	201.6	206.0	4.2	
87V-04	62.8	63.9	1.1	1.2	100.0	11037	4C3		0.96	0.77	0.19	22.00		2.10	31.10	33.20	206.0	209.7	4.0	
87V-04	63.9	64.9	1.0	1.2	100.0	11038	4C3		0.35	0.19	0.16	10.00		2.42	21.88	24.30	209.7	213.0	3.9	
87V-04	64.9	66.8	1.8	2.2	100.0	11039	4A3		0.49	0.20	0.29	10.00		3.35	17.55	20.90	213.0	219.0	7.2	
87V-04	66.8	68.3	1.6	1.5	98.0	11040	4A3		1.07	0.36	0.71	10.00		1.41	17.39	18.80	219.0	224.1	5.0	
87V-04	68.3	69.8	1.5	1.8	100.0	11041	4C3		1.89	0.34	1.55	12.00		3.76	15.54	19.30	224.1	229.1	5.9	
87V-04	69.8	70.2	0.3	0.3	100.0	11042	3C3		1.70	1.43	0.27	18.00		6.94	1.48	8.42	229.1	230.2	1.1	
87V-04	70.2	71.6	1.4	1.5	100.0	11043	4C3		0.60	0.26	0.34	12.00		2.53	23.97	26.50	230.2	234.8	5.0	
87V-04	71.6	73.1	1.5	1.5	100.0	11044	4C3		0.63	0.19	0.44	12.00		1.55	25.25	26.80	234.8	239.8	5.0	
87V-04	73.1	74.3	1.2	1.5	100.0	11045	4C3		0.33	0.20	0.13	10.00		1.60	24.70	26.30	239.8	243.8	4.8	
87V-04	74.3	75.7	1.4	1.5	100.0	11046	4C3		0.30	0.13	0.17	10.00		1.36	21.34	22.70	243.8	248.5	4.8	
87V-04	75.7	77.2	1.5	1.5	100.0	11047	4C3		0.23	0.10	0.13	10.00		2.75	26.35	29.10	248.5	253.3	5.0	
87V-04	77.2	78.7	1.5	1.5	100.0	11048	4C3		0.78	0.25	0.53	20.00		2.92	28.58	31.50	253.3	258.1	5.0	
87V-04	78.7	80.1	1.4	1.5	100.0	11049	4C3		0.41	0.18	0.23	14.00		4.26	29.94	34.20	258.1	262.7	5.0	
87V-04	80.1	81.4	1.4	1.5	100.0	11050	4C3		0.81	0.20	0.61	12.00		2.90	23.80	26.70	262.7	267.2	5.0	
87V-04	81.4	83.1	1.6	1.5	94.3	11051	4C3		6.98	3.24	3.74	52.00		8.28	21.72	30.00	267.2	272.5	5.0	
87V-04	83.1	84.3	1.3	1.5	100.0	11052	4C3		0.90	0.40	0.50	22.00		1.75	37.15	38.90	272.5	276.7	5.0	
87V-04	84.3	85.6	1.3	1.5	100.0	11053	4C3		1.52	0.50	1.02	25.00		4.26	22.34	26.60	276.7	281.0	5.0	

Hole Number: 87V-05

Number of intervals: 52

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/ton)	Au (g/ton)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY	MISSING SAMP
87V-05	24.6	25.3	0.7	0.7	100.0	11451	4H4*		12.70	9.62	3.08	95.00		3.06	31.54	34.60	80.8	83.0	2.3		
87V-05	25.3	26.6	1.3	1.4	100.0	11452	4G4B*		20.70	10.00	10.70	156.00		4.03	14.07	18.10	83.0	87.2	4.5		
87V-05	26.6	27.5	0.9	1.0	100.0	11453	4G4B*		11.50	5.72	5.78	89.00		11.80	11.70	23.50	87.2	90.1	3.4		
87V-05	27.5	28.3	0.9	1.1	100.0	11454	4G4B*		5.50	2.83	2.67	46.00		29.40	7.40	36.80	90.1	92.9	3.7		
87V-05	28.3	29.7	1.4	1.4	100.0	11455	4G4*		11.73	4.87	6.86	78.00		21.60	-5.60	16.00	92.9	97.5	4.6	*	
87V-05	29.7	31.0	1.3	1.4	100.0	11456	4G4*		2.95	1.20	1.75	26.00	0.00	8.04	26.56	34.60	97.5	101.7	4.7		
87V-05	31.0	32.4	1.4	1.4	100.0	11457	4G4*		6.47	3.14	3.33	46.00		7.39	22.01	29.40	101.7	106.4	4.7		
87V-05	32.4	33.3	0.9	0.9	100.0	11458	4E4*		1.58	0.67	0.91	15.00		12.30	28.90	41.20	106.4	109.4	3.0		
87V-05	33.3	34.3	0.9	1.0	100.0	11459	4E4*		3.46	1.64	1.82	30.00		10.60	27.20	37.80	109.4	112.4	3.4		
87V-05	34.3	35.7	1.4	1.4	97.9	11435	4G4*		12.85	5.17	7.68	83.00		1.50	16.10	17.60	112.4	117.1	4.6		
87V-05	35.7	36.9	1.2	1.4	100.0	11436	4G4*		13.72	4.88	8.84	83.00		0.88	14.42	15.30	117.1	121.0	4.5		
87V-05	36.9	38.2	1.3	1.3	100.0	11437	4G4*		12.43	5.33	7.10	87.00		2.08	19.52	21.60	121.0	125.4	4.4		
87V-05	38.2	39.5	1.3	1.4	100.0	11438	4G4*		10.62	4.55	6.07	66.00		5.30	21.60	26.90	125.4	129.7	4.6		
87V-05	39.5	40.9	1.3	1.6	100.0	11439	4G4*		12.18	4.93	7.25	81.00		4.24	12.86	17.10	129.7	134.1	5.2		
87V-05	40.9	42.2	1.3	1.3	100.0	11440	4A4*		4.53	1.87	2.66	29.00		1.70	11.10	12.80	134.1	138.5	4.4		
87V-05	42.2	43.4	1.2	1.2	100.0	11441	4E0*		7.07	2.58	4.49	64.00		1.02	31.88	32.90	138.5	142.5	4.0		
87V-05	43.4	44.7	1.3	1.4	100.0	11442	4E0*		11.29	3.76	7.53	84.00		1.14	30.76	31.90	142.5	146.8	4.7		
87V-05	44.7	45.5	0.8	1.1	100.0	11443	4A4*		7.36	2.56	4.80	42.00		1.24	12.66	13.90	146.8	149.4	3.6		
87V-05	45.5	46.5	1.0	1.0	100.0	11444	4E0*		2.10	0.59	1.51	17.00		1.32	34.88	36.20	149.4	152.7	3.3		
87V-05	46.5	47.7	1.1	1.5	100.0	11445	4G4B		13.70	4.95	8.75	76.00		4.12	5.73	9.85	152.7	156.4	4.9		
87V-05	47.7	49.1	1.4	1.6	100.0	11446	4G4B		13.77	5.73	8.04	93.00		5.49	8.21	13.70	156.4	161.0	5.3		
87V-05	49.1	50.2	1.2	1.2	100.0	11447	4G4B		13.29	6.18	7.11	103.00		3.64	7.46	11.10	161.0	164.8	3.8		
87V-05	50.2	51.9	1.6	1.8	100.0	11448	3C0*		4.50	2.06	2.44	32.00		5.72	2.88	8.60	164.8	170.2	5.9		
87V-05	51.9	53.0	1.2	1.2	100.0	11449	4G4B*		15.18	7.15	8.03	104.00		7.39	7.71	15.10	170.2	174.0	4.0		
87V-05	53.0	54.3	1.2	1.3	100.0	11450	3C*		0.85	0.26	0.59	7.00		6.46	0.30	6.76	174.0	178.0	4.2		
87V-05	54.3	55.0	0.8	1.0	100.0	11481	4H4B		8.33	3.07	5.26	46.00		22.30	5.40	27.70	178.0	180.5	3.2		
87V-05	55.0	56.0	0.9	0.8	83.9	11482	4E41		5.38	2.65	2.73	33.00		11.30	18.60	29.90	180.5	183.6	2.6		
87V-05	56.0	57.3	1.3	1.4	100.0	11483	4D3*		4.50	2.90	1.60	43.00		11.90	14.40	26.30	183.6	187.9	4.5		
87V-05	57.3	58.5	1.2	1.4	100.0	11484	4D3*		4.36	1.97	2.39	29.00		11.20	16.00	27.20	187.9	192.0	4.6		
87V-05	58.5	59.8	1.3	1.3	100.0	11485	4D3*		1.96	0.82	1.14	15.00		8.63	20.67	29.30	192.0	196.3	4.4		
87V-05	59.8	61.3	1.4	1.5	100.0	11486	4D3*		0.00						0.00		196.3	201.0	4.8		*
87V-05	61.3	62.8	1.6	1.7	100.0	11460	4C0B		0.47	0.13	0.34	4.00		8.25	12.15	20.40	201.0	206.1	5.6		
87V-05	62.8	64.3	1.5	1.7	100.0	11461	4E1B		1.56	0.52	1.04	11.00		10.70	20.40	31.10	206.1	211.0	5.6		
87V-05	64.3	65.7	1.4	1.5	100.0	11462	4E1B		0.74	0.17	0.57	11.00		7.31	23.29	30.60	211.0	215.5	4.8		
87V-05	65.7	67.1	1.5	1.5	100.0	11463	4E1B		0.76	0.23	0.53	9.00		7.98	18.22	26.20	215.5	220.3	4.8		
87V-05	67.1	68.6	1.4	1.4	100.0	11464	4E1B		0.83	0.24	0.59	9.00		9.73	17.47	27.20	220.3	225.0	4.7		
87V-05	68.6	69.9	1.3	1.4	100.0	11465	4E1B		0.74	0.32	0.42	9.00		6.66	24.64	31.30	225.0	229.4	4.6		
87V-05	69.9	71.4	1.5	1.5	100.0	11466	4E1B		0.37	0.18	0.19	9.00		8.25	24.15	32.40	229.4	234.4	5.0		
87V-05	71.4	72.8	1.3	1.4	100.0	11467	4E1B		0.91	0.29	0.62	9.00		11.40	24.40	35.80	234.4	238.7	4.6		
87V-05	72.8	74.4	1.6	1.6	98.1	11468	4E1B		2.32	0.65	1.67	15.00		13.70	17.80	31.50	238.7	244.0	5.2		
87V-05	74.4	74.6	0.3	0.3	100.0	11469	4E44		17.22	5.62	11.60	45.00		24.20	7.80	32.00	244.0	244.9	1.0		
87V-05	74.6	75.8	1.2	1.4	100.0	11470	4C3B		1.25	0.62	0.63	9.00		13.60	13.10	26.70	244.9	248.8	4.6		
87V-05	75.8	77.2	1.3	1.4	100.0	11471	4C3B		1.18	0.38	0.80	8.00		12.30	19.00	31.30	248.8	253.2	4.5		
87V-05	77.2	78.4	1.2	1.3	100.0	11472	4C3B		1.77	0.49	1.28	9.00		11.20	20.30	31.50	253.2	257.1	4.4		
87V-05	78.4	79.8	1.4	1.4	97.8	11473	4C3B		1.45	0.43	1.02	8.00		12.20	17.10	29.30	257.1	261.7	4.5		
87V-05	79.8	81.2	1.4	1.5	100.0	11474	4C3B		1.06	0.40	0.66	8.00		9.20	16.90	26.10	261.7	266.4	4.9		
87V-05	81.2	82.8	1.6	1.8	100.0	11475	4C3B		2.36	1.21	1.15	14.00		12.30	11.80	24.10	266.4	271.7	5.8		
87V-05	82.8	84.5	1.6	1.7	100.0	11476	4C3B		0.70	0.42	0.28	6.00		6.52	14.68	21.20	271.7	277.1	5.6		
87V-05	84.5	86.0	1.6	1.6	100.0	11477	4C3B		1.03	0.51	0.52	10.00		5.66	14.24	19.90	277.1	282.3	5.4		

Hole Number: 87V-05

Number of intervals: 52

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-05	86.0	87.3	1.3	1.0	76.2	11478	4C08		2.09	1.36	0.73	10.00		8.81	6.39	15.20	282.3	286.5	3.2	
87V-05	87.3	88.4	1.0	1.3	100.0	11479	4C08		1.66	0.93	0.73	10.00		6.20	6.60	12.80	286.5	289.9	4.4	
87V-05	88.4	89.6	1.3	1.3	100.0	11480	4C08		0.40	0.13	0.27	4.00		3.74	6.20	9.94	289.9	294.1	4.3	

Hole Number: 87V-06

Number of intervals: 41

DDHID	FROM (m)	TD (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/ton)	Au (g/ton)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-06	36.9	37.5	0.6	0.3	50.0	11054	#?		11.46	4.56	6.90	84.00		1.92	8.78	10.70	121.0	123.0	1.0	
87V-06	37.5	38.6	1.1	1.5	100.0	11055	4E4		17.34	8.53	8.81	128.00		1.78	25.62	27.40	123.0	126.5	5.0	
87V-06	38.6	39.6	1.1	1.2	100.0	11094	4E4		8.91	3.48	5.43	73.00		0.94	34.76	35.70	126.5	130.0	4.0	
87V-06	39.6	40.9	1.3	1.4	100.0	11056	4L2		3.04	1.36	1.68	27.00		2.63	10.47	13.10	130.0	134.2	4.6	
87V-06	40.9	42.1	1.2	1.3	100.0	11057	4E4		8.27	5.07	3.20	73.00		2.06	34.44	36.50	134.2	138.0	4.2	
87V-06	42.1	43.0	1.0	1.2	100.0	11058	4E4		14.62	7.16	7.46	117.00		2.23	23.37	25.60	138.0	141.2	3.9	
87V-06	43.0	43.7	0.6	1.1	100.0	11059	4H42#		10.70	4.58	6.12	65.00		14.90	13.70	28.60	141.2	143.3	3.5	
87V-06	43.7	45.2	1.5	1.5	98.0	11060	4G48#		13.31	4.99	8.32	77.00		2.70	14.60	17.30	143.3	148.2	4.8	
87V-06	45.2	46.6	1.4	1.2	85.1	11061	4G48#		11.52	4.94	6.58	63.00		3.69	11.01	14.70	148.2	152.9	4.0	
87V-06	46.6	47.7	1.1	1.1	97.3	11062	4E0		2.67	1.29	1.38	12.00		2.38	38.42	40.80	152.9	156.6	3.6	
87V-06	47.7	49.5	1.8	1.6	93.1	11063	4G48		13.12	4.92	8.20	85.00		2.28	16.72	19.00	156.6	162.4	5.4	
87V-06	49.5	50.9	1.4	1.5	100.0	11064	4G48		13.70	5.79	7.91	79.00		2.59	16.71	19.30	162.4	167.0	5.0	
87V-06	50.9	51.8	0.9	1.3	100.0	11065	4E48		6.40	2.69	3.71	36.00		10.20	30.60	40.80	167.0	170.0	4.3	
87V-06	51.8	53.0	1.2	1.2	100.0	11066	4E48		6.61	3.69	2.92	51.00		9.30	30.60	39.90	170.0	173.8	3.9	
87V-06	53.0	54.1	1.1	1.3	100.0	11067	4E48		5.36	2.71	2.65	44.00		12.80	28.30	41.10	173.8	177.5	4.2	
87V-06	54.1	55.3	1.2	1.2	100.0	11068	4E17B		4.14	2.07	2.07	34.00		9.74	26.76	36.50	177.5	181.3	4.1	
87V-06	55.3	55.9	0.6	0.7	100.0	11069	3B2		1.99	0.70	1.29	40.00		9.58	18.22	27.80	181.3	183.4	2.4	
87V-06	55.9	57.2	1.2	1.3	100.0	11070	4E4		5.48	2.62	2.86	44.00		5.20	32.70	37.90	183.4	187.5	4.4	
87V-06	57.2	59.4	2.3	1.6	68.0	11071	4E4		10.48	5.60	4.88	59.00		6.70	31.60	38.30	187.5	195.0	5.1	
87V-06	59.4	61.5	2.0	1.1	53.7	11072	4G48		11.34	4.53	6.81	65.00		2.72	7.98	10.70	195.0	201.7	3.6	
87V-06	61.5	63.5	2.0	0.9	45.5	11073	4E41#		7.01	3.34	3.67	34.00		6.17	27.73	33.90	201.7	208.3	3.0	
87V-06	63.5	65.2	1.7	1.8	100.0	11074	4E10B		1.07	0.39	0.68	8.00		2.58	33.92	36.50	208.3	214.0	6.0	
87V-06	65.2	66.4	1.2	1.3	100.0	11075	4G48#		12.28	8.00	4.28	51.00		3.52	21.68	25.20	214.0	217.8	4.3	
87V-06	66.4	67.4	1.0	0.9	88.2	11076	4G48#		7.55	4.76	2.79	45.00		16.10	12.70	28.80	217.8	221.2	3.0	
87V-06	67.4	68.6	1.2	1.2	100.0	11077	4E48#		5.41	3.87	1.54	53.00		13.80	23.40	37.20	221.2	225.0	4.0	
87V-06	68.6	70.0	1.4	1.7	100.0	11078	4C39		0.75	0.44	0.31	20.00		2.24	27.46	29.70	225.0	229.7	5.5	
87V-06	70.0	71.5	1.5	1.7	100.0	11079	4C39		0.20	0.10	0.10	8.00		1.73	22.77	24.50	229.7	234.6	5.7	
87V-06	71.5	73.3	1.8	1.7	94.9	11080	4C39		0.32	0.15	0.17	14.00		2.09	32.91	35.00	234.6	240.5	5.6	
87V-06	73.3	74.7	1.4	1.5	100.0	11081	4A3		0.20	0.10	0.10	6.00		1.68	19.72	21.40	240.5	245.0	4.8	
87V-06	74.7	76.5	1.8	1.6	88.3	11082	4A3		0.53	0.25	0.28	20.00		1.21	18.79	20.00	245.0	251.0	5.3	
87V-06	76.5	77.7	1.2	1.5	100.0	11083	4A3		0.77	0.20	0.57	16.00		1.77	12.83	14.60	251.0	254.8	5.0	
87V-06	77.7	79.2	1.6	1.7	100.0	11084	4C0		0.45	0.15	0.30	8.00		1.73	7.61	9.34	254.8	260.0	5.6	
87V-06	79.2	80.1	0.9	1.1	100.0	11085	3B43#		0.69	0.13	0.56	4.00		4.92	25.38	30.30	260.0	262.8	3.5	
87V-06	80.1	81.0	0.9	1.4	100.0	11086	4C8#		0.49	0.14	0.35	12.00		2.93	3.86	6.79	262.8	265.9	4.5	
87V-06	81.0	82.4	1.3	1.5	100.0	11087	4C8#		2.24	0.75	1.49	16.00		6.64	22.86	29.50	265.9	270.2	5.0	
87V-06	82.4	83.8	1.4	1.6	100.0	11088	4C8#		1.78	0.60	1.18	10.00		6.18	17.42	23.60	270.2	274.8	5.1	
87V-06	83.8	85.0	1.3	1.5	100.0	11089	4C8#		2.78	0.76	2.02	14.00		10.00	16.40	26.40	274.8	279.0	4.8	
87V-06	85.0	86.4	1.3	1.4	100.0	11090	4C8#		1.62	0.46	1.16	12.00		4.97	20.13	25.10	279.0	283.4	4.7	
87V-06	86.4	87.8	1.4	1.4	97.8	11091	4L0		0.22	0.04	0.18	2.00		3.54	1.87	5.41	283.4	288.0	4.5	
87V-06	87.8	89.3	1.5	1.7	100.0	11092	4C8		1.54	0.68	0.86	31.00		2.48	24.02	26.50	288.0	293.0	5.5	
87V-06	89.3	91.0	1.6	1.8	100.0	11093	4C8		1.43	0.60	0.83	30.00		4.37	23.93	28.30	293.0	298.4	6.0	

Hole Number: 87V-07

Number of intervals: 56

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-07	15.3	16.8	1.5	1.8	100.0	11301	4E48		1.56	0.72	0.84	17		16.80	26.50	43.30	50.2	55.1	5.8	
87V-07	16.8	18.6	1.8	1.9	100.0	11302	4E48		2.35	1.14	1.21	19		12.30	29.80	42.10	55.1	61.0	6.1	
87V-07	18.6	20.4	1.8	1.7	96.6	11303	4E48		3.55	1.94	1.61	34		7.74	28.96	36.70	61.0	66.9	5.7	
87V-07	20.4	21.8	1.4	1.4	100.0	11304	4E48		5.93	3.30	2.63	42		10.80	24.80	35.60	66.9	71.5	4.6	
87V-07	21.8	22.7	0.9	1.1	100.0	11305	4G4		12.54	5.10	7.44	77		1.89	9.51	11.40	71.5	74.5	3.7	
87V-07	22.7	24.2	1.5	1.3	86.0	11306	4G4		14.08	5.96	8.12	93		1.13	15.07	16.20	74.5	79.5	4.3	
87V-07	24.2	25.8	1.5	1.6	100.0	11307	4E468		9.28	3.57	5.71	60		2.54	22.86	25.40	79.5	84.5	5.1	
87V-07	25.8	27.0	1.2	1.5	100.0	11308	4E468		9.23	4.33	4.90	71		5.47	24.33	29.80	84.5	88.5	4.9	
87V-07	27.0	28.0	1.1	1.4	100.0	11309	4E468		12.98	5.42	7.56	77		2.94	15.96	18.90	88.5	92.0	4.7	
87V-07	28.0	29.7	1.7	1.7	100.0	11310	4A4		5.42	1.84	3.58	22		2.82	3.95	6.77	92.0	97.5	5.5	
87V-07	29.7	31.2	1.5	1.8	100.0	11311	4A4		3.74	1.28	2.46	18		3.88	2.06	5.94	97.5	102.5	5.8	
87V-07	31.2	32.7	1.4	1.7	100.0	11312	3G48		0.20	0.03	0.17	2		3.41	1.19	4.60	102.5	107.2	5.6	
87V-07	32.7	33.8	1.2	1.4	100.0	11313	4A4		5.60	2.07	3.53	34		4.88	1.38	6.26	107.2	111.0	4.5	
87V-07	33.8	35.8	2.0	1.5	75.4	11314	4A4		4.58	1.82	2.76	28		3.36	0.89	4.25	111.0	117.5	4.9	
87V-07	35.8	36.3	0.5	0.5	100.0	11315	3B3		0.60	0.08	0.52	4		7.26	0.63	7.89	117.5	119.2	1.8	
87V-07	36.3	38.1	1.7	1.9	100.0	11316	4A0		4.40	1.49	2.91	28		4.33	2.36	6.69	119.2	124.9	6.3	
87V-07	38.1	39.6	1.6	1.8	100.0	11317	3G08		0.20	0.04	0.16	2		3.20	1.25	4.45	124.9	130.0	5.8	
87V-07	39.6	41.3	1.7	1.8	100.0	11318	3G08		0.20	0.04	0.16	2		3.29	0.35	3.64	130.0	135.5	5.8	
87V-07	41.3	42.5	1.2	1.4	100.0	11319	4A4		5.23	2.70	2.53	32		2.26	2.11	4.37	135.5	139.4	4.6	
87V-07	42.5	44.0	1.5	1.6	100.0	11320	4A4		4.79	1.62	3.17	26		2.98	4.03	7.01	139.4	144.3	5.1	
87V-07	44.0	44.3	0.3	0.4	100.0	11321	3B4		0.14	0.03	0.11	2		3.20	4.41	7.61	144.3	145.3	1.2	
87V-07	44.3	45.9	1.6	1.7	100.0	11322	4E0		11.44	4.14	7.30	67		1.08	15.02	16.10	145.3	150.5	5.7	
87V-07	45.9	47.5	1.6	1.8	100.0	11323	4E0		4.62	1.42	3.20	32		0.91	26.29	27.20	150.5	155.9	5.8	
87V-07	47.5	49.4	1.9	1.9	100.0	11324	4B48		12.68	4.77	7.91	83		2.83	10.57	13.40	155.9	162.0	6.3	
87V-07	49.4	50.2	0.8	0.8	100.0	11325	3B3		0.23	0.03	0.20	4		5.56	0.59	6.15	162.0	164.7	2.7	
87V-07	50.2	51.9	1.7	1.7	100.0	11326	4B48		15.06	7.70	7.36	105		9.51	8.89	18.40	164.7	170.3	5.7	
87V-07	51.9	53.4	1.5	1.5	98.0	11327	3C4G		7.97	3.96	4.01	53		12.40	4.40	16.80	170.3	175.3	4.9	
87V-07	53.4	55.0	1.6	1.6	100.0	11328	4H431		6.40	3.71	2.69	55		25.90	7.80	33.70	175.3	180.5	5.2	
87V-07	55.0	56.6	1.6	1.7	100.0	11329	4E18		1.85	1.01	0.84	24		9.64	27.96	37.60	180.5	185.8	5.5	
87V-07	56.6	58.2	1.6	1.5	98.0	11330	4E18		0.84	0.33	0.51	14		6.50	30.40	36.90	185.8	190.9	5.0	
87V-07	58.2	59.6	1.4	1.5	100.0	11331	4C83		4.36	2.36	2.00	32		11.60	15.50	27.10	190.9	195.6	5.0	
87V-07	59.6	61.0	1.4	1.5	100.0	11332	4C83		3.18	1.50	1.68	22		13.60	15.50	29.10	195.6	200.2	4.9	
87V-07	61.0	62.4	1.3	1.5	100.0	11333	4C83		3.84	2.31	1.53	28		19.60	14.40	34.00	200.2	204.6	4.9	
87V-07	62.4	63.8	1.4	1.5	100.0	11334	4C83		2.73	1.73	1.00	28		21.00	10.10	31.10	204.6	209.2	5.0	
87V-07	63.8	65.2	1.5	1.5	100.0	11335	4C7		2.50	1.51	0.99	22		28.00	3.40	31.40	209.2	214.0	5.0	
87V-07	65.2	66.7	1.5	1.7	100.0	11336	4C7		1.39	0.56	0.83	11		25.60	5.40	31.00	214.0	218.8	5.6	
87V-07	66.7	68.2	1.5	1.6	100.0	11337	4C8		1.03	0.50	0.53	22		18.90	8.50	27.40	218.8	223.7	5.1	
87V-07	68.2	69.8	1.6	1.6	96.2	11338	4C8		0.71	0.26	0.45	8		12.00	10.20	22.20	223.7	229.0	5.1	
87V-07	69.8	71.2	1.4	1.6	100.0	11339	4C8		1.36	0.74	0.62	14		15.70	13.30	29.00	229.0	233.6	5.1	
87V-07	71.2	72.6	1.4	1.5	100.0	11340	4C8		3.93	1.96	1.97	26		18.10	12.10	30.20	233.6	238.2	5.0	
87V-07	72.6	74.1	1.5	1.6	100.0	11341	4C8		4.38	1.35	3.03	20		15.00	19.30	34.30	238.2	243.0	5.1	
87V-07	74.1	75.1	1.0	1.2	100.0	11342	4C8		0.66	0.24	0.42	10		11.60	19.30	30.90	243.0	246.4	3.9	
87V-07	75.1	76.2	1.1	1.2	100.0	11343	4C8		1.51	0.55	0.96	10		8.33	22.07	30.40	246.4	250.1	4.0	
87V-07	76.2	77.3	1.1	1.1	100.0	11344	4C8		0.85	0.40	0.45	10		7.53	17.87	25.40	250.1	253.7	3.6	
87V-07	77.3	78.8	1.5	1.6	100.0	11345	4C8		4.81	4.03	0.78	38		7.59	15.41	23.00	253.7	258.6	5.2	
87V-07	78.8	80.2	1.4	1.6	100.0	11346	4C8		4.72	3.87	0.85	36		6.31	12.39	18.70	258.6	263.2	5.3	
87V-07	80.2	81.7	1.5	1.7	100.0	11347	4C8		2.76	1.16	1.60	12		17.50	15.00	32.50	263.2	268.1	5.5	
87V-07	81.7	83.2	1.5	1.6	100.0	11348	4C8		1.80	0.72	1.08	9		17.00	11.30	28.30	268.1	273.1	5.2	
87V-07	83.2	84.6	1.4	1.6	100.0	11349	4C8		6.20	3.25	2.95	30		15.80	11.50	27.30	273.1	277.7	5.1	

Hole Number: 87V-07

Number of intervals: 56

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-07	84.6	86.0	1.3	1.3	100.0	11350	4C8		0.64	0.48	0.16	6		4.62	12.98	17.60	277.7	282.0	4.3	
87V-07	86.0	87.1	1.2	1.2	100.0	11351	4C8		1.65	0.84	0.81	13		10.40	14.20	24.60	282.0	285.9	3.9	
87V-07	87.1	88.3	1.2	1.3	100.0	11352	4C8		1.28	0.59	0.69	9		9.44	15.86	25.30	285.9	289.8	4.3	
87V-07	88.3	90.0	1.7	1.8	100.0	11353	4C0#		0.78	0.55	0.23	9		3.58	13.22	16.80	289.8	295.3	6.0	
87V-07	90.0	91.7	1.7	1.8	100.0	11354	4L624		0.64	0.25	0.39	6		4.09	5.57	9.66	295.3	301.0	5.9	
87V-07	91.7	93.3	1.6	1.7	100.0	11355	4L624		0.49	0.19	0.30	6		4.00	4.88	8.88	301.0	306.1	5.5	
87V-07	93.3	95.0	1.7	1.7	100.0	11356	4L624		0.07	0.01	0.06	2		4.70	5.40	10.10	306.1	311.6	5.6	

Hole Number: 87V-08

Number of intervals: 54

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY	MISSING	SAMP
87V-08	21.5	22.2	0.7	0.7	100.0	11246	4A4		11.90	5.18	6.72	97		0.72	6.97	7.69	70.6	72.9	2.3			
87V-08	22.2	23.7	1.4	1.6	100.0	11247	4E4		16.45	6.45	10.00	75		0.48	32.12	32.60	72.9	77.6	5.2			
87V-08	23.7	25.1	1.4	1.5	100.0	11248	4E4		16.25	7.75	8.50	79		0.52	33.18	33.70	77.6	82.3	5.0			
87V-08	25.1	26.0	0.9	1.1	100.0	11249	4E4		18.47	8.47	10.00	109		0.54	30.36	30.90	82.3	85.4	3.7			
87V-08	26.0	26.5	0.5	0.5	100.0	11250	4DL		13.50	6.24	7.26	101		0.57	15.33	15.90	85.4	87.0	1.7			
87V-08	26.5	27.3	0.8	0.9	100.0	11251	4E4		19.81	8.91	10.90	138		0.51	30.69	31.20	87.0	89.7	3.0			
87V-08	27.3	28.5	1.2	1.3	100.0	11252	4E4		22.40	10.50	11.90	85		0.68	29.72	30.40	89.7	93.6	4.3			
87V-08	28.5	29.4	0.9	1.0	100.0	11253	4E4		17.98	8.04	9.94	117		1.02	30.18	31.20	93.6	96.4	3.4			
87V-08	29.4	31.5	2.1	2.0	92.8	11254	4A4		4.99	1.86	3.13	28		1.29	14.91	16.20	96.4	103.3	6.4			
87V-08	31.5	33.0	1.5	2.0	100.0	11255	4A4		3.71	1.45	2.26	22		1.32	12.08	13.40	103.3	108.3	6.4			
87V-08	33.0	34.1	1.1	1.2	100.0	11256	4E4		12.09	5.28	6.81	75		0.79	34.11	34.90	108.3	112.0	4.1			
87V-08	34.1	35.2	1.1	1.2	100.0	11257	4E4		13.70	5.56	8.14	73		1.31	32.49	33.80	112.0	115.5	3.8			
87V-08	35.2	36.2	1.0	1.2	100.0	11258	4E4		11.67	4.90	6.77	71		6.13	28.17	34.30	115.5	118.9	3.9			
87V-08	36.2	37.9	1.7	1.9	100.0	11259	4A4		8.43	3.37	5.06	42		4.79	9.01	13.80	118.9	124.5	6.1			
87V-08	37.9	39.1	1.2	1.5	100.0	11260	3G06		6.00	1.92	4.08	28		6.17	3.36	9.53	124.5	128.4	4.8			
87V-08	39.1	40.6	1.5	1.5	100.0	11261	3G06		2.10	0.65	1.45	12		3.59	1.91	5.50	128.4	133.2	4.8			
87V-08	40.6	41.4	0.8	1.2	100.0	11262	4E4		8.76	3.54	5.22	61	0.00	3.86	22.14	26.00	133.2	135.8	3.8			
87V-08	41.4	42.8	1.4	1.5	100.0	11263	4G48		13.53	4.60	8.93	79		1.89	8.61	10.50	135.8	140.3	4.9			
87V-08	42.8	43.2	0.5	0.5	100.0	11264	3G046		2.59	1.32	1.27	20		8.13	1.87	10.00	140.3	141.8	1.8			
87V-08	43.2	44.6	1.4	1.3	97.8	11265	4H47#		16.20	7.46	8.74	89		9.19	11.11	20.30	141.8	146.3	4.4			
87V-08	44.6	46.7	2.1	2.3	100.0	11266	4E48		7.38	3.93	3.45	59		9.95	23.55	33.50	146.3	153.3	7.4			
87V-08	46.7	47.6	0.9	1.0	100.0	11267	4G48#		14.68	5.87	8.81	89		3.69	12.61	16.30	153.3	156.1	3.4			
87V-08	47.6	49.6	2.0	1.2	58.5	11268	4G48#		11.75	5.12	6.63	77		5.09	9.41	14.50	156.1	162.6	3.8			
87V-08	49.6	52.8	3.2	0.9	28.6	11269	4E4		1.93	1.42	0.51	16		0.33	2.80	3.13	162.6	173.1	3.0			
87V-08	52.8	53.6	0.9	0.8	93.1	11270	4E4		9.14	4.08	5.06	38		0.56	17.94	18.50	173.1	176.0	2.7			
87V-08	53.6	54.7	1.1	1.1	100.0	11271	4G48		9.97	4.36	5.61	53		6.05	19.45	25.50	176.0	179.6	3.6			
87V-08	54.7	55.7	1.0	0.9	93.7	11272	4G48		17.84	7.64	10.20	75		1.16	12.14	13.30	179.6	182.8	3.0			
87V-08	55.7	57.1	1.3	1.5	100.0	11273	4E48		6.43	3.55	2.88	45		7.26	30.34	37.60	182.8	187.2	5.0			
87V-08	57.1	59.1	2.1	1.6	75.0	11274	4E48		0.00						0.00		187.2	194.0	5.1			
87V-08	59.1	60.5	1.4	1.4	100.0	11275	4E08#		3.62	2.19	1.43	24		3.26	29.44	32.70	194.0	198.5	4.5			
87V-08	60.5	61.5	1.0	1.7	100.0	11276	4C3#		1.61	0.38	1.23	14		3.47	16.13	19.60	198.5	201.8	5.6			
87V-08	61.5	63.0	1.5	1.7	100.0	11277	4C3#		0.82	0.55	0.27	10		0.68	19.12	19.80	201.8	206.7	5.5			
87V-08	63.0	63.9	0.9	1.3	100.0	11278	4G48		12.64	6.91	5.73	69		2.59	7.61	10.20	206.7	209.7	4.3			
87V-08	63.9	65.0	1.1	1.3	100.0	11279	4G48		10.52	5.53	4.99	49		3.02	7.38	10.40	209.7	213.3	4.4			
87V-08	65.0	66.2	1.2	1.5	100.0	11280	4E0#		1.92	1.53	0.39	20		1.92	27.18	29.10	213.3	217.3	4.8			
87V-08	66.2	67.6	1.4	1.5	100.0	11281	4E4#		5.52	3.41	2.11	42		3.06	28.34	31.40	217.3	221.8	4.8			
87V-08	67.6	68.5	0.9	1.1	100.0	11282	4G48		8.50	3.92	4.58	47		8.19	11.41	19.60	221.8	224.8	3.6			
87V-08	68.5	70.7	2.2	1.9	87.5	11283	4E10		0.42	0.28	0.14	12		3.48	29.32	32.80	224.8	232.0	6.3			
87V-08	70.7	72.1	1.4	1.4	100.0	11284	4C0		0.51	0.25	0.26	18		1.66	19.64	21.30	232.0	236.5	4.6			
87V-08	72.1	73.5	1.4	1.1	80.4	11285	4C0		0.28	0.13	0.15	14		3.39	25.01	28.40	236.5	241.1	3.7			
87V-08	73.5	74.8	1.3	1.3	100.0	11286	4C0		0.29	0.16	0.13	14		2.67	21.13	23.80	241.1	245.5	4.4			
87V-08	74.8	76.0	1.2	1.3	100.0	11287	4C0		0.41	0.17	0.24	16		3.10	22.70	25.80	245.5	249.5	4.4			
87V-08	76.0	77.2	1.2	1.2	100.0	11288	4C0		0.41	0.17	0.24	12		3.41	22.09	25.50	249.5	253.4	4.1			
87V-08	77.2	79.8	2.6	2.7	100.0	11289	4C3#		0.96	0.89	0.07	14		1.86	25.24	27.10	253.4	261.8	8.9			
87V-08	79.8	81.1	1.3	1.6	100.0	11290	4C08		1.21	0.73	0.48	16		3.62	28.68	32.30	261.8	266.1	5.1			
87V-08	81.1	82.6	1.5	1.5	100.0	11291	4C08		0.50	0.19	0.31	10		3.43	15.57	19.00	266.1	271.0	4.9			
87V-08	82.6	84.0	1.4	1.5	100.0	11292	4C08		0.68	0.28	0.40	12		2.04	17.66	19.70	271.0	275.6	4.9			
87V-08	84.0	85.4	1.4	1.4	100.0	11293	4C08		0.66	0.28	0.38	14		1.73	21.17	22.90	275.6	280.1	4.6			
87V-08	85.4	86.8	1.4	1.6	100.0	11294	4C08		0.49	0.17	0.32	12		1.62	21.58	23.20	280.1	284.7	5.2			

Hole Number: 87V-08

Number of intervals: 54

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-08	86.8	88.3	1.5	1.7	100.0	11295	4C08		0.43	0.18	0.25	14		2.45	21.75	24.20	284.7	289.7	5.5	
87V-08	88.3	89.7	1.4	1.5	100.0	11296	4C08		0.34	0.17	0.17	26		1.87	26.53	28.40	289.7	294.4	5.0	
87V-08	89.7	91.4	1.7	1.8	100.0	11297	4C3		0.88	0.44	0.44	30		3.52	31.08	34.60	294.4	299.9	5.8	
87V-08	91.4	93.2	1.8	1.9	100.0	11298	4C3		1.37	0.78	0.59	34		4.99	22.71	27.70	299.9	305.9	6.2	
87V-08	93.2	95.1	1.9	1.7	90.2	11299	4C3		2.53	1.12	1.41	37		5.61	24.09	29.70	305.9	312.0	5.5	

Hole Number: 87V-09

Number of intervals: 62

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-09	20.4	21.9	1.5	0.3	20.0	30201	4A0		0.83	0.48	0.35	9		0.96	1.25	2.21	67.0	72.0	1.0	
87V-09	21.9	23.6	1.6	2.3	100.0	30202	4AC		0.52	0.16	0.36	4		2.72	4.54	7.26	72.0	77.4	7.7	
87V-09	23.6	24.3	0.7	0.7	100.0	30203	5D4		1.84	0.06	1.78	2		10.60	2.20	12.80	77.4	79.8	2.4	
87V-09	24.3	25.9	1.6	1.9	100.0	30204	4A0		0.71	0.25	0.46	4		2.74	3.83	6.57	79.8	85.1	6.2	
87V-09	25.9	27.6	1.6	1.7	100.0	30205	4A0		2.14	0.62	1.52	9		2.37	2.24	4.61	85.1	90.4	5.6	
87V-09	27.6	28.9	1.4	1.5	100.0	30206	4A4		4.23	2.55	1.68	30		3.56	2.99	6.55	90.4	94.9	5.0	
87V-09	28.9	30.3	1.4	1.5	100.0	30207	4A4		8.79	3.06	5.73	46		1.85	4.14	5.99	94.9	99.5	5.0	
87V-09	30.3	31.6	1.3	1.4	100.0	30208	4L4		2.53	1.11	1.42	21		10.80	1.40	12.20	99.5	103.7	4.5	
87V-09	31.6	32.8	1.2	1.3	100.0	30209	4D8		4.58	1.60	2.98	27		12.40	4.00	16.40	103.7	107.5	4.3	
87V-09	32.8	33.8	1.0	1.1	100.0	30210	4L		3.10	1.76	1.34	23		19.80	17.90	37.70	107.5	110.8	3.6	
87V-09	33.8	34.9	1.2	1.2	100.0	30211	4HL		3.61	1.94	1.67	28		6.98	2.18	9.16	110.8	114.6	4.0	
87V-09	34.9	36.4	1.4	1.5	100.0	30212	4H4		16.93	9.07	7.86	105		28.60	3.80	32.40	114.6	119.3	5.0	
87V-09	36.4	37.5	1.2	1.2	100.0	30213	4D4		9.16	4.17	4.99	63		7.33	11.17	18.50	119.3	123.1	4.1	
87V-09	37.5	38.4	0.9	0.9	100.0	30214	4E46		5.60	2.77	2.83	44		7.45	24.65	32.10	123.1	126.0	3.1	
87V-09	38.4	39.9	1.5	1.5	100.0	30215	464		11.57	5.34	6.23	81		1.98	13.92	15.90	126.0	130.8	5.0	
87V-09	39.9	41.1	1.3	1.5	100.0	30216	464		10.99	3.38	7.61	43		0.87	14.13	15.00	130.8	135.0	4.8	
87V-09	41.1	42.5	1.3	1.5	100.0	30217	464		34.10	10.90	23.20	44		0.23	49.27	49.50	135.0	139.3	4.9	*
87V-09	42.5	43.6	1.2	1.4	100.0	30218	4648		10.59	5.13	5.46	77		8.26	15.84	24.10	139.3	143.2	4.6	
87V-09	43.6	44.9	1.3	1.3	100.0	30219	4648		11.44	6.11	5.33	75		16.90	15.10	32.00	143.2	147.4	4.3	
87V-09	44.9	46.1	1.1	1.2	100.0	30220	4648		12.68	6.13	6.55	81		8.11	13.59	21.70	147.4	151.1	4.1	
87V-09	46.1	47.2	1.2	1.3	100.0	30221	4648		14.60	6.12	8.48	99		2.56	14.64	17.20	151.1	154.9	4.2	
87V-09	47.2	48.4	1.2	1.3	100.0	30222	46		12.65	5.66	6.99	85		4.65	9.15	13.80	154.9	158.9	4.2	
87V-09	48.4	49.1	0.7	0.7	95.7	30223	464		11.78	4.44	7.34	67		2.68	8.82	11.50	158.9	161.2	2.2	
87V-09	49.1	50.4	1.3	1.5	100.0	30224	464		1.30	0.45	0.85	10		1.44	6.89	8.33	161.2	165.4	4.8	*
87V-09	50.4	51.9	1.5	1.5	100.0	30225	464		11.50	3.83	7.67	63		1.97	10.83	12.80	165.4	170.4	5.0	
87V-09	51.9	53.2	1.2	1.4	100.0	30226	464		17.98	6.78	11.20	115		1.04	11.96	13.00	170.4	174.4	4.7	
87V-09	53.2	54.5	1.3	1.5	100.0	30227	464		7.73	2.79	4.94	53		3.78	5.94	9.72	174.4	178.8	4.8	
87V-09	54.5	55.8	1.3	1.4	100.0	30228	464		12.14	4.58	7.56	85		2.14	10.46	12.60	178.8	183.1	4.5	
87V-09	55.8	57.0	1.2	1.3	100.0	30229	464		8.78	3.20	5.58	59		1.50	8.70	10.20	183.1	187.0	4.2	
87V-09	57.0	58.8	1.8	1.9	100.0	30230	464		12.50	3.80	8.70	67		3.00	8.70	11.70	187.0	192.9	6.2	
87V-09	58.8	60.0	1.2	1.3	100.0	30231	4E4		3.68	2.60	1.08	45		8.27	33.33	41.60	192.9	197.0	4.3	
87V-09	60.0	61.4	1.3	1.4	100.0	30232	4E4		7.59	5.03	2.56	83		10.40	26.40	36.80	197.0	201.3	4.5	
87V-09	61.4	62.4	1.0	1.0	100.0	30233	464		13.45	6.24	7.21	95		4.73	8.77	13.50	201.3	204.7	3.4	
87V-09	62.4	63.6	1.2	1.3	100.0	30234	464		13.55	5.47	8.08	85		2.34	10.66	13.00	204.7	208.5	4.3	
87V-09	63.6	64.8	1.3	1.3	100.0	30235	4D4		11.32	5.44	5.88	56		16.30	8.30	24.60	208.5	212.7	4.4	
87V-09	64.8	65.5	0.7	0.8	100.0	30236	4D4		15.54	7.78	7.76	76		16.10	10.20	26.30	212.7	215.0	2.6	
87V-09	65.5	67.1	1.6	1.6	100.0	30237	4D38		6.02	3.00	3.02	29		16.60	15.10	31.70	215.0	220.1	5.1	
87V-09	67.1	68.6	1.5	1.5	100.0	30238	4D38		3.66	1.57	2.09	21		8.66	17.74	26.40	220.1	225.0	5.0	
87V-09	68.6	70.0	1.5	1.5	100.0	30239	4C38		1.98	0.94	1.04	19		10.20	12.80	23.00	225.0	229.8	5.0	
87V-09	70.0	71.0	0.9	1.0	100.0	30240	4C38		3.14	1.96	1.18	19		31.80	8.60	40.40	229.8	232.8	3.2	
87V-09	71.0	72.0	1.0	1.1	100.0	30241	4C38		1.13	0.57	0.56	17		22.30	10.40	32.70	232.8	236.1	3.7	
87V-09	72.0	73.1	1.1	1.1	100.0	30242	4E1		1.13	0.74	0.39	12		25.00	18.30	43.30	236.1	239.7	3.6	
87V-09	73.1	73.9	0.8	0.8	100.0	30243	4E1		1.97	0.89	1.08	16		4.14	2.35	6.49	239.7	242.3	2.7	
87V-09	73.9	75.2	1.3	1.4	100.0	30244	4CB		0.59	0.16	0.43	6		6.84	0.92	7.76	242.3	246.6	4.5	
87V-09	75.2	76.6	1.4	1.5	100.0	30245	4CB		2.30	1.36	0.94	17		18.50	10.90	29.40	246.6	251.2	5.0	
87V-09	76.6	77.8	1.3	1.3	100.0	30246	4CB		1.33	0.49	0.84	12		17.40	8.80	26.20	251.2	255.4	4.3	
87V-09	77.8	79.2	1.4	1.5	100.0	30247	4CB		0.65	0.29	0.36	8		15.70	13.40	29.10	255.4	259.9	5.0	
87V-09	79.2	80.7	1.5	1.5	100.0	30248	4CB		1.00	0.40	0.60	12		20.40	15.30	35.70	259.9	264.8	4.9	
87V-09	80.7	82.1	1.4	1.5	100.0	30249	4CB		0.70	0.27	0.43	8		18.90	15.10	34.00	264.8	269.3	4.9	

Hole Number: 87V-09

Number of intervals: 62

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY	MISSING SAMP
87V-09	82.1	83.5	1.4	1.5	100.0	30250	4C8		2.54	1.40	1.14	17		10.10	17.50	27.60	269.3	273.9	4.9		
87V-09	83.5	84.9	1.4	1.6	100.0	30155	4C8		0.82	0.29	0.53	8		9.33	13.87	23.20	273.9	278.5	5.2		
87V-09	84.9	86.3	1.5	1.6	100.0	30156	4C8		1.58	0.62	0.96	10		8.32	16.68	25.00	278.5	283.3	5.1		
87V-09	86.3	87.8	1.4	1.5	100.0	30157	4C8		1.64	0.70	0.94	11		8.67	13.93	22.60	283.3	288.0	5.0		
87V-09	87.8	89.1	1.3	1.5	100.0	30158	4C0		13.64	5.18	8.46	85		2.98	20.42	23.40	288.0	292.4	4.8	*	
87V-09	89.1	90.4	1.2	1.5	100.0	30159	4C0		0.42	0.18	0.24	4		4.43	9.57	14.00	292.4	296.5	4.9		
87V-09	90.4	91.8	1.5	1.4	97.9	30160	4C0		0.32	0.07	0.25	4		6.57	7.83	14.40	296.5	301.3	4.7		
87V-09	91.8	92.6	0.7	0.8	100.0	30161	4C0		0.33	0.19	0.14	4		12.40	1.00	13.40	301.3	303.7	2.6		
87V-09	92.6	94.2	1.6	1.7	100.0	30162	360796		0.20	0.07	0.13	2		4.96	1.58	6.54	303.7	308.9	5.5		
87V-09	94.2	95.7	1.6	1.6	100.0	30163	360796		1.77	1.32	0.45	19		5.80	10.20	16.00	308.9	314.0	5.3		
87V-09	95.7	97.2	1.5	1.6	100.0	30164	360796		0.27	0.10	0.17	4		5.44	0.76	6.20	314.0	319.0	5.2		
87V-09	97.2	98.9	1.7	1.6	98.2	30165	360796		0.55	0.13	0.42	2		6.24	0.90	7.14	319.0	324.5	5.4		
87V-09	98.9	99.4	0.5	0.5	100.0	30166	360796		0.67	0.32	0.35	8		8.66	0.79	9.45	324.5	326.1	1.6		

Hole Number: 87V-10

Number of intervals: 52

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/ton)	Au (g/ton)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-10	18.9	20.4	1.5	0.8	50.0	30614	4A4		4.70	3.04	1.66	30		0.59	2.93	3.52	62.0	67.0	2.5	
87V-10	20.4	21.9	1.5	1.1	74.0	30615	4A4		6.87	2.20	4.67	32		0.86	2.78	3.64	67.0	72.0	3.7	
87V-10	21.9	23.5	1.5	1.5	100.0	30616	4A4		4.36	1.37	2.99	22		1.47	2.87	4.34	72.0	77.0	5.0	
87V-10	23.5	24.8	1.3	1.5	100.0	30617	4A4		3.98	1.21	2.77	20		1.16	1.75	2.91	77.0	81.3	4.9	
87V-10	24.8	25.9	1.1	1.4	100.0	30618	4A4		7.93	2.30	5.63	42		1.13	1.43	2.56	81.3	85.0	4.6	
87V-10	25.9	27.4	1.5	1.8	100.0	30619	4A4		7.60	2.61	4.99	46		0.80	2.27	3.07	85.0	90.0	5.9	
87V-10	27.4	29.6	2.1	1.4	67.1	30620	4A4		5.06	1.87	3.19	34		0.83	3.00	3.83	90.0	97.0	4.7	
87V-10	29.6	31.9	2.3	2.3	98.7	30621	4A4		6.84	2.54	4.30	40		0.54	6.70	7.24	97.0	104.6	7.5	
87V-10	31.9	33.2	1.3	1.2	93.2	30622	4L6		1.04	0.15	0.89	4		2.51	1.80	4.31	104.6	109.0	4.1	
87V-10	33.2	34.3	1.0	1.1	100.0	30623	4A4		5.13	1.40	3.73	24		4.17	-4.04	0.13	109.0	112.4	3.6	*
87V-10	34.3	35.1	0.9	0.9	100.0	30624	4E48		10.91	5.22	5.69	73		5.91	-2.70	3.21	112.4	115.2	3.1	
87V-10	35.1	36.9	1.8	1.9	100.0	30625	4L124		0.00						0.00		115.2	121.0	6.1	*
87V-10	36.9	37.8	0.9	1.2	100.0	30626	4L126		0.51	0.07	0.44	2		3.92	1.52	5.44	121.0	124.0	4.0	
87V-10	37.8	39.2	1.4	1.5	100.0	30627	10Q9		0.23	0.04	0.19	2		2.43	1.87	4.30	124.0	128.5	5.0	
87V-10	39.2	40.5	1.4	1.5	100.0	30628	4L124		0.20	0.05	0.15	2		3.70	0.70	4.40	128.5	133.0	5.0	
87V-10	40.5	42.1	1.6	1.5	98.0	30629	4L124		1.54	0.62	0.92	10		6.08	4.22	10.30	133.0	138.1	5.0	
87V-10	42.1	43.6	1.5	1.5	100.0	30630	4L124		0.72	0.17	0.55	4		5.55	2.47	8.02	138.1	143.1	5.0	
87V-10	43.6	45.0	1.3	1.6	100.0	30631	4L124		1.21	0.35	0.86	6		4.65	4.97	9.62	143.1	147.5	5.3	
87V-10	45.0	46.4	1.4	1.4	100.0	30632	4E48		7.33	4.38	2.95	67		9.69	25.21	34.90	147.5	152.1	4.7	
87V-10	46.4	47.8	1.4	1.4	100.0	30633	4G48		11.52	5.62	5.90	77		7.11	17.39	24.50	152.1	156.8	4.7	
87V-10	47.8	49.1	1.3	1.4	100.0	30634	4G48		12.61	5.50	7.11	69		9.88	12.32	22.20	156.8	161.1	4.7	
87V-10	49.1	50.4	1.3	1.4	100.0	30635	4H491		1.80	0.73	1.07	13		0.90	62.00	62.90	161.1	165.3	4.5	*
87V-10	50.4	52.0	1.6	1.6	100.0	30636	4E814		4.05	2.19	1.86	31		15.30	27.20	42.50	165.3	170.5	5.3	
87V-10	52.0	53.4	1.4	1.5	100.0	30637	4G48		7.45	3.19	4.26	48		5.13	14.87	20.00	170.5	175.1	5.0	
87V-10	53.4	54.7	1.3	1.5	100.0	30638	4G48		10.18	4.20	5.98	62		4.27	19.23	23.50	175.1	179.5	4.9	
87V-10	54.7	56.0	1.3	1.4	100.0	30639	4G48		12.78	5.58	7.20	81		1.71	10.09	11.80	179.5	183.7	4.7	
87V-10	56.0	57.5	1.6	1.4	88.2	30640	4E01		3.12	1.05	2.07	15		4.39	32.11	36.50	183.7	188.8	4.5	
87V-10	57.5	58.5	1.0	1.0	100.0	30641	4E01		2.15	1.34	0.81	15		1.78	27.72	29.50	188.8	192.0	3.3	
87V-10	58.5	59.6	1.0	1.1	100.0	30642	4G4#8		9.10	3.41	5.69	54		1.50	18.50	20.00	192.0	195.4	3.5	
87V-10	59.6	60.4	0.8	0.9	100.0	30643	4E#48		11.79	5.34	6.45	69		2.04	33.26	35.30	195.4	198.0	3.0	
87V-10	60.4	61.9	1.6	1.5	96.1	30644	4G4#8		10.62	3.53	7.09	46		1.87	21.23	23.10	198.0	203.1	4.9	
87V-10	61.9	63.2	1.3	1.4	100.0	30645	4G4#8		11.93	4.30	7.63	71		1.88	18.92	20.80	203.1	207.5	4.6	
87V-10	63.2	64.5	1.2	1.4	100.0	30646	4G4#8		9.56	3.23	6.33	55		1.98	19.02	21.00	207.5	211.6	4.7	
87V-10	64.5	65.7	1.2	1.4	100.0	30647	4G4#8		11.68	4.87	6.81	65		1.86	16.94	18.80	211.6	215.5	4.5	
87V-10	65.7	67.1	1.4	1.6	100.0	30648	4K4#		1.54	0.94	0.60	22		1.27	19.13	20.40	215.5	220.2	5.1	
87V-10	67.1	68.5	1.3	1.5	100.0	30649	4K4#		1.85	1.41	0.44	24		1.84	15.36	17.20	220.2	224.6	5.0	
87V-10	68.5	69.8	1.4	1.4	100.0	30650	4K4#		0.77	0.55	0.22	12		1.29	20.61	21.90	224.6	229.1	4.6	
87V-10	69.8	71.1	1.3	1.4	100.0	30651	4K4#		1.94	1.18	0.76	14		1.21	20.89	22.10	229.1	233.4	4.7	
87V-10	71.1	72.5	1.4	1.5	100.0	30652	4K4#		2.46	1.46	1.00	20		1.55	18.55	20.10	233.4	238.0	4.8	
87V-10	72.5	74.1	1.5	1.7	100.0	30653	4E10		1.01	0.41	0.60	12		2.91	29.19	32.10	238.0	243.0	5.5	
87V-10	74.1	75.4	1.4	1.6	100.0	30654	4E10		0.45	0.17	0.28	12		2.30	26.90	29.20	243.0	247.5	5.3	
87V-10	75.4	76.8	1.4	1.4	100.0	30655	4E10		0.89	0.39	0.50	14		1.81	24.39	26.20	247.5	252.0	4.5	
87V-10	76.8	78.1	1.3	1.4	100.0	30656	4E10		0.32	0.20	0.12	8		6.03	20.87	26.90	252.0	256.3	4.5	
87V-10	78.1	79.5	1.3	1.4	100.0	30657	4E10		0.62	0.41	0.21	19		3.60	19.50	23.10	256.3	260.7	4.7	
87V-10	79.5	80.8	1.3	1.4	100.0	30658	4E10		3.32	1.38	1.94	12		7.02	19.68	26.70	260.7	265.0	4.7	
87V-10	80.8	82.2	1.4	1.4	97.9	30659	4E10		0.79	0.26	0.53	21		2.59	21.71	24.30	265.0	269.7	4.6	
87V-10	82.2	83.5	1.3	1.4	100.0	30660	4E10		1.46	0.27	1.19	21		2.47	18.63	21.10	269.7	274.1	4.7	
87V-10	83.5	84.7	1.2	1.5	100.0	30661	4E10		1.38	0.45	0.93	4		2.84	20.16	23.00	274.1	278.0	4.9	
87V-10	84.7	85.8	1.1	1.1	100.0	30662	4L67		1.27	0.93	0.34	33		4.12	0.61	4.73	278.0	281.5	3.6	

Hole Number: 87V-10

Number of intervals: 52

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-10	85.8	87.3	1.5	1.7	100.0	30663	4D483		5.88	2.92	2.96	14		4.62	15.38	20.00	281.5	286.5	5.5	
87V-10	87.3	88.7	1.4	1.6	100.0	30664	4C38		1.50	0.93	0.57	14		5.76	19.34	25.10	286.5	291.1	5.2	
87V-10	88.7	90.4	1.7	1.7	100.0	30665	4C38		1.14	0.39	0.75	10		5.86	15.54	21.40	291.1	296.7	5.7	

Hole Number: 87V-11

Number of intervals: 55

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	ZSOL. Fe	ZINSOL. Fe	ZTOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY	MISSING SAMP
87V-11	25.0	25.9	0.9	1.1	100.0	30299	4A4		7.65	2.77	4.88	38		0.84	3.67	4.51	82.0	85.0	3.7		
87V-11	25.9	27.3	1.4	1.5	100.0	30300	4A0		2.23	0.80	1.43	18		0.53	12.97	13.50	85.0	89.7	5.0		
87V-11	27.3	28.8	1.5	1.6	100.0	30301	4A0		1.08	0.45	0.63	9		0.52	12.68	13.20	89.7	94.6	5.1		
87V-11	28.8	30.1	1.3	1.6	100.0	30302	4A0		0.93	0.43	0.50	9		0.33	12.37	12.70	94.6	98.9	5.3		
87V-11	30.1	31.7	1.6	1.5	98.0	30303	4A0		0.58	0.36	0.22	4		0.44	7.40	7.84	98.9	104.0	5.0		
87V-11	31.7	33.1	1.4	1.6	100.0	30304	4A0		2.25	0.80	1.45	11		1.18	4.58	5.76	104.0	108.7	5.3		
87V-11	33.1	34.7	1.6	1.6	100.0	30305	4A0		1.95	0.96	0.99	13		0.59	4.81	5.40	108.7	113.8	5.2		
87V-11	34.7	37.2	2.5	1.6	65.9	30306	4A4		9.72	4.60	5.12	56		23.10	8.00	31.10	113.8	122.0	5.4	*	
87V-11	37.2	37.9	0.7	0.8	100.0	30307	3C47#		2.51	0.29	2.22	2		7.12	1.59	8.71	122.0	124.3	2.7		
87V-11	37.9	38.9	1.0	1.5	100.0	30308	4A0		2.02	0.57	1.45	6		3.15	3.33	6.48	124.3	127.5	5.0		
87V-11	38.9	40.1	1.2	1.4	100.0	30309	4A0		4.37	1.50	2.87	18		2.43	2.11	4.54	127.5	131.6	4.6		
87V-11	40.1	41.3	1.2	1.4	100.0	30310	4A0		3.74	1.81	1.93	22		3.07	2.90	5.97	131.6	135.4	4.6		
87V-11	41.3	42.6	1.3	1.4	100.0	30311	4A0		6.69	2.27	4.42	27		1.58	3.60	5.18	135.4	139.8	4.7		
87V-11	42.6	43.4	0.8	0.8	96.3	30312	4D44		14.98	4.78	10.20	56		3.21	8.79	12.00	139.8	142.5	2.6		
87V-11	43.4	44.7	1.3	1.3	97.7	30313	4L6		8.99	3.70	5.29	45		7.86	4.64	12.50	142.5	146.8	4.2		
87V-11	44.7	46.3	1.6	1.8	100.0	30314	4L61		1.94	0.90	1.04	12		4.42	2.66	7.08	146.8	151.9	5.8		
87V-11	46.3	47.3	1.0	1.5	100.0	30315	4L6		2.73	1.43	1.30	21		9.78	4.72	14.50	151.9	155.1	5.0		
87V-11	47.3	48.3	1.0	1.1	100.0	30316	4E48		9.33	4.39	4.94	48		9.57	15.83	25.40	155.1	158.4	3.5		
87V-11	48.3	49.3	1.1	1.2	100.0	30317	4E48		7.08	3.29	3.79	41		2.67	20.73	23.40	158.4	161.9	3.8		
87V-11	49.3	50.9	1.6	1.3	86.3	30318	464		0.00						0.00		161.9	167.0	4.4	*	
87V-11	50.9	51.9	1.0	1.0	100.0	30319	464		16.10	7.82	8.28	91		1.59	10.81	12.40	167.0	170.2	3.2		
87V-11	51.9	52.9	1.1	1.3	100.0	30320	464		10.91	4.02	6.89	44		0.99	11.31	12.30	170.2	173.7	4.4		
87V-11	52.9	54.1	1.2	1.3	100.0	30321	464		9.06	3.14	5.92	31		0.56	23.64	24.20	173.7	177.6	4.3		
87V-11	54.1	55.2	1.0	1.2	100.0	30322	464		11.54	4.14	7.40	43		0.80	19.80	20.60	177.6	181.0	3.9		
87V-11	55.2	56.2	1.1	1.2	100.0	30323	464		11.67	5.04	6.63	76		1.16	18.54	19.70	181.0	184.5	3.8		
87V-11	56.2	57.2	1.0	1.1	100.0	30324	4E08		4.21	1.76	2.45	25		9.23	29.47	38.70	184.5	187.8	3.5		
87V-11	57.2	58.5	1.3	1.4	100.0	30325	3B4H		4.63	2.00	2.63	25		3.74	14.56	18.30	187.8	192.0	4.5		
87V-11	58.5	59.6	1.1	1.2	100.0	30326	464		9.09	3.42	5.67	58		1.96	18.54	20.50	192.0	195.6	3.9		
87V-11	59.6	60.4	0.8	0.8	100.0	30327	464		18.66	9.78	8.88	149		2.10	13.30	15.40	195.6	198.3	2.7		
87V-11	60.4	61.2	0.8	0.9	100.0	30328	4E08		3.16	1.94	1.22	29		11.37	25.73	37.10	198.3	200.8	2.8		
87V-11	61.2	62.5	1.3	1.4	100.0	30329	464		11.72	5.27	6.45	74		8.46	10.14	18.60	200.8	205.1	4.5		
87V-11	62.5	63.9	1.3	1.4	100.0	30330	464		10.67	3.97	6.70	62		2.58	10.42	13.00	205.1	209.5	4.6		
87V-11	63.9	65.1	1.3	1.4	100.0	30331	464		12.25	5.22	7.03	85		2.69	11.81	14.50	209.5	213.7	4.5		
87V-11	65.1	66.4	1.3	1.4	100.0	30332	464		12.31	6.29	6.02	112		1.06	12.94	14.00	213.7	218.0	4.5		
87V-11	66.4	67.8	1.4	1.4	100.0	30333	10Q		6.44	3.07	3.37	41		3.41	8.39	11.80	218.0	222.6	4.7		
87V-11	67.8	68.9	1.0	1.0	100.0	30334	3C#6		9.03	4.13	4.90	54		13.30	5.00	18.30	222.6	225.9	3.3		
87V-11	68.9	70.3	1.4	1.5	100.0	30683	4E418#		5.05	3.53	1.52	41		24.40	20.10	44.50	225.9	230.6	5.0		
87V-11	70.3	71.6	1.3	1.4	100.0	30684	4648#		13.95	7.16	6.79	93		8.64	7.56	16.20	230.6	235.0	4.6		
87V-11	71.6	72.8	1.1	1.3	100.0	30685	4648#		13.60	5.81	7.79	95		4.09	6.61	10.70	235.0	238.7	4.3		
87V-11	72.8	74.1	1.4	1.4	100.0	30686	4648#		12.04	3.88	8.16	77		1.19	7.33	8.52	238.7	243.2	4.7		
87V-11	74.1	75.3	1.1	1.3	100.0	30687	4648		8.54	3.19	5.35	47		5.11	4.63	9.74	243.2	246.9	4.3		
87V-11	75.3	76.2	0.9	1.0	100.0	30688	4648		11.96	4.92	7.04	73		3.84	13.76	17.60	246.9	250.0	3.4		
87V-11	76.2	77.5	1.3	1.5	100.0	30689	4D0 +/-8		5.01	1.95	3.06	29		8.39	16.31	24.70	250.0	254.4	5.0		
87V-11	77.5	79.2	1.6	1.6	96.2	30690	4D0 +/-8		2.98	1.36	1.62	22		6.54	16.76	23.30	254.4	259.7	5.1		
87V-11	79.2	80.1	0.9	1.0	100.0	30691	3696		1.66	0.77	0.89	12		4.11	1.48	5.59	259.7	262.8	3.4		
87V-11	80.1	81.4	1.3	1.3	100.0	30692	4C789		4.06	2.44	1.62	28		27.10	7.00	34.10	262.8	267.0	4.4		
87V-11	81.4	82.9	1.5	1.4	94.0	30693	4C789		1.82	1.13	0.69	16		26.00	7.40	33.40	267.0	272.0	4.7		
87V-11	82.9	84.2	1.3	1.3	100.0	30694	4C789		0.89	0.38	0.51	12		23.00	6.40	29.40	272.0	276.2	4.3		
87V-11	84.2	85.8	1.6	1.7	100.0	30695	4C078		1.30	0.41	0.89	8		12.30	12.90	25.20	276.2	281.6	5.5		

Hole Number: 87V-11

Number of intervals: 55

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-11	85.8	86.9	1.1	1.2	100.0	30696	4L126		1.33	0.72	0.61	10		8.72	16.88	25.60	281.6	285.2	4.0	
87V-11	86.9	88.1	1.2	1.4	100.0	30697	4L126		1.45	0.75	0.70	12		8.09	17.81	25.90	285.2	289.1	4.6	
87V-11	88.1	89.4	1.3	1.4	100.0	30698	4L126		3.54	2.17	1.37	24		6.45	11.65	18.10	289.1	293.4	4.6	
87V-11	89.4	90.6	1.2	1.5	100.0	30699	4L127		3.72	1.50	2.22	20		14.40	2.60	17.00	293.4	297.4	5.0	
87V-11	90.6	92.0	1.4	1.4	100.0	30700	4L127		0.91	0.30	0.61	6		9.20	1.80	11.00	297.4	302.0	4.6	
87V-11	92.0	93.5	1.4	1.5	100.0	30298	4L127		0.36	0.16	0.20	6		10.50	-1.03	9.47	302.0	306.6	5.0	

Hole Number: 87V-12

Number of intervals: 28

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	ZSOL. Fe	ZINSOL. Fe	XTOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY	MISSING SAMP
87V-12	28.0	28.8	0.8	1.0	100.0	11201	5D4		0.79	0.46	0.33	198		1.22	20.08	21.30	92.0	94.6	3.3		
87V-12	28.8	30.3	1.5	1.5	100.0	11202	4E4		19.32	12.30	7.02	175		4.03	22.87	26.90	94.6	99.5	4.9		
87V-12	30.4	31.5	1.0	1.3	100.0	11203	4EG4		15.48	8.12	7.36	89		0.93	18.97	19.90	99.9	103.2	4.4		
87V-12	31.5	33.2	1.7	1.5	87.5	11204	4EL4		8.09	5.01	3.08	87		4.95	23.85	28.80	103.2	108.8	4.9		
87V-12	33.2	35.4	2.3	1.6	73.0	11205	3G4		3.04	1.43	1.61	18		6.93	3.06	9.99	108.8	116.2	5.4		
87V-12	35.4	38.6	3.1	2.2	70.9	11206	5D4		1.50	0.50	1.00	14		9.10	1.20	10.30	116.2	126.5	7.3		
87V-12	38.6	39.2	0.6	0.8	100.0	11207	4E4		6.41	3.09	3.32	85		4.92	31.08	36.00	126.5	128.6	2.5		
87V-12	39.2	41.4	2.2	1.9	87.5	11208	4L06		0.56	0.09	0.47	0		4.74	0.81	5.55	128.6	135.8	6.3		
87V-12	41.4	44.8	3.4	2.0	59.8	11209	4L06		0.15	0.00	0.15	0		4.35	0.39	4.74	135.8	147.0	6.7		
87V-12	52.9	54.2	1.3	1.2	86.4	11210	4L0		1.01	0.17	0.84	40		0.70	7.88	8.58	173.4	177.8	3.8		
87V-12	54.2	55.3	1.1	1.2	100.0	11211	4E4		10.19	3.93	6.26	48		2.81	22.39	25.20	177.8	181.3	3.8		
87V-12	55.3	56.5	1.2	1.4	100.0	11212	4EG4		15.71	4.11	11.60	67		2.48	15.32	17.80	181.3	185.4	4.5		
87V-12	56.5	57.6	1.1	1.2	100.0	11213	4L0		4.95	1.65	3.30	20		5.46	6.94	12.40	185.4	188.9	4.1		
87V-12	57.6	60.0	2.5	1.7	67.9	11214	3G486		0.67	0.11	0.56	2		5.96	0.90	6.86	188.9	197.0	5.5		
87V-12	60.0	62.1	2.0	1.7	83.6	11215	3G486		3.58	1.10	2.48	22		6.46	1.27	7.73	197.0	203.7	5.6		
87V-12	64.6	66.1	1.5	1.7	100.0	11216	4E48		0.58	0.16	0.42	8		3.16	24.24	27.40	212.0	217.0	5.5		
87V-12	66.1	67.5	1.3	1.3	100.0	11217	4L0		0.65	0.08	0.57	2		4.00	3.22	7.22	217.0	221.4	4.4		
87V-12	69.3	70.9	1.6	1.4	92.2	11218	4L24		0.45	0.03	0.42	2		5.30	1.56	6.86	227.4	232.5	4.7		
87V-12	70.9	72.1	1.2	1.7	100.0	11219	4L24		0.55	0.16	0.39	4		2.08	1.08	3.16	232.5	236.6	5.6		
87V-12	72.1	72.6	0.5	0.5	100.0	11220	4EL		7.58	3.98	3.60	40		2.48	15.72	18.20	236.6	238.2	1.8		
87V-12	72.6	74.0	1.4	1.4	100.0	11221	4A7		1.52	0.40	1.12	6		2.65	2.07	4.72	238.2	242.9	4.7		
87V-12	83.1	84.6	1.5	1.7	100.0	11222	4G48		11.19	4.67	6.52	80		3.31	17.39	20.70	272.7	277.6	5.6		
87V-12	84.6	85.0	0.4	0.7	100.0	11223	4CL		1.53	0.54	0.99	14		4.18	11.32	15.50	277.6	279.0	2.2		
87V-12	85.0	86.4	1.4	1.5	100.0	11224	4G4		12.10	5.10	7.00	202		2.04	15.06	17.10	279.0	283.5	4.8		
87V-12	86.4	87.8	1.4	1.5	100.0	11225	4GE		11.59	5.80	5.79	77		2.65	21.55	24.20	283.5	288.0	4.9		
87V-12	87.8	88.7	0.9	0.9	100.0	11226	4E4		8.32	4.47	3.85	91		3.22	26.68	29.90	288.0	291.0	3.0		
87V-12	88.7	89.8	1.1	1.0	97.1	11227	4E4		5.58	2.48	3.10	52		3.50	26.60	30.10	291.0	294.5	3.4		
87V-12	89.8	91.4	1.6	1.7	100.0	11228	4E4		8.31	3.52	4.79	46		7.73	26.27	34.00	294.5	299.8	5.6		

Hole Number: 87V-13

Number of intervals: 46

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	ZSOL. Fe	ZINSOL. Fe	ZTOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-13	41.9	42.8	0.9	0.9	100.0	30951	4G4		12.24	5.00	7.24	73		1.62	6.09	7.71	137.4	140.3	2.9	
87V-13	42.8	44.2	1.4	1.4	100.0	30952	4E0		0.88	0.61	0.27	16		1.71	37.69	39.40	140.3	144.9	4.6	
87V-13	44.2	44.8	0.6	0.6	100.0	30953	4G4		13.79	4.89	8.90	56		2.93	11.57	14.50	144.9	147.0	2.1	
87V-13	44.8	46.3	1.5	1.5	100.0	30954	4G4		22.50	11.50	11.00	107		2.70	10.60	13.30	147.0	152.0	5.0	
87V-13	46.3	47.7	1.4	1.6	100.0	30955	4E48		11.58	5.16	6.42	52		7.93	26.27	34.20	152.0	156.6	5.1	
87V-13	47.7	48.8	1.0	1.2	100.0	30956	4E0		4.86	1.87	2.99	18		4.85	34.05	38.90	156.6	160.0	4.1	
87V-13	48.8	49.7	0.9	0.9	100.0	30957	4E#0		0.78	0.45	0.33	14		0.99	30.61	31.60	160.0	162.9	3.0	
87V-13	49.7	50.7	1.0	1.3	100.0	30958	4E#0		2.91	0.99	1.92	14		1.94	25.46	27.40	162.9	166.3	4.3	
87V-13	50.7	51.6	0.9	1.0	100.0	30959	4G48		12.15	5.50	6.65	69		2.71	6.26	8.97	166.3	169.2	3.2	
87V-13	51.6	52.8	1.2	1.2	100.0	30960	4E08#		4.33	2.88	1.45	32		6.80	24.60	31.40	169.2	173.2	4.0	
87V-13	52.8	53.9	1.1	1.1	100.0	30961	4E08#		4.82	2.50	2.32	26		9.83	21.27	31.10	173.2	176.7	3.5	
87V-13	53.9	55.1	1.2	1.4	100.0	30962	4E1		0.58	0.34	0.24	16		4.92	32.28	37.20	176.7	180.7	4.5	
87V-13	55.1	56.4	1.3	1.3	100.0	30963	4E1		0.21	0.11	0.10	12		4.53	33.57	38.10	180.7	185.1	4.4	
87V-13	56.4	57.4	1.0	1.1	100.0	30964	4E1		1.04	0.82	0.22	16		6.39	26.81	33.20	185.1	188.3	3.7	
87V-13	57.4	59.0	1.6	1.6	100.0	30965	4E1#		0.72	0.63	0.09	14		1.66	29.34	31.00	188.3	193.5	5.2	
87V-13	59.0	60.3	1.3	1.4	100.0	30966	4E1		4.87	3.73	1.14	36		4.93	25.87	30.80	193.5	197.7	4.7	
87V-13	60.3	61.3	1.0	1.0	100.0	30967	4G4#8		10.09	4.40	5.69	50		3.19	18.01	21.20	197.7	201.0	3.3	
87V-13	61.3	62.6	1.3	1.3	100.0	30968	4J483		7.54	4.41	3.13	54		17.50	18.50	36.00	201.0	205.4	4.4	
87V-13	62.6	63.8	1.2	1.2	100.0	30969	4C3		0.84	0.51	0.33	19		3.38	26.42	29.80	205.4	209.4	4.0	
87V-13	63.8	65.2	1.3	1.4	100.0	30970	4C3		0.69	0.31	0.38	14		2.38	24.82	27.20	209.4	213.8	4.5	
87V-13	65.2	66.2	1.1	1.3	100.0	30971	4C3		2.78	1.51	1.27	35		3.31	24.79	28.10	213.8	217.3	4.3	
87V-13	66.2	67.5	1.3	1.4	100.0	30972	4C3		0.65	0.20	0.45	17		9.92	15.98	25.90	217.3	221.6	4.5	
87V-13	67.5	68.8	1.2	1.3	100.0	30973	4C3		1.58	0.56	1.02	17		2.14	20.06	22.20	221.6	225.7	4.3	
87V-13	68.8	70.1	1.3	1.3	100.0	30974	4C3		0.68	0.29	0.39	19		4.74	17.16	21.90	225.7	230.0	4.4	
87V-13	70.1	71.3	1.2	1.4	100.0	30975	4C3		0.79	0.41	0.38	23		2.44	30.76	33.20	230.0	233.9	4.6	
87V-13	71.3	72.2	0.9	0.9	100.0	30976	4C3		0.64	0.26	0.38	21		3.17	27.13	30.30	233.9	237.0	3.1	
87V-13	72.2	73.9	1.6	1.7	100.0	30977	4C0		0.80	0.36	0.44	17		4.08	15.72	19.80	237.0	242.4	5.6	
87V-13	73.9	75.0	1.1	1.0	97.1	30978	4L2C		1.64	0.45	1.19	14		4.02	14.28	18.30	242.4	245.9	3.4	
87V-13	75.0	75.9	0.9	1.3	100.0	30979	4L2C		1.62	0.41	1.21	10		5.05	8.55	13.60	245.9	249.0	4.3	
87V-13	75.9	78.7	2.8	2.6	91.4	30980	4L0		0.40	0.06	0.34	2		3.57	0.62	4.19	249.0	258.3	8.5	
87V-13	78.7	79.9	1.1	1.1	100.0	30981	4HE		1.15	0.38	0.77	20		13.20	25.80	39.00	258.3	262.0	3.7	
87V-13	79.9	81.0	1.1	1.0	94.4	30982	4E0		6.82	1.80	5.02	32		12.20	23.90	36.10	262.0	265.6	3.4	
87V-13	81.0	81.6	0.7	0.8	100.0	30983	4E0		7.99	3.15	4.84	44		8.77	30.73	39.50	265.6	267.8	2.5	
87V-13	81.6	83.0	1.3	1.5	100.0	30984	4E48		14.26	7.82	6.44	115		7.59	26.61	34.20	267.8	272.2	5.0	
87V-13	83.0	84.4	1.5	1.6	100.0	30985	4E48		15.44	9.64	5.80	107		7.77	26.83	34.60	272.2	277.0	5.1	
87V-13	84.4	85.9	1.5	1.5	98.0	30986	4E48		8.10	3.71	4.39	51		9.09	28.61	37.70	277.0	281.9	4.8	
87V-13	85.9	87.0	1.1	1.5	100.0	30987	4E48		9.98	5.17	4.81	69		5.61	29.99	35.60	281.9	285.5	4.8	
87V-13	87.0	88.7	1.7	1.7	100.0	30988	4G4		12.37	5.93	6.44	83		3.82	12.58	16.40	285.5	291.0	5.7	
87V-13	88.7	90.3	1.6	1.7	100.0	30989	4G4		7.51	3.09	4.42	52		8.82	18.38	27.20	291.0	296.2	5.7	
87V-13	90.3	91.6	1.3	1.2	90.5	30990	4HL		8.48	3.66	4.82	55		2.28	27.92	30.20	296.2	300.4	3.8	
87V-13	91.6	93.2	1.6	1.7	100.0	30991	4HL		5.60	2.35	3.25	41		1.92	24.28	26.20	300.4	305.8	5.5	
87V-13	93.2	94.5	1.2	1.3	100.0	30992	4E4		11.15	4.33	6.82	47		11.70	18.10	29.80	305.8	309.9	4.4	
87V-13	94.5	95.7	1.2	1.4	100.0	30993	4E4		18.24	6.34	11.90	64		6.30	21.50	27.80	309.9	313.9	4.6	
87V-13	95.7	97.3	1.6	1.6	100.0	30994	4E08		0.45	0.16	0.29	19		13.40	33.10	46.50	313.9	319.1	5.4	
87V-13	97.3	98.1	0.9	1.1	100.0	30995	4E1		1.03	0.18	0.85	14		5.84	29.46	35.30	319.1	322.0	3.5	
87V-13	98.1	99.4	1.2	1.2	97.5	30996	4E1		0.38	0.10	0.28	19		3.11	37.19	40.30	322.0	326.0	3.9	

Hole Number: 87V-14

Number of intervals: 11

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-14	9.9	11.5	1.6	1.7	100.0	11142	4C0		0.34	0.11	0.23	10		1.60	30.50	32.10	32.5	37.8	5.5	
87V-14	11.5	12.5	0.9	1.4	100.0	11143	4C0		0.98	0.18	0.80	4		1.30	8.80	10.10	37.8	40.9	4.5	
87V-14	12.5	13.8	1.3	1.3	95.5	11144	4E8		0.82	0.33	0.49	20		3.28	33.72	37.00	40.9	45.3	4.2	
87V-14	13.8	14.8	1.0	1.2	100.0	11145	4E8		1.39	0.75	0.64	26		8.31	28.69	37.00	45.3	48.5	3.8	
87V-14	14.8	16.1	1.3	1.4	100.0	11146	4E8		4.57	2.35	2.22	50		10.80	27.60	38.40	48.5	52.7	4.7	
87V-14	16.1	16.7	0.6	0.6	100.0	11147	4D43		4.30	1.61	2.69	35		3.26	25.14	28.40	52.7	54.7	2.0	
87V-14	16.7	17.7	1.1	1.2	100.0	11148	4D4#8		11.42	7.76	3.66	46		1.53	9.97	11.50	54.7	58.2	4.0	
87V-14	17.7	19.1	1.4	1.0	71.7	11149	4E#		1.05	0.63	0.42	14		2.48	22.32	24.80	58.2	62.8	3.3	
87V-14	19.1	20.3	1.2	1.5	100.0	11150	4E8		1.46	0.76	0.70	24		4.57	32.23	36.80	62.8	66.6	5.0	
87V-14	20.3	21.8	1.5	1.5	100.0	11151	4E8		0.82	0.47	0.35	19		2.78	27.32	30.10	66.6	71.4	4.8	
87V-14	21.8	22.9	1.1	1.4	100.0	11152	4E8		2.82	1.44	1.38	28		4.41	30.79	35.20	71.4	75.0	4.6	

Hole Number: 87V-15

Number of intervals: 17

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM.(ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-15	9.4	10.8	1.3	1.5	100.0	11229	4E48		9.58	5.22	4.36	67		12.10	18.40	30.50	31.0	35.3	4.9	
87V-15	10.8	12.2	1.4	1.4	95.7	11230	4E48		9.33	5.14	4.19	69		12.20	18.10	30.30	35.3	40.0	4.5	
87V-15	12.2	13.4	1.2	1.2	100.0	11231	4E48		6.60	3.44	3.16	50		6.19	25.61	31.80	40.0	44.0	4.0	
87V-15	13.4	14.4	1.0	1.2	100.0	11232	4G4		19.71	7.91	11.80	117		3.05	12.45	15.50	44.0	47.4	3.9	
87V-15	14.4	15.8	1.3	1.6	100.0	11233	4L612		4.06	1.58	2.48	24		2.73	7.15	9.88	47.4	51.7	5.2	
87V-15	15.8	17.1	1.4	1.5	100.0	11234	4G4&8		13.48	4.94	8.54	81		1.61	17.89	19.50	51.7	56.2	4.9	
87V-15	17.1	18.6	1.5	1.5	100.0	11235	4G4&8		13.67	4.77	8.90	77		2.87	15.13	18.00	56.2	61.0	4.8	
87V-15	18.6	19.9	1.3	1.5	100.0	11236	4G4&8		16.19	6.51	9.68	99		2.71	10.39	13.10	61.0	65.4	4.8	
87V-15	19.9	20.8	0.9	1.0	100.0	11237	4E48*		23.00	12.60	10.40	140		13.20	15.30	28.50	65.4	68.3	3.2	
87V-15	20.8	21.9	1.1	1.1	100.0	11238	4E48*		25.30	15.10	10.20	142		14.70	15.40	30.10	68.3	72.0	3.7	
87V-15	21.9	23.2	1.2	1.5	100.0	11239	4G4&8		18.12	8.02	10.10	91		2.97	10.83	13.80	72.0	76.0	4.9	
87V-15	23.2	24.1	0.9	0.9	100.0	11240	4C38&		5.83	2.10	3.73	40		4.12	20.68	24.80	76.0	79.0	3.0	
87V-15	24.1	25.3	1.2	1.5	100.0	11241	4C38&		2.47	1.28	1.19	30		6.10	21.10	27.20	79.0	82.9	5.0	
87V-15	25.3	26.2	0.9	0.9	100.0	11242	4E0&1		2.18	1.20	0.98	26		3.86	35.84	39.70	82.9	86.0	3.1	
87V-15	26.2	27.0	0.8	0.9	100.0	11243	4E0&1		0.39	0.11	0.28	14		1.46	40.64	42.10	86.0	88.7	3.1	
87V-15	27.0	28.4	1.4	1.5	100.0	11244	4C3&8		0.83	0.32	0.51	18		4.54	29.46	34.00	88.7	93.3	4.9	
87V-15	28.4	29.4	1.0	1.4	100.0	11245	4C3&8		1.02	0.44	0.58	16		7.31	27.89	35.20	93.3	96.5	4.6	

Hole Number: 87V-16

Number of intervals: 14

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-16	3.7	5.2	1.5	0.3	20.0	11490	4G4		12.02	6.42	5.60	99		3.58	8.92	12.50	12.0	17.0	1.0	
87V-16	5.2	6.0	0.8	0.9	100.0	11491	4G4		14.73	5.79	8.94	87		1.13	14.47	15.60	17.0	19.6	3.0	
87V-16	6.0	7.3	1.3	1.6	100.0	11492	4L62		2.45	1.10	1.35	13		2.63	2.14	4.77	19.6	24.0	5.3	
87V-16	7.3	8.4	1.1	1.5	100.0	11493	4E48		9.92	4.62	5.30	57		5.73	21.67	27.40	24.0	27.7	5.0	
87V-16	8.4	9.4	1.0	1.0	100.0	11494	4L24		1.80	0.38	1.42	9		5.26	4.94	10.20	27.7	30.9	3.2	
87V-16	18.9	19.8	0.9	1.2	100.0	11495	4A4		2.23	0.90	1.33	15		2.93	6.61	9.54	61.9	65.0	3.8	
87V-16	19.8	20.9	1.1	1.1	100.0	11496	4A4		5.72	2.12	3.60	28		3.45	5.58	9.03	65.0	68.5	3.5	
87V-16	27.7	28.9	1.1	1.2	100.0	11497	4G4		9.25	3.66	5.59	69		2.28	16.82	19.10	91.0	94.7	4.1	
87V-16	28.9	29.7	0.9	1.3	100.0	11498	4G4		15.90	7.04	8.86	88		4.23	17.17	21.40	94.7	97.5	4.2	
87V-16	29.7	31.1	1.4	1.3	95.6	11499	4G4		16.33	7.32	9.01	92		3.17	14.43	17.60	97.5	102.0	4.3	
87V-16	31.1	32.3	1.2	1.5	100.0	11500	4E468		14.60	7.11	7.49	71		8.80	19.10	27.90	102.0	106.0	5.0	
87V-16	32.3	33.3	1.0	1.3	100.0	30151	4E0		10.68	4.98	5.70	59		9.08	20.72	29.80	106.0	109.3	4.3	
87V-16	33.3	34.7	1.4	1.4	100.0	30152	4E0		3.86	1.76	2.10	34		4.72	28.78	33.50	109.3	113.9	4.7	
87V-16	34.7	35.8	1.1	1.5	100.0	30153	4E1		2.96	1.14	1.82	25		6.53	24.47	31.00	113.9	117.6	5.0	

Hole Number: 87V-17

Number of intervals: 16

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-17	7.8	8.4	0.7	0.8	100.0	30376	4G4		14.70	6.60	8.10	80		1.80	12.60	14.40	25.5	27.7	2.5	
87V-17	8.4	10.0	1.6	1.6	100.0	30377	4E081		2.37	1.78	0.59	23		7.12	29.38	36.50	27.7	32.9	5.4	
87V-17	10.0	11.3	1.2	1.4	100.0	30378	4E08		2.16	1.18	0.98	17		7.73	33.07	40.80	32.9	37.0	4.7	
87V-17	11.3	12.8	1.5	1.5	100.0	30379	4E081		1.02	0.59	0.43	14		3.77	31.33	35.10	37.0	42.0	5.0	
87V-17	12.8	13.9	1.1	1.4	100.0	30380	4E08		2.10	0.67	1.43	14		8.78	3.42	12.20	42.0	45.7	4.7	
87V-17	13.9	15.3	1.4	1.5	100.0	30381	4E08		2.33	0.92	1.41	16		10.90	31.30	42.20	45.7	50.2	5.0	*
87V-17	15.3	16.1	0.8	0.8	100.0	30382	4E48		9.12	3.62	5.50	32		9.60	19.80	29.40	50.2	52.7	2.6	
87V-17	16.1	17.4	1.3	1.5	100.0	30383	4E18		1.09	0.46	0.63	22		6.45	34.15	40.60	52.7	57.0	4.9	
87V-17	17.4	18.8	1.5	0.9	58.3	30384	4E18		2.11	1.24	0.87	22		5.08	29.32	34.40	57.0	61.8	2.8	
87V-17	18.8	19.9	1.0	1.1	100.0	30385	4C38		1.44	0.71	0.73	18		8.63	16.57	25.20	61.8	65.2	3.5	
87V-17	19.9	20.7	0.8	0.9	100.0	30386	4C08		4.21	2.58	1.63	32		8.07	10.03	18.10	65.2	67.8	2.9	
87V-17	20.7	21.9	1.3	1.3	100.0	30387	4C3		1.58	0.68	0.90	14		8.77	18.53	27.30	67.8	72.0	4.4	
87V-17	21.9	23.5	1.5	1.6	100.0	30388	4C0		0.72	0.25	0.47	14		4.32	24.28	28.60	72.0	77.0	5.1	
87V-17	23.5	24.5	1.1	1.3	100.0	30389	4C0		1.96	1.46	0.50	18		3.41	18.59	22.00	77.0	80.5	4.3	
87V-17	24.5	25.7	1.2	1.5	100.0	30390	4C0		2.15	1.73	0.42	22		4.50	17.10	21.60	80.5	84.4	4.8	
87V-17	25.7	27.1	1.4	1.4	100.0	30391	4C0		3.76	1.55	2.21	66		4.63	17.27	21.90	84.4	88.9	4.7	

Hole Number: 87V-18

Number of intervals: 19

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-18	8.9	9.9	1.0	0.9	84.8	11300	4A4		6.47	2.07	4.40	32		4.48	10.02	14.50	29.3	32.6	2.8	
87V-18	9.9	10.9	0.9	1.5	100.0	11386	4L62		0.78	0.13	0.65	4		4.63	1.76	6.39	32.6	35.7	4.8	
87V-18	10.9	12.0	1.1	1.5	100.0	11387	464		13.00	5.21	7.79	76		4.33	14.47	18.80	35.7	39.4	4.8	
87V-18	12.0	13.1	1.1	1.4	100.0	11388	464		12.92	5.74	7.18	83		6.50	12.30	18.80	39.4	43.0	4.6	
87V-18	13.1	13.9	0.8	0.9	100.0	11389	4D4		10.64	3.59	7.05	56		3.92	8.98	12.90	43.0	45.7	3.0	
87V-18	13.9	15.5	1.5	1.9	100.0	11390	4L624		1.61	0.62	0.99	10		3.38	1.98	5.36	45.7	50.7	6.3	
87V-18	15.5	16.9	1.4	1.4	100.0	11391	4L624		0.91	0.17	0.74	2		4.49	1.89	6.38	50.7	55.3	4.6	
87V-18	16.9	17.9	1.1	1.5	100.0	11392	4L624		0.80	0.21	0.59	4		6.88	4.22	11.10	55.3	58.8	4.8	
87V-18	17.9	20.1	2.2	1.6	72.2	11393	4L624		0.45	0.03	0.42	0		4.76	1.83	6.59	58.8	66.0	5.2	
87V-18	20.1	21.2	1.1	1.1	100.0	11394	5B6		0.36	0.04	0.32	0		2.29	0.98	3.27	66.0	69.6	3.6	
87V-18	21.2	21.8	0.5	0.6	100.0	11395	4L124		1.14	0.11	1.03	2		2.78	7.92	10.70	69.6	71.4	2.0	
87V-18	21.8	23.1	1.4	1.3	95.6	11396	4E41		5.88	2.40	3.48	48		7.26	24.74	32.00	71.4	75.9	4.3	
87V-18	23.1	24.2	1.0	1.4	100.0	11397	4E41		6.63	4.82	1.81	75		5.22	30.98	36.20	75.9	79.3	4.5	
87V-18	24.2	25.4	1.2	1.2	97.6	11398	4C3		0.64	0.11	0.53	17		2.27	29.73	32.00	79.3	83.4	4.0	
87V-18	25.4	26.4	0.9	1.2	100.0	11399	4C3		0.96	0.19	0.77	15		2.17	28.03	30.20	83.4	86.5	4.1	
87V-18	26.4	27.9	1.5	1.7	100.0	11400	4E0		7.70	3.13	4.57	40		5.67	25.43	31.10	86.5	91.5	5.7	
87V-18	27.9	29.4	1.5	1.7	100.0	11487	4E0		1.27	0.31	0.96	21		4.21	22.29	26.50	91.5	96.3	5.5	
87V-18	29.4	30.7	1.3	1.4	100.0	11488	4E0		2.60	0.87	1.73	27		5.22	22.18	27.40	96.3	100.7	4.7	
87V-18	30.7	32.0	1.3	1.4	100.0	11489	4E0		2.37	0.26	2.11	15		7.58	23.82	31.40	100.7	104.9	4.6	

Hole Number: 87V-19

Number of intervals: 17

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-19	7.1	8.4	1.3	1.3	100.0	30666	4E48		10.40	6.02	4.38	95		5.13	17.17	22.30	23.3	27.6	4.4	
87V-19	8.4	10.0	1.6	1.9	100.0	30667	4L024		1.33	0.83	0.50	10		2.94	2.66	5.60	27.6	32.8	6.2	
87V-19	15.6	16.2	0.6	0.7	100.0	30668	4L12		0.94	0.12	0.82	6		13.90	16.10	30.00	51.1	53.2	2.3	
87V-19	16.2	18.7	2.5	0.8	32.9	30669	4LE		3.05	0.89	2.16	18		9.12	12.08	21.20	53.2	61.4	2.7	
87V-19	18.7	20.4	1.7	2.1	100.0	30670	4E4		6.20	2.09	4.11	30		14.80	18.10	32.90	61.4	67.0	7.0	
87V-19	20.4	22.3	1.9	2.0	100.0	30671	4E41		6.67	2.59	4.08	26		7.04	21.46	28.50	67.0	73.1	6.4	
87V-19	22.3	23.8	1.5	1.6	100.0	30672	4D348		3.68	1.07	2.61	14		6.55	19.25	25.80	73.1	78.0	5.4	
87V-19	23.8	25.5	1.8	1.3	72.4	30673	4D348		11.38	4.68	6.70	40		5.08	20.12	25.20	78.0	83.8	4.2	
87V-19	25.5	26.8	1.3	1.5	100.0	30674	4C3		3.51	1.08	2.43	26		3.52	25.98	29.50	83.8	88.0	5.0	
87V-19	26.8	28.3	1.5	1.7	100.0	30675	4C3		2.30	0.39	1.91	14		5.26	21.14	26.40	88.0	93.0	5.6	
87V-19	28.3	29.6	1.2	1.4	100.0	30676	4EC		7.96	1.66	6.30	26		7.51	18.09	25.60	93.0	97.0	4.6	
87V-19	29.6	30.6	1.0	1.1	100.0	30677	4E418		20.42	9.12	11.30	117		13.00	11.60	24.60	97.0	100.3	3.5	
87V-19	30.6	31.8	1.2	1.2	92.7	30678	4E418		10.66	6.12	4.54	65		13.10	15.20	28.30	100.3	104.4	3.8	
87V-19	31.8	33.2	1.4	1.4	100.0	30679	4C0		1.12	0.27	0.85	14		5.29	16.11	21.40	104.4	109.0	4.7	
87V-19	33.2	36.0	2.7	0.8	30.0	30680	4EL		1.10	0.33	0.77	8		4.74	8.56	13.30	109.0	118.0	2.7	
87V-19	36.0	36.9	0.9	0.8	83.3	30681	4L06		0.38	0.14	0.24	6		4.03	6.17	10.20	118.0	121.0	2.5	
87V-19	36.9	37.8	0.9	0.9	93.3	30682	4E08		2.13	0.70	1.43	20		8.51	25.69	34.20	121.0	124.0	2.8	

Hole Number: 87V-20

Number of intervals: 10

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-20	16.3	17.7	1.5	1.8	100.0	30351	4B4		13.97	6.16	7.81	101		3.30	16.70	20.00	53.4	58.2	5.8	
87V-20	17.7	18.7	1.0	1.0	100.0	30352	4E08		4.61	1.99	2.62	40		7.96	33.64	41.60	58.2	61.4	3.2	
87V-20	18.7	19.7	1.0	1.1	100.0	30353	4F4		14.63	6.17	8.46	91		22.90	-6.90	16.00	61.4	64.6	3.2	
87V-20	19.7	20.7	1.0	1.0	100.0	30354	4E08		3.64	2.15	1.49	32		7.24	3.56	10.80	64.6	67.8	3.2	
87V-20	20.7	21.8	1.1	1.3	100.0	30355	4E08		0.93	0.61	0.32	24		9.48	24.52	34.00	67.8	71.5	4.3	
87V-20	21.8	23.1	1.3	1.4	100.0	30356	4E08		2.73	1.47	1.26	32		9.40	26.00	35.40	71.5	75.8	4.5	
87V-20	23.1	24.4	1.3	1.3	100.0	30357	4A4		9.16	3.36	5.80	53		2.16	8.14	10.30	75.8	80.0	4.3	
87V-20	24.4	25.4	1.0	1.1	100.0	30358	4A4		7.33	2.64	4.69	40		2.56	6.89	9.45	80.0	83.4	3.6	
87V-20	25.4	26.8	1.3	1.6	100.0	30359	4A0		3.97	1.85	2.12	27		2.99	8.01	11.00	83.4	87.8	5.2	
87V-20	26.8	28.1	1.4	1.6	100.0	30360	4A0		3.45	1.22	2.23	18		3.73	5.47	9.20	87.8	92.3	5.3	

Hole Number: 87V-21

Number of intervals: 15

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-21	7.5	9.8	2.3	1.3	58.7	30361	4E0		5.54	4.91	0.63	71		0.67	39.33	40.00	24.5	32.0	4.4	
87V-21	9.8	11.2	1.5	0.7	45.8	30362	4E0		3.28	2.81	0.47	59		0.58	39.42	40.00	32.0	36.8	2.2	
87V-21	11.2	15.2	4.0	2.7	67.4	30363	5B6		1.15	0.66	0.49	8		0.89	5.36	6.25	36.8	50.0	8.9	
87V-21	15.2	18.5	3.2	3.3	100.0	30364	5B6		2.00	0.84	1.16	10		4.54	2.33	6.87	50.0	60.6	10.7	
87V-21	18.5	19.5	1.0	1.5	100.0	30365	4E4		11.92	5.85	6.07	91		2.62	22.88	25.50	60.6	64.0	4.9	
87V-21	19.5	20.8	1.3	1.8	100.0	30366	4G48		13.06	5.09	7.97	83		3.42	9.08	12.50	64.0	68.2	5.8	
87V-21	20.8	22.1	1.3	1.4	100.0	30367	4E08		2.22	1.00	1.22	16		4.33	28.47	32.80	68.2	72.6	4.7	
87V-21	22.1	23.5	1.3	1.8	100.0	30368	4E08		4.28	2.08	2.20	38		6.56	22.64	29.20	72.6	77.0	5.8	
87V-21	23.5	24.9	1.4	1.5	100.0	30369	4E08		4.07	1.98	2.09	32		11.00	18.60	29.60	77.0	81.6	5.0	
87V-21	24.9	26.2	1.3	1.6	100.0	30370	5A196		1.62	0.46	1.16	10		3.96	4.23	8.19	81.6	86.0	5.1	
87V-21	26.2	27.3	1.1	1.4	100.0	30371	5A196		0.39	0.11	0.28	4		2.45	2.47	4.92	86.0	89.5	4.7	
87V-21	27.3	28.4	1.2	1.5	100.0	30372	5A196		0.47	0.08	0.39	4		3.17	2.11	5.28	89.5	93.3	5.0	
87V-21	28.4	29.6	1.2	1.5	100.0	30373	5A196		0.34	0.06	0.28	4		1.97	1.79	3.76	93.3	97.1	5.0	
87V-21	29.6	31.1	1.5	1.6	100.0	30374	4E0		1.86	1.06	0.80	26		4.84	27.26	32.10	97.1	102.0	5.2	
87V-21	31.1	31.7	0.6	0.8	100.0	30375	4C5		2.93	1.46	1.47	26		2.96	8.54	11.50	102.0	104.0	2.5	

Hole Number: 87V-22

Number of intervals: 16

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY	MISSING SAMP
87V-22	7.4	8.8	1.4	1.5	100.0	30335	464		12.37	5.65	6.72	99		1.08	11.32	12.40	24.3	29.0	5.0		
87V-22	8.8	10.2	1.3	1.5	100.0	30336	464		12.12	5.21	6.91	70		1.56	6.98	8.54	29.0	33.4	4.8		
87V-22	10.2	11.1	0.9	1.2	100.0	30337	464		13.21	5.26	7.95	49		4.20	12.70	16.90	33.4	36.5	4.0		
87V-22	11.1	12.8	1.7	0.5	29.1	30338	4E4		19.83	10.70	9.13	99		3.03	16.27	19.30	36.5	42.0	1.6		
87V-22	12.8	14.2	1.4	1.7	100.0	30339	4E4		16.63	10.40	6.23	111		4.67	21.13	25.80	42.0	46.5	5.5		
87V-22	14.2	15.0	0.8	1.5	100.0	30340	4E4		5.74	2.78	2.96	91		4.09	31.31	35.40	46.5	49.2	4.8		
87V-22	15.0	16.1	1.1	1.5	100.0	30341	464		13.93	6.40	7.53	61		5.09	12.91	18.00	49.2	52.8	4.8		
87V-22	16.1	17.5	1.4	1.5	100.0	30342	464		14.84	7.31	7.53	67		6.60	10.20	16.80	52.8	57.5	5.0		
87V-22	17.5	18.2	0.7	0.8	100.0	30343	4E0		1.87	0.73	1.14	40		3.52	32.78	36.30	57.5	59.7	2.6		
87V-22	18.2	19.2	1.0	1.1	100.0	30344	10B9		11.82	3.15	8.67	46		7.78	2.22	10.00	59.7	63.0	3.5		
87V-22	19.2	19.8	0.6	0.9	100.0	30345	4E0		8.76	5.15	3.61	69		4.52	29.28	33.80	63.0	64.9	2.8		
87V-22	19.8	21.5	1.7	1.5	85.7	30346	4L24		2.07	1.18	0.89	10		4.86	6.34	11.20	64.9	70.5	4.8		
87V-22	21.5	22.6	1.2	1.4	100.0	30347	10B9		3.18	1.35	1.83	14		4.76	6.74	11.50	70.5	74.3	4.5		
87V-22	22.6	23.7	1.1	1.6	100.0	30348	464		0.00	0.00					0.00		74.3	77.9	5.2		
87V-22	23.7	25.0	1.2	1.1	90.2	30349	4L24		1.86	0.68	1.18	6		5.61	8.09	13.70	77.9	82.0	3.7		
87V-22	25.0	25.3	0.3	0.5	100.0	30350	4E45		2.86	0.98	1.88	14		9.49	21.51	31.00	82.0	83.1	1.5		

Hole Number: 87V-23

Number of intervals: 17

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-23	5.1	6.7	1.6	1.4	84.9	30997	464		14.15	6.40	7.75	99		0.51	10.99	11.50	16.7	22.0	4.5	
87V-23	6.7	8.4	1.6	0.5	27.8	30998	464		12.89	4.41	8.48	64		4.62	13.38	18.00	22.0	27.4	1.5	
87V-23	8.4	10.5	2.1	2.0	95.7	30999	5B62		1.04	0.15	0.89	0		9.93	0.87	10.80	27.4	34.3	6.6	
87V-23	10.5	11.6	1.2	1.2	100.0	31000	4D84		4.79	2.02	2.77	19		8.82	14.28	23.10	34.3	38.2	4.1	
87V-23	11.6	12.8	1.2	1.1	97.4	30601	4D84		5.69	2.41	3.28	25		9.69	15.01	24.70	38.2	42.0	3.7	
87V-23	12.8	14.2	1.4	1.5	100.0	30602	4C3		0.79	0.37	0.42	4		4.11	24.99	29.10	42.0	46.6	4.9	
87V-23	14.2	15.3	1.1	1.1	100.0	30603	4D8		4.46	2.45	2.01	27		20.20	10.30	30.50	46.6	50.1	3.5	
87V-23	15.3	16.1	0.9	0.8	89.3	30604	4D8		4.98	2.13	2.85	33		11.20	15.40	26.60	50.1	52.9	2.5	
87V-23	16.1	17.1	0.9	1.1	100.0	30605	4C0		3.46	1.21	2.25	26		6.34	17.46	23.80	52.9	56.0	3.6	
87V-23	17.1	18.4	1.3	1.4	100.0	30606	4E14		10.24	4.70	5.54	57		19.00	13.70	32.70	56.0	60.4	4.5	
87V-23	18.4	19.7	1.2	1.4	100.0	30607	4E14		8.13	4.39	3.74	53		23.20	11.00	34.20	60.4	64.5	4.6	
87V-23	19.7	20.9	1.2	1.3	100.0	30608	4E14		4.50	2.84	1.66	37		14.20	17.80	32.00	64.5	68.6	4.2	
87V-23	20.9	21.8	0.9	0.9	100.0	30609	4D7		4.82	3.06	1.76	39		21.40	3.60	25.00	68.6	71.6	3.0	
87V-23	21.8	23.2	1.3	1.5	100.0	30610	4E14B		12.00	5.38	6.62	66		8.96	10.64	19.60	71.6	76.0	5.0	
87V-23	23.2	24.4	1.2	1.4	100.0	30611	4E18		1.96	0.68	1.28	20		7.39	20.81	28.20	76.0	79.9	4.6	
87V-23	24.4	25.4	1.0	1.5	100.0	30612	4C0		1.44	0.68	0.76	18		3.87	16.33	20.20	79.9	83.3	4.8	
87V-23	25.4	26.7	1.3	1.5	100.0	30613	4C0		0.97	0.25	0.72	11		6.46	13.74	20.20	83.3	87.5	5.0	

Hole Number: 87V-25

Number of intervals: 36

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-25	27.4	29.0	1.5	0.3	20.0	30251	4A0		1.18	0.78	0.40	29		2.06	1.05	3.11	90.0	95.0	1.0	
87V-25	29.0	33.3	4.3	0.5	10.6	30167	4A0		6.94	3.79	3.15	38		2.83	7.77	10.60	95.0	109.1	1.5	
87V-25	33.3	34.7	1.5	1.0	67.3	30168	4E4		13.32	8.34	4.98	84		5.61	27.39	33.00	109.1	114.0	3.3	
87V-25	34.7	35.7	0.9	0.9	100.0	30169	4E4B		10.23	5.38	4.85	72		13.70	15.00	28.70	114.0	117.0	3.0	
87V-25	35.7	36.6	1.0	1.0	100.0	30170	4E4B		9.03	5.34	3.69	80		14.30	19.30	33.60	117.0	120.2	3.4	
87V-25	36.6	38.1	1.5	1.5	100.0	30171	4G4#		16.95	7.52	9.43	116		2.12	12.28	14.40	120.2	125.1	4.9	
87V-25	38.1	39.9	1.8	1.5	84.7	30172	4G4#		8.81	4.19	4.62	56		3.64	15.06	18.70	125.1	131.0	5.0	
87V-25	39.9	40.8	0.9	0.9	96.7	30173	4E44		12.21	4.86	7.35	62		4.15	23.05	27.20	131.0	134.0	2.9	
87V-25	40.8	41.8	0.9	0.6	66.7	30174	4E44		12.90	4.98	7.92	66		7.60	17.70	25.30	134.0	137.0	2.0	
87V-25	41.8	43.3	1.5	0.9	60.0	30175	4E#0		3.87	2.49	1.38	25		3.33	33.27	36.60	137.0	142.0	3.0	
87V-25	43.3	44.8	1.5	1.3	84.0	30176	4E#0		4.66	3.37	1.29	27	0.00	3.23	31.27	34.50	142.0	147.0	4.2	
87V-25	44.8	46.3	1.5	1.2	78.0	30177	4E#0		3.19	1.68	1.51	14		3.78	30.12	33.90	147.0	152.0	3.9	
87V-25	46.3	46.9	0.6	0.8	100.0	30178	4E#0		3.65	1.84	1.81	17		3.85	29.65	33.50	152.0	154.0	2.5	
87V-25	46.9	48.4	1.5	1.5	100.0	30179	4E64		11.38	4.46	6.92	69		2.09	19.01	21.10	154.0	158.8	5.0	
87V-25	48.4	49.1	0.7	0.8	100.0	30180	4E46		15.96	9.40	6.56	73		3.38	16.62	20.00	158.8	161.0	2.5	
87V-25	49.1	50.3	1.2	0.8	65.0	30181	4E4		8.62	3.66	4.96	41		2.22	26.48	28.70	161.0	165.0	2.6	
87V-25	50.3	51.9	1.6	1.8	100.0	30182	4G4		14.16	5.23	8.93	54		3.22	14.08	17.30	165.0	170.3	5.8	
87V-25	51.9	53.0	1.1	1.3	100.0	30183	4E4		5.96	2.24	3.72	26		4.32	30.18	34.50	170.3	174.0	4.4	
87V-25	53.0	53.9	0.9	1.1	100.0	30184	4E46#		9.55	4.30	5.25	45		2.34	27.36	29.70	174.0	177.0	3.5	
87V-25	53.9	54.9	0.9	1.3	100.0	30185	4E46#		10.77	4.62	6.15	41		2.29	24.81	27.10	177.0	180.1	4.4	
87V-25	54.9	56.2	1.3	1.4	100.0	30186	4E46#		11.70	4.86	6.84	54		2.31	23.79	26.10	180.1	184.5	4.6	
87V-25	56.2	58.5	2.3	1.4	61.3	30187	4G4		13.00	4.65	8.35	67		2.45	15.55	18.00	184.5	192.0	4.6	
87V-25	58.5	60.0	1.5	1.2	80.0	30188	4L62		9.03	3.12	5.91	41		7.00	10.20	17.20	192.0	197.0	4.0	*
87V-25	60.0	61.5	1.5	1.5	98.0	30189	4E44		9.52	3.53	5.99	59		4.11	26.09	30.20	197.0	201.9	4.8	
87V-25	61.5	62.5	0.9	0.4	41.9	30190	4AL		9.11	3.52	5.59	56		4.86	7.54	12.40	201.9	205.0	1.3	
87V-25	62.5	63.6	1.1	0.7	66.7	30191	4E64		13.78	5.94	7.84	79		2.86	19.24	22.10	205.0	208.6	2.4	
87V-25	63.6	65.2	1.6	2.3	100.0	30192	4G4		14.35	5.43	8.92	81		2.60	18.90	21.50	208.6	214.0	7.5	
87V-25	65.2	66.6	1.4	1.8	100.0	30193	4G4		16.83	8.36	8.47	110		3.57	18.03	21.60	214.0	218.6	6.0	
87V-25	66.6	68.1	1.5	1.9	100.0	30194	4G4		13.14	5.48	7.66	85		2.81	18.39	21.20	218.6	223.4	6.3	
87V-25	68.1	69.2	1.1	1.2	100.0	30195	4G4		14.57	6.38	8.19	97		6.86	17.94	24.80	223.4	227.0	4.1	
87V-25	69.2	70.3	1.1	1.3	100.0	30196	4G4		19.10	9.19	9.91	102		4.46	20.04	24.50	227.0	230.5	4.4	
87V-25	70.3	71.2	1.0	1.3	100.0	30197	4G4		15.12	6.92	8.20	71		3.25	17.05	20.30	230.5	233.7	4.2	
87V-25	71.2	72.3	1.1	1.2	100.0	30198	4G4		16.13	6.61	9.52	89		2.45	19.85	22.30	233.7	237.3	3.8	
87V-25	72.3	73.5	1.1	1.5	100.0	30199	4E0		6.39	3.76	2.63	52		7.31	29.49	36.80	237.3	241.0	5.0	
87V-25	73.5	75.0	1.6	1.5	96.2	30200	4E0		6.66	3.82	2.84	58		4.07	34.83	38.90	241.0	246.2	5.0	
87V-25	75.0	75.6	0.5	0.7	100.0	30252	4L0		8.42	3.35	5.07	60		4.64	7.66	12.30	246.2	248.0	2.2	

Hole Number: 87V-26

Number of intervals: 2

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tnn)	Au (g/tnn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-26	46.4	47.7	1.3	1.6	100.0	11401	4L24		0.63	0.10	0.53	2		4.84	3.60	8.44	152.3	156.5	5.2	
87V-26	47.7	48.8	1.1	1.4	100.0	11402	4L24		0.27	0.04	0.23	2		4.02	1.58	5.60	156.5	160.0	4.5	

Hole Number: 87V-27

Number of intervals: 45

DDHID	FROM (m)	TO (m)	INT.(m)	REC.(m)	REC.(%)	SAMPLE #	ROCK TYPE	PULP S.G.	% Pb+Zn	% Pb	% Zn	Ag (g/tonn)	Au (g/tonn)	%SOL. Fe	%INSOL. Fe	%TOT. Fe	FROM (ft)	TO (ft)	REC.(ft)	RE-ASSAY MISSING SAMP
87V-27	30.8	32.6	1.8	1.4	76.3	30253	4A4		2.17	1.01	1.16	16		2.48	4.12	6.60	100.9	106.8	4.5	
87V-27	32.6	33.5	0.9	1.2	100.0	30254	4A4		9.01	2.74	6.27	46		1.06	-0.41	0.65	106.8	109.8	3.9	*
87V-27	33.5	35.1	1.6	1.4	88.5	30255	4A0		0.60	0.26	0.34	10		0.67	8.37	9.04	109.8	115.0	4.6	
87V-27	35.1	36.4	1.3	1.4	100.0	30256	4A0		1.03	0.38	0.65	14		1.45	12.15	13.60	115.0	119.4	4.7	
87V-27	36.4	37.8	1.4	1.5	100.0	30257	4A0		0.48	0.14	0.34	10		0.70	11.80	12.50	119.4	123.9	4.9	
87V-27	37.8	39.1	1.3	1.5	100.0	30258	4A0		0.50	0.20	0.30	10		0.80	12.20	13.00	123.9	128.3	4.8	
87V-27	39.1	40.3	1.2	1.4	100.0	30259	4A0		0.80	0.19	0.61	12		0.91	13.79	14.70	128.3	132.1	4.7	
87V-27	40.3	41.8	1.5	1.5	100.0	30260	4A0		1.70	0.43	1.27	10		0.85	11.15	12.00	132.1	137.0	5.0	
87V-27	41.8	43.0	1.2	1.4	100.0	30261	4A0		0.00						0.00		137.0	141.1	4.6	*
87V-27	43.0	44.2	1.2	1.5	100.0	30262	4A0		0.50	0.14	0.36	4		1.05	5.67	6.72	141.1	145.1	4.9	
87V-27	44.2	45.6	1.3	1.5	100.0	30263	4A0		0.74	0.45	0.29	22		2.11	28.49	30.60	145.1	149.5	4.9	
87V-27	45.6	46.9	1.4	1.5	100.0	30264	4A0		1.08	0.51	0.57	12		1.37	6.18	7.55	149.5	154.0	5.0	
87V-27	46.9	48.1	1.1	1.5	100.0	30265	4A0		7.39	3.08	4.31	56		3.08	13.12	16.20	154.0	157.7	5.0	
87V-27	48.1	49.6	1.5	1.3	89.8	30266	4A0		2.61	1.15	1.46	17		1.46	3.26	4.72	157.7	162.6	4.4	
87V-27	49.6	51.1	1.5	1.3	89.8	30267	4A0		1.48	0.40	1.08	8		0.98	4.11	5.09	162.6	167.5	4.4	
87V-27	51.1	53.0	2.0	1.5	76.9	30268	4A0		0.78	0.24	0.54	7		0.65	5.30	5.95	167.5	174.0	5.0	
87V-27	53.0	54.3	1.2	1.4	100.0	30269	4A0		1.61	0.70	0.91	15		0.99	5.17	6.16	174.0	178.0	4.7	
87V-27	54.3	55.5	1.2	1.5	100.0	30270	4A0		2.48	1.16	1.32	17		1.37	4.81	6.18	178.0	182.0	4.9	
87V-27	55.5	56.8	1.4	1.5	100.0	30271	4A0		2.60	1.04	1.56	15		2.21	6.29	8.50	182.0	186.5	4.8	
87V-27	56.8	58.2	1.4	1.5	100.0	30272	4A0		0.34	0.10	0.24	6		1.26	7.23	8.49	186.5	191.0	4.8	
87V-27	58.2	59.5	1.2	1.4	100.0	30273	4A0		0.78	0.12	0.66	6		1.47	10.43	11.90	191.0	195.1	4.7	
87V-27	59.5	60.9	1.4	1.4	97.8	30274	4A0		2.10	0.85	1.25	19		1.88	4.74	6.62	195.1	199.7	4.5	
87V-27	60.9	62.2	1.3	1.4	100.0	30275	4A4		6.93	2.21	4.72	29		1.85	1.52	3.37	199.7	204.0	4.7	
87V-27	62.2	63.3	1.2	1.3	100.0	30276	4A4		6.53	2.24	4.29	35		1.35	2.51	3.86	204.0	207.8	4.2	
87V-27	63.3	64.6	1.3	1.3	100.0	30277	4A4		7.02	1.98	5.04	27		1.38	2.79	4.17	207.8	212.1	4.3	
87V-27	64.6	65.3	0.6	0.7	100.0	30278	4E4		13.70	5.39	8.31	81		1.55	28.05	29.60	212.1	214.2	2.2	
87V-27	65.3	67.1	1.9	2.0	100.0	30279	4L6		0.28	0.01	0.27	2		3.66	0.79	4.45	214.2	220.3	6.5	
87V-27	67.1	68.5	1.4	1.5	100.0	30280	4L6		2.65	0.98	1.67	14		4.71	3.63	8.34	220.3	224.8	4.9	
87V-27	68.5	68.9	0.4	0.6	100.0	30281	4H4		17.98	7.78	10.20	107		30.70	1.80	32.50	224.8	226.0	2.0	
87V-27	68.9	70.2	1.3	1.4	100.0	30282	4L76		1.60	0.70	0.90	12		41.60	-36.21	5.39	226.0	230.2	4.6	*
87V-27	70.2	70.8	0.6	0.6	100.0	30283	4G48		13.88	4.91	8.97	87		5.50	5.80	11.30	230.2	232.2	2.0	
87V-27	70.8	72.3	1.6	1.7	100.0	30284	4LD		1.98	0.84	1.14	14		7.13	1.31	8.44	232.2	237.3	5.6	
87V-27	72.3	73.5	1.2	1.3	100.0	30285	4L		2.81	1.97	0.84	38		7.74	1.29	9.03	237.3	241.2	4.2	
87V-27	73.5	74.9	1.4	1.7	100.0	30286	4HJ		15.72	8.78	6.94	87		31.00	1.20	32.20	241.2	245.7	5.5	
87V-27	74.9	75.6	0.7	0.8	100.0	30287	4G4		14.44	6.44	8.00	109		13.80	7.70	21.50	245.7	248.0	2.5	
87V-27	75.6	76.9	1.3	1.3	100.0	30288	4L124		2.78	1.27	1.51	26		3.35	3.95	7.30	248.0	252.4	4.4	
87V-27	76.9	78.8	1.8	1.9	100.0	30289	4E4		14.21	6.21	8.00	32		1.89	22.41	24.30	252.4	258.4	6.3	
87V-27	78.8	80.1	1.3	1.5	100.0	30290	4E4		0.00						0.00		258.4	262.8	5.0	*
87V-27	80.1	80.9	0.8	1.0	100.0	30291	4D4		11.61	5.60	6.01	91		9.38	10.32	19.70	262.8	265.5	3.2	
87V-27	80.9	82.0	1.0	1.2	100.0	30292	4G4		11.15	5.10	6.05	67		2.11	17.29	19.40	265.5	268.9	3.8	
87V-27	82.0	83.3	1.4	1.4	100.0	30293	4E48		5.95	2.98	2.97	40		16.90	13.80	30.70	268.9	273.4	4.7	
87V-27	83.3	84.2	0.9	1.2	100.0	30294	4E1		2.73	1.11	1.62	24		5.46	25.14	30.60	273.4	276.3	3.8	
87V-27	84.2	85.9	1.6	1.7	100.0	30295	4E148		8.11	2.71	5.40	34		5.62	15.08	20.70	276.3	281.7	5.5	
87V-27	85.9	86.5	0.7	0.7	100.0	30296	4E148		1.35	0.44	0.91	10		14.20	12.60	26.80	281.7	283.9	2.4	
87V-27	86.5	87.4	0.9	0.9	100.0	30297	5B624		0.45	0.18	0.27	6		6.80	3.60	10.40	283.9	286.7	3.1	