

020253 Grum
Excl
metallurgy

Curragh Resources Inc.

Inter-Office Memorandum

TO: Colin Benner, Jim Moore, Gregg Jilson, Eric Beaumont, Cam Reid
FROM: Godfrey McDonald
SUBJECT: Grum Deposit - Stage 1 Pit DATE: February 13, 1991
Metallurgical Testwork

The laboratory test programme run in 1989-90 involved four ore composites that were prepared from diamond drill whole and split core. These composites were identified by rock type and represented the entire ore reserve (Stage 1 and the Final open pit areas). A description of the 1989-90 composites is as follows:

- Composite G1
 - contains 4A material (sulphide-bearing, ribbon-banded, graphitic quartzite)
 - represents 53% of Stage 1 pit ore and 49 % of final pit ore
- Composite G^{2 ?}@
 - high-grade non-carbonaceous quartz
 - represents 13% of Stage 1 pit ore and 14% of final pit ore
- Composite G3
 - massive sulphide (core contained drilling additives that are possibly deleterious to metallurgical performance)
- Composite G4
 - massive sulphide (clean core - not drilling additives)
 - represents 33% of Stage 1 pit ore and 37% of final pit ore.

The process flowsheet, reagent scheme and projected metallurgical response for each ore type has been developed, refer to the Lakefield Research report "the Recovery of Lead and Zinc from Grum Ore Samples - Progress Report 3, January 25, 1990."

The on-going metallurgical programme must focus on the Stage 1 pit ore and especially the first 12 month production period. The programme will involve:

a) Inspect several diamond drill holes to access the degree of porous, altered ore that exists.

- 68W/2.5N there is an upper massive sulphide lense (look at DD hole 87-G-05)
- 66W/2.5-3.0N there is more massive sulphide, the FAGU159 area (look at DD hole 89-G-29).

Godfrey
+
Carr

b) To select and inspect several diamond drill holes that have massive sulphide intersections which appear altered and finer grained than the rest of the massive sulphide occurrences.

- 60W (look at DD hole 88-G-03, ~~89-G-34~~, and ~~89-G-35~~)

11

c) Do mineralogy and laboratory flotation tests to determine the metallurgical performance.

If this investigation does detect a poorer metallurgical response than projected from the 1989-90 programme; then identification of the problematic ore (type and deposition) must be made, relative tonnages calculated and a large sample acquired for laboratory testwork, even a pilot plant test would be considered.

Schedule

Inspect diamond drill core February 18 to 22, 1991
Review diamond drill logs

Mineralogy March 1991
Laboratory testwork

