

020256

CIRQUE PROJECT

Rock Type 1		INCREMENT				ASSAYS				UNITS				REMAINING
HOLE #	SAMPLE #	FROM	TO	LENGTH	SPL. WT.	Pb%	Zn%	Ag g/t	Cu%	Pb	Zn	Ag	Cu	
90-08-20	41266	45.0	47.2	1.0	800	2.95	5.60	34.9	34.00					2277
	41267	47.2	48.8	1.6	1200	2.10	7.04	33.2	41.70					48
	41268	48.8	50.9	2.1	1600	1.09	5.59	32.4	36.40					385
	41269	50.9	52.7	1.8	1400	0.23	4.40	20.0	38.40					—
	41270	52.7	53.5	0.8	480	1.50	3.20	18.6	42.00					—
	41271	53.5	54.9	1.4	1200	3.60	3.57	18.3	38.50					—
	41272	54.9	56.2	1.3	1040	5.70	6.10	34.9	30.00					2850
90-08-21	41282	42.7	44.0	1.3	1040	1.76	4.45	23.7	28.50					1186
	41283	44.0	44.8	0.8	640	2.49	12.25	60.2	8.64					265
	41284	44.8	45.7	0.9	720	1.37	9.98	47.3	19.00					1169
	41285	45.7	47.2	1.5	1200	0.44	3.82	54.0	17.70					178
	41286	47.2	49.7	2.5	720	3.10	6.60	35.8	28.40					925
	41288	49.7	51.2	1.5	1200	2.15	5.87	44.0	32.00					178
	41289	51.2	52.4	1.2	960	2.08	4.05	28.3	39.60					1846
	41290	52.4	53.3	0.9	720	6.42	3.86	16.1	38.00					364
90-08-23	41388	48.9	50.3	1.4	1120	5.12	9.60	38.8	30.40					2484
	41389	50.3	51.8	1.5	1200	1.39	8.33	41.0	2.70					1144
	41390	51.8	53.3	1.5	1200	0.85	4.87	16.2	38.20					2250
	41391	53.3	54.9	1.6	1200	4.08	5.50	14.6	33.20					2328
90-08-24	41612	55.7	57.2	1.5	1200	3.37	6.63	38.2	33.00					2857
	41613	57.2	58.7	1.5	1200	4.13	6.62	44.7	34.10					2893
	41614	58.7	59.5	0.8	640	2.51	9.05	44.3	31.80					1808
90-08-25	41659	70.4	71.9	1.5	1200	1.63	6.64	40.0	32.70					2247
	41660	71.9	73.4	1.5	1200	1.20	8.23	38.3	33.80					2762
	41661	73.4	74.9	1.5	1200	2.60	7.38	35.6	33.20					3478
	41662	74.9	76.4	1.5	1200	1.16	6.36	33.8	35.00					3134
	41663	76.4	77.9	1.5	1200	0.84	5.54	18.5	33.70					3038
	41680	87.0	88.1	1.1	880	3.99	6.14	40.3	35.00					1724
	41682	88.1	89.3	1.2	960	3.62	7.40	43.2	34.00					1637
90-08-20	41919	52.7	54.9	2.2	1760	2.03	7.60	48.0	27.50					50
	41920	54.9	56.4	1.5	1200	3.18	11.20	73.8	19.40					—
	41921	56.4	57.9	1.5	1200	1.44	5.94	40.0	32.00					—
	41922	57.9	59.4	1.5	1200	4.25	8.17	87.0	24.10					50
	41923	59.4	61.0	1.6	1200	3.91	6.80	68.4	25.00					—
	41924	61.0	62.5	1.5	1200	4.26	11.40	117.0	18.90					709
	41925	62.5	63.4	0.9	720	1.82	7.24	40.4	29.50					50
90-08-21	42010	84.7	86.4	1.7	1360	5.74	8.00	63.7	29.00					2880
	42011	86.4	87.9	1.5	1200	4.00	7.56	62.9	31.00					2459
	42012	87.9	89.8	1.9	1520	3.19	8.83	68.1	31.90					1686
90-08-24	42461	79.7	80.2	0.5	1200	3.56	7.96	61.6	32.50					2261
	42462	80.2	81.8	1.6	1280	3.97	8.20	66.0	19.00					2802
	42463	81.8	83.1	1.3	1040	2.89	8.93	59.2	29.40					2662
	42464	83.1	84.4	1.3	1040	3.40	7.62	50.4	33.00					1938
	42465	84.4	85.4	1.0	800	3.19	6.41	44.3	29.20					1520
	42466	85.4	86.7	1.3	1040	3.12	6.97	55.0	22.60					230
	42467	86.7	88.1	1.4	1120	4.60	8.19	75.8	30.70					2778
	42468	88.1	89.1	1.0	800	2.20	6.63	31.5	33.20					314
90-08-25	41240	115.2	116.4	1.2	960	2.37	9.60	43.7	32.10					568
	41241	116.4	117.3	0.9	720	2.67	6.50	32.1	36.00					820
	41242	117.3	118.9	1.6	1280	3.84	2.97	28.4	41.60					980
	41243	118.9	119.5	0.6	720	6.15	3.76	38.2	36.30					1053
	41244	119.5	120.4	0.9	480	4.97	5.10	30.8	37.40					2313
	41245	120.4	122.0	1.6	1280	4.90	4.85	25.5	29.90					50
	41246	122.0	123.4	1.4	880	12.10	7.04	58.0	22.60					1464
SUBTOTAL														

CIRQUE PROJECT

Rock Type #		INCREMENT				ASSAYS						UNITS		(B) REMAINING	
SOLE #	SAMPLE #	FROM	TO	LENGTH	SPL. WT.	Pb%	Zn%	Ag g/t	Ba%	Pb	Zn	Ag	Ba		
90-05-06	41022	54.7	55.3	0.6	450	2.23	4.45	11.7	17.90					.400	
	41033	56.2	57.1	0.9	675	7.75	3.82	48.1	28.23					.900	
90-05-11	41092	56.8	57.9	1.1	825	1.55	9.44	56.0	24.00					2741	
	41093	57.8	59.0	1.2	825	2.52	14.25	90.6	17.50					3049	
	41094	59.0	59.3	0.3	975	3.02	12.00	76.2	19.40					3550	
	41100	70.1	71.5	1.4	1125	2.40	6.17	34.5	25.10					3589	
	41104	71.6	73.1	1.5	1125	2.23	4.76	51.2	26.60					7605	
	41106	74.1	75.0	0.9	675	1.38	7.02	41.5	22.48					1511	
	41115	85.4	86.5	1.1	825	3.18	7.40	60.0	24.10					8530	
90-05-12	41125	42.7	44.2	1.5	1125	3.77	8.80	62.0	20.00					3138	
	41125	44.2	45.4	1.2	900	2.96	8.21	66.0	22.20					2647	
	41127	45.4	46.9	1.5	1050	3.01	5.80	56.2	26.00					2604	
	41128	46.9	48.0	1.2	900	3.15	9.80	61.7	20.40					2739	
	41133	53.5	55.8	2.2	1650	7.90	12.00	93.0	15.30					806	
90-05-15	41165	73.0	74.7	1.7	1275	2.05	5.60	42.3	27.50					3046	
	41165	74.7	76.0	1.3	975	2.39	5.64	51.8	23.90					1231	
	41167	76.0	77.2	1.2	900	2.78	15.00	94.0	10.20					736	
	41168	77.2	79.0	1.8	1350	2.70	7.60	41.9	24.20					2447	
90-05-22	41415	41.1	42.5	1.4	1350	3.96	8.75	89.0	8.95					-	
	41416	42.9	44.5	1.6	1200	4.03	10.20	73.5	18.10					3044	
	41417	44.5	45.5	1.0	1500	3.92	6.73	52.6	19.60					-	
	41418	46.5	48.0	1.5	1725	1.34	3.80	66.0	14.40					30	
	41419	48.0	50.2	2.2	1050	2.59	5.99	47.9	27.80					1182	
	41420	50.2	51.7	1.5	825	2.20	5.00	49.0	24.00					474	
	90-05-24	41597	36.5	38.1	1.6	1200	2.88	6.22	62.0	38.40					2246
41598		38.1	39.6	1.5	1125	4.87	7.18	65.7	29.00					3117	
41599		39.6	41.1	1.5	1125	3.02	4.91	51.0	35.50					2526	
41601		42.6	44.2	1.6	1200	3.02	8.00	66.0	13.50					-	
90-05-26	41683	44.2	42.7	1.5	1125	1.21	13.60	71.7	18.30					2445	
	41684	42.7	44.2	1.5	1125	3.37	8.43	53.6	25.30					3364	
	41688	48.4	49.9	1.5	1125	3.38	8.39	40.8	30.30					2926	
90-05-27	41711	42.7	44.2	1.5	1125	1.08	4.56	27.9	32.70					2349	
	41712	44.2	45.4	1.2	900	2.28	9.02	56.7	21.80					816	
	41713	45.4	46.9	1.5	1125	3.77	12.90	74.2	17.00					1538	
	41714	46.9	48.1	1.2	900	2.79	9.37	48.4	24.50					2106	
90-05-28	41765	53.3	54.8	1.5	1125	1.02	5.82	41.4	26.70					2864	
	41766	54.8	56.3	1.5	1125	1.41	4.23	24.2	32.30					2465	
	41767	56.3	57.0	0.7	525	0.72	5.19	27.9	34.30					671	
	41770	60.4	61.9	1.5	1125	1.82	8.45	54.1	24.40					2714	
	41771	61.9	63.4	1.5	1125	1.30	8.89	34.2	34.10					1933	
	41772	63.4	64.9	1.5	1125	1.41	4.43	25.6	38.40					2258	
	41773	64.9	66.4	1.5	1125	2.62	10.31	34.0	29.20					2327	
	41774	66.4	67.4	1.0	750	4.15	3.81	21.9	36.60					647	
	90-05-29	41888	38.7	38.1	0.6	1800	2.49	7.09	40.2	20.40					108
41889		38.1	40.2	2.1	1875	2.47	8.85	51.6	28.70					1104	
41890		40.2	41.1	0.9	675	3.18	8.82	64.9	26.40					673	
41891		41.1	42.7	1.6	1200	2.37	6.39	47.6	30.00					2395	
41892		42.7	44.2	1.5	1125	2.00	10.95	85.0	22.40					-	
41893		44.2	45.4	1.2	1200	3.00	9.20	73.3	23.40					4989	
41895		45.4	46.9	1.5	1575	2.40	11.80	55.7	19.00					2605	
41897		46.9	51.1	4.2	900	2.25	5.94	31.3	34.40					2605	
41898		51.1	52.1	1.0	750	1.49	5.75	28.0	35.10					2131	
SUBTOTAL:															

TISSUE PROJECT

Rock Type 3		INCREMENT				ASSAYS				UNITS				(g)
HOLE #	SAMPLE #	FROM	TO	LENGTH	SPLE. WT.	Pct	Zn%	Pg g/t	Se%	Pb	Zn	Ag	Sa	Remainder
90-05-29	41896	47.8	69.9	2.1	1650	2.40	11.80	85.7	19.30					-
	41899	50.1	53.4	1.3	1040	1.27	13.00	71.8	18.60					2780
	41900	53.4	84.9	1.5	1200	8.06	14.90	94.3	14.70					2759
	41901	54.9	65.6	1.7	1260	3.42	15.70	109.0	13.20					2749
	41902	56.6	57.9	1.3	1040	3.60	9.56	58.2	22.10					3010
90-05-31	41992	62.2	47.4	1.2	460	2.80	8.00	54.5	16.50					1650
	41993	63.4	65.1	1.7	1360	2.33	9.00	47.0	14.70					3143
	41999	71.6	73.2	1.6	1280	2.83	8.46	56.3	26.90					50
	42000	73.2	73.8	0.6	480	1.78	19.00	90.3	1.68					446
	42001	73.8	75.3	1.5	1200	4.03	15.40	72.4	18.40					-
	42002	75.3	77.1	0.8	640	3.82	12.90	87.5	15.00					704
	42004	77.1	78.1	1.0	800	1.56	12.60	74.9	20.70					714
	42013	89.8	91.3	1.5	1200	2.20	10.40	82.4	5.18					2095
	42014	94.4	95.7	1.3	1040	4.85	14.50	119.0	7.76					2671
	42015	95.7	97.0	1.3	1040	4.54	15.00	122.0	2.19					2493
	42016	97.0	99.2	1.2	460	1.38	14.80	101.0	2.82					2871
	42017	99.2	99.4	1.2	460	4.63	25.00	182.0	1.50					428
	42018	99.4	100.6	1.2	460	5.16	23.90	181.0	1.19					2811
	42019	100.6	101.9	1.3	1040	4.80	24.00	180.0	1.82					2904
	42020	101.9	103.3	1.4	1120	6.02	26.40	176.8	0.84					-
42021	103.3	104.4	1.1	880	1.34	6.62	157.0	0.40					-	
90-05-33	42259	43.4	43.8	1.4	1120	2.45	7.98	59.8	12.20					1876
	42260	43.8	45.0	1.2	460	5.64	12.20	89.2	14.00					1597
	42261	45.0	45.9	0.9	720	4.00	10.80	68.4	15.00					2041
90-05-34	42449	65.2	65.7	0.5	480									-
	42451	66.4	67.3	0.9	720									89
	42452	67.3	68.7	1.0	800									-
	42453	70.15	72.1	1.3	1040									-
	42456	72.1	73.1	1.0	800									-
	42458	89.1	90.8	1.7	1360	2.00	6.92	83.8	5.40					1759
	42470	90.8	92.1	1.3	1040	0.99	7.00	55.0	4.90					1144
	42471	92.1	93.2	1.1	880	0.57	3.04	23.7	4.95					752
	42472	93.2	94.8	1.6	1280	2.18	14.00	79.0	3.52					1749
	42473	94.8	95.9	1.1	880	4.20	18.00	86.0	3.20					457
	42474	95.9	97.0	1.1	880	3.56	21.50	129.0	2.20					2308
	42475	97.0	98.0	1.0	800	6.02	23.50	155.0	5.10					2563
	42476	98.0	99.1	1.1	880	4.29	20.40	101.5	2.90					1345
	42477	99.1	100.8	1.4	1120	5.84	26.70	132.0	1.00					2472
	90-05-08	41295	0.0	1.0	1.0	800	4.82	17.90	93.0	5.40				
41296		1.0	2.4	1.4	1120	4.15	17.50	195.0	5.80					-
41297		2.4	4.1	1.7	1360	5.57	16.70	89.4	6.22					-
41298		4.1	6.8	1.5	1200	6.00	15.60	90.0	4.26					1286
41299		6.8	7.0	1.1	1120	7.18	12.10	94.5	15.90					493
41304		10.4	14.5	1.1	880	4.75	13.98	79.0	3.85					862
41305		15.0	16.6	0.8	480	1.39	11.20	71.8	1.80					-
41306		16.6	17.4	0.8	640	1.80	9.27	65.0	5.05					-
41307		17.4	17.1	0.7	560	2.11	11.40	74.0	2.80					-
41308		18.1	19.2	0.7	560	1.52	14.00	62.7	4.40					317
41309		19.2	20.4	1.1	1280	3.58	16.10	75.8	6.05					1715
41310		20.4	21.9	1.5	1200	4.40	17.70	89.4	4.40					1748
41311		21.9	23.4	1.5	1200	4.36	16.40	79.8	4.50					1635
41312		23.4	24.9	1.5	1200	4.45	15.50	89.5	6.55					1856
41313		24.9	25.5	1.0	1280	2.39	19.80	92.0	2.25					1377
41314		25.5	28.0	1.5	1200	1.75	16.40	82.0	2.75					1043
41315		28.0	29.3	1.3	1200	4.48	16.30	83.7	4.40					469
41316		29.3	30.1	1.3	1200	2.75	11.90	70.0	4.35					1710
41317		30.1	32.1	1.5	1280	3.57	20.10	101.0	3.50					481
41318		32.1	33.3	1.4	1120	4.71	9.37	53.7	4.04					433
41320	33.3	37.2	1.5	1280	1.07	8.00	83.8	4.10					518	
41321	37.2	38.5	1.3	1040	1.20	11.70	92.0	4.40					748	
SUBTOTAL					60080 gms									

CORONA PROJECT

Rock Type 5		INCREMENT				ASSAYS						UNITS	(g)		
SOLE #	SAMPLE #	FROM	TO	LENGTH	SPL. WT.	Pb%	Zn%	Ag g/t	Cu%	Pt	Zr	As	Sr	Remainder	
90-CU-06	41322	38.5	40.0	1.5	1200	4.86	16.80	118.0	1.24					1640	
	41323	40.0	41.5	1.5	960	4.97	16.80	142.0	1.50					387	
	41327	41.5	43.0	1.5	480	9.80	19.00	86.0	3.88					1485	
	41328	43.0	44.5	1.5	1200	9.43	18.70	80.5	3.28					1515	
90-CU-07	41338	11.4	12.9	1.5	960	4.46	11.40	56.0	2.20					-	
90-CU-10	41459	9.0	1.5	1.5	1200	6.18	19.20	179.0	1.60					1664	
	41460	1.5	3.0	1.5	720	21.00	23.40	158.0	0.60					321	
	41461	3.0	4.5	1.5	1280	5.15	18.50	121.0	2.68					1614	
	41462	4.5	6.0	1.5	1200	5.74	19.90	139.0	2.42					1649	
	41463	6.0	7.5	1.5	1200	7.76	19.60	152.0	1.44					1258	
	41464	7.5	9.0	1.5	560	8.10	17.30	131.0	1.88					674	
	41465	9.0	10.5	1.5	1200	7.97	17.40	132.0	2.61					1687	
	41467	10.5	12.0	1.5	1280	4.20	11.70	59.4	3.05					1599	
	41468	12.0	13.5	1.5	1200	5.15	18.70	129.0	1.28					1329	
	41469	13.5	15.0	1.5	1200	4.31	18.80	138.0	1.57					1749	
	41470	15.0	16.5	1.5	1200	8.95	12.60	151.0	3.04					1784	
	41471	16.5	18.0	1.5	1200	4.82	17.40	127.0	3.20					1802	
	41472	18.0	19.5	1.5	1280	3.65	10.90	89.6	13.80					—	
	41474	21.0	22.5	1.5	720	3.05	12.40	90.0	10.90					—	
41475	22.5	24.0	1.5	1280	5.60	14.90	152.0	9.60					—		
41476	24.0	25.5	1.5	1200	2.19	6.04	42.3	28.10					—		
90-CU-11	41484	9.0	1.5	1.5	1200	2.41	14.00	67.0	15.30					812	
	41485	1.5	3.0	1.5	1200	6.77	10.30	43.9	24.60					462	
	41486	3.0	4.5	1.5	1040	6.86	11.00	48.7	17.60					281	
	41487	4.5	6.0	1.5	960	3.84	14.50	66.0	14.30					612	
	41488	6.0	7.5	1.5	1200	5.16	17.00	119.0	7.10					1125	
	41491	7.5	9.0	1.5	1200	3.28	11.30	66.0	9.20					1116	
	41492	9.0	10.5	1.5	1200	2.85	12.40	58.0	11.40					1640	
	41493	10.5	12.0	1.5	1200	6.00	16.20	78.0	8.10					1652	
	41494	12.0	13.5	1.5	1280	4.17	18.40	86.4	9.15					1868	
	41495	13.5	15.0	1.5	1200	6.99	12.50	53.5	20.60					1493	
	41496	15.0	16.5	1.5	1200	6.92	12.50	56.1	14.10					1856	
	41497	16.5	18.0	1.5	1200	6.60	12.60	58.1	19.90					1457	
	41498	18.0	19.5	1.5	1120	6.63	11.25	45.6	16.50					1296	
	90-CU-15	41703	2.8	3.9	1.1	680	7.64	12.64	64.3	5.77					656
90-CU-17	41769	8.0	1.2	1.2	960	5.05	20.05	162.0	2.21					798	
	41790	1.2	2.4	1.2	960	6.17	23.10	114.0	1.83					776	
	41791	2.4	3.6	1.2	880	4.51	21.65	138.0	1.27					416	
	41792	3.6	4.8	1.2	800	5.93	17.30	133.0	0.75					176	
	41793	4.8	6.0	1.2	880	5.11	15.83	151.0	1.20					76	
41797	10.1	10.6	0.5	480	4.42	12.23	111.5	1.60					-		
90-CU-19	41799	9.0	1.1	1.1	880	6.48	21.55	98.6	5.42					881	
	41799	1.1	2.2	1.1	1120	6.72	13.40	92.1	5.39					628	
	41800	2.2	3.3	1.1	400	1.84	9.92	63.2	2.65					1297	
	41801	3.3	4.4	1.1	1040	3.76	12.05	67.9	2.70					306	
	41802	4.4	5.5	1.1	800	3.55	10.71	54.0	3.60					664	
	41802	5.5	6.6	1.1	1120	4.00	17.80	72.3	7.80					807	
	41807	6.6	7.7	1.1	1040	3.91	12.75	71.9	10.60					812	
	41808	7.7	8.8	1.1	1040	5.01	15.73	80.0	8.10					416	
	41809	8.8	9.9	1.1	1040	3.91	15.30	74.0	6.90					80	
	41810	9.9	10.9	1.0	480	2.00	15.83	74.2	12.80					-	
90-CU-20	41865	5.0	6.4	1.4	1120	3.96	13.50	93.0	5.70					-	
SUBTOTAL					53600 gms.										

DIRGUE PROJECT

Rock Type 3		INCREMENT				ASSAYS					UNITS				(g)
SOLE #	SAMPLE #	FROM	TO	LENGTH	SPL. WT.	Pb%	Zn%	Ag g/t	Ba%	Pb	Zn	Ag	Ba	Remain	
90-00-27 ...Cont.	42160	19.4	20.4	1.0	800	3.91	8.30	51.7	21.50					72	
	42161	20.4	21.9	1.5	1200	4.37	13.50	12.6	18.00					1502	
	42162	21.9	22.9	1.0	800	3.34	12.25	94.5	18.50					480	
	42163	24.6	25.1	0.5	1200	3.55	12.75	109.5	18.00					954	
	42164	25.1	28.0	2.9	1520	6.42	19.00	121.0	8.20					1514	
	42165	28.0	29.6	1.6	1200	2.50	16.25	101.0	11.00					703	
42169	32.5	34.1	1.6	1200	3.14	13.25	78.0	18.70					1003		
90-00-29	42205	3.6	5.9	2.3	1040	0.80	9.80	85.9	8.60					1301	
	42219	12.7	14.0	1.3	1040	4.29	12.80	71.0	7.20					715	
	42220	15.0	15.0	0.0	800	7.16	15.00	90.0	7.40					110	
	42221	15.0	18.1	3.1	880	4.57	11.60	77.5	8.00					685	
	42222	16.1	17.7	1.6	1200	7.80	18.90	120.0	6.90					1956	
	42223	17.7	19.2	1.5	1200	5.14	23.90	151.0	1.50					561	
	42224	19.2	19.7	0.5	400	9.60	17.70	123.0	4.50					206	
	42226	20.7	22.0	1.3	1200	3.24	18.30	98.0	3.40					1049	
	42227	22.2	23.9	1.7	1200	3.16	16.20	94.5	11.00					1423	
	42228	23.8	25.3	1.5	1200	3.58	14.30	83.7	7.25					1524	
	42228	25.3	26.3	1.0	600	3.47	15.50	101.0	3.20					666	
	42233	26.0	29.9	3.9	1520	7.50	19.00	87.0	2.50					1779	
	42234	29.9	31.4	1.5	1200	4.17	19.70	83.4	1.00					1869	
	42235	31.4	32.9	1.5	1200	3.32	17.40	81.9	2.50					1374	
	42236	32.9	34.4	1.5	1200	2.75	21.80	108.0	1.00					1428	
	42237	34.4	34.0	-0.4	1200	3.88	19.50	93.8	1.02					1291	
	42238	36.0	37.5	1.5	1200	1.94	14.50	92.0	3.30					1549	
	42237	37.5	39.0	1.5	1200	1.48	18.00	110.0	2.90					1093	
42240	39.0	39.8	0.8	640	5.55	15.80	122.0	4.00					271		
42241	39.8	41.0	1.2	460	9.99	14.40	109.0	6.00					1077		
42249	41.0	42.0	1.0	1760	4.77	11.20	94.0	8.00					2243		
42250	42.0	42.0	0.0	640	3.28	9.00	60.7	18.10					360		
* 90-00-30	42265	12.2	13.4	1.2	460	16.85	13.25	91.7	7.10					695	
	42266	13.4	14.8	1.4	1120	2.90	18.00	82.0	11.20					-	
	42267	14.8	16.1	1.3	1040	3.52	15.50	84.0	8.25					-	
	42295	24.5	25.2	0.7	560	2.58	8.22	80.3	7.20					25	
	42309	43.9	44.3	0.4	320	3.07	12.50	50.0	4.93					-	
90-00-31	42336	28.0	29.9	1.9	680	1.53	16.75	60.0	9.55					804	
	42337	29.9	31.4	1.5	1200	2.00	13.25	70.0	10.10					1204	
	42338	31.4	32.9	1.5	1200	4.85	20.25	90.5	4.60					1104	
	42339	32.9	34.4	1.5	1200	3.64	19.50	98.5	8.00					1151	
	42340	34.4	36.0	1.6	1200	1.66	13.00	87.4	10.30					2815	
	42345	41.3	43.7	2.4	1420	3.28	15.30	91.8	8.30					1227	
	42353	44.7	46.3	1.6	1200	3.41	11.50	88.0	2.01					525	
	42355	56.3	57.2	0.9	720	3.93	12.40	85.4	4.20					1264	
42356	57.2	58.8	1.6	1200	4.01	12.10	102.0	4.80					-		
90-00-34	42374	19.5	22.3	2.8	2240	4.84	19.80	120.0	4.00					50	
	42376	22.3	23.8	1.5	1200	2.07	18.50	118.0	0.50					230	
	42376	23.8	25.3	1.5	1200	4.35	19.20	128.0	0.80					439	
	42377	25.3	26.8	1.5	1200	5.57	15.40	88.5	4.50					50	
	42378	26.8	28.3	1.5	1200	4.38	21.00	144.0	1.10					50	
	42379	28.3	29.6	1.3	1040	1.50	12.50	86.4	11.00					233	
	42381	29.6	31.0	1.4	800	2.18	13.50	88.9	4.70					1140	
	42383	31.4	32.9	1.5	1200	3.17	12.40	78.0	5.70					593	
	42384	32.9	33.5	0.6	480	1.42	22.00	91.5	3.75					740	
	42387	33.5	36.3	2.8	960	3.60	12.10	85.9	26.00					149	
	42388	36.3	37.3	1.0	800	7.09	14.70	110.0	3.50					44	
	42389	37.3	39.0	1.7	1200	4.34	14.80	85.4	3.70					783	
	42390	39.0	40.5	1.5	1200	3.50	16.50	109.0	4.12					50	
	42391	40.5	42.1	1.6	1200	5.72	21.80	158.0	7.85					50	
	42392	42.1	43.6	1.5	1200	3.85	15.70	88.3	1.35					-	
	42393	43.6	44.1	0.5	400	4.00	16.30	100.0	0.70					-	
42394	44.1	44.3	0.2	100	36.20	8.80	122.0	4.75					-		
SUBTOTAL:					67800 gms										

