

Samples for 1st Met. Test
(Composites)

Hole	No of samples	ft	ft x value					No of Samples x value						
			Cu	Pb	Zn	Ag	Au	Cu	Pb	Zn	Ag	Au		
4603-4607	10	5 ✓	184.3-202.8	18.5	0.20	5.69	6.93	2.77	0.06	3.70	105.34	128.21	51.22	1.11
4608-4613	11	6 ✓	200-251	28.0	0.51	2.27	2.64	1.06	0.02	14.28	63.58	73.98	29.60	0.56
4614-4630	17	17 ✓	259-338.2	79.2	0.39	2.78	3.58	1.47	0.03	30.98	220.782	283.698	116.04	2.376
4635	13	1 ✓	85-92	7.0	0.41	4.06	4.46	1.50	0.02	2.87	28.72	30.94	10.50	0.14
4638-4642	5	5 ✓	165.4-186	20.6	0.41	1.63	2.75	0.85	0.01	8.46	33.407	50.394	17.51	0.206
4717-4720	15	4 ✓	128-144.6	16.6	0.14	3.04	3.02	1.65	0.01	2.324	50.406	50.060	27.39	0.249
4723-4739	17	17 ✓	164.9-246	81.1	.28	2.93	5.09	1.94	0.02	22.708	237.88	412.42	157.334	1.622
4751-4753	16	3 ✓	86.3-102	15.7	.03	1.74	3.33	.55	.01	0.471	27.281	52.356	8.63	0.157
4757-4761	16	5 ✓	198-223	25.0	.28	4.55	4.16	1.90	.04	7.000	113.75	104.00	47.50	1.000
4762-4765	16	4 ✓	220-241	18.0	.30	1.79	1.75	.86	.04	5.40	32.21	31.42	15.48	0.720
4781-4783	18	3 ✓	103-113	10.0	.45	6.28	5.07	2.50	0.025	4.50	62.80	50.70	25.00	0.250
4794-4797	11	4 ✓	163-183	20.0	.41	2.71	3.11	1.16	.02	8.20	54.20	62.20	23.80	0.40
4810-4813, 4828	20	5 ✓	191.6-210.5	18.9	0.15	7.78	8.60	4.42	.02	2.235	146.95	162.57	83.538	0.378
4886-4890	5	5 ✓	210.5-234	23.5	.06	.874	1.234	.52	Tr.	1.41	20.55	29.005	12.22	-
4814-16, 4891/2	5	5 ✓	234-253.4	19.4	.30	2.02	3.76	1.56	.02	5.82	39.146	72.998	30.264	0.388
4822-4824	21	3 ✓	198.5-213.5	15.0	.33	3.30	3.15	1.13	.03	4.95	49.50	47.25	16.95	0.45
4829-4832	26	4 ✓	107-127	20.0	0.18	2.01	4.20	1.44	0.02	3.60	40.20	82.0	28.2	0.40
4837-4841	11	8 ✓	215-255	40.0	0.23	3.08	5.20	1.90	0.03	9.20	123.2	208.0	76.0	1.20
4852-4861	27	10 ✓	220-266.7	46.7	.11	2.859	5.426	1.64	0.018	5.44	133.538	253.395	76.75	0.83
4862-4865	4	4 ✓	278-293	20.0	.15	3.123	3.715	2.62	.02	3.00	62.46	74.30	52.40	0.40
4869	28	1 ✓	60-65	5.0	0.40	2.04	7.09	1.40	0.03	2.00	10.20	35.45	7.00	0.15
4892-4904	30	7 ✓	178-209+(C)	31.4	.07	2.853	4.559	1.50	0.005	2.198	89.588	143.166	46.95	0.157
4905-908	4	4 ✓	226.6-242	19.4	0.23	2.547	5.535	2.04	0.015	4.462	49.406	107.378	39.576	0.291
4923-946	33	24 ✓	75-195	120.0	0.21	3.04	6.04	2.11	.02	25.20	364.8	724.8	253.20	2.40
4964-67	11	4 ✓	280-300	20.0	0.28	2.91	6.49	1.48	.02	5.60	58.2	129.8	29.6	.40
		158		739.0	0.25	3.00	4.60	1.736	0.022	186.294	2,27.494	3,40.431	1,882.67	16.224

Met. Test: Samples from Holes 10, 13, 15, 16, 18, 21, 26, 27, 28, 30 and 33

Total core length 739'

Avg grade: 0.25% Cu 3.00% Pb 4.60% Zn 1.736% Ag 0.022% Au

Total No of Samples used for test composite 158