



NOV 2 1964



020727
PHONE: 876-4111

CABLE ADDRESS "ELDRICO"

FILE NO. A.3-R.1-64 14535

DATE October 30, 1964

To: Kerr Addison Mines Ltd.
402 - 1112 West Pender Street
Vancouver, B. C.
Copy: Toronto Office

Certificate of Assay
COAST ELDRIDGE
ENGINEERS & CHEMISTS LTD.
125 EAST 4TH AVE. VANCOUVER 10, CANADA

Drill Core

We Hereby Certify that the following are the results of assays made by us upon submitted _____ samples

| MARKED | GOLD | | SILVER | PER CENT. | Lead (Pb) | PER CENT. | Zinc (Zn) | PER CENT. | PER CENT. |
|-------------------|----------------|---------------|----------------|-----------|-----------|-----------|-----------|-----------|-----------|
| | OUNCES PER TON | VALUE PER TON | OUNCES PER TON | | PER CENT. | | PER CENT. | | |
| 114 ¹⁰ | | \$ | | | 0.54 | | 1.20 | | |
| 115 | | | | | 3.80 | | 6.75 | | |
| 116 | | | | | 1.07 | | 2.87 | | |
| 117 | | | | | 2.04 | | 5.80 | | |
| 118 | | | | | 6.12 | | 7.11 | | |
| 119 | | | | | 4.95 | | 7.95 | | |
| 120 | | | | | 2.24 | | 6.99 | | |
| 121 | | | | | 1.22 | | 1.87 | | |
| 122 | | | | | 2.45 | | 3.88 | | |
| 123 | | | | | 1.12 | | 1.34 | | |
| 124 | | | | | 2.37 | | 7.66 | | |
| 125 | | | | | 3.19 | | 6.87 | | |
| 126 | | | | | 2.09 | | 4.50 | | |
| 127 | | | | | 2.91 | | 6.61 | | |
| 128 | | | | | 2.30 | | 6.89 | | |

*Re. Vanguarda Mines
Drill Core Samples*

W.S.R.
K.C.G.
E.F.
R.D.S.
E.C.B.
P.M.K. ✓
G.W.M.
H.A.P.
C.K.W. ✓
J.B.S.
G.P.R.
K.F.L.
J.B.
E.C.

Gold calculated at \$ _____ per ounce

Note. Rejects retained one week.
Pulps retained one month.
Pulps and rejects may be stored for a maximum of one year by special arrangement.
Unless it is specifically stated otherwise, gold and silver values reported on these sheets have not been adjusted to compensate for losses and gains inherent in the fire assay process.

H. Shingles

Provincial Assayer



PHONE: 876-4111

CABLE ADDRESS "ELDRICO"

FILE NO. A.3-X.1-64 14535

DATE October 30, 1964

Certificate of Assay
COAST ELDRIDGE
ENGINEERS & CHEMISTS LTD.

125 EAST 4TH AVE. VANCOUVER 10, CANADA

To: Kerr Addison Hinson Ltd.402 - 1112 West Pender StreetVancouver, B. C.Copy: Toronto OfficeWe Hereby Certify that the following are the results of assays made by us upon submitted Drill Core samples

| MARKED | GOLD | | SILVER | PER CENT. | Lead (Pb) | PER CENT. | Zinc (Zn) | PER CENT. | PER CENT. |
|--------|----------------|---------------|----------------|-----------|-----------|-----------|-----------|-----------|-----------|
| | OUNCES PER TON | VALUE PER TON | OUNCES PER TON | | PER CENT. | | PER CENT. | | |
| 129 | | \$ | | | 3.03 | | 7.16 | | |
| 130 | | | | | 3.37 | | 7.38 | | |
| 131 | | | | | 3.62 | | 2.97 | | |
| 132 | | | | | 2.55 | | 3.21 | | |
| 133 | | | | | 0.82 | | 2.18 | | |
| 134 | | | | | 0.46 | | 2.49 | | |
| 135 | | | | | 2.68 | | 6.97 | | |
| 136 | | | | | 2.70 | | 3.83 | | |
| 137 | | | | | 1.99 | | 6.08 | | |
| 138 | | | | | 3.56 | | 7.38 | | |
| 139 | | | | | 3.70 | | 8.63 | | |
| 140 | | | | | 3.44 | | 7.76 | | |
| 141 | | | | | 2.75 | | 5.75 | | |
| 142 | | | | | 2.14 | | 1.82 | | |
| 143 | | | | | 2.02 | | 3.65 | | |

Gold calculated at \$.....per ounce

Note. Rejects retained one week.
Pulps retained one month.
Pulps and rejects may be stored for a maximum of one year by special arrangement.

Unless it is specifically stated otherwise, gold and silver values reported on these sheets have not been adjusted to compensate for losses and gains inherent in the fire assay process.

Provincial Assayer



PHONE: 876-4111

CABLE ADDRESS "ELDRICO"

FILE NO. **A.3-E.1-64 14535**DATE **October 30, 1964**To: **Kerr Addison Mines Ltd.****402 - 1112 West Pender Street****Vancouver, B. C.****Copy: Toronto Office**

Certificate of Assay
COAST ELDRIDGE
ENGINEERS & CHEMISTS LTD.
 125 EAST 4TH AVE. VANCOUVER 10, CANADA

We Hereby Certify that the following are the results of assays made by us upon submitted **Drill Core** samples

| MARKED | GOLD | | SILVER | PER CENT. | Lead (Pb) | PER CENT. | Zinc (Zn) | PER CENT. | PER CENT. |
|--------|----------------|---------------|----------------|-----------|-----------|-----------|-----------|-----------|-----------|
| | OUNCES PER TON | VALUE PER TON | OUNCES PER TON | | PER CENT. | | PER CENT. | | |
| 144 DD | | \$ | | | 1.58 | | 5.27 | | |
| 145 | | | | | 3.39 | | 9.34 | | |
| 146 | | | | | 3.95 | | 7.21 | | |
| 147 | | | | | 8.72 | | 9.05 | | |
| 148 | | | | | 3.52 | | 10.20 | | |
| 149 | | | | | 3.24 | | 7.93 | | |
| 150 | | | | | 1.33 | | 6.97 | | |
| 151 | | | | | 2.37 | | 7.59 | | |
| 152 | | | | | 4.00 | | 4.84 | | |
| 1 | | | | | 3.06 | | 2.59 | | |

Gold calculated at \$.....per ounce

Note. Rejects retained one week.
 Pulp retained one month.
 Pulps and rejects may be stored for a maximum of one year by special arrangement.

Unless it is specifically stated otherwise, gold and silver values reported on these sheets have not been adjusted to compensate for losses and gains inherent in the fire assay process.

H. Charles

Provincial Assayer