

KERR AL ISON MINES LIMITED

(FOR INTER-OFFICE USE ONLY)

Vangorda SEP 16 9 1968

cc of Y/5:13

To P. M. Kavanagh From W. M. Sirola

Subject Swim Lakes - Vangorda Metallurgical Sampling Date September 5, 1968

16-19

020729

W.S.R.	
K.C.G.	
J.H.S.	✓
E.F.	
R.D.S.	
D.C.R.	
G.W.M.	
R.O.M.	
C.K.W.	
J.B.S.	
G.P.R.	
K.F.L.	
J.L.R.	
E.C.I.	✓

By this weekend we will have made the following distribution of core for metallurgical testing:

Swim Lakes "A" Group - DDH #A-24, 151.7 - 200.5 = 48.8 feet averaging 3.7% Pb, 4.8% Zn and 1.8 oz. Ag to be shipped to Mr. Ogiri of Toyomenka in Vancouver who in turn will send it to Japan. I estimate that the core from this hole will weigh approximately 60 lbs.

63 lbs actual

From the Vangorda deposit we have core from drill holes 15-C and 15-D. I will send the upper section from 15-C (160 - 200 feet) which should weigh approximately 40 lbs to Galigher. The lower section from 15-C (201 - 250 feet) which should weigh approximately 50 lbs will go to Mr. Ogiri.

1.66 Ag  
4.30 Pb  
5.06 Zn  
0.12 Cu

36 lbs actual

36 lbs actual

Each of these sections of core will be crushed to 1/4" and then sampled for lead, zinc, silver and copper prior to shipment.

We will have remaining for possible future use, all of the split core from DDH #A-12 at Swim Lakes. This is a section from 320.5 - 399.0 feet, or 78.5 feet averaging 3.8% Pb, 4% Zn, and 1.2 oz of Ag, plus all of DDH #15-D from Vangorda. This latter hole was drilled to a depth of 250 feet.

100 lbs

120 lbs

W. M. Sirola

W. M. Sirola.

WMS/lk

N.B. The assay results written by hand above are the assay results by Eldridge in Vancouver of the actual samples being sent out to Dow & Galigher.

Pmk.  
Sept. 13/68.

Recent assay of other half of core:  
1.62 Ag  
3.96 Pb  
4.60 Zn  
0.21 Cu