

Samples analyzed by Chemex Labs Ltd. using ICP-AES for 32 elements and FA-AAS for Au																
SAMPLE	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K
	ppb	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%
JH96-4A	<5	1.4	0.42	22	160	0.5	<2	0.14	<0.5	1	28	2	2.06	<10	<1	0.38
JH96-5A	<5	2.6	0.38	10	170	<0.5	<2	<0.01	<0.5	<1	29	<1	1.23	<10	1	0.36
JH96-5B	<5	0.6	0.34	12	140	0.5	<2	0.05	0.5	2	19	5	3.89	<10	1	0.3
JH96-5C	<5	0.4	0.56	10	180	1	<2	0.09	<0.5	2	9	5	2.99	<10	1	0.44
JH96-12B	<5	2	0.56	6	230	0.5	<2	0.32	2.5	1	11	14	1.35	<10	<1	0.5
JH96-15B	575	4.4	0.25	30	190	<0.5	<2	4.41	>100.0	3	59	4930	4.5	<10	3	0.17
JH96-30-2	45	1	1.45	200	180	0.5	<2	0.66	2.5	7	109	219	6.34	<10	1	0.24
JH96-30-3	10	0.4	1.69	66	50	0.5	<2	0.96	<0.5	16	51	391	9.9	<10	<1	0.49
JH96-33-2	<5	0.2	1.18	52	150	<0.5	<2	0.81	<0.5	3	68	43	2.31	<10	1	0.24
WZ 014	<5	<0.2	0.99	6	30	<0.5	<2	0.51	<0.5	3	55	3	1.27	<10	<1	0.08
WZ 015	<5	<0.2	1.54	2	30	<0.5	<2	1.33	<0.5	5	48	3	1.94	<10	<1	0.06
SAMPLE	Mg	Mn	Mo	Na	Ni	P	Pb	Sb	Sc	Sr	Ti	Tl	U	V	W	Zn
	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm
JH96-4A	0.04	335	4	0.01	1	150	58	<2	<1	11	<0.01	<10	<10	<1	<10	20
JH96-5A	0.01	15	14	<0.01	<1	30	44	<2	<1	5	<0.01	<10	<10	<1	<10	60
JH96-5B	0.03	8470	15	<0.01	<1	230	8	2	<1	12	<0.01	<10	<10	<1	<10	338
JH96-5C	0.09	3990	4	<0.01	<1	250	12	<2	<1	16	<0.01	<10	<10	<1	<10	132
JH96-12B	0.06	85	19	<0.01	<1	100	926	<2	<1	12	<0.01	<10	<10	<1	<10	386
JH96-15B	1.82	1395	2	<0.01	3	<10	212	16	<1	77	<0.01	<10	<10	<1	<10	>10000
JH96-30-2	0.74	1090	9	<0.01	31	1650	40	2	1	48	0.01	<10	<10	120	<10	404
JH96-30-3	0.76	8690	1	0.01	96	2190	2	2	2	43	0.04	<10	<10	83	<10	108
JH96-33-2	0.66	475	3	<0.01	10	1900	12	<2	1	47	<0.01	<10	<10	20	<10	30
WZ 014	0.6	310	<1	0.03	1	810	2	<2	2	25	0.07	<10	<10	5	<10	26
WZ 015	0.57	405	<1	0.01	1	1270	2	<2	1	89	0.07	<10	<10	6	<10	12
Samples analyzed by Chemex Labs Ltd. using ICP-AES for 32 elements and FA-AAS for Au																
SAMPLE	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K
	g/t	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%
JH97-42	<0.005	0.2	0.13	<2	<10	<0.5	<2	0.22	<0.5	1	179	480	0.4	<10	<1	0.02
JH97-42A	<0.005	1	0.31	<2	<10	<0.5	<2	0.22	<0.5	3	219	1420	0.86	<10	<1	0.04
JH97-43	0.03	2.6	0.63	<2	<10	<0.5	<2	0.44	22.5	3	158	6750	1.88	<10	<1	<0.01
JH97-45	<0.005	<0.2	1.28	<2	<10	<0.5	<2	0.35	<0.5	11	33	17	3.26	<10	<1	<0.01
JH97-102	<0.005	29.8	0.62	10	20	<0.5	<2	0.16	4	6	169	2760	1.19	<10	2	0.05
SAMPLE	Mg	Mn	Mo	Na	Ni	P	Pb	Sb	Sc	Sr	Ti	Tl	U	V	W	Zn
	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm
JH97-42	0.09	55	1	<0.01	3	10	152	2	<1	3	<0.01	<10	<10	4	<10	16
JH97-42A	0.24	90	3	0.01	4	40	126	<2	1	3	<0.01	<10	<10	11	<10	54
JH97-43	0.56	220	3	0.01	4	30	324	<2	2	19	<0.01	<10	<10	26	<10	2730
JH97-45	0.93	460	<1	0.11	<1	340	2	<2	6	25	0.15	<10	<10	29	<10	48
JH97-102	0.38	100	50	<0.01	5	30	1725	20	2	4	0.01	<10	<10	17	<10	582
Samples analyzed by ACME Analytical Laboratories Ltd. using ICP-AES for 32 elements and FA-AAS for Au																
SAMPLE	Au	Ag	Al	As	B	Ba	Bi	Ca	Cd	Co	Cr	Cu	Fe	Hg	K	La
	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	%	ppm
JH98-108	3	1.2	0.66	10	29	365	<3	0.02	<2	3	6	11	18.46	<1	0.25	148
JH98-A1	<2	2.2	0.31	81	6	36	<3	0.01	<2	2	7	17	4.64	<1	0.25	128
JH98-A11	<2	0.3	0.25	35	15	12	<3	<0.1	<2	7	7	8	12.15	<1	0.23	17
RE JH98-A11	<2	0.6	0.25	35	16	12	<3	<0.1	<2	7	8	8	11.87	<1	0.23	17

JH98-A111	<2	1.4	0.14	49	11	19	<3	2.87	<2	3	5	33	11.74	<1	0.11	27
JH98-C	<2	<.3	<.01	<2	<3	20	<3	33.93	0.3	1	2	<1	0.17	<1	0.01	2
SAMPLE	Mg	Mn	Mo	Na	Ni	P	Pb	Sb	Sr	Ti	Th	Tl	U	V	W	Zn
	%	ppm	ppm	%	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
JH98-108	0.03	91	1	0.01	1	0.053	50	<3	4	<.01	23	<5	<8	2	<2	157
JH98-A1	0.02	79	24	0.01	35	0.01	50	6	3	<.01	17	<5	<8	4	2	7
JH98-A11	0.02	35	4	0.01	11	0.002	65	<3	1	<.01	3	5	<8	1	4	3
RE JH98-A11	0.02	37	3	0.01	11	0.001	59	<3	1	<.01	3	5	9	1	4	4
JH98-A111	1.02	361	6	0.02	2	0.024	765	5	17	<.01	4	<5	<8	<1	4	14
JH98-C	0.23	29	<1	0.01	<1	0.002	<3	<3	87	<.01	<2	<5	<8	<1	<2	9

[illegible]

[illegible]